We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists



186,000

200M



Our authors are among the

TOP 1% most cited scientists





WEB OF SCIENCE

Selection of our books indexed in the Book Citation Index in Web of Science™ Core Collection (BKCI)

Interested in publishing with us? Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected. For more information visit www.intechopen.com



Comparison of Apatite-Wollastonite Glass-Ceramic and β-tricalcium Phosphate used as Bone Graft Substitutes after Curettage of Bone Cysts

Pavel Sponer, Karel Urban and Tomas Kucera Charles University in Prague, Faculty of Medicine and University Hospital in Hradec Kralove Czech Republic

1. Introduction

The need to treat the bone defects arises throughout the whole spectrum of orthopaedic surgery. It is possible to produce materials with specific mechanical properties, architecture and biodegradability. The essential attributes for regeneration of new osseous tissue include biocompatibility, osteointegration, osteoconductivity, osteoinductivity and osteogenicity. Biocompatibility means that the immunogenic response and foreign body reactions to the implanted material are minimised or absent. Osteointegration is defined as a process leading to close bonding of the newly formed mineralised tissue with the implant material. Beyond these bone regeneration essentials, other matrix properties can influence the suitability of a material for its intended clinical applications, such as surface roughness, the mechanical integrity of the matrix and the matrix's porosity [1]. Several osteoconductive bone graft substitutes are available for clinical application, including coralline hydroxyapatite, collagen-based matrices, calcium phosphates, calcium sulphate and deproteinised bovine bone. These materials vary substantially in tems of their chemical composition, mechanical properties and biodegradability. Orthopaedic surgeons should understand the differences between the various bone graft substitutes to ensure they select a material that provides the desired properties for the intended clinical application.

An ideal synthetic bone graft substitute should be a porous matrix with interconnecting porosity that promotes rapid bone ingrowth, and at the same time, it should possess a sufficient strength to prevent its crushing under physiological loads during osteointegration and healing. Hydroxyapatite (Ca₁₀(PO₄)₆(OH)₂), β -tricalcium phosphate (Ca₃(PO₄)₂), their derivatives and combinations are the most commonly used ceramic materials in orthopaedics. While hydroxyapatite ceramic materials provide an osteoconductive matrix for bone ingrowth and ongrowth, slow in-vivo resorption profiles can potentially limit their clinical applications [2]. Although β -tricalcium phosphate ceramic has been studied substantially in animal models and its biocompatibility, osteoconductivity and resorbability have been reported, there have been only limited data regarding long-term outcome of its clinical use in surgery for bone tumours [3-12]. However, the informations about biological responses such as bone bonding and resorption of ceramics are very important in clinical applications [13-15].

The goal of this study was to analyze and compare the clinical and radiological outcome in patients after implantation of the nonresorbable oxyhydroxyapatite glass-ceramic and Beta-Tricalcium phosphate used to fill the defects of long bones after curettage of bone cysts.

2. Materials and methods

2.1 Patients

This retrospective study was approved by the local research ethics committee, and all participants gave their written, informed consent. We evaluated 39 consecutive patients who fulfilled the following inclusion criteria: (i) histologically confirmed unicameral bone cyst, (ii) treatment by curettage of the lesion and implantation of glass-ceramic or betatricalcium phosphate, (iii) follow-up after at least 24 months to confirm a static radiographic outcome without recurrence of benign bone lesion. There were 28 male and 11 female patients. The age of the 21 patients with the implanted nonresorbable glass-ceramic at the time of surgery was 4-44 years with an average age of 15 years. The age of the 18 patients with implanted beta-tricalcium phosphate at the time of surgery was 7-30 years with an average age of 14 years. The unicameral bone cysts were located in the humerus (16 patients), femur (13), fibula (4), tibia (2), calcaneus (2), ulna (1), and iliac bone (1). All patients had curettage of the cyst and filling of the resulting bone defect with glass-ceramic (15 male and 6 female) or tricalcium phosphate (13 male and 5 female). Cortical fenestration was carried out using an osteotome and the soft tissue membrane was removed by a curette. After the filling of the bone defect with glass-ceramic or tricalcium phosphate, the cortical window was replaced. Internal fixation was employed in four patients because a pathological fracture occurred in 3 cases and an impending fracture was in 1 patient. Splints or bandages were used postoperatively for patients judged to be at risk of pathological fracture. Full weight bearing was allowed after 8-12 weeks. The patients were scheduled for follow-up evaluations which included clinical and radiographic examinations at 4-6, 10-14 weeks, 6 and 12 months intervals. Thereafter they were seen yearly.

2.2 Filling

A bioactive glass-ceramic material with wollastonite, oxyhydroxyapatite, residual glass phase, and whitlockite at a ratio of 45–30–20–5% (BAS-0, Lasak Ltd., Prague, Czech Republic) was used. The apatite-wollastonite glass-ceramic was dense with a porosity of less than 0.5%. The sintering temperature was 1200°C, the bending strength 170 MPa and the compression strength 400MPa. Granules 2–4mm in diameter were implanted during operations. The amount of the glass-ceramic used ranged from 5 to 45 g.

 β -tricalcium phosphate (Poresorb[®], Lasak Ltd., Prague, Czech Republic) in granule form with particle size of 0,6 to 2 mm was implanted. The porosity of the interconnected β tricalcium phosphate scaffold was 35±5 %, the average macropore size was 100 µm in diameter, the size of micropores was 1-5 µm, and the sintering temperature was 1180°C. The quantity of implanted β -tricalcium phosphate ranged from 3 to 66 g.

2.3 Clinical and radiographic follow-up

Clinical and radiographic examinations of all patients were carried out at 3–12 years (7 years on average) after implantation of the bioactive glass–ceramic and at 2–8 years (4 years on average) after implantation of tricalcium phosphate. The clinical follow-up included

subjective complaints, objective findings focused on soft tissue status in the area of synthetic bone graft substitute filling, range of movement in adjacent joints and weight-bearing ability of the treated extremity. The radiographs were taken in standard projections and evaluated independently by three investigators. The results were then compared for inter-observer agreement and, in case of differences, the patient's radiograph was reviewed by all three observers together. The radiographic integration of bioactive glass-ceramic was evaluated according to the criteria of Uchida et al. [16] to determine the presence of the markedly seen bridging trabeculae at the recipient bone-implant interface and the amount of incorporation of glass-ceramic. The radiographic integration of tricalcium phosphate was classified according to the criteria of Nigro and Grace [17]. Complete integration was associated with radiographical homogeneity of host bone and bone graft substitute, and trabecular remodelling was seen. Integration was judged to be partial when the formation of a partial gap between synthetic bone graft substitute and host bone was observed. Resorption was defined as gradually decreased radiopacity of the bone graft substitute until complete resorption.

3. Results

3.1 AW glass-ceramic

The clinical evaluation showed that 10 patients had no subjective complaints, 4 reported transient pain, 3 had pain at activity, 2 reported pain during weather changes, 1 woman observed pain during pregnancy, and 1 patient had pain at rest. No restriction in weightbearing of the limb treated was reported by any of the patients. Radiographs obtained immediately after surgery showed radiolucent zones between the implanted glassceramic and the surrounding bone. Periodic assessments revealed that, during the period of 3-4.5 months, the radiolucent zones faded and new bone developed. Continuing radiographic observations up to a maximum of 12 years after implantation have shown no evidence of biodegradation of the apatite-wollastonite glass-ceramic material. The distinct bridging bone trabeculae bound to the surface of glass-ceramic granules were observed in all patients (Fig. 1). In the metaphyseal region of long bones, the incorporated glass-ceramic granules still remained distinct and seemed to be connected to each other. However, in the diaphyseal region of long bones, there was little distinction between the glass-ceramic granules and adjacent bone. Increased bone density around the incorporated glass-ceramic material with remodeling of the cortex in the diaphyseal region of long bones was found in six of the nine patients. No degenerative changes were encountered in adjacent joints. No postoperative infections or fractures were observed in our patients. Recurrence of bone cysts was identified in one case. The patient had further curettage of recurrence located in the area surrounding an incorporated glass-ceramic material and the cavity was filled with allogeneic cancellous bone grafts; this patient had no pain. One male with a small residual defect required no further surgery.

3.2 Tricalcium phosphate

Neither postoperative infection nor adverse reaction due to the material were encountered. No patient complained of local pain af final examination and all patients were satisfied with their limb function. Radiographs obtained immediately after surgery demonstrated radiolucent zones between the implanted tricalcium phosphate and the surrounding bone. Over time, radiolucent zones faded and new bone developed in all 18 patients. The mean





Inte

)en

b)

a)

Comparison of Apatite-Wollastonite Glass-Ceramic and β -tricalcium Phosphate used as Bone Graft Substitutes after Curettage of Bone Cysts



9h



d)



e)

Fig. 1. Anteroposterior radiograph of the left proximal femur showing a large unicameral bone cyst in a 13-year-old boy preoperatively (a); complete filling of the curetted cavity with autologous cancellous bone grafts 2 months after surgery (b); recurrence of the cyst 4 years later (c); complete filling of defect with apatite-wollastonite glass-ceramic granules 3 months after curettage of the recurrence (d); bone trabeculae bound to the glass-ceramic granules which still remained distinct 10 years after surgery (e)

period necessary for disappearance of these radiolucent zones was 9 weeks (range 5-13 weeks). Periodic radiographic assessments revealed decreased radiographic density of β -tricalcium phosphate and replacement of β -tricalcium phosphate granules by newly formed bone trabeculae. These processes apper to have started on the periphery of the synthetic filling and progressed centrally. Signs of the implanted β -tricalcium phosphate still remained radiographically at the final follow-up in all 18 cases, but the material was incorporated in the surrounding bone and gradually resorbed.

Postoperative fractures were recorded in two patients with a unicameral bone cyst in the humerus. One male fell 3 weeks after surgery; the fracture was treated conservatively. The other male patient has had a car accident 20 months after surgery; the displaced diaphyseal fracture was treated with open reduction and plate osteosynthesis. In two young patients, growth arrest or deformity were seen before curretage of the cyst and implantation of β -tricalcium phosphate. Premature closure of the physeal plate with resulting shortening of the upper extremity was found as a complications after pathological fracture of proximal humerus in one male with unicameral bone cyst. Recurrences of the unicameral bone cyst

were seen only in 2 cases. Both patients had further curettage of recurrence in the area surrounding an incorporated tricalcium phosphate. In the skeletaly mature male patient, the cavity was filled with autologous cancellous bone grafts; in other patient, β -tricalcium phosphate was added to the cavity at the time of repeated curettage (Fig. 2).



a)







c)

d)



Fig. 2. Anteroposterior radiograph of the right proximal femur showing a large unicameral bone cyst in a 11-year-old boy preoperatively (a); complete filling of the curetted cavity with β -tricalcium phosphate after surgery (b); decreased radiographic density of β -tricalcium phosphate apparent on the periphery of filling with recurrence of the cyst localized between the implanted material and growth plate 7 months later (c); further progression of the recurrence 13 months after surgery (d); large multicameral recurrence of unicameral bone cyst in 15 years of age (e); β -tricalcium phosphate added to the cavity at the time of repeated curettage (f)

4. Discussion

Conventional bone grafting with an autologous bone harvested from the iliac crest is the current gold standard because the autografts contain marrow cells including nondifferentiated mesenchymal stem cells, osteogenic bone cells, an osteoconductive matrix and osteoinductive proteins. However, the availability of autologous bone grafts is limited, their harvesting requires a further operation with prolonged operative time and is often associated with donor-site morbidity. The processed allograft bone is an attractive alternative to the autologous bone [18]. These allogeneic bone grafts are primarily osteoconductive, but they retain a variable number of osteoinductive proteins. The host immune response to freezedried allografts is less vigorous than the response to fresh or fresh-frozen allografts [19]. The transmission of infectious agents from donor to recipient with allogeneic bone grafts is their major risk and a loss of mechanical properties is their important disadvantage. The infectious risk is increased when fresh allografts are used and, therefore, serological testing has to be performed to reduce that risk.

In an effort to overcome limitations of autografts and allografts, the synthetic bone graft substitutes were developed from a variety of materials, including calcium phosphates,

480

calcium sulphates, bioactive glasses and glass-ceramics which appear to be the ideal substances for use as matrices because the inorganic component of bone is composed of hydroxyapatite. Bioceramics can be divided into three categories: bioinert ceramics (alumina), surface-bioactive ceramics (sintered hydroxyapatite, bioactive glasses and apatite-wollastonite glass-ceramics), and resorbable bioactive ceramics (low-crystalline hydroxyapatite and tricalcium phosphate) [2].

The used dense bioactive glass-ceramic with main crystalic phases, oxyhydroxyapatite, and wollastonite, when compared with beta-tricalcium phosphate ceramic, has no microporosity and nanoporosity. After the filling of the bone cavity with 2–4-mm granules of nonresorbable material, new bone tissue ingrowth was seen in the interspaces between granules [20,22]. The nonresorbable bone graft substitutes can offer an excellent permanent function in certain conditions. In contrast, these synthetic materials can also affect tissue reparation and function. After osteointegration of the rigid nonresorbable material, the surrounding bone tissue is often mechanically influenced and protected (the stress-shielding phenomenon), thereby changing the local mechanical signals. This adversely affects the surrounding bone tissue can generally cause pain or mechanical failure [21, 22]. Equalizing to the mechanical properties of the surrounding bone is essential, because the mechanical signals are important mediators for the differentiation of connective tissue progenitor cells.

The ideal biodegradable bone graft substitutes should fulfill some requirements such as biocompatibility, adequate initial strength and stiffness, retention of mechanical properties throughout sufficient time to assure its biofunctionality and non-toxicity of the degradation by-products [23-25]. The continuous degradation of a resorbable material causes a gradual load transfer to the healing tissue, preventing stress-shielding phenomenon and stimulates the healing and remodeling of bones [22, 26]. The surgeon should be concerned with the mechanical and biological properties of the bone graft substitute as well as the handling and ability to assess healing of the grafted site.

Aside from chemical composition, the microstructure (the volume, density and size of pores and interconnections, the specific surface) plays a role in the bone ingrowth of porous biomaterials. An increase of porosity would make bone ingrowth inside synthetic materials easier but would decrease their biomechanical properties. The interconnections in a porous material act only as pathways for nutritional elements, vascularization and cells between the pores that are the sites for bone tissue growth proceeding from the outside to the inside [2]. Therefore, the size of pores should be larger than the size of interconnections [27]. Macroporosity (pore size >50 μ m), microporosity (pore size <10 μ m) and pore wall roughness play an essential role in new bone formation [12, 28-33]. The larger surface area can support a higher bone inducing protein adsorption, ion exchange and bone-like apatite formation by dissolution and reprecipitation while the surface roughness enhances attachment, proliferation and differentiation of bone forming cells [2, 32]. Thus, these data imply that more extensive dissolution and reprecipitation of low-crystalline calcium phosphates can cause more osteoconductive and cell-mediated degradation characteristics [34].

Resorption is an important characteristic of bone graft substitutes and can be divided in two mechanisms: solution-mediated dissolution processes and cell-mediated (phagocytic) processes. The degradation attributes of calcium phosphates are dependent on the chemical composition, crystal structure, crystal and grain size, microporosity, neck geometry, and neck dissolution rates of the materials [34]. The density of pores and interconnections which expresses the quantity of connections between pores of porous materials plays a more

important role than their size that is modified during degradation of resorbable bioceramics, whereas the sizes and the densities are equally important in unresorbable biomaterials [2, 27]. Although tricalcium phosphate was incorporated in the surrounding bone and gradually resorbed, signs of the implanted β -tricalcium phosphate still remained radiographically in all cases. In our opinion, the implanted quantity of tricalcium phosphate was higher in our patients compared to other authors [5-7, 15]. More experimental and clinical studies will be required in order to resolve the healing problems of large bone defects combining scaffolds with osteoinductive factors and cell cultures. According to this study, interconnected β -tricalcium phosphate is a successful and safe bone graft substitute for the treatment of benign bone tumours and tumour-like lesions because of its biocompatibility and bioresorbability.

5. References

- [1] Khan Y, Yaszemski MJ, Mikos AG, Laurencin CT (2008) Tissue engineering of bone: material and matrix consideration. J Bone Joint Surg Am 90-A:S36–42
- [2] Sponer P, Urban K, Kucera T, Kohout A, Brtkova J, Knizek J (2011) The use of interconnected β-tricalcium phosphate as bone substitute after curettage of benign bone tumours. Eur J Orthop Surg 21:235-241
- [3] Merten HA, Wiltfang J, Grohmann U, Hoenig JF (2001) Intraindividual comparative animal study of α-and β-tricalcium phosphate degradation in conjunction with simultaneous insertion of dental implants. J Craniofacial Surg 12:59-67
- [4] Wiltfang J, Merten HA, Schlegel KA, Schultze-Mosgau S, Kloss FR, Rupprecht S, Kessler P (2002) Degradation characteristics of α and β tri-calcium-phosphate (TCP) in minipigs J Biomed Mater Res (Appl Biomater) 63: 115–121
- [5] Galois L, Mainard D, Delagoutte JP (2002) Beta-tricalcium phosphate ceramic as a bone substitute in orthopaedic surgery. Inter Orthop 26:109–115
- [6] Ogose A, Hotta T, Kawashima H, Kondo N, Gu W, Kamura T, Endo N (2005) Comparison of hydroxyapatite and beta tricalcium phosphate as bone substitutes after excision of bone tumors J Biomed Mater Res Part B: Appl Biomater 72B:94–101
- [7] Hirata M, Murata H, Takeshita H, Sakabe T, Tsuji Y, Kubo T (2006) Use of purified betatricalcium phosphate for filling defects after curettage of benign bone tumours. Inter Orthop 30: 510-513
- [8] Brunner TJ, Grass RN, Bohner M, Stark WJ (2007) Effect of particle size, crystal phase and crystallinity on the reactivity of tricalcium phosphate cements for bone reconstruction. J Mater Chem 17:4072–4078
- [9] Walsh WR, Vizesi F, Michael D, Auld J, Langdown A, Oliver R, Yu Y, Irie H, Bruce W (2008) β-TCP bone graft substitutes in a bilateral rabbit tibial defect model. Biomaterials 29:266–271
- [10] Stubbs D, Deakin M, Chapman-Sheath P, Bruce W, Debes J, Gillies RM, et al. (2004) In vivo evaluation of resorbable bone graft substitutes in a rabbit tibial defect model. Biomaterials 25:5037–5044
- [11] Gál P, Ondruš Š, Škvařil J, Straka M, Jochymek J, Plánka L (2009) Synthetic biocompatible degradable material for juvenilie bone cyst treatment. Acta Chir Orthop Traumatol Cech 76:495-500

482

- [12] von Doernberg MC, von Rechenberg B, Bohner M, Grunenfelder S, van Lenthe GH, Muller R, et al. (2006) In vivo behavior of calcium phosphate scaffolds with four different pore sizes. Biomaterials 27:5186–5198
- [13] Hibi A, Ishikawa T, Asano M, Ohsawa S, Tsuge K, Iyoda K. (1994) A study of failed implantation of hydroxyapatite for benign bone tumor. Orthoped Surg (Sekiekgeka) 45: 1423-1428
- [14] Matsumine A, Myoui A, Kusazaki K, Araki N, Seto M, Yoshikawa H, Uchida A (2004) Calcium hydroxyapatite ceramic implants in bone tumour surgery: a long-term follow-up study. J Bone Joint Surg 86-B:719–725
- [15] Nicholas RW, Lange TA (1994) Granular tricalcium phosphate grafting of cavitary lesions in human bone. Clin Orthop Rel Res 306:197-203
- [16] Uchida A, Araki N, Shinto Y, Yoshikawa H, Kurisaki E, Ono K (1990) The use of calcium hydroxyapatite ceramic in bone tumour surgery. J Bone Joint Surg 72-B:298-302
- [17] Nigro N, Grace D (1996) Radiographic evaluation of bone grafts. J Foot Ankle Surg 35:378–385
- [18] Sponer P, Urban K, Urbanova E, Karpas K, Mathew PG (2009). Behaviour of nonresorbable bioactive glass-ceramic implanted into long bone defects: comparison with cancellous allografts. Arch Orthop Trauma Surg 129:1353–1360
- [19] DeLong WG, Einhorn TA, Koval K, McKee M, Smith W, Sanders R, Watson T (2007) Bone grafts and bone graft substitutes in orthopaedic trauma surgery. J Bone Joint Surg 89-A:649–658.
- [20] Strnad Z (1992) Role of the glass phase in bioactive glass-ceramics. Biomaterials 13:317– 321.
- [21] Muschler GF, Nakamoto C, Griffith LG (2004) Engineering principles of clinical cellbased tissue engineering. J Bone Joint Surg Am 86-A:1541–1558
- [22] Sponer P, Urban K, Urbanova E, Karpas K, Mathew PG (2010) Behavior of bioactive glass-ceramic implanted into long bone defects: a scintigraphic study. J Pediatr Orthop B 19:102-107
- [23] Botez P, Sirbu P, Simion L, Munteanu F, Antonia I (2009) Application of a biphasic macroporous synthetic bone substitutes CERAFORM®: clinical and histological results. Eur J Orthop Surg Traumatol 19:387–395
- [24] Mano JF, Sousa RA, Boesel LF, Neves NM, Reis RL (2004) Bioinert, biodegradable and injectable polymeric matrix composites for hard tissue replacement: state of the art and recent developments. Compos Sci Technol 64:789- 817
- [25] Naito K, Obayashi O, Mogami A, Itoi A, Kaneko K (2008) Fracture of the calcium phosphate bone cement which used to enchondroma of the hand: a case report. Eur J Orthop Surg Traumatol 18:405–408
- [26] Dorozhkin SV (2009) Calcium orthophosphate-based biocomposites and hybrid biomaterials. J Mater Sci 44:2343–2387
- [27] Lu JX, Flautre B, Anselme K, Hardouin P, Gallur A, Descamps M, et al. (1999) Role of interconnections in porous bioceramics on bone recolonization in vitro and in vivo. J Mater Sci Mater Med 10:111–120
- [28] Bohner M, Baumgart F. (2004) Effects of geometrical factors on the resorption of calcium phosphate bone substitutes. Biomaterials 25:3569–3582

- [29] Daculsi G, Passuti N. (1990) Effect of macroporosity for osseous substitution of calcium phosphate ceramics. Biomaterials 11:86–87
- [30] Eggli PS, Muller W, Schenk RK. (1988) Porous hydroxyapatite and tricalcium phosphate cylinders with two different macropore size ranges implanted in the cancellous bone of rabbits. Clin Orthop 232:127–138
- [31] Galois L, Mainard D. (2004) Bone ingrowth into two porous ceramics with different pore sizes: an experimental study. Acta Orthop Belg 70:598–603
- [32] Karageorgiou V, Kaplan D. (2005) Porosity of 3D biomaterial scaffolds and osteogenesis. Biomaterials 26:5474–5491
- [33] Yuan H, Kurashina K, de Bruijn JD, Li Y, de Groot K, Zhang X. (1999) A preliminary study on osteoinduction of two kinds of calcium phosphate ceramics. Biomaterials 20:1799–1806
- [34] Oonishi H, Hench LL, Wilson J, Sugihara F, Tsuji E, Kushitani S,Iwaki H (1999) Comparative bone growth behavior in granules of bioceramic materials of various sizes. J Biomed Mater Res 44:31–43





Advances in Ceramics - Electric and Magnetic Ceramics, Bioceramics, Ceramics and Environment Edited by Prof. Costas Sikalidis

ISBN 978-953-307-350-7 Hard cover, 550 pages Publisher InTech Published online 06, September, 2011 Published in print edition September, 2011

The current book consists of twenty-four chapters divided into three sections. Section I includes fourteen chapters in electric and magnetic ceramics which deal with modern specific research on dielectrics and their applications, on nanodielectrics, on piezoceramics, on glass ceramics with para-, anti- or ferro-electric active phases, of varistors ceramics and magnetic ceramics. Section II includes seven chapters in bioceramics which include review information and research results/data on biocompatibility, on medical applications of alumina, zirconia, silicon nitride, ZrO2, bioglass, apatite-wollastonite glass ceramic and b-tri-calcium phosphate. Section III includes three chapters in applications of ceramics in environmental improvement and protection, in water cleaning, in metal bearing wastes stabilization and in utilization of wastes from ceramic industry in concrete and concrete products.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Pavel Sponer, Karel Urban and Tomas Kucera (2011). Comparison of Apatite-Wollastonite Glass-Ceramic and β-tricalcium Phosphate used as Bone Graft Substitutes after Curettage of Bone Cysts, Advances in Ceramics -Electric and Magnetic Ceramics, Bioceramics, Ceramics and Environment, Prof. Costas Sikalidis (Ed.), ISBN: 978-953-307-350-7, InTech, Available from: http://www.intechopen.com/books/advances-in-ceramics-electricand-magnetic-ceramics-bioceramics-ceramics-and-environment/comparison-of-apatite-wollastonite-glassceramic-and-tricalcium-phosphate-used-as-bone-graft-substit

INTECH

open science | open minds

InTech Europe

University Campus STeP Ri Slavka Krautzeka 83/A 51000 Rijeka, Croatia Phone: +385 (51) 770 447 Fax: +385 (51) 686 166 www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai No.65, Yan An Road (West), Shanghai, 200040, China 中国上海市延安西路65号上海国际贵都大饭店办公楼405单元 Phone: +86-21-62489820 Fax: +86-21-62489821 © 2011 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the <u>Creative Commons Attribution-NonCommercial-ShareAlike-3.0 License</u>, which permits use, distribution and reproduction for non-commercial purposes, provided the original is properly cited and derivative works building on this content are distributed under the same license.



