We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Electrochemistry of Curium in Molten Chlorides

Alexander Osipenko¹, Alexander Mayershin¹, Valeri Smolenski^{2,*},
Alena Novoselova² and Michael Kormilitsyn¹

¹*Radiochemical Division, Research Institute of Atomic Reactors,*

²*Institute of High-Temperature Electrochemistry,
Ural Division, Russian Academy of Science,*

Russia

1. Introduction

Molten salts and especially fused chlorides are the convenient medium for selective dissolution and deposition of metals. The existence of a wide spectrum of individual salt melts and their mixtures with different cation and anion composition gives the real possibility of use the solvents with the optimum electrochemical and physical-chemical properties, which are necessary for solving specific radiochemistry objects. Also molten alkali metal chlorides have a high radiation resistance and are not the moderator of neutrons as aqua and organic mediums [Uozumi, 2004; Willit, 2005].

Nowadays electrochemical reprocessing in molten salts is applied to the oxide and metal fuel. Partitioning and Transmutation (P&T) concept is one of the strategies for reducing the long-term radiotoxicity of the nuclear waste. For this case pyrochemical reprocessing methods including the recycling and transmutation can be successfully used for conversion more hazardous radionuclides into short-lived or even stable elements. For that first of all it is necessary to separate minor actinides (Np, Am, Cm) from other fission products (FP).

Pyrochemical reprocessing methods are based on a good knowledge of the basic chemical and electrochemical properties of actinides and fission products. This information is necessary for creation the effective technological process [Bermejo et al., 2007, 2008; Castrillejo et al., 2005a, 2005b, 2009; De Cordoba et al., 2004, 2008; Fusselman et al., 1999; Kuznetsov et al., 2006; Morss, 2008; Novoselova & Smolenski, 2010, 2011; Osipenko et al., 2010, 2011; Roy et al., 1996; Sakamura et al., 1998; Serp et al., 2004, 2005a, 2005b, 2006; Serrano & Taxil, 1999; Shirai et al., 2000; Smolenski et al., 2008, 2009].

Curium isotopes in nuclear spent fuel have a large specific thermal flux and a long half-life.

So, they must be effectively separated from highly active waste and then undergo transmutation.

The goal of this work is the investigation of electrochemical and thermodynamic properties of oxide and oxygen free curium compounds in fused chlorides.

2. Experimental

2.1 Preparation of starting materials

The solvents LiCl (Roth, 99.9%), NaCl (Reachim, 99.9%), KCl (Reachim, 99.9%), and CsCl (REP, 99.9%) were purified under vacuum in the temperatures range 293-773 K. Then the reagents were fused under dry argon atmosphere. Afterwards these reagents were purified by the operation of the direct crystallization [Shishkin & Mityaev, 1982]. The calculated amounts of prepared solvents were melted in the cell before any experiment [Korshunov et al., 1979].

Curium trichloride was prepared by using the operation of carbochlorination of curium oxide in fused solvents in vitreous carbon crucibles. Cm^{3+} ions, in the concentration range 10^{-2} - 10^{-3} mol kg^{-1} were introduced into the bath in the form of CmCl_3 solvent mixture.

The obtained electrolytes were kept into glass ampoules under atmosphere of dry argon in inert glove box.

2.2 Potentiometric method

The investigations were carried out in the cell, containing platinum-oxygen electrode with solid electrolyte membrane which was made from ZrO_2 stabilized by Y_2O_3 supplied by Interbil Spain (inner diameter 4 mm, outer diameter 6 mm). This electrode was used as indicating electrode for measuring the oxygen ions activity in the investigated melt. The measurements were carried out versus classic Cl^-/Cl_2 reference electrode [Smirnov, 1973]. The difference between indicator and reference electrodes in the following galvanic cell

is equal to

$$\varepsilon = \varepsilon^0 - \frac{RT}{2F} \ln \frac{a_{\text{O}^{2-}} \cdot p_{\text{Cl}_2}}{a_{\text{Cl}^-}^2 \cdot p_{\text{O}_2}^{1/2}} \quad (2)$$

where a is the activity of the soluble product in the melt (in $\text{mol} \cdot \text{kg}^{-1}$); P is the gas pressure (in atm.); ε^0 is the difference of standard electrode potentials of the reaction 3 (in V); T is the absolute temperature (in K); R is the ideal gas constant (in $\text{J} \cdot \text{mol}^{-1} \cdot \text{K}^{-1}$); n is the number of electrons exchanged and F is the Faraday constant ($96500 \text{ C} \cdot \text{mol}^{-1}$).

The value ε^0 of the reaction (3) is the following

$$\varepsilon^0 = E_{\text{Cl}_2/\text{Cl}^-}^0 - E_{\text{O}_2/\text{O}^{2-}}^0 = \frac{-\Delta G^0}{2F} \quad (4)$$

where ΔG^0 is the change of the standard Gibbs energy of the reaction 3 (in $\text{kJ} \cdot \text{mol}^{-1} \cdot \text{K}^{-1}$).

$$E_{O_2/O^{2-}} = E_{O_2/O^{2-}}^* - \frac{RT}{2F} \ln \left[m_{eq}(O^{2-}) \right] \quad (5)$$

where $E_{O_2/O^{2-}}$ is the equilibrium potential of O_2/O^{2-} system (in V); $E_{O_2/O^{2-}}^*$ is an apparent standard potential of the system (in V).

The value of apparent standard potential E^* in contrast to the standard potential E^o describes the dilute solutions, where the activity coefficient $\gamma_{O^{2-}}$ is constant at low concentrations [Smirnov, 1973] and depends from the nature of molten salts. It can be calculated experimentally with high precision according to expression (5). The introducing of oxide ions in the solution was done by dropping calculated amounts of BaO (Merck, 99,999%) which completely dissociates in the melt [Cherginetz, 2004].

All reagents were handled in a glove box to avoid contamination of moisture. The experiments were performed under an inert argon atmosphere.

The potentiometric study was performed with Autolab PGSTAT302 potentiostat/galvanostat (Eco-Chimie) with specific GPES electrochemical software (version 4.9.006).

2.3 Transient electrochemical technique

The experiments were carried out under inert argon atmosphere using a standard electrochemical quartz sealed cell using a three electrodes setup. Different transient electrochemical techniques were used such as linear sweep, cyclic, square wave, differential and semi-integral voltammetry, as well as potentiometry at zero current. The electrochemical measurements were carried out using an Autolab PGSTAT302 potentiostat-galvanostat (Eco-Chimie) with specific GPES electrochemical software (version 4.9.006).

The inert working electrode was prepared using a 1.8 mm metallic W wire (Goodfellow, 99.9%). It was immersed into the molten bath between 3 - 7 mm. The active surface area was determined after each experiment by measuring the immersion depth of the electrode. The counter electrode consisted of a vitreous carbon crucible (SU - 2000). The Cl^-/Cl_2 or Ag/Ag^+ ($0.75 \text{ mol} \cdot \text{kg}^{-1} \text{ AgCl}$) electrodes were used as standard reference electrodes. The experiments were carried out in vitreous carbon crucibles; the amount of salt was (40-60 g). The total curium concentrations were determined by taking samples from the melt and then analyzed by ICP-MS.

3. Results and discussion

3.1 Potentiometric investigations

The preliminary investigations of fused $3LiCl-2KCl$ eutectic and equimolar $NaCl-KCl$ by of O^{2-} ions are present in Table 1. In this case, the potential of the pO^{2-} indicator electrode vs. the concentrations of added O^{2-} ions follows a Nernst behavior (eq. 5). The experiment slope is closed to its theoretical value for a two-electron process, which shows the Nernstian behavior of the system.

To identify curium oxide species and to determine their stability, the titration of Cm^{3+} by O^{2-} ions was performed. To estimate stoichiometric coefficients of reactions that involve initial components, the ligand number “ α ” was used.

Molten solvent	Temperature, K	$E_{O_2/O^{2-}}^*$ (in V vs. Cl ⁻ /Cl ₂)	$\frac{RT}{2F}$ (exp.)	$\frac{RT}{2F}$ (theor.)
3LiCl-2KCl	723	-1.087±0.001	0.072±0.001	0.072
	823	-1.102±0.001	0.082±0.001	0.082
	923	-1.275±0.004	0.091±0.001	0.0911
NaCl-KCl	1023	-1.351±0.001	0.101±0.001	0.101
	1073	-1.448±0.003	0.134±0.002	0.106
	1123	-1.374±0.001	0.111±0.001	0.111
NaCl-2CsCl	823	-0.751±0.001	0.083±0.001	0.083
	923	-0.771±0.001	0.092±0.001	0.092
	1023	-0.985±0.001	0.113±0.009	0.102

Table 1. The parameters of calibration curve for 3LiCl-2KCl, NaCl-KCl and NaCl-2CsCl melts, (molality scale)

$$\alpha = \frac{[O^{2-}]_{added}}{[Cm^{3+}]_{initial}}$$

(6)

where $[O^{2-}]_{added}$ is the added concentration of oxide ions in the melt, (in mol·kg⁻¹); $[Cm^{3+}]_{initial}$ is the initial Cm³⁺ concentration, (in mol·kg⁻¹).

Fig. 1. Potentiometric titration of Cm³⁺ solution by O²⁻ ions in NaCl-2CsCl at 1023 K. [Cm³⁺] = 1.2·10⁻³ mol·kg⁻¹

The potentiometric titration curve pO^{2-} versus a in the $NaCl-2CsCl-CmCl_3$ melt shows one equivalent point for a equal to 1, Fig. 1. This can be assigned to the production of solid oxychloride, $CmOCl$. The shape of an experimental curve shows the possibility of formation of soluble product CmO^+ in the beginning of titration [Cherginets, 2004]. The precipitation of Cm_2O_3 did not fixed on experimental curves. One of the reasons of these phenomena may be the kinetic predicaments in formation of insoluble compound Cm_2O_3 .

Therefore, the titration reactions can be written as:

Combine expressions (8) and (9), $Cm_2O_{3(s)}$ formation is described by (10):

The chloride ions activity in the melt is one. By applying mass balance equations (11, 12) and the expressions of the equilibrium constant of the reaction (7) and the solubility constants of the reactions (8, 10) it is possible to calculate the concentration of CmO^+ ions and the solubility of $CmOCl$ and Cm_2O_3 in the melt:

$$[O^{2-}]_{bulk} = [O^{2-}]_{added} - [CmO^+]_{bulk} - [CmOCl]_{precipitated} - 3[Cm_2O_3]_{precipitated} \quad (11)$$

$$[Cm^{3+}]_{bulk} = [Cm^{3+}]_{initial} - [CmO^+]_{bulk} - [CmOCl]_{precipitated} - 2[Cm_2O_3]_{precipitated} \quad (12)$$

where $[O^{2-}]_{bulk}$ is the equilibrium concentration of oxide ions in the melt, (in $mol \cdot kg^{-1}$);

$[Cm^{3+}]_{bulk}$ is the equilibrium concentration of curium ions in the melt, (in $mol \cdot kg^{-1}$);

$[CmO^+]_{bulk}$ is the equilibrium concentration of curium oxide ions in the melt, (in $mol \cdot kg^{-1}$).

$$K_{eq}^{CmO^+} = \frac{[CmO^+]}{[Cm^{3+}] \cdot [O^{2-}]} \quad (13)$$

$$K_s^{CmOCl} = [Cm^{3+}] \cdot [O^{2-}] \cdot [Cl^-] \quad (14)$$

$$K_s^{Cm_2O_3} = [Cm^{3+}]^2 \cdot [O^{2-}]^3 \quad (15)$$

The formation of CmO^+ ions in the range ($0 < \alpha < 0.5$) is described by the following theoretical titration curve:

$$\alpha = \frac{\left[O^{2-}\right]_{bulk} \cdot \left[\frac{K_{eq}^{CmO^+}}{\left[Cm^{3+}\right]_{initial}} + \left[O^{2-}\right]_{bulk} \right]}{\left[Cm^{3+}\right] + 1} \cdot \frac{1}{K_{eq} + \left[O^{2-}\right]_{bulk}} \tag{16}$$

When CmOCl is precipitating ($0.5 < \alpha < 1.0$), the theoretical titration curve can be written as:

$$\alpha = 1 + \frac{1}{\left[Cm^{3+}\right]_{initial}} \left[\left[O^{2-}\right]_{bulk} - \frac{K_s^{CmOCl}}{\left[O^{2-}\right]_{bulk}} \right] \tag{17}$$

In the range ($1.0 < \alpha < 1.5$), where Cm₂O₃ is precipitating, the theoretical titration curve is:

$$\alpha = 1.5 + \frac{1}{\left[Cm^{3+}\right]_{initial}} \left[\left[O^{2-}\right]_{bulk} - \frac{1.5 \cdot \left(K_s^{Cm_2O_3}\right)^{1/2}}{\left[O^{2-}\right]_{bulk}^{3/2}} \right] \tag{18}$$

Molten solvent	Temperature, K	$pK_{eq}^{CmO^+}$	pK_s^{CmOCl}	$pK_s^{Cm_2O_3}$
3LiCl-2KCl	723	2.5±0.2	7.5±0.2	15.5±0.5
	823	2.4±0.2	5.7±0.2	12.7±0.5
	923	0.8±0.1	5.2±0.2	12.5±0.5
NaCl-KCl	1023	2.6±0.2	5.9±0.2	12.9±0.4
	1073	2.4±0.2	5.8±0.2	12.6±0.4
	1123	1.3±0.1	5.6±0.2	12.1±0.4
NaCl-2CsCl	829	4.2±0.2	7.9±0.2	20.1±0.3
	923	3.4±0.2	7.5±0.2	18.5±0.3
	1023	3.7±0.2	6.7±0.2	16.8±0.3

Table 2. The experimental values of dissociation constants of CmO⁺, CmOCl и Cm₂O₃ in fused solvents at different temperatures, (molatility scale)

The best conformity of the experimental and theoretical titration curves at different temperatures is obtained with the constants, offers in Table 2. All results are presented in Tables 3-5. Thermodynamic data allowed us to draw the potential-*pO*²⁻ diagrams, Fig. 2-4, which summarized the stability areas of curium compounds in different solvents a various temperatures.

The decreasing of the temperature and the shift of the ionic radius of the solvent (in *z/r*, nm) [Lebedev, 1993] from LiCl up to CsCl mixtures show regular decreasing of the solubility of curium in the solvents [Yamana, 2003].

System	Expression for equilibrium potential	Apparent standard potential (V vs. Cl ⁻ /Cl ₂) [Cm ³⁺] = 1 mol·kg ⁻¹
1. Cm ³⁺ + 3e ⁻ ↔ Cm	$E_1 = E_1^* + \frac{2.3RT}{3F} \log [Cm^{3+}]$	$E^*(1) = -2.924$
2. CmO ⁺ + 3e ⁻ ↔ Cm + O ²⁻	$E_2 = E_1^* - \frac{2.3RT}{3F} pK_{eq(CmO^+)} + \frac{2.3RT}{3F} \log [CmO^+] + \frac{2.3RT}{3F} \log pO^{2-}$	$E^*(2) = -3.055$
3. CmOCl + 3e ⁻ ↔ Cm + O ²⁻ + Cl ⁻	$E_3 = E_1^* - \frac{2.3RT}{3F} pK_{S(CmOCl)} + \frac{2.3RT}{3F} pO^{2-}$	$E^*(3) = -3.220$
4. Cm ₂ O ₃ + 6e ⁻ ↔ 2Cm + 3O ²⁻	$E_4 = E_1^* - \frac{2.3RT}{6F} pK_{S(Cm_2O_3)} + \frac{2.3RT}{2F} pO^{2-}$	$E^*(4) = -3.286$
5. Cm ³⁺ + O ²⁻ ↔ CmO ⁺	$pK_{eq} = -4.7455 + 5426/T$	$pK_{eq} = 2.5$
6. Cm ³⁺ + O ²⁻ + Cl ⁻ ↔ CmOCl	$pK_s = 1.5132 + 3394/T$	$pK_s = 7.5$
7. 2Cm ³⁺ + 3O ²⁻ ↔ Cm ₂ O ₃	$pK_s = 0.779 + 10407.5/T$	$pK_s = 15.5$

Table 3. Equilibrium potentials and values of apparent standard potentials of redox system in 3LiCl-2KCl at 723 K. [Cm³⁺] = 1 mol·kg⁻¹. Potentials are given vs. Cl⁻/Cl₂ reference electrode

Fig. 2. Potential- pO_2 diagram for curium in 3LiCl-2KCl eutectic at 723 K. $[Cm^{3+}] = 1 \text{ mol}\cdot\text{kg}^{-1}$. Potentials are given vs. Cl⁻/Cl₂ reference electrode

Fig. 3. Potential- pO_2 diagram for curium in equimolar NaCl-KCl at 1023 K. $[Cm^{3+}] = 1 \text{ mol}\cdot\text{kg}^{-1}$. Potentials are given vs. Cl⁻/Cl₂ reference electrode

System	Expression for equilibrium potential	Apparent standard potential (V vs. Cl ⁻ /Cl ₂) [Cm ³⁺] = 1 mol·kg ⁻¹
1. Cm ³⁺ + 3e ⁻ ↔ Cm	$E_1 = E_1^* + \frac{2.3RT}{3F} \log [Cm^{3+}]$	$E^*(1) = -2.727$
2. CmO ⁺ + 3e ⁻ ↔ Cm + O ²⁻	$E_2 = E_1^* - \frac{2.3RT}{3F} pK_{eq(CmO^+)} + \frac{2.3RT}{3F} \log [CmO^+] + \frac{2.3RT}{3F} pO^{2-}$	$E^*(2) = -2.915$
3. CmOCl + 3e ⁻ ↔ Cm + O ²⁻ + Cl ⁻	$E_3 = E_1^* - \frac{2.3RT}{3F} pK_{S(CmOCl)} + \frac{2.3RT}{3F} pO^{2-}$	$E^*(3) = -3.128$
4. Cm ₂ O ₃ + 6e ⁻ ↔ 2Cm + 3O ²⁻	$E_4 = E_1^* - \frac{2.3RT}{6F} pK_{S(Cm_2O_3)} + \frac{2.3RT}{2F} pO^{2-}$	$E^*(4) = -3.165$
5. Cm ³⁺ + O ²⁻ ↔ CmO ⁺	$pK_{eq} = -4.7455 + 5426/T$	$pK_{eq} = 2.6$
6. Cm ³⁺ + O ²⁻ + Cl ⁻ ↔ CmOCl	$pK_s = 1.5132 + 3394/T$	$pK_s = 5.9$
7. 2Cm ³⁺ + 3O ²⁻ ↔ Cm ₂ O ₃	$pK_s = 0.779 + 10407.5/T$	$pK_s = 12.9$

Table 4. Equilibrium potentials and values of apparent standard potentials of redox system in equimolar NaCl-KCl at 1023 K. [Cm³⁺] = 1 mol·kg⁻¹. Potentials are given vs. Cl⁻/Cl₂ reference electrode

System	Expression for equilibrium potential	Apparent standard potential (V vs. Cl ⁻ /Cl ₂) [Cm ³⁺] = 1 mol·kg ⁻¹
1. Cm ³⁺ + 3e ⁻ ↔ Cm	$E_1 = E_1^* + \frac{2.3RT}{3F} \log[Cm^{3+}]$	$E^*(1) = -2.996$
2. CmO ⁺ + 3e ⁻ ↔ Cm + O ²⁻	$E_2 = E_1^* - \frac{2.3RT}{3F} pK_{eq(CmO^+)} + \frac{2.3RT}{3F} \log[CmO^+] + \frac{2.3RT}{3F}$	$E^*(2) = -3.220$
3. CmOCl + 3e ⁻ ↔ Cm + O ²⁻ + Cl ⁻	$E_3 = E_1^* - \frac{2.3RT}{3F} pK_{s(CmOCl)} + \frac{2.3RT}{3F} pO^{2-}$	$E^*(3) = -3.430$
4. Cm ₂ O ₃ + 6e ⁻ ↔ 2Cm + 3O ²⁻	$E_4 = E_1^* - \frac{2.3RT}{6F} pK_{s(Cm_2O_3)} + \frac{2.3RT}{2F} pO^{2-}$	$E^*(4) = -3.546$
5. Cm ³⁺ + O ²⁻ ↔ CmO ⁺	$pK_{eq} = -4.7455 + 5426/T$	$pK_{eq} = 4.2$
6. Cm ³⁺ + O ²⁻ + Cl ⁻ ↔ CmOCl	$pK_s = 1.5132 + 3394/T$	$pK_s = 7.9$
7. 2Cm ³⁺ + 3O ²⁻ ↔ Cm ₂ O ₃	$pK_s = 0.779 + 10407.5/T$	$pK_s = 20.1$

Table 5. Equilibrium potentials and values of apparent standard potentials of redox system in NaCl-2CsCl eutectic at 829 K. [Cm³⁺] = 1 mol·kg⁻¹. Potentials are given vs. Cl⁻/Cl₂ reference electrode

Fig. 4. Potential- pO_2^- diagram for curium in equimolar NaCl-2CsCl at 829 K. $[Cm^{3+}] = 1 \text{ mol} \cdot \text{kg}^{-1}$. Potentials are given vs. Cl^-/Cl_2 reference electrode

3.2 Transient electrochemical technique

3.2.1 Voltammetric studies on inert electrodes

The reaction mechanism of the soluble-insoluble $Cm(III)/Cm(0)$ redox system was investigated by analyzing the cyclic voltammetric curves obtained at several scan rates, Fig. 5, 6. It shows that the cathodic peak potential (E_p) is constant from 0.04 V/s up to 0.1 V/s and independent of the potential sweep rate, Fig. 7. It means that at small scan rates the reaction $Cm(III)/Cm(0)$ is reversible. In the range from 0.1 V/s up to 1.0 V/s the dependence is linear and shifts to the negative values with the increasing of the sweep rate. So in this case (scan range $> 0.1 \text{ V/s}$) the reaction $Cm(III)/Cm(0)$ is irreversible and controlled by the rate of the charge transfer. On the other hand the cathodic peak current (I_p) is directly proportional to the square root of the polarization rate (v). According to the theory of the linear sweep voltammetry technique [Bard & Folkner, 1980] the redox system $Cm(III)/Cm(0)$ is reversible and controlled by the rate of the mass transfer at small scan rates and is irreversible and controlled by the rate of the charge transfer at high scan rates.

The number of electrons of the reduction of $Cm(III)$ ions for the reversible system was calculated at scan rates from 0.04 up to 0.1 V/s:

$$E_p - E_{p/2} = -0.77 \frac{RT}{nF} \quad (19)$$

where E_p is a peak potential (V), $E_{p/2}$ is a half-peak potential (V), F is the Faraday constant ($96500 \text{ C} \cdot \text{mol}^{-1}$), R is the ideal gas constant ($\text{J} \cdot \text{K}^{-1} \cdot \text{mol}^{-1}$) and T is the absolute temperature (K), n is the number of exchanged electrons. The results are 3.01 ± 0.04 .

Fig. 5. Cyclic voltammograms of fused 2LiCl-3KCl-CmCl₃ salt at different sweep potential rates at 723 K. Working electrode: W (S = 0.36 cm²). [Cm(III)] = 5.0·10⁻² mol·kg⁻¹

Fig. 6. Cyclic voltammograms of NaCl-2CsCl-CmCl₃ at different sweep potential rates at 823 K. Working electrode: W (S = 0.31 cm²). [Cm(III)] = 4.4·10⁻² mol·kg⁻¹

Fig. 7. Variation of the cathodic peak potential as a function Naperian logarithm of the sweep rate in fused NaCl-2CsCl-CmCl₃ at 823K. Working electrode: W (S = 0.59 cm²). [Cm(III)] = 4.4·10⁻² mol·kg⁻¹

Fig. 8. Square wave voltammogram of NaCl-2CsCl-CmCl₃ at 25 Hz at 823 K. Working electrode: W (S = 0.29 cm²). [Cm(III)] = 9.7·10⁻³ mol·kg⁻¹

The square wave voltammetry technique was used also to determine the number of electrons exchanged in the reduction of Cm(III) ions in the molten eutectic NaCl-2CsCl. Fig. 8 shows the cathodic wave obtained at 823 K. The number of electrons exchanged is determined by measuring the width at half height of the reduction peak, $W_{1/2}$ (V), registered at different frequencies (6–80 Hz), using the following equation [Bard & Folkner, 1980]:

$$W_{1/2} = 3.52 \frac{RT}{nF} \tag{20}$$

where T is the temperature (in K), R is the ideal gas constant (in $\text{J K}^{-1} \text{mol}^{-1}$), n is the number of electrons exchanged and F is the Faraday constant (in $\text{C}\cdot\text{mol}^{-1}$).

At middle frequencies (12-30 Hz), a linear relationship between the cathodic peak current and the square root of the frequency was found. The number of electrons exchanged determined this way was close to three ($n = 2.99 \pm 0.15$).

The same results were found in the system $3\text{LiCl}\cdot 2\text{KCl}\cdot \text{CmCl}_3$ [Osipenko, 2011].

On differential pulse voltammogram only one peak was fixed at potential range from -1.5 up to -2.2 V vs. Ag/Ag^+ reference electrode, Fig. 9. It means that the curium ions reduction process at the electrode is a single step process.

Potentiostatic electrolysis at potentials of the cathodic peaks shows the formation of the solid phase on tungsten surface after polarization. One plateau on the dependence potential – time curves was obtained, Fig. 10.

So the mechanism of the cathodic reduction of curium (III) ions is the following:

Fig. 9. Differential pulse voltammogram of $\text{NaCl}\cdot 2\text{CsCl}\cdot \text{CmCl}_3$ melt at 923 K. $[\text{Cm(III)}] = 4.4 \cdot 10^{-2} \text{ mol}\cdot\text{kg}^{-1}$

3.2.2 Diffusion coefficient of Cm (III) ions

The diffusion coefficient of Cm(III) ions in molten chloride media was determined using the cyclic voltammetry technique and applying Berzins–Delahay equation, valid for reversible soluble-insoluble system at the scan rates 0.04-0.1 V/s [Bard & Faulkner, 1980]:

$$I_p = 0.61(nF)^{3/2} C_0 S \left(\frac{Dv}{RT} \right)^{1/2} \quad (22)$$

Fig. 10. The potential–time dependences after anodic polarization of W working electrode in NaCl-2CsCl-CmCl₃ melt at different temperatures. [Cm(III)] = 4.4·10⁻² mol·kg⁻¹. The value of polarization is equal -2.1 ÷ -2.2 V. The time of polarization is equal 5 ÷ 15 s. 1 – 1023 K; 2 – 923 K; 3 – 823K

where S is the electrode surface area (in cm²), C_0 is the solute concentration (in mol cm⁻³), D is the diffusion coefficient (in cm² s⁻¹), F is the Faraday constant (in 96500 C mol⁻¹), R is the ideal gas constant (in J K⁻¹ mol⁻¹), n is the number of exchanged electrons, v is the potential sweep rate (in V/s) and T is the absolute temperature (in K).

The values obtained for the different molten chlorides tested at several temperatures are quoted in Table 6.

The diffusion coefficient values have been used to calculate the activation energy for the diffusion process. The influence of the temperature on the diffusion coefficient obeys the Arrhenius’s law through the following equation:

$$D = D_o \exp\left(-\frac{E_A}{RT}\right) \pm \Delta$$

(23)

Solvent	T/K	D/cm ² .s ⁻¹	-E _A /kJ.mol ⁻¹
LiCl-KCl	723	9.27·10 ⁻⁶	28.2
	823	1.62·10 ⁻⁵	
	923	2.57·10 ⁻⁵	
NaCl-2CsCl	873	6.97·10 ⁻⁶	44.5
	973	1.33·10 ⁻⁵	
	1023	2.49·10 ⁻⁵	

Table 6. Diffusion coefficient of Cm(III) ions in molten alkali metal chlorides at several temperatures. Activation energy for the curium ions diffusion process

where E_A is the activation energy for the diffusion process (in $\text{kJ}\cdot\text{mol}^{-1}$), D_o is the pre-exponential term (in $\text{cm}^2\cdot\text{s}^{-1}$) and Δ is the experimental error.

From this expression, the value of the activation energy for the Cm(III) ions diffusion process was calculated in the different melts tested (Table 6).

The average value of the radius of molten mixtures (r_{R^+}) was calculated by using the following equation [Lebedev, 1993]:

$$r_{R^+} = \sum_{i=1}^N c_i r_i \quad (24)$$

where c_i is the mole fraction of i cations; r_i is the radius of i cations in molten mixture, consist of N different alkali chlorides, nm.

The diffusion coefficient of curium (III) ions becomes smaller with the increase of the radius of the cation of alkali metal in the line from Li to Cs (Table 6). Such behaviour takes place due to an increasing on the strength of complex ions and the decrease in contribution of D to the "hopping" mechanism. The increase of temperature leads to the increase of the diffusion coefficients in all the solvents.

3.2.3 Apparent standard potentials of the redox couple Cm(III)/Cm(0)

The apparent standard potential of the redox couple Cm(III)/Cm(0) was determined at several temperatures. For the measurement, the technique of open-circuit chronopotentiometry of a solution containing a CmCl_3 was used (e.g. Fig. 10). A short cathodic polarisation was applied, 5-15 seconds, in order to form in situ a metallic deposit of Cm on the W electrode, and then the open circuit potential of the electrode was measured versus time (Fig. 10). The pseudo-equilibrium potential of the redox couple Cm(III)/Cm(0) was measured and the apparent standard potential, E^* , was determined using the Nernst equation:

$$E_{\text{Cm(III)/Cm(0)}} = E_{\text{Cm(III)/Cm(0)}}^* + \frac{RT}{nF} \ln X_{\text{CmCl}_3} \quad (25)$$

being,

$$E_{\text{Cm(III)/Cm(0)}}^* = E_{\text{Cm(III)/Cm(0)}}^o + \frac{RT}{nF} \ln \gamma_{\text{CmCl}_3} \quad (26)$$

The apparent standard potential is obtained in the mole fraction scale versus the Ag/AgCl ($0.75 \text{ mol}\cdot\text{kg}^{-1}$) reference electrode and then transformed into values of potential versus the Cl-/Cl₂ reference electrode scale or direct versus Cl-/Cl₂ reference electrode. For this purpose the special measurements were carried out for building the temperature dependence between Ag/AgCl ($0.75 \text{ mol}\cdot\text{kg}^{-1}$) and Cl-/Cl₂ reference electrodes. From the experimental data obtained in this work the following empirical equation for the apparent standard potential of the Cm(III)/Cm(0) system versus the Cl-/Cl₂ reference electrode was obtained using:

$$E_{Cm(III)/Cm(0)}^* = -(3.285 \pm 0.004) + (5.48 \pm 0.15) \cdot 10^{-4} T \pm 0.002 \text{ V} \text{ [3LiCl-2KCl, 723-923 K]}$$

(27)

$$E_{Cm(III)/Cm(0)}^* = -(3.750 \pm 0.006) + (9.98 \pm 0.16) \cdot 10^{-4} T \pm 0.003 \text{ V} \text{ [NaCl-KCl, 1023-1123 K]}$$

(28)

$$E_{Cm(III)/Cm(0)}^* = -(3.407 \pm 0.005) + (5.42 \pm 0.14) \times 10^{-4} T \pm 0.002 \text{ V} \text{ [NaCl-2CsCl, 823-1023 K]}$$

(29)

The relative stability of complex actinides ions increases with the increase of the solvent cation radius, and the apparent standard redox potential shifts to more negative values [Barbanel, 1985]. Our results are in a good agreement with the literature ones [Smirnov, 1973].

3.2.4 Thermodynamics properties

The apparent standard Gibbs energy of formation $\Delta G_{CmCl_3}^*$ was calculated according by the following expression:

$$\Delta G_{CmCl_3}^* = nFE_{Cm(III)/Cm(0)}^*$$

(30)

The least square fit of the standard Gibbs energy versus the temperature allowed us to determine the values of ΔH^* and ΔS^* more precisely by the following equation:

$$\Delta G_{CmCl_3}^* = \Delta H_{CmCl_3}^* - T\Delta S_{CmCl_3}^*$$

(31)

from which, values of enthalpy and entropy of formation can be obtained:

$$\Delta G_{CmCl_3}^* = -950.5 + 0.182 \cdot T \pm 0.6 \text{ kJ mol}^{-1} \text{ 3LiCl-2KCl}$$

(32)

$$\Delta G_{CmCl_3}^* = -1085.3 + 0.312 \cdot T \pm 0.8 \text{ kJ mol}^{-1} \text{ NaCl-KCl}$$

(33)

$$\Delta G_{CmCl_3}^* = -986.4 + 0.174 \cdot T \pm 0.6 \text{ kJ mol}^{-1} \text{ NaCl-2CsCl}$$

(34)

The calculated values are summarized in Table 7. The average value of the radius of these molten mixtures in this line, *pro tanto*, is 0.094 nm for fused 3LiCl-2KCl eutectic; 0.1155 nm for fused equimolar NaCl-KCl and 0.143 nm for fused NaCl-2CsCl eutectic [Lebedev, 1993]. From the data given in Table 7 one can see that the relative stability of curium (III) complexes ions is naturally increased in the line (3LiCl-2KCl)_{eut.} – (NaCl-2CsCl)_{eut.}

Thermodynamic properties	3LiCl-2KCl	NaCl-KCl	NaCl-2CsCl
E [*] /V	-2.752	-2.779	-2.880
ΔG [*] /(kJ mol ⁻¹)	-773.4	-781.7	817.1
ΔH [*] /(kJ mol ⁻¹)	-950.5	-1085.3	-986.4
ΔS [*] /(J ·K ⁻¹ mol ⁻¹)	0.182	0.312	0.174

Table 7. The comparison of the base thermodynamic properties of Cm in molten alkali metal chlorides at 973 K. Apparent standard redox potentials are given in the molar fraction scale

The changes of the thermodynamic parameters of curium versus the radius of the solvent cation show the increasing in strength of the Cm-Cl bond in the complex ions $[CmCl_6]^{3-}$ in the line from LiCl to CsCl [Barbanel, 1985].

4. Conclusion

The electrochemical behaviour of $CmCl_3$ in molten alkali metal chlorides has been investigated using inert (W) electrode at the temperatures range 723-1123 K. Different behaviour was found for the reduction process. At low scan rates (< 0.1 V/s) Cm(III) ions are reversible reduced to metallic curium in a single step, but at scan rates (> 0.1 V/s) this reaction is irreversible.

The diffusion coefficient of Cm(III) ions was determined at different temperatures by cyclic voltammetry. The diffusion coefficient showed temperature dependence according to the Arrhenius law. The activation energy for diffusion process was found.

Potentiostatic electrolysis showed the formation of curium deposits on inert electrodes.

The apparent standard potential and the Gibbs energy of formation of $CmCl_3$ have been measured using the chronopotentiometry at open circuit technique.

The influence of the nature of the solvent (ionic radius) on the thermodynamic properties of curium compound was assessed. It was found that the strength of the Cm-Cl bond increases in the line from Li to Cs cation.

The obtained fundamental data can be subsequently used for feasibility assessment of the curium recovery processes in molten chlorides.

5. Acknowledgement

This work was carried out with the financial support of ISTC project # 3261.

6. References

- Barbanel, Ya.A. (1985). *Coordination Chemistry of f-elements in Melts*, Energoatomizdat, Moscow, Russia
- Bard, A.J. & Faulkner, L.R. (1980). *Electrochemical Methods. Fundamentals and Applications*, John Wiley & Sons Inc., ISBN 0-471-05542-5, USA
- Bermejo, M.R.; de la Rosa, F.; Barrado, E. & Castrillejo, Y. (2007). Cathodic behaviour of europium(III) on glassy carbon, electrochemical formation of Al_4Eu , and oxoacidity reactions in the eutectic LiCl-KCl, In: *Journal of Electroanalytical Chemistry*, Vol. 603, No. 1, (May 2007), pp. 81- 95, ISSN 0022-0728
- Bermejo, M.R.; Barrado, E.; Martinez, A.M. & Castrillejo, Y. (2008). Electrodeposition of Lu on W and Al electrodes: Electrochemical formation of Lu-Al alloys and oxoacidity reactions of Lu(III) in eutectic LiCl-KCl, In: *Journal of Electroanalytical Chemistry*, Vol. 617, No. 1, (June 2008), pp. 85- 100, ISSN 0022-0728
- Castrillejo, Y.; Bermejo, M.R.; Diaz Arocas, P.; Martinez, A.M. & Barrado, E. (2005). The electrochemical behavior of praseodymium(III) in molten chlorides, In: *Journal of Electroanalytical Chemistry*, Vol. 575, No. 1, (January 1995), pp. 61- 74, ISSN 0022-0728

- Castrillejo, Y.; Bermejo, M.R.; Barrado, A.I.; Pardo, R.; Barrado, E. & Martinez, A.M. (2005). Electrochemical behavior of dysprosium in the eutectic LiCl-KCl at W and Al electrodes, In: *Electrochimica Acta*, Vol. 50, No. 10, (March 2005), pp. 2047- 2057, ISSN 0013-4686
- Castrillejo, Y.; Fernandes, P.; Bermejo, M.R.; Barrado, A.I. & Martinez, A.M. (2009). Electrochemistry of thulium on inert electrodes and electrochemical formation of a Tm-Al alloy from molten chlorides, In: *Electrochimica Acta*, Vol. 54, No. 26, (November 2009), pp. 6212-6222, ISSN 0013-4686
- Cherginets, V.L. (2004) *Chemistry of Oxocompounds in Ionic Melts*, Institute of Monocrystiles, Kharkov, Ukraina, ISBN 966-02-3244-6
- De Cordoba, G. & Caravaca, C. (2004). An electrochemical study of samarium ions in the molten eutectic LiCl+KCl, In: *Journal of Electroanalytical Chemistry*, Vol. 572, No. 1, (October 2004), pp. 145-151, ISSN 0022-0728
- De Cordoba, G.; Laplace, A.; Conocar, O.; Lacquement, G. & Caravaca, C. (2008). Determination of the activity coefficients of neodymium in liquid aluminum by potentiometric methods, In: *Electrochimica Acta*, Vol. 54, No. 2, (December 2008), pp. 280-288, ISSN 0013-4686
- Korshunov, B.G.; Safonov, V.V. & Drobot, D.V. (1979). *Phase equilibriums in halide systems*, Metallurgiya, Moscow, USSR
- Kuznetsov, S.A.; Hayashi, H.; Minato, K. & Gaune-Escard, M. (2006). Electrochemical transient techniques for determination of uranium and rare-earth metal separation coefficients in molten salts, In: *Electrochimica Acta*, Vol. 51, No. 12 (February 2006), pp. 2463-2470, ISSN 0013-4686
- Lebedev, V.A. (1993). *Selectivity of Liquid Metal Electrodes in Molten Halide*, Metallurgiya, ISBN 5-229-00962-4, Russia
- Novoselova, A. & Smolenski, V. (2010). Thermodynamic properties of thulium and ytterbium in molten caesium chloride, In: *Journal of Chemical Thermodynamics*, Vol. 42, No. 8, (August 2010), pp. 973-977, ISSN 0021-9614
- Novoselova, A. & Smolenski, V. (2011). Thermodynamic properties of thulium and ytterbium in fused NaCl-KCl-CsCl eutectic, In: *Journal of Chemical Thermodynamics*, Vol. 43, No. 7, (July 2011), pp. 1063-1067, ISSN 0021-9614
- Osipenko, A.; Maershin, A.; Smolenski, V.; Novoselova, A.; Kormilitsyn, M. & Bychkov, A. (2010). Electrochemistry of oxygen-free curium compounds in fused NaCl-2CsCl eutectic, In: *Journal of Nuclear Materials*, Vol. 396, No. 1, (January 2010), pp. 102-1067, ISSN 0022-3115
- Osipenko, A.; Maershin, A.; Smolenski, V.; Novoselova, A.; Kormilitsyn, M. & Bychkov, A. (2011). Electrochemical behaviour of curium (III) ions in fused 3LiCl-2KCl eutectic, In: *Journal of Electroanalytical Chemistry*, Vol. 651, No. 1, (January 2011), pp. 67-71, ISSN 0022-0728
- Roy, J.J.; Grantham, L.F.; Grimmer, D.L.; Fusselman, S.P.; Krueger, C.L.; Storvick, T.S.; Inoue, T.; Sakamura, Y. & Takahashi, N. (1996). Thermodynamic properties of U, Np, Pu, and Am in molten LiCl-KCl eutectic and liquid cadmium, In: *Journal of The Electrochemical Society*, Vol. 143, No. 8, (August 1996), pp. 2487-2492, ISSN 0013-4651
- Sakamura, Y.; Hijikata, T.; Kinoshita, K.; Inoue, T.; Storvick, T.S.; Krueger, C.L.; Roy, J.J.; Grimmer, D.L.; Fusselman, S.P. & Gay, R.L. (1998). Measurement of standard potentials of actinides (U, Np, Pu, Am) in LiCl-KCl eutectic salt and separation of

- actinides from rare earths by electrorefining, In: *Journal of Alloys and Compounds*, Vol. 271-273, (June 1998), pp. 592-596, ISSN 0925-8388
- Serp, J.; Konings, R.J.M.; Malmbeck, R.; Rebizant, J.; Scheppler, C. & Glatz, J-P. (2004). Electrochemical of plutonium ion in LiCl-KCl eutectic melts, In: *Journal of Electroanalytical Chemistry*, Vol. 561, (January 2004), pp. 143-148, ISSN 0022-0728
- Serp, J.; Allibert, M.; Terrier, A.L.; Malmbeck, R.; Ougier, M.; Rebizant, J. & Glatz, J-P. (2005). Electrochemical separation of actinides from lanthanides on solid aluminum electrode in LiCl-KCl eutectic melts, In: *Journal of The Electrochemical Society*, Vol. 152, No. 3, (March 2005), pp. C167-C172, ISSN 0013-4651
- Serp, J.; Lefebvre, P.; Malmbeck, R.; Rebizant, J.; Vallet, P. & Glatz, J-P. (2005). Separation of plutonium from lanthanum by electrolysis in LiCl-KCl onto molten bismuth electrode, In: *Journal of Nuclear Materials*, Vol. 340, No. 2-3, (April 2005), pp. 266-270, ISSN 0022-3115
- Serp, J.; Chamelot, P.; Fourcaudot, S.; Konings, R.J.M.; Malmbeck, R.; Pernel, C.; Poignet, J.C.; Rebizant, J. & Glatz, J-P. (2006). Electrochemical behavior of americium ions in LiCl-KCl eutectic melt, In: *Electrochimica Acta*, Vol. 51, No. 19, (May 2006), pp. 4024-4032, ISSN 0013-4686
- Serrano, K. & Taxil, P. (1999). Electrochemical nucleation of uranium in molten chlorides, In: *Journal of Applied Electrochemistry*, Vol. 29, No. 4, (April 1999), pp. 505-510, ISSN 0021-891X
- Shishkin, V.Yu. & Mityaev, V.S. (1982). Purification of alkali chloride metals by direct crystallization. In: Proceedings of the Academy of Sciences. *Journal of Inorganic materials*, Vol. 18, No. 11 (November 1982), pp. 1917-1918, ISSN 0002-337X
- Shirai, O.; Iizuka, M.; Iwai, T.; Suzuki, Y. & Arai, Y. (2000). Electrode reaction of plutonium at liquid cadmium in LiCl-KCl eutectic melts, In: *Journal of Electroanalytical Chemistry*, Vol. 490, No. 1-2, (August 2000), pp. 31-36, ISSN 0022-0728
- Smirnov, M.V. (1973). *Electrode Potentials in Molten Chlorides*, Nauka, Moscow, USSR
- Smolenski, V.; Novoselova, A.; Osipenko, A.; Caravaca, C. & de Cordoba, G. (2008). Electrochemistry of ytterbium(III) in molten alkali chlorides, In: *Electrochimica Acta*, Vol. 54, No. 2, (December 2008), pp. 382-387, ISSN 0013-4686
- Smolenski, V.; Novoselova, A.; Osipenko, A. & Kormilitsyn, M. (2009). The influence of electrode material nature on the mechanism of cathodic reduction of ytterbium (III) ions in fused NaCl-KCl-CsCl eutectic, In: *Journal of Electroanalytical Chemistry*, Vol. 633, No. 2, (August 2009), pp. 291-296, ISSN 0022-0728
- Uozumi, K.; Iizuka, M.; Kato, T.; Inoue, T.; Shirai, O.; Iwai, T. & Arai, Y. (2004). Electrochemical behaviors of uranium and plutonium at simultaneous recoveries into liquid cadmium cathodes, In: *Journal of Nuclear Materials*, Vol. 325, No. 1, (February 2004), pp. 34-43, ISSN 0022-3115
- Willit J. (2005). 7th International Symposium on Molten Salts Chemistry & Technology, *Proceeding of Overview and Status of Pyroprocessing Development at Argonne National Laboratory*, Toulouse, France, August 2005
- Yamana, H.; Fujii, T. & Shirai, O. (2003). UV/Vis Adsorption Spectrophotometry of some f-elements in Chloride Melt, *Proceeding of International Symposium on Ionic Liquids on Honor of Marcelle Gaune-Escard*, Carry le Rouet, France, June 2003

Recent Trend in Electrochemical Science and Technology

Edited by Dr. Ujjal Kumar Sur

ISBN 978-953-307-830-4

Hard cover, 306 pages

Publisher InTech

Published online 27, January, 2012

Published in print edition January, 2012

This book titled "Recent Trend in Electrochemical Science and Technology" contains a selection of chapters focused on advanced methods used in the research area of electrochemical science and technologies; descriptions of electrochemical systems; processing of novel materials and mechanisms relevant for their operation. This book provides an overview on some of the recent development in electrochemical science and technology. Particular emphasis is given both to the theoretical and the experimental aspect of modern electrochemistry. Since it was impossible to cover the rich diversity of electrochemical techniques and applications in a single issue, the focus is on the recent trends and achievements related to electrochemical science and technology.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Alexander Osipenko, Alexander Mayershin, Valeri Smolenski, Alena Novoselova and Michael Kormilitsyn (2012). Electrochemistry of Curium in Molten Chlorides, Recent Trend in Electrochemical Science and Technology, Dr. Ujjal Kumar Sur (Ed.), ISBN: 978-953-307-830-4, InTech, Available from: <http://www.intechopen.com/books/recent-trend-in-electrochemical-science-and-technology/electrochemistry-of-curium-in-molten-chlorides>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2012 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](https://creativecommons.org/licenses/by/3.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

IntechOpen

IntechOpen