We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Sintering and Properties of Nb₄AlC₃ Ceramic

Chunfeng Hu¹, Qing Huang¹,
Yiwang Bao² and Yanchun Zhou³

¹Ningbo Institute of Material Science and Technology,
Chinese Academy of Sciences, Ningbo

²State Key Laboratory of Green Building Materials,
China Building Materials Academy, Beijing

³Ceramic and Composites, Aerospace Research
Institute of Materials and Technology, Beijing,
China

1. Introduction

Layered ternary compounds, $M_{n+1}AX_n$ (where M is an early transition metal, A is an A group element, X is C or N, and $n = 1-3$), also called the MAX phases, are layered carbides or nitrides crystallizing with hexagonal symmetry structure [1,2]. These ceramics combine the characteristics of metals and ceramics such as high strength and modulus, low density, good electrical and thermal conductivity, easy machinability, damage tolerance, and resistance to thermal shock and high temperature oxidation. To date, more than 50 M_2AX compounds (not list for brevity), five M_3AX_2 compounds (Ti_3SiC_2 , Ti_3GeC_2 , Ti_3AlC_2 , Ta_3AlC_2 , and Ti_3SnC_2), and seven M_4AX_3 (Ta_4AlC_3 , Ti_4AlN_3 , Ti_4SiC_3 , Ti_4GeC_3 , Nb_4AlC_3 , V_4AlC_3 , and Ti_4GaC_3) were identified. For 413 phases, it has been determined that there are two kinds of atomic stacking sequences along [0001] direction. Ti_4AlN_3 , Ti_4SiC_3 , Ti_4GeC_3 , α - Ta_4AlC_3 , Nb_4AlC_3 , and V_4AlC_3 have the same Ti_4AlN_3 -type crystal structure with atomic arrangement of $AB\bar{A}BACBC\bar{B}C$ along [0001] direction. Only β - Ta_4AlC_3 was determined to have the $AB\bar{A}BABAB\bar{A}B$ atomic arrangement along [0001] direction. In detail, the difference of atomic arrangements between β - Ta_4AlC_3 and α - Ta_4AlC_3 lay in the diversity of atomic positions. The atomic positions of β - Ta_4AlC_3 were described as Ta1 at (4f) (1/3, 2/3, 0.05524), Ta2 at (4f) (2/3, 1/3, 0.16016), Al at (2c) (1/3, 2/3, 1/4), C1 at (2a) (0, 0, 0), and C2 at (4e) (0, 0, 0.11125). While, the atomic positions of α - Ta_4AlC_3 were determined as Ta1 at (4f) (1/3, 2/3, 0.05453), Ta2 at (4e) (0, 0, 0.15808), Al at (2c) (1/3, 2/3, 1/4), C1 at (2a) (0, 0, 0), and C2 at (4f) (2/3, 1/3, 0.10324).

Ti_4AlN_3 -type Nb_4AlC_3 was firstly discovered by heat treating Nb_2AlC at 1700°C, and the crystal structure was determined using a combined technique of *ab initio* calculation and high resolution scanning transmission electron microscopy. Additionally, the single phase Nb_4AlC_3 could be synthesized by hot pressing and spark plasma sintering. The microstructure, electrical, thermal, and mechanical properties of as-prepared Nb_4AlC_3 were systematically described.

2. Crystal structure

Figure 1 compares the projection of atoms (Figs. 1(a) and (b)) and the Z-contrast image of Nb_4AlC_3 (Fig. 1(c)), wherein the layer stacking sequence of Nb and Al atoms along the [0001] direction was directly shown. In one Nb-C slab, the number of Nb layers was four, i.e., the regular atomic arrangement was four Nb atoms layers per Al atoms layer alternately stacking along the [0001] direction. The Nb layers were separated by close packed Al atom (0001) planes. The Z-contrast image confirmed that the Nb_4AlC_3 crystallized in the Ti_4AlN_3 -type crystal structure. It basically consisted of two units: nonstoichiometric $\text{NbC}_{0.75}$ slab and Al atomic plane. The atom arrangement of Nb and Al was ABABACBCBC [3].

Fig. 1. (a) and (b) Atom arrangement of Nb_4AlC_3 . (c) High-resolution Z-contrasting TEM image after FFT filtering of Nb_4AlC_3 [3].

3. Hot pressing

3.1 Synthesis procedure

Commercial powders of niobium (99%, -200 mesh), aluminum (99%, -300 mesh), and graphite (99%, -200 mesh) were used as starting materials. Firstly, the molar ratio of Nb : Al : C = 4 : 1.3 : 2.7 was selected for investigating the reaction path of Nb_4AlC_3 . Excess Al and less graphite were used because Al might lose during high temperature processing and C-deficient existed in most of Al-containing MAX phases. The powders were dryly mixed in a resin jar, ball milled for 12 hours, and then sieved. The mixed powders were uniaxially pressed at 5 MPa to form the green compacts in a BN-coated graphite die. Afterwards, the green compacts were heated to 1500, 1550, 1600, 1650, and 1700°C, with a heating rate of 15°C/min in a flowing Ar atmosphere. The samples were held at target temperatures for 60 minutes under a pressure of 5 MPa, and then cooled down to room temperature with the furnace cooling rate. After composition optimization, single-phase dense Nb_4AlC_3 was

prepared using the starting materials with the molar ratio of Nb : Al : C = 4 : 1.1 : 2.7. The green compact was held at 1700°C for 60 minutes under a pressure of 30 MPa.

Temperature	Phase compositions
1500°C	NbC, Nb ₂ AlC, Nb ₄ AlC ₃ , C, Nb ₂ Al, Al ₃ Nb, Nb ₃ Al ₂ C
1550°C	NbC, Nb ₂ AlC, Nb ₄ AlC ₃ , Al ₃ Nb
1600°C	NbC, Nb ₂ AlC, Nb ₄ AlC ₃ , Al ₃ Nb
1650°C	Nb ₂ AlC, Nb ₄ AlC ₃ , Al ₃ Nb
1700°C	Nb ₄ AlC ₃ , Al ₃ Nb

Table 1. Phase compositions of the samples sintered at the temperatures range from 1500 to 1700°C [4].

Figure 2 shows the X-ray diffraction patterns of the samples sintered at 1500-1700°C using initial powders with the molar ratio of Nb : Al : C = 4 : 1.3 : 2.7. The identified phase compositions of the samples were listed in Table 1. At 1500°C, the phases in the sample were NbC, Nb₂AlC, Nb₄AlC₃, C, Nb₂Al, Al₃Nb, and Nb₃Al₂C (Fig. 2(a)). As the temperature was raised to 1550°C, only NbC, Nb₂AlC, Nb₄AlC₃, and Al₃Nb were detected in the sample (Fig. 2(b)). C, Nb₂Al, and Nb₃Al₂C were completely consumed. The formation of Nb₂AlC was probably associated with the reactions in equations (1) and (2):

When the temperature increased to 1600°C, the amount of Nb₄AlC₃ increased with the consumption of Nb₂AlC and NbC (Fig. 2(c)). Possibly, the reaction occurred as following:

When the temperature reached 1650°C, the diffraction peaks of NbC disappeared. The main crystalline phase was Nb₄AlC₃, together with small quantities of Nb₂AlC and Al₃Nb (Fig. 2(d)). When a higher temperature of 1700°C was used, the final sample contained only Nb₄AlC₃ and Al₃Nb (Fig. 2(e)). All diffraction peaks of Nb₂AlC disappeared. The decomposition reaction could be described as:

Figure 3 shows the X-ray diffraction pattern of single phase Nb₄AlC₃. All the diffraction peaks corresponded to Nb₄AlC₃. The crystal structure of Nb₄AlC₃ prepared by the present method was Ti₄AlN₃-type. No impurity phases were detected.

www.intechopen.com

3.2 Microstructure

The etched surface of Nb₄AlC₃ was shown in Fig. 4. Plate-like Nb₄AlC₃ grains distributed irregularly with a few equiaxed grains. The average grain size of Nb₄AlC₃ was 50 μm in length and 17 μm in width.

Fig. 4. Scanning electron microscope (SEM) micrograph of etched surface of Nb₄AlC₃ [4].

3.3 Properties evaluation

Fig. 5. Temperature dependences of electrical conductivity and electrical resistivity of Nb₄AlC₃ [4].

Figure 5 shows the electrical conductivity and electrical resistivity of Nb₄AlC₃ in the temperature range of 5-300 K. With the increasing temperature, the electrical conductivity of Nb₄AlC₃ decreased from $3.35 \times 10^6 \text{ } \Omega^{-1} \text{ m}^{-1}$ to $1.33 \times 10^6 \text{ } \Omega^{-1} \text{ m}^{-1}$. The electrical resistivity of Nb₄AlC₃ increased linearly above 50 K, indicating a metallic characteristic. Fitting the resistivity in the temperature range from 50 to 300 K, the temperature dependence of electrical resistivity was obtained with a coefficient of determination, r^2 , of 0.99:

$$\rho(\mu\Omega \cdot m) = \rho_0(1 - \beta\Delta T) = 7.133[1 - 0.0025(273.15 - T)] \tag{5}$$

where ρ_0 was the electrical resistivity at 273.15 K ($\mu\Omega\text{ m}$), T the absolute temperature (K), and β the temperature coefficient of resistivity (K^{-1}). The temperature coefficient of resistivity was 0.0025 K^{-1} .

The thermal expansion coefficient of Nb_4AlC_3 was measured as $7.2 \times 10^{-6}\text{ K}^{-1}$ in the temperature range of 200-1100°C. Figure 6 shows the temperature dependences of molar heat capacity and thermal conductivity of Nb_4AlC_3 . The molar heat capacity increased linearly with increment of temperature, which fitted a third-order polynomial. The molar heat capacity of Nb_4AlC_3 approached to a plateau above 1227°C. At room temperature, the molar heat capacity of Nb_4AlC_3 was determined as $158\text{ J}\cdot(\text{mol}\cdot\text{K})^{-1}$. A least square fitting the temperature dependence of thermal conductivity for Nb_4AlC_3 was described as:

$$\lambda = 11.6 + 0.0064T$$

(6)

with r^2 of 0.99. At 25°C, the thermal conductivity of Nb_4AlC_3 was deduced to $13.5\text{ W}\cdot(\text{m}\cdot\text{K})^{-1}$. Up to 1227°C, the thermal conductivity of Nb_4AlC_3 increased to $21.2\text{ W}\cdot(\text{m}\cdot\text{K})^{-1}$. The total thermal conductivity was associated with both the electron and phonon contributions:

$$\lambda_{\text{total}} = \lambda_{\text{electron}} + \lambda_{\text{phonon}}$$

(7)

in which $\lambda_{\text{electron}} = L_0\sigma T$ (Wiedmann-Franz Law), where σ was the electrical conductivity at the selected temperature T , and $L_0 = 2.45 \times 10^{-8}\text{ W}\cdot\Omega\cdot\text{K}^{-2}$. At room temperature, the calculated result was $9.6\text{ W}\cdot(\text{m}\cdot\text{K})^{-1}$, about 71% of total thermal conductivity. Therefore, the electrons mainly contributed to the conductivity at 25°C.

Fig. 6. Temperature dependences of molar heat capacity and thermal conductivity of Nb_4AlC_3 [4].

Figure 7 shows the indentation load dependence of Vickers hardness of Nb_4AlC_3 . The insets were the Vickers indentation on the polished surface of Nb_4AlC_3 under a load of 10 N. With increasing load from 3 to 200 N, the hardness gradually decreased from 6.2 to 2.6 GPa. At a

lower load, the bigger scatter was seen due to the anisotropic nature of grains. Above 50 N, the hardness value converged to 2.6 GPa. Therefore, the intrinsic hardness of Nb_4AlC_3 was 2.6 GPa. The morphology of the indent produced by a load of 10 N showed that no cracks initiated and propagated from the diagonals, and the material was pushed out around the indent (Fig. 7(a)). The microscale plasticity was associated with intragrain multiple basal-plane slips between microlamellae, intergrain sliding, lamellae or grain push out, and microfailures at the ends of the constrained shear-slips (Fig. 7(b)). In addition, the zigzag crack propagation was observed in an individual Nb_4AlC_3 grain (Fig. 7(c)). Additionally, the measured shear strength of Nb_4AlC_3 was 116 MPa. The low shear strength implied good damage tolerance and easy machinability of Nb_4AlC_3 .

Fig. 7. Vickers hardness of Nb_4AlC_3 as a function of indentation loads. The insets show (a) push-out, (b) delamination, kink, and basal plane slips, and (c) zigzag crack propagation in a grain in an indent under a load of 10 N [4].

Figure 8(a) shows the temperature dependences of normalized Young's moduli of Nb_4AlC_3 , Nb_2AlC , $\beta\text{-Ta}_4\text{AlC}_3$, and Ta_2AlC . The temperature dependences of mechanical damping, Q^{-1} , of Nb_4AlC_3 , Nb_2AlC , $\beta\text{-Ta}_4\text{AlC}_3$, and Ta_2AlC were shown in Fig. 8(b). Below 1400°C, a slight linear decrease of Young's modulus of Nb_4AlC_3 was observed with increasing temperature. Whereas, a break was seen at a temperature between 1400 and 1500°C. Similar turning points were also observed at 1200-1300°C for Nb_2AlC , 800-900°C for $\beta\text{-Ta}_4\text{AlC}_3$, and 800-900°C for Ta_2AlC (Fig. 8(a)). Corresponding to the accelerated decrease of Young's modulus, the mechanical damping of Nb_4AlC_3 also started to increase at 1400°C (Fig. 8(b)). Above 1500°C, more rapid decrease of Young's modulus of Nb_4AlC_3 was observed with increasing temperature. The rapid decrease of Young's modulus started at 1300°C, 900°C, and 900°C, respectively, for Nb_2AlC , $\beta\text{-Ta}_4\text{AlC}_3$, and Ta_2AlC . The higher critical temperature for the rapid decrease of Young's modulus of Nb_4AlC_3 indicated that this material could be used at much higher temperatures. The Young's modulus of Nb_4AlC_3 could retain up to 1580°C with a loss of 21%. The modulus loss of Nb_4AlC_3 was 16% at 1400°C and 21% at 1580°C (Fig.

8(a)). Therefore, the flexural strength of Nb_4AlC_3 might still possess a high value up to 1580°C . Figure 9 displays the temperature dependence of flexural strength for Nb_4AlC_3 . Obviously, the flexural strength of Nb_4AlC_3 could retain up to 1400°C without any degradation.

Fig. 8. Temperature dependences of (a) normalized Young’s moduli and (b) mechanical damping, Q^{-1} , of Nb_4AlC_3 , Nb_2AlC , $\beta\text{-Ta}_4\text{AlC}_3$, and Ta_2AlC [4].

Fig. 9. Temperature dependent flexural strength of Nb_4AlC_3 and $\beta\text{-Ta}_4\text{AlC}_3$ [4].

4. Spark plasma sintering

4.1 Synthesis procedure

Commercial powders of niobium (45 μm , 99.9%), aluminum (30 μm , 99.9%), and carbon black (20 nm, 99%) were used for investigating the synthesis of Nb_4AlC_3 using the SPS technique. For investigating the reaction path, niobium, aluminum, and carbon black powders with a molar ratio of 4 : 1.5 : 2.7 were weighed using an electrical balance with an accuracy of 10^{-2} g. The powders were put into an agate jar and milled for 12 hours using

ethanol as the dispersant. After milling, the mixed powders were dried in air and sieved using a 100 mesh sieve. The obtained mixture was put into a graphite die with a diameter of 20 mm. A layer of carbon sheet (~0.2 mm thickness) was put in the inner of die for lubrication. A layer of heat isolation carbon fiber was used to wrap the die for inhibiting the rapid heat diffusion. The mixture was firstly cold pressed as a compact green. Then the green together with the die was heated in a spark plasma sintering facility (100 kN SPS-1050, Syntex Inc., Japan). The sintering temperature was measured by an optical pyrometer focusing on a hole in the wall of die. From ambient temperature to 700°C, it took 5 minutes to heat the sample. Between 700 and 1400°C, a heating speed of 50°C/min was adopted. Above 1400°C, the heating speed was set as 10°C/min. The annealing temperatures were selected as 800, 1000, 1200, 1400, and 1600°C, respectively. The vacuum degree was 7-10 Pa. The holding time was 2 minutes.

Fig. 10. XRD patterns of samples sintered at different temperatures using Nb, Al, and carbon black mixture powders with the molar ratio of 4 : 1.5 : 2.7: (a) ambient temperature, (b) 800°C, (c) 1000°C, (d) 1200°C, (e) 1400°C, and (f) 1600°C [5].

Figure 10 shows XRD patterns of samples sintered from ambient temperature to 1600°C using Nb, Al, and carbon black mixture powders with the molar ratio of 4 : 1.5 : 2.7. The XRD data of initial mixture powder was shown in Fig. 10(a). Carbon black could not be detected, which might be due to the fine structure. When the temperature was increased to 800°C, Al₃Nb was detected in the sample by XRD (Fig. 10(b)). The melting point of aluminum was 660°C, which meant that the melting aluminum probably combined niobium to form Al₃Nb during the heating process:

When increasing the temperature up to 1000°C, Nb₂Al and Nb₂C appeared in the sample with the consumption of Al₃Nb (Fig. 10(c)). The reaction could be possibly described as:

Additionally, Nb₂C was formed due to the reaction between Nb and carbon black:

As temperature increased to 1200°C, the diffraction analysis showed that new phases of NbC and Nb₂AlC became the main phases in the sintered sample (Fig. 10(d)). The amounts of Nb₂Al and Nb₂C also increased with the consumption of Nb, Al, and Al₃Nb. Probably, the formation of NbC was ascribed to the reaction:

Nb₂AlC was probably formed due to the reaction between Nb₂Al and carbon black. The reaction equation was described as:

When the temperature increased up to 1400-1600°C, the existed phases in the samples were only NbC, Nb₂AlC, and Nb₄AlC₃. In hot pressing, it was found that Nb₃Al₂C existed in the sample sintered by hot pressing at 1500°C. Due to the initial composition difference (Nb : Al : C = 4 : 1.3 : 2.7), it might be due to the kinetics of phase formation. At 1400°C, Nb₄AlC₃ was detected in the prepared sample (Fig. 10(e)). Probably, it was ascribed to the following two equations:

and

It was supposed that carbon black has been completely consumed at this temperature. When the temperature rose to 1600°C, Nb₄AlC₃ became the main phase with the consumption of Nb₂AlC and NbC (Fig. 10(f)).

In order to get single phase Nb₄AlC₃, the sintering temperature was further increased. Figure 11 shows the effect of annealing temperatures on the synthesis of Nb₄AlC₃. When the annealing temperature was 1620°C, only Nb₄AlC₃ and Nb₂AlC could be detected in the sample (Fig. 11(a)). NbC has been completely consumed during the reaction process (Eq. (14)). When increasing the temperature as 1650°C, less Nb₂AlC could be detected in the sample by XRD (Fig. 11(b)). However, Al₃Nb appeared again:

When the annealing temperature was increased up to 1665°C, more Al₃Nb was formed and a small quantity of NbC also appeared in the sample (Fig. 11(c)). NbC was from the decomposition of Nb₄AlC₃ due to the loss of Al. Up to 1680°C, the amount of NbC increased and Al₃Nb disappeared in the sample (Fig. 11(d)). The optimized annealing temperature in present work was 1650°C.

Fig. 11. Effect of annealing temperature on the synthesis of Nb₄AlC₃: (a) 1620°C, (b) 1650°C, (c) 1665°C, and (d) 1680°C [5].

In order to investigate the effect of initial composition on the synthesis of Nb₄AlC₃, the initial mixture powders with different molar ratios of Nb : Al : C = 4 : 1.1 : 2.7, 4 : 1.3 : 2.7, 4 : 1.4 : 2.7, and 4 : 1.5 : 2.7 were selected and sintered at the optimized temperature of 1650°C. Figure 12 shows the XRD patterns of sintered samples. With the increasing Al content in the initial compositions, the amount of NbC in the sample decreased continuously (Figs. 12(a)-(d)). The optimized composition for synthesizing Nb₄AlC₃ by hot pressing in a flowing argon atmosphere was Nb : Al : C = 4 : 1.1 : 2.7. Because of the high vacuum level in SPS furnace (7-10 Pa), Al element was easier to evaporate at high temperature. Therefore, more Al element was added into the compositions. When the initial composition of Nb : Al : C = 4 : 1.5 : 2.7 was used for preparing Nb₄AlC₃, there were only a small quantity of Nb₂AlC and a trace of Al₃Nb existing in the sample. Therefore, the optimized composition was selected as 4 : 1.5 : 2.7. Additionally, it was hoped to eliminate the impurities of Nb₂AlC and Al₃Nb by modifying the holding time. However, when prolonging the holding time from 2 to 4 minutes, though Al₃Nb has disappeared, a plenty of NbC appeared in the sample and Nb₂AlC couldn't be removed, as shown in Fig. 13. Therefore, the optimized holding time in present work was 2 minutes.

Based on the above investigations, the optimized parameters were used to synthesize dense bulk Nb₄AlC₃. Figure 14 shows the X-ray diffraction pattern of as-prepared Nb₄AlC₃. The

primary phase was Nb₄AlC₃ and a few amount of Nb₂AlC and Al₃Nb existed in the sample. The impurities of Nb₂AlC and Al₃Nb were less than 6 wt%.

Fig. 12. Effect of initial element compositions (molar ratio of Nb, Al, and C) on the synthesis of Nb₄AlC₃: (a) 4 : 1.1 : 2.7, (b) 4 : 1.3 : 2.7, (c) 4 : 1.4 : 2.7, and (d) 4 : 1.5 : 2.7 [5].

Fig. 13. Effect of holding time on the synthesis of Nb₄AlC₃: (a) 2 minutes and (b) 4 minutes [5].

Fig. 14. XRD pattern of dense Nb₄AlC₃ synthesized using the optimized parameters under a pressure of 30 MPa [5].

4.2 Microstructure

Figure 15 shows the etched surface and fracture surface of Nb₄AlC₃. Laminar grains could be clearly observed in the etched surface. The growth of grain did not show the preferable direction, i.e., textured microstructure. The mean grain size was determined as 21 μm in length and 9 μm in width. In the fracture surface, Nb₄AlC₃ grains exhibited the multiplex damage modes, such as transgranular fracture, intergranular fracture, kink bands, and delaminations.

Fig. 15. SEM micrographs of (a) etched surface and (b) fracture surface of dense Nb₄AlC₃ sample [5].

4.3 Properties evaluation

The thermal expansion and technical thermal expansion coefficient of Nb₄AlC₃ sample were shown in Fig. 16. With increasing temperature, the thermal expansion of Nb₄AlC₃ showed the linear change. Fitting the thermal expansion in the temperature range from -128 to 282°C, the temperature dependence of thermal expansion was obtained with a coefficient of determination, *r*², of 0.99:

$$\frac{\Delta L}{L_0} = -0.18204 + 6.5483 \times 10^{-4} T$$

(16)

in which Δ*L* (m) was the length change at temperature *T* (K), and *L*₀ (m) was the length of sample at 5°C (initial room temperature). The technical thermal expansion coefficient, α_{tech.} (K⁻¹), was defined as:

$$\alpha_{tech.} = \frac{1}{L_{145K}} \frac{\Delta L_K - \Delta L_{145K}}{T_K - 145}$$

(17)

in which *L*_{145K} (m) was the length of sample at -128°C, Δ*L*_{145K} (m) the length change at -128°C, and Δ*L*_{*K*} (m) the length change at temperature *T*_{*K*} (K). The calculated thermal expansion coefficient at 282°C was 6.7 × 10⁻⁶ K⁻¹. The technical thermal expansion coefficient of Nb₄AlC₃ increased from -128 to about -73°C rapidly, which might be attributed to the nonlinear increase of instrument temperature. Above -73°C, the technical thermal expansion coefficient approached a constant.

Fig. 16. Temperature dependence of thermal expansion and technical thermal expansion coefficient of Nb₄AlC₃ in a temperature range of -128 and 282°C [5].

Figure 17 shows the temperature dependent electrical conductivity and electrical resistivity of Nb₄AlC₃ in a temperature range of 25-827°C. With increasing temperature, the electrical conductivity decreased corresponding to the increase of electrical resistivity. The measured electrical conductivity of Nb₄AlC₃ at 25°C was $2.25 \times 10^6 \text{ } \Omega^{-1} \text{ m}^{-1}$, higher than that of hot pressed sample ($1.33 \times 10^6 \text{ } \Omega^{-1} \text{ m}^{-1}$), which might be due to the existence of Nb₂AlC ($3.45 \times 10^6 \text{ } \Omega^{-1} \text{ m}^{-1}$) and Al₃Nb. The electrical resistivity of Nb₄AlC₃ increased with a linear rule below 300°C. Fitting the electrical resistivity in the temperature range of 25-300°C, the temperature dependent resistivity could be obtained with a determination coefficient of 0.99:

$$\rho(\mu\Omega \cdot m) = \rho_0(1 - \beta\Delta T) = 0.44371[1 - 0.003048(298 - T)]$$

(18)

in which ρ_0 was the electrical resistivity at 298 K ($\mu\Omega \cdot m$), T the absolute temperature (K), and β the temperature coefficient of resistivity (K^{-1}). However, the temperature dependent electrical resistivity showed the nonlinear increase above 300°C with the increment of temperature. At 827°C, Nb₄AlC₃ still had a high electrical conductivity of $0.76 \times 10^6 \text{ } \Omega^{-1} \text{ m}^{-1}$, indicating the excellent high temperature conductive capability.

Fig. 17. Temperature dependence of electrical conductivity of Nb₄AlC₃ in a temperature range of ambient temperature and 827°C [5].

The measured Vickers hardness of as-prepared Nb_4AlC_3 was 3.7 GPa, which was close to the value of hot pressed Nb_4AlC_3 . Figure 18 displays the three cycles load versus depth-of-microindentation of one Nb_4AlC_3 grain whose basal plane was perpendicular to the surface. Inset was the loops of single cycle indentation on both perpendicular (PE) and parallel (PA) directions, in comparison with that of ZrB_2 . The three indentation cycles were all open without reversibility. However, the open scope, i.e., loop area, was decreasing with more cycles, which showed the slight harder behavior. Additionally, the indentation responses were different along PA and PE directions. Obviously, the indentation depth and loop area along PA direction were larger than those along PE direction. It was easier to form kink bands along PA direction because the top surface was unconstrained. Pop-in appeared during the indentation when along PE direction, which was probably due to the delaminations between basal planes. In comparison with the hexagonal ZrB_2 , the smaller elastic recovery indicated the more effective energy dispersive capability.

Fig. 18. Typical load vs. depth of indentation response of one Nb_4AlC_3 grain whose basal plane is perpendicular to the surface. Inset is the loops of single indentation on both perpendicular (PE) and parallel (PA) directions, in comparison with that of ZrB_2 (hexagonal structure) [5].

The ambient flexural strength of Nb₄AlC₃ was tested as 455 MPa, higher than that of hot pressed Nb₄AlC₃ (346 MPa), which might be ascribed to the finer grain size. When the samples were tested at 1000 and 1400°C, the flexural strength of Nb₄AlC₃ were 297 and 230 MPa, respectively. The decrease of flexural strength might be ascribed to the existence of Al₃Nb in the samples, which caused the plasticity deformation of bars at high temperatures.

5. Summary

In this chapter, bulk Nb₄AlC₃ ceramic was prepared by an *in situ* reaction/hot pressing method and spark plasma sintering using Nb, Al, and carbon as the starting materials. The reaction path was investigated. Additionally, it was found that when different sintering methods were adopted the final properties of ceramic were different. *Hot pressing*: The thermal expansion coefficient was determined as $7.2 \times 10^{-6} \text{ K}^{-1}$ in the temperature range of 200–1100°C. The thermal conductivity of Nb₄AlC₃ increased from $13.5 \text{ W} \cdot (\text{m} \cdot \text{K})^{-1}$ at room temperature to $21.2 \text{ W} \cdot (\text{m} \cdot \text{K})^{-1}$ at 1227°C, and the electrical conductivity decreased from 3.35×10^6 to $1.13 \times 10^6 \text{ } \Omega^{-1} \cdot \text{m}^{-1}$ in a temperature range of 5–300 K. Nb₄AlC₃ possessed a low hardness of 2.6 GPa and high flexural strength of 346 MPa. Most significantly, Nb₄AlC₃ could retain high modulus and strength up to very high temperatures. The Young's modulus at 1580°C was 241 GPa (79% of that at room temperature), and the flexural strength could retain the ambient strength value without any degradation up to the maximum measured temperature of 1400°C. *Spark plasma sintering*: The coefficient of thermal expansion was measured as $6.7 \times 10^{-6} \text{ K}^{-1}$ from -128 to 282°C. The electrical conductivity was tested as $0.76 \times 10^6 \text{ } \Omega^{-1} \cdot \text{m}^{-1}$ at 827°C, showing excellent high temperature conductivity. The Vickers hardness and flexural strength were measured as 3.7 GPa and 455 MPa, respectively. The micro-indentation evaluation indicated the anisotropic response of Nb₄AlC₃ grains, reflecting the anisotropic crystal structure. Additionally, the flexural strength could remain a high value of 230 MPa up to 1400°C.

Acknowledgements: This work is supported by the “Chunlei” program in Ningbo Institute of Material Technology and Engineering in China.

6. References

- [1] H. Nowotny, “Strukturchemie einiger Verbindungen der Übergangsmetalle mit den Elementen C, Si, Ge, Sn,” *Prog. Solid State Chem.*, 2, 27 (1970).
- [2] M. W. Barsoum, “The M_{N+1}AX_N Phases: A New Class of Solids; Thermodynamically Stable Nanolaminates,” *Prog. Solid State Chem.*, 28, 201–81 (2000).
- [3] C. F. Hu, F. Z. Li, J. Zhang, J. M. Wang, J. Y. Wang, and Y. C. Zhou, “Nb₄AlC₃: A New Compound Belonging to the MAX Phases,” *Scripta Mater.*, 57, 893–6 (2007).
- [4] C. F. Hu, F. Z. Li, L. F. He, M. Y. Liu, J. Zhang, J. M. Wang, Y. W. Bao, J. Y. Wang, and Y. C. Zhou, “*In Situ* Reaction Synthesis, Electrical and Thermal, and Mechanical Properties of Nb₄AlC₃,” *J. Am. Ceram. Soc.*, 91, 2258–63 (2008).

- [5] C. F. Hu, Y. Sakka, H. Tanaka, T. Nishimura, and S. Grasso, "Low Temperature Thermal Expansion, High Temperature Electrical Conductivity, and Mechanical Properties of Nb_4AlC_3 Ceramic Synthesized by Spark Plasma Sintering," *J. Alloys Compd.*, 487, 675-81 (2009).

IntechOpen

IntechOpen

Sintering of Ceramics - New Emerging Techniques

Edited by Dr. Arunachalam Lakshmanan

ISBN 978-953-51-0017-1

Hard cover, 610 pages

Publisher InTech

Published online 02, March, 2012

Published in print edition March, 2012

The chapters covered in this book include emerging new techniques on sintering. Major experts in this field contributed to this book and presented their research. Topics covered in this publication include Spark plasma sintering, Magnetic Pulsed compaction, Low Temperature Co-fired Ceramic technology for the preparation of 3-dimesinal circuits, Microwave sintering of thermistor ceramics, Synthesis of Bio-compatible ceramics, Sintering of Rare Earth Doped Bismuth Titanate Ceramics prepared by Soft Combustion, nanostructured ceramics, alternative solid-state reaction routes yielding densified bulk ceramics and nanopowders, Sintering of intermetallic superconductors such as MgB_2 , impurity doping in luminescence phosphors synthesized using soft techniques, etc. Other advanced sintering techniques such as radiation thermal sintering for the manufacture of thin film solid oxide fuel cells are also described.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Chunfeng Hu, Qing Huang, Yiwang Bao and Yanchun Zhou (2012). Sintering and Properties of Nb_4AlC_3 Ceramic, Sintering of Ceramics - New Emerging Techniques, Dr. Arunachalam Lakshmanan (Ed.), ISBN: 978-953-51-0017-1, InTech, Available from: <http://www.intechopen.com/books/sintering-of-ceramics-new-emerging-techniques/synthesis-and-properties-of-nb4alc3-ceramic-fabricated-by-hot-pressing-and-spark-plasma-sintering>

INTech
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2012 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](https://creativecommons.org/licenses/by/3.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

IntechOpen

IntechOpen