

We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,900

Open access books available

185,000

International authors and editors

200M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com



TiO₂ Applications as a Function of Controlled Surface Treatment

Nika Veronovski

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/intechopen.72945>

Abstract

For the end use, the structure and morphology of the coated film are very important since they determine the final properties of the resultant material. The effect of coatings largely depends on their composition and method of application, which may give porous or dense coatings. To achieve uniform coatings on dispersed TiO₂ particles, various compounds were deposited one after another under specific conditions by the wet chemical deposition method starting from rutile TiO₂, produced by the sulfate method in Cinkarna Celje. With the synthesis of composite particles consisting of a core TiO₂ particle coated with a functional shell with dimensions in the nano scale, we prepared advanced materials, where the shell protects the particles from undesirable interactions with the environment and improves surface reactive properties of the dispersed particles to meet special requirements. The morphology of surface-treated TiO₂ particles has been identified directly using electron microscopy, while the degree of functionalization by various hydroxides was determined using X-ray fluorescence spectrometer (XRF). In addition, zeta potential (ZP) measurements have been utilized to determine the electrochemical properties of resultant particles. The precipitation of hydroxides on the TiO₂ surface resulted in the shift of the isoelectric point (IEP). UV-Vis spectroscopy has been used for determining light scattering efficiency. In addition to internal characterization, light fastness of durable grade intended for the application in laminates has been tested by the end user.

Keywords: TiO₂, pigment, surface treatment

1. Introduction

Titanium dioxide (TiO₂) is used in a variety of applications, all of which have different sets of performance requirements. As a result, the pigments designed for the various applications

are different. Variations in crystal structure (anatase/rutile), inorganic coating and organic treatments provide a wide range of titanium dioxide grades, each with different properties.

Generally, the properties of a pigment are determined by the particle size distribution of the base pigment, the chemical composition and the morphology of the surface treatment. The morphology of the treatment layers can, in turn, have an effect on the final properties of the pigment.

TiO₂ pigments are generally coated to improve their performance in many end-use applications. Thus, the pH, temperature, reagents, order of addition and other factors can affect product characteristics. Optimum treatment conditions need to be determined after the surface treatment chemicals have been selected [1].

There are differences between grades, partially based on the fact that TiO₂ particle surfaces may be modified differently with inorganic and organic post treatments. With regard to colloidal chemistry, a TiO₂ with an Al₂O₃ surface treatment behaves completely different from one having a SiO₂ surface treatment [2]. Both of these, again, are different from a pure, untreated TiO₂, which has its IEP at pH values between 4.5 and 6.5.

Surface treatment of TiO₂ particles by colorless inorganic compounds of low solubility affects dispersibility of the pigments in the matrix and weather resistance and lightfastness of the pigmented organic matrix [3].

These treatments are most commonly precipitated in layers. However, some of the components can be co-precipitated to alter the pigment characteristics [1]. There are many works regarding this subject in literature [4–14].

Inorganic surface treatment influences optical performance of the pigment approximately in proportion to the decrease in the TiO₂ content. Surface coatings prevent direct contact between the binder matrix and the reactive surface of the TiO₂. The treatment process also affects dispersibility of the pigment, and therefore a compromise often has to be made. High weather resistance and good dispersibility of the pigment in the binder or matrix are usually desired. These effects are controlled by using different coating densities and porosities. In addition, organic substances can be added during the final milling of the dried pigment [3].

Several types of treatment are known:

- Deposition from the gas phase by hydrolysis or decomposition of volatile substances.
- Addition of oxides, hydroxides or substances that can be absorbed onto the surface during pigment grinding, which results in partial coating of the pigment surface.
- Precipitation of the coating from aqueous solution onto the suspended TiO₂ particles by batch processes in stirred tanks starting from various compounds, which are deposited one after another under specific conditions. The most common are oxides, oxide hydrates, silicates and/or phosphates of titanium, zirconium, silicon and aluminum.

Typical groups of inorganic coatings are as follows:

1. Pigments with dense surface coatings for paints or plastic made by

- Homogeneous precipitation of SiO₂ with precise control of temperature, pH and precipitation rate.

- After-treatment with Zr, Ti, Al and Si compounds.
 - After-treatment with merely 1–3% of alumina [15–18].
2. Pigments with porous coating for use in emulsion paints obtained by simple treatment with Ti, Al and Si compounds, giving a silica content of 10% and a TiO₂ content of 80–85%.
 3. Lightfast pigments with dense surface coatings for the paper laminate industry that have a highly stabilized lattice and a surface coating based on silicates or phosphates of titanium, zirconium and aluminum: cca. 90% TiO₂.

For coloring of plastics, usually smaller TiO₂ particles are used with typically less than 3% of inorganic coating (TiO₂ typically >95%).

Before micronizing the pigment in a jet-mill and sometimes also before drying, the pigment surface is further modified by adding organic substances to improve dispersibility and facilitate further processing. The nature of the compounds used depends on the intended use of the pigment [3].

1.1. About TiO₂

1.1.1. Pigment properties

Scattering power, hiding power (tinting strength), brightness, mass tone (or color), gloss formation, gloss haze, dispersibility, lightfastness and weather resistance are the most important pigment properties of TiO₂ pigments; these properties are a function of chemical purity, lattice stabilization, primary particle size, particle size distribution and the coating.

TiO₂'s theoretical optimum particle size is between 0.2 and 0.3 μm, but the pigment obtained is considerably larger mainly because of the formation of agglomerates while handling during the manufacturing process. The presence of agglomerates affects hiding power, tinting strength and other end-use properties of the coating. The graph in **Figure 1** illustrates the effect of TiO₂'s dispersion states vs. particle size distribution on pigment properties. A well-dispersed system helps to develop coatings with improved optical properties, hiding power, tinting strength and gloss.

1.1.2. Uses of TiO₂

Titanium dioxide pigment (TiO₂) is an important material used in many applications due to its opacity, high chemical stability, excellent whiteness and brightness. It is required in applications such as the following:

- paints and coatings
- printing inks
- plastics
- paper




Figure 1. TiO_2 dispersion states as a function of particle size distribution.

1.1.3. Stability towards light and weather

When subjected to intense radiation or weathering, systems with incorporated TiO_2 show color or structural changes. Yellowing, chalking and loss of gloss occur due to photocatalytic activity of TiO_2 . Formation of extremely reactive radicals (OH , HO_2), that cause deterioration of the coating matrix can be suppressed by doping or coating the surface of the pigment [3, 19–21].

1.2. About surface treatment

1.2.1. Silica

Rutile TiO_2 particles must be coated with protective layers of SiO_2 and Al_2O_3 through wet chemistry processes in order to decrease their photoactivity, increase weather durability and increase dispersibility in certain media [4, 22–24]. The morphology of the SiO_2 coating layers on the surface of TiO_2 powders can be controlled by adjusting the reaction temperature, pH value of the reaction solution and the SiO_2 loading [4].

Depending on the silica precipitation conditions, very disparate pigment characteristics could be produced. “Fluffy” coating, which provides better spacing and optical efficiency, increases oil absorption and decreases gloss forms at acidic or neutral pH [1]. An example of a “fluffy” coating composed of submicroscopic particles joined together in a gel-like structure is presented in **Figure 2**.

During slow deposition at basic pH, silica can also be formed as a dense, glassy shell that encapsulates the particle and provides the highest durability available. Durability of the silica layer and the amount of energy needed to develop gloss are proportional to the amount of silica in the layer [1]. A dense, glass-like coating is shown in **Figure 3**. Coating is a few nm thick, encapsulating the entire surface of the pigment.

Island-like SiO_2 coating layers can be formed on a TiO_2 surface when the reaction temperature, the pH value and the mole ratio of Na_2SiO_3 to TiO_2 are low. Continuous and uniform SiO_2 coating layers form in an alkaline pH ranging from 9 to 10. The thickness of the coating




Figure 2. Silica surface treatment as a fluffy layer.

layer increases with the increase of the mole ratio of Na₂SiO₃ to TiO₂. The SiO₂ coating layers are anchored onto the TiO₂ surface by the Ti—O—Si bonding. Dispersibility of the SiO₂-coated TiO₂ powders is affected by the morphology of the SiO₂ coating [4].

1.2.2. Coating process of the SiO₂ layer

Isoelectric point (IEP) of rutile TiO₂ is usually located around pH 3.5 [24, 25]. The rutile TiO₂ surface is negatively charged under conditions where the pH value of the reaction solution is greater or equal to 7. Under conditions where pH values of the reaction solutions are in the range 7–8, Na₂SiO₃ rapidly hydrolyzes to form a large number of siliceous micelles. The resultant siliceous micelles anchor on the surface of TiO₂ powders via Ti—O—Si bonding to obtain island-like coating layers.

The hydrolysis rate of Na₂SiO₃ should be lowered by increasing the pH value to 9–10. This results in the formation of small-sized or less aggregated siliceous micelles. Small-sized micelles anchor on the surface of TiO₂ powders initially via Ti—O—Si bonding. Later, the micelles present in the solution and the anchored micelles condense via Si—O—Si bonding resulting in the formation of continuous and uniform coating layers. Over pH 10.5, silicon




Figure 3. Silica surface treatment as a dense, glass-like layer.

species exist as single silicate anions, or less aggregated siliceous micelles with very small particle size, which should be more negatively charged. The single silicate anions and the highly negatively charged siliceous micelles do not react with the negatively charged TiO_2 surface due to the strong electrostatic repulsion. Therefore, no SiO_2 coating layers forms on the TiO_2 surface at this high pH value.

Raising the temperature of the reaction affects the covering extent and causes the formation of a dense SiO_2 coating layer on the surface of the rutile TiO_2 powder.

1.2.3. Alumina

Hydrous aluminum oxide is probably the most common treatment agent of TiO_2 pigments. Various reagents can be used for deposition, e.g., sodium aluminate, which reacts with acid (see **Figure 4**), or aluminum sulfate, which reacts with base (see **Figure 5**).

Alumina can also be deposited from a combination of sodium aluminate and aluminum sulfate, which neutralize each other (**Figure 6**).

Irrespective of the reagent used, under controlled conditions of surface treatment, a thin, even layer, which entirely encapsulate the surface of TiO_2 is formed.

1.2.4. Coating process of the Al_2O_3 layer

By coating the surface of TiO_2 uniformly with alumina, coated particles behave in some ways similar to pure alumina. Alumina coating increase the amount of $-\text{OH}$ groups on particle surface and consequently improve dispersibility of particles in aqueous solution and provide more active sites for further organic modification [24].

The level of alumina depends on the gloss, tint strength and opacity needed in the pigment. Low alumina levels yield better gloss but lower tint strength compared with higher levels [10].

The morphology of the alumina layer depends on the deposition conditions. Aluminum oxide and hydrous alumina have many different structures, which can give many different properties to coated particles. Formation of aluminum layers as a function of the suspension's pH is




Figure 4. Sodium aluminate as a source of aluminum hydroxide.




Figure 5. Aluminum sulfate as a source of aluminum hydroxide.

presented in **Figure 7**. From literature, we know that the structure of the alumina layer on TiO₂ pigment varies with the pH, i.e., the alumina tends to deposit as a pseudoboehmite in basic solutions. Alumina deposits in an amorphous form in the acid solutions. The transition pH is temperature-sensitive and tends to shift to lower pH at higher temperature [1].

Parameters such as temperature, pH, coating reagent concentration, core particle concentration and particle surface characteristics significantly affect precipitation coating process [26]. Hydrolysis polymerization, a precipitation process of the coating reagent as well as the coating morphology is influenced by pH and temperature. At high pH values, hydrolysis of Al³⁺ is accelerated and more multinuclear OH–Al species are formed compared to the situation at low pH [27]. The number of Al³⁺ ions depends on pH and Al³⁺ concentration, while the structure of the OH–Al species depends on the process conditions, e.g., concentration of Al³⁺, temperature and stirring strength [28]. pH also affects the protonation and deprotonation reactions on the core particle surface [29].

Condensation between OH–Al species and –OH groups on the TiO₂ particle surface occurs when the OH–Al species collide with TiO₂ particles through random collisions. Formation of




Figure 6. Sodium aluminate and aluminum sulfate as a source of aluminum hydroxide.




Figure 7. Formation of aluminum layers as a function of the suspension’s pH.

Ti—OvAl bond formed via condensation of —OH groups from TiO₂ surface and OH—Al species is presented in **Figure 8**.

When the pH is higher than the isoelectric point, the TiO₂ particles carry negative charge [11]. The number of —OH groups on the particle surface that could provide protons is large; the surface is easy to provide protons, which facilitated the condensation between the OH—Al species and the —OH groups on the particle surface. In such a case, heterogeneous precipitation is




Figure 8. At pH higher than the IEP, the number of —OH groups on the particle surface that could provide protons is large and the condensation with the OH—Al species easily occurs [13].

preferred. Since a large amount of —OH groups on the particle surface could provide protons at higher pH, there were many OH—Al species that condense with the —OH groups on the particle surface; neighboring condensed OH—Al species easily condense each other, forming a continuous film coating, as shown in **Figure 9**.

When the pH is lower than the IEP, the number of —OH groups on the particle surface that could provide protons is small and condensation with the OH—Al species hardly occurs; here, homogeneous nucleation or the dotted layer is preferred (**Figure 10**).

At high pH, the OH—Al species are large, having a certain shape, and their sedimentation leads to a loose floccule or flake-like layer (**Figure 11**).

The layer morphology mainly depends on the sedimentation speed and the directed growth speed of the OH—Al species [30]. When the temperature is in the middle range, the sedimentation speed and the directed growth speed of the OH—Al species are about the same. At increased temperature, the directed growth speed of the OH—Al species dominates the precipitation




Figure 9. TEM image of a continuous film aluminum hydroxide coating.




Figure 10. Image of TiO₂ particles with dotted alumina layer.




Figure 11. TEM image provides an excellent view of the shell covering of a crystalline core of TiO_2 with a loose floccule or flake-like layer.

process regardless of the pH and size of the OH–Al species, which results in a directed growth [10]. Layer morphology changes from uniform and continuous film to loose floccules.

Temperature has a significant effect on the direction and growth speed of the OH–Al species in gel precipitation or coating, while also affecting the self-assembly of the OH–Al species in the aging process. Under high pH conditions, the OH–Al species form a large particle size, which facilitates the formation of boehmite $\text{Al}(\text{OH})_3$ gels or a floccule/flake coating. Amorphous $\text{Al}(\text{OH})_3$ gel forms only under conditions when the precipitation and aging proceed at a low temperature and pH; it can be converted to boehmite under high pH or temperature conditions.

However, boehmite gel cannot be converted to the amorphous form when the pH and temperature are low in the aging process [10].

2. TiO_2 grades

2.1. Highly coated TiO_2 grades

There is a special route for improving TiO_2 light scattering efficiency that is closely related to targeted spacing—the encapsulation of the TiO_2 particles by a thick, porous material. This coating material, which in practice is aluminosilicates, needs to be thick enough to effectively prevent close contact of the TiO_2 portion of these pigments and highly porous because a solid coating would unnecessarily dilute the TiO_2 content of the pigment. Even with high porosity, these coatings dilute the weight percent of TiO_2 in the pigment to roughly 80%.

It is important to manage the process under controlled conditions. **Figures 12** and **13** indicate differences between two highly coated TiO_2 , produced under controlled and uncontrolled conditions. Surface of TiO_2 , coated under appropriate conditions is uniform with coatings covering the entire surface of the particles (**Figure 13**). Increased SiO_2 loading up to 10 wt.% resulted in thicker layers. Coating TiO_2 particles under neutral conditions yields fluffy coatings with coating thickness up to 50 nm. Pigment particles are separated from each other, showing no agglomeration.

On the contrary, uncontrolled coating process yielded incomplete coatings (**Figure 12**). Homogeneous coating was not attained and some particles were not coated with the silica layer.




Figure 12. Highly surface treated TiO₂ (uncontrolled conditions).




Figure 13. Highly surface treated TiO₂ (controlled conditions).

2.1.1. Particle size distribution

The particle size relevant for inorganic pigments stretch between several tens of nanometers for transparent pigment types to approximately 2 μm. For practical applications, it is desirable to determine not only the mean particle size but also the whole distribution [3].

The distribution of highly surface-treated TiO₂ in a controlled process indicates narrow particle size distribution, while an uncontrolled process yields material with broad particle size

distribution. Different populations are evident, meaning that the sample consists of many small and many over-sized particles (**Figure 14**).

Surface modification treatment in the suspension brings a significant shift in the pattern toward the higher particle diameter region due to high hydroxide loadings of silica and alumina imparted on the TiO_2 surface. The higher degree of surface modification and greater tendency for particle agglomeration can be attributed for the higher average particle diameter.

If we take into account only the mean particle sizes, we can conclude that we have two very similar samples. But, if we look at the whole distribution, it is obvious that the samples consist of very different populations. With this, we confirmed the fact that it is significant to determine not only the mean particle size but also the whole distribution.

After the grinding operation, particle size distribution again shifted to the lower particle diameter region. The sample produced by an uncontrolled process again contain over-sized particles (**Figure 15**).

2.1.2. Optical density

The problem with particle size distribution measurements is that the data cannot be directly related to the scattering power without using a theoretical model. An optical density test has been developed to provide a direct measure of the actual pigment scattering potential, which can then be used to evaluate performance in end-use applications [31–33].

A lab-dispersed sample in water is accurately diluted and analyzed for its total light transmission T . We have used the 'DuPont optical density', which is defined as $-\log(\text{total } T)/\text{concentration}$ and defines the scattering potential of the pigment. Compared to standard end-use tests of scattering power such as tint strength, optical density (OD) measurement offers the advantage of faster turn-around and improved precision with standard deviations less than 0.5% of the mean value.

The optical density was determined by UV-Vis spectrophotometer. To determine the optical density, 1 L of the diluted suspension of pigment particles TiO_2 in ethanol ($c \text{ TiO}_2 = 30 \text{ mg/L}$) was prepared. During the analysis, the suspension was subjected to ultrasound stirring. The




Figure 14. Particle size distribution of highly coated TiO_2 in slurry after controlled (narrow curve) and uncontrolled (wider curve) surface treatment.




Figure 15. Particle size distribution of micronized highly coated TiO₂ after controlled (narrow curve) and uncontrolled (wider curve) surface treatment.

optical density method determines the optical properties of the particles. This method determines the dispersibility or degree of particles agglomeration.

The results of the optical density determination indicated the differences between particles coated under different process conditions, controlled and uncontrolled (**Figure 16**). The light scattering highly depends on the particle size and the distribution of the size and degree of agglomeration of the material. Agglomeration always reduces the effectiveness of pigment light scattering. With the results obtained, we gained information about the light scattering efficiency, which is most likely a consequence of the particle size distribution and the degree of dispersion. Differences in dispersion between differently coated particles are the result of a different particle size distribution, the degree of milling step and the controlled coating mode, where the particle surface was completely coated with a layer of hydroxide. Surface treatment is important in determination of the physical properties of the particle surface and thus, affects the dispersion in a particular medium. The quality of surface treatment defines how the pigment will perform when incorporated into a particular medium. Light scattering efficiency (LSE) will depend on how well the pigment will be dispersed. Differently agglomerated particles should exhibit different OD value.

Results of the OD method indicate that coating the surface in a controlled manner resulted in particles with higher LSE (gray curve) in comparison with the particles coated under




Figure 16. Light scattering efficiency of TiO₂ particles coated under controlled and uncontrolled process conditions.

uncontrolled conditions (black curve). Consequently, differences in undertone for both samples were evident.

Smaller particles ($\leq 0.2 \mu\text{m}$) scatter the light of the short wavelength more strongly; therefore, they have a slightly blue undertone, while the larger particles scatter the light of a longer wavelength, i.e., they have a yellow undertone.

2.2. Weather resistant grades

Due to the light absorption in the near UV, electrons are hoisted from the energy level of the valence band of TiO_2 into that of the conductive band, thus leaving a positively charged hole in the valence band. The separated electron-hole pair is called an 'exciton'. The generation of excitons is the cause for the light induced semiconductor properties of TiO_2 . The photoactivity of TiO_2 is generally not preferred, since the excitons can have an oxidizing influence on its surroundings and, for example, destroy a polymer matrix in which it is embedded. Therefore, the TiO_2 pigment industry takes some efforts to diminish the photoactivity of TiO_2 . On the other hand, this property is utilized purposefully in TiO_2 photocatalysts [2].

From experience, anatase pigments are generally much less photo- and weather-resistant than rutile pigments [2]. Since a durable pigment is in demand, a heavy dense silica treatment is used. In addition, alumina has been chosen as the final layer over the silica treatment. Examples of surface treatment for weather resistant grades are presented in **Figures 17** and **18**. **Figure 17** presents the dense silica-alumina coating while **Figure 18** presents the dense silica-zirconia-alumina coating, covering the entire surface of TiO_2 particles.

Due to the fact that anatase is more photocatalytically active in the crystalline form than rutile, we selected material with the highest level of rutile crystalline structure as a base material. The level of rutile crystalline structure was determined before surface treatment using XRD (see **Table 1**).

Weather resistant grades can be produced by various surface treatments. We decided on two different versions, depending on the final applications. The structure of the coatings is presented in **Table 2**.




Figure 17. Dense silica-alumina coating.




Figure 18. Special Al-Si-Zr surface treatment.

Sample	R [%]
TiO ₂ –Al–Si	99.7
TiO ₂ –Al–Si–Zr	99.8

Table 1. Level of rutile crystalline structure in TiO₂.

Sample	SiO ₂ [%]	Al ₂ O ₃ [%]	ZrO ₂ [%]
TiO ₂ –Al–Si	3.6	3.1	—
TiO ₂ –Al–Si–Zr	3.4	2.1	0.39

Table 2. Metal oxides determination.

2.3. TiO₂ for applications in printing inks

2.3.1. Gloss effect

Gloss is a visual impression gained when light is reflected at a surface in a preferential direction. The gloss of a coating system is determined by a number of factors. Pigments can influence the gloss of a coating through their concentration, particle size distribution and degree of dispersion in the binder system [34].

A conventional, high quality TiO₂ pigment has a mean particle diameter (weight average) of approximately 0.3 μm. The particle size distribution should not exceed the 1 μm limit in order to be useful for high gloss coatings [2].

Only those pigment particles lying directly below the surface of the coating are involved in this process. The higher the concentration of pigment, the greater the number of gloss-reducing particles and lower the gloss [34].

2.3.2. Rheology

An ink with required rheological properties can be successfully applied to the image on a plate, transferred correctly to the stock and finally, retain its form as a print. Each printing technique has specific requirements. For opacity, it is important to select pigment and pigment volume concentrations that play a role on opacity, gloss and whiteness, but also on the rheology of the ink. Different pigment grades have different medium absorption. As a consequence, the rheology of the ink at the time of application will be affected. Many ingredients, apart from TiO_2 pigments, will affect the final rheology of the ink. It is important to note that formulation of inks calls for much practical experience and skill.

It is vital to incorporate TiO_2 pigment into the printing ink medium in a way that maximum dispersion is achieved. In the case of a poor dispersion stability even viscosity could be affected.

2.3.3. Solubility parameters and dispersion

From the economical point of view, the best dispersion state of TiO_2 should be obtained in the shortest time and with minimum expenditure of energy.

Inorganic and organic surface treatments of TiO_2 could be optimized in order to maximize pigment affinity with both binder and solvents. This results in pigments with better dispersion and stabilization in a wide range of printing ink formulations, i.e., improved opacity, gloss and color [35].

The end-user of printing inks has the skill to select a range product (TiO_2 grade); the best suited grade for a particular purpose.

Optical properties of the pigment are defined by the particle size distribution, while the applicative properties are determined by the surface treatment. By implementation of more intensive milling, we prepared a slurry of more dispersed TiO_2 particles. The prepared TiO_2 slurry has been used for further surface treatment. Our goal was to keep the particles separated from each other through the whole process.

The influence of milling and coating process on optical properties are presented in **Table 3**. In order to improve the applicable properties, it is important to coat TiO_2 particles under




Figure 19. Alumina surface-treated TiO_2 intended for printing inks applications.

Sample	Gloss	Scattering
Poorly milled material	24.4	97.4
More intense milling	40.5	104.1

Table 3. Influence of milling and coating process on optical properties.

controlled conditions (T , pH, precursor dosing rate). Under such conditions, the alumina surface-treated particles are separated from each other; coating is uniform and dense, covering the entire surface of the particle (**Figure 19**). Such particles exhibit excellent optical properties, as demonstrated in **Table 3**. In the case where the process of surface treatment started from suspension with more dispersed or deagglomerated particles (intense milling), higher gloss was obtained for the system with incorporated TiO₂.

2.3.4. Optical density

A layer of alumina oxide layer can increase the amount of —OH groups on the particle surface, which can improve the dispersibility of the particles and provide more active sites for further organic modification; this was evidenced from the results obtained by OD method. TiO₂ particles surface-treated under controlled conditions exhibit significantly higher light scattering efficiency due to complete aluminum layer coating the entire TiO₂ surface. Lower LSE was determined for TiO₂ particles with incomplete coatings, produced under uncontrolled conditions (**Figure 20**).

Printing ink with incorporated TiO₂ particles with incomplete coatings was highly viscous. For printing inks production approximately 10% more solvent was needed. Since the viscosity




Figure 20. Light scattering efficiency (LSE) for pigmentary TiO₂ with complete and incomplete coatings.

of the dispersion and the type of optical properties (especially the undertone and gloss) are strongly dependent on the degree of particulate dispersion, we can conclude that in controlled surface treatment, we obtained more dispersed particles.

2.4. TiO_2 applications in paper laminates

As already mentioned before, TiO_2 is a semi-conducting material and show some intrinsic photocatalytic activity. During weathering, interaction of UV light with TiO_2 occurs resulting in the formation of free electrons and electron-holes in the crystal lattice. These radicals react easily with neighboring organic molecules and, result in degradation of the medium [36–38].

The interaction of UV light with TiO_2 particles results in the formation of Ti^{3+} centers that are violet-colored species. For that reason, discoloration (greying) of the exposed area might be observed. This is usually described in terms of the lightfastness [37].

Generally, commercial TiO_2 grades are surface-treated with hydrated compounds of aluminum, silicon and zirconium [39–42]. Silica contributes to durability, while zirconia improves gloss and durability. Alumina is usually used as a final layer to increase dispersion stability. Sometimes, special surface treatment, for example, with aluminum phosphate is required to provide high lightfastness in applications such as decorative papers [43]. Scanning transmission electron microscopy (STEM) image of TiO_2 surface treated with aluminum phosphate is presented in **Figure 21**.

2.4.1. Lightfastness

The lightfast properties of printing inks can be defined as the amount of resistance to fade or color change of a printed surface when exposed to daylight (or an artificial light source) over a set period of time.

For determination of lightfastness of prints, Blue Wool Scale is utilized. According to this method, samples are exposed to a standard xenon light in appropriate equipment.




Figure 21. STEM image of TiO_2 with aluminum phosphate coating.

The lightfastness is indicated by the grades on the Blue Wool Scale: BWS 1 = poor, BWS 2 = low, BWS 3 = average, BWS 4 = rather good, BWS 5 = good, BWS 6 = very good, BWS 7 = extremely good, BWS 8 = excellent.

TiO₂ with aluminum phosphate coating successfully underwent testing by the end-user with grades 4/5 on the Gray Scale (grades 1–5) and with grade > 6 on the Blue Wool Scale; we met the requirements of the user.

2.4.2. Electrochemical properties determination

IEP of pure TiO₂ particles is about pH 4. Modifying the pigment surface with inorganic layers of, for example, Al₂O₃, SiO₂, ZrO₂, phosphates changes the IEPs [2]. Whereas, for example, Al₂O₃ (IEP = 9) and Al(OH)₃ species (IEP is about 6.8) shifts the IEP to higher pH values, other substances normally tend to reduce the IEP to lower pH values (IEP of SiO₂ = 2, IEP of ZrO₂ = 4). Phosphates, used for surface treatment form acidic groups on the surface of particles, which are acidic and becomes a potential determinant [2, 14].

In **Figure 22**, the zeta potential as a function of pH for untreated and surface-treated TiO₂ pigments are presented. IEP of pure TiO₂ particles is about 4 and according to literature [2], IEP of aluminum surface-treated TiO₂ is 8.65, which is close to the values determined for Al₂O₃. IEP of Si surface-treated TiO₂ shifted to pH 2.5, close to IEP characteristic for SiO₂. Complete alumina layers contributed to shift IEP to higher pH values (pH 8.6), which proves a successful surface treatment, since the IEP value of surface-treated samples lies close to the IEP value characteristic for alumina. The results are in agreement with literature. Multi-layered surface treatments, alumina in combination with silica and phosphate, shifted IEP to lower pH. IEP values for all samples are presented in **Table 4**. The uniformity and the properties of hydroxide coatings influenced the surface properties of the pigment particles because the coated particles show similar surface characteristic, such as surface charge and surface active sites or groups, as the coating material.




Figure 22. Zeta potential as a function of pH.

Sample	IEP
TiO ₂	4.1
TiO ₂ -Si	2.5
TiO ₂ -Al	8.65
TiO ₂ -Si-Al	7.3
TiO ₂ -Al-P	6.3

Table 4. IEPs for untreated and surface-treated TiO₂ particles.

3. Conclusions

Surface treatment of TiO₂ particles is one of the most important steps in the production of TiO₂ pigment. It is a delicate and complex process. Process parameters such as pH and temperature have to be carefully controlled, as this is essential to ensure the formation of uniform oxide coatings and achieving the desired useful features. Surface-treated TiO₂ particles were prepared starting from various precursors by the chemical liquid deposition method. Uniform hydroxide layers formed on the surfaces of the TiO₂ particles under mild hydrolysis rate of, for example, sodium aluminate, aluminum sulfate or sodium silicate in gel precipitation and aging. The morphology of the layers was significantly affected by the temperature and pH value of the reaction solution. Formation of thin and uniform hydroxide layers influenced optical and electrochemical properties. Surface-treated particles altered their electrokinetic behavior in a way similar to the coating material, suggesting formation of a complete hydroxide layer on the TiO₂ surface. We can conclude that inappropriate pH conditions can lead to undesirable phases of hydroxides or to an incomplete layer. By applying a dense silica layer of colorless alumina phosphate, photoactivity of TiO₂ pigments was successfully suppressed.

Author details

Nika Veronovski

Address all correspondence to: nika.veronovski@cinkarna.si

Cinkarna-Metallurgical and Chemical Industry Celje, Inc, Celje, Slovenia

References

[1] Tyler F. Tailoring TiO₂ treatment chemistry to achieve desired performance properties. *Paint & Layers Industry*. 2000;**32**:16-32

- [2] Winkler J. Titanium Dioxide. Vincentz: Hannover; 2003
- [3] In: Buxbaum G, Pfaff G, editors. Industrial Inorganic Pigments. 3rd ed. Weinheim: Wiley-VCH; 2005
- [4] Liu Y, Ge C, Ren M, Yin H, Wang A, Zhang D, Liu C, Chen J, Feng H, Yao H, Jiang T, editors. Effects of coating parameters on the morphology of SiO₂-coated TiO₂ and the pigmentary properties. *Applied Surface Science*. 2008;**254**:2809-2819
- [5] Liu Y, Zhang Y, Ge C, Yin H, Wang A, Ren M, Feng H, Chen J, Jiang T, Yu L. Evolution mechanism of alumina coating layer on rutile TiO₂ powders and the pigmentary properties. *Applied Surface Science*. 2009;**255**:7427-7433
- [6] Zhang Y, Liu Y, Ge C, Yin H, Ren M, Wang A, Jiang T, Yu L. Evolution mechanism of alumina nanofilms on rutile TiO₂ starting from sodium metaaluminate and the pigmentary properties. *Powder Technology*. 2009;**192**:171-177
- [7] Zhang Y, Yin H, Wang A, Ren M, Gu Z, Liu Y, Shen Y, Yu L, Jiang T. Deposition and characterization of binary Al₂O₃/SiO₂ coating layers on the surfaces of rutile TiO₂ and the pigmentary properties. *Applied Surface Science*. 2010;**257**:1351-1360
- [8] Zhang Y, Yin H, Wang A, Liu C, Yu L, Jiang T, Hang Y. Evolution of zirconia coating layer on rutile TiO₂ surface and the pigmentary property. *Journal of Physics and Chemistry of Solids*. 2010;**71**:1458-1466
- [9] Wu HX, Wang TJ, Duan JL, Jin Y. Effects of SO₄²⁻ on the heterogeneous precipitation coating of hydrous alumina on TiO₂ particles in an aqueous process. *Industrial and Engineering Chemistry Research*. 2007;**46**:3590-3594
- [10] Wu HX, Wang TJ, Jin Y. Morphology “phase diagram” of the hydrous alumina coating on TiO₂ particles during aqueous precipitation. *Industrial and Engineering Chemistry Research*. 2006;**45**:5274-5278
- [11] Wu HX, Wang TJ, Jin Y. Film-coating process of hydrated alumina on TiO₂ particles, *Industrial and Engineering Chemistry Research*. 2006;**45**:1337-1342
- [12] Veronovski N, Lešnik M, Verhovšek D. Surface treatment optimization of pigmentary TiO₂ from an industrial aspect. *JCT Research*. 2014;**11**:255-264
- [13] Veronovski N, Lesnik M, Verhovšek D. Alumina surface treated pigmentary titanium dioxide with suppressed photoactivity. *LifeScience Global*. 2014;**1**:51-58
- [14] Veronovski N. Alumina surface treated TiO₂—From process to application. *Journal of Surface Science and Technology*. 2015;**2-1**:6-12
- [15] Jeer RK. DuPont. US 2885366; 1956
- [16] Evans AW, Shon C. Tioxide Group Ltd. GB 1008652; 1961
- [17] Rechmann H, Vial F, Weber H. Kronos Titangesellschaft Mbh. DE 1208438; 1960
- [18] Moody JR, Lederer G. British Titanium Products. DE 146712; 1965

- [19] Brugger K, Jehle N. In: Congress FATIPEC XII (EREC); Paris. 1976. p. 15
- [20] Volz HG, Kampf G, Fitzky HG, Klaeren A. The chemical nature of chalking in the presence of titanium dioxide pigments. Photodegradation and Photostabilization of Coatings. In: ACS Symposium Series. 151; 1981 p. 163
- [21] Volz HG, Kampf G, Fitzky HG. Surface reactions on titanium dioxide pigments in paint films during weathering. In: Progress in Organic Coatings. 1974;**2-3**:223-235
- [22] Powell QH, Fotou GP, Kodas TT, Anderson B. Coating of TiO₂ with metal oxides by gas-phase reactions. Journal of Aerosol Science. 1995;**26**:557-558
- [23] Atou Y, Suzuki H, Kimura Y, Sato T, Tanigaki T, Saito Y, Kaito C. Novel method for the preparation of silicon oxide layer on TiO₂ particle and dynamic behavior of silicon oxide layer on TiO₂ particle. Physica E. 2003;**16**:179-189
- [24] Lin YL, Wang TJ, Jin Y. Surface characteristics of hydrous silica coated TiO₂ particles. Powder Technology. 2002;**123**:194-198
- [25] Yin H, Wada Y, Kitamura T, Kambe S, Murasawa S, Mori H, Sakata T, Yanagida S. Journal of Materials Chemistry. 2001;**11**:1694-1703
- [26] He YX. Ceramic composites through solution precipitation coating [thesis]. Berkeley, CA: University of California; 1998
- [27] Lu XQ, Chen ZL, Yang XH. Spectroscopic study of aluminum speciation in removing humic substances by Al coagulation. Water Research. 1999;**33**:3271
- [28] Bi SP, Wang CY, Cao Q, Zhang CH. Studies on the mechanism of hydrolysis and polymerization of aluminum salts in aqueous solution: Correlations between the "core-links" model and "cage-like" keggins-Al₁₃ model. Coordination Chemistry Reviews. 2004;**248**:441
- [29] Tomba'cz E, Libor Z, Ille's E, Majzik A, Klumpp E. The role of reactive surface sites and complexation by humic acids in the interaction of clay mineral and iron oxide particles. Organic Geochemistry. 2004;**35**:257
- [30] Shen Z, Zhao ZG, Wang GT. Colloid and Surface Chemistry. Beijing, China: Chemistry Industry Press; 2004
- [31] Shedding light on white. European Coatings Journal. Vincentz Network 06/200
- [32] US Patent 6,040,913, March 21; 2000
- [33] US Patent 6,236,460, May 22; 2001
- [34] Brock T, Groteklaes M, Mischke P. European Coating Handbook. 2nd revised ed. Hannover, Germany: Vincentz Network; p. 120
- [35] Efficient use of TiO₂ in white printing inks. Tioxide Group. Available from: <http://www.tio2.net> [Accessed: 2017-11-02]
- [36] Diebold MP. The causes and prevention of titanium dioxide induced photo-degradation of paints. Part I: Theoretical considerations and durability. Surface Coatings International. 1995;**6**:250-256

- [37] Woditsch P, Westerhaus A. Industrial Inorganic Pigments. 3rd ed. New York: VCH Weinheim; 1993
- [38] Li X, Cabbage JW, Tetzlaff TA, Jenks WS. Photocatalytic degradation of 4-chlorophenol. 1. The hydroquinone pathway. The Journal of Organic Chemistry. 1999;**64**:8509-8524
- [39] Decolibus RL. TiO₂ pigment coated with porous alumina/silica and dense silica. US Patent No. 3928057 assigned to Wilmington, DE: E.I. Du Pont de Nemours & Company; 1975
- [40] Thomas DC. Process of treating titanium dioxide pigments. US Patent No. 3876442 assigned to Oklahoma City, OK: Kerr-McGee Chemical Co.; 1975
- [41] Jacobson HW. Alumina coated TiO₂. US Patent No. 4416699; 1983
- [42] Tuomo L. Process of coating titanium dioxide pigments. US Patent No. 5165995 assigned to Helsinki, FI: KemiraOy; 1992
- [43] George J, Gireesh VS, Ninan G, Krishnan Nair S. Modification of TiO₂ surface for improved light fastness. International Journal of Industrial Chemistry. 2015;**6-3**:133-141

IntechOpen

