We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists



186,000

200M



Our authors are among the

TOP 1% most cited scientists





WEB OF SCIENCE

Selection of our books indexed in the Book Citation Index in Web of Science™ Core Collection (BKCI)

Interested in publishing with us? Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected. For more information visit www.intechopen.com



Bio-adsorbents for the Removal of Heavy Metals from Water

Khathutshelo Catherine Mqehe-Nedzivhe, Khathutshelo Makhado, Oluwasayo Folasayo Olorundare, Omotayo Ademola Arotiba, Elizabeth Makhatha, Philiswa Nosizo Nomngongo and Nonhlangabezo Mabuba

Additional information is available at the end of the chapter

http://dx.doi.org/10.5772/intechopen.73570

Abstract

The work represents the bio-adsorption of arsenic(III) from standard solutions and real water samples using a powdered avocado seed as a bio-adsorbent. The adsorbent was synthesized, demineralized, and characterized by X-ray diffraction (XRD), scanning electron microscope coupled with energy dispersive spectroscopy (SEM-EDS), Fourier transformation infrared spectroscopy (FTIR), and Brunauer-Emmett-Teller (BET) theory. Batch adsorption studies were carried out by using avocado seed, and As^{III} was analyzed by using inductively coupled plasma optical emission spectroscopy (ICPOES) after optimizing the following parameters: pH 6, analyte concentration 2 mg L⁻¹, bio-adsorbent dosage 0.8 g, contact time 120 min between analyte and adsorbent, and temperature from 22 to 40°C. The adsorption capacity of 93.75 mg/g was obtained, and the Langmuir isotherm was adopted by the adsorbent due to the chemisorption that occurs on the surface between the functional groups of the bio-adsorbent and As^{III}.

Keywords: arsenic(III), bio-adsorption, inductively coupled plasma optical emission spectroscopy

IntechOpen

© 2018 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (http://creativecommons.org/licenses/by/3.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

1. Introduction

Arsenic (As) is the 20th most abundant element in the earth's crust, and its concentration on the soil level is about 5–13 mg/kg [1]. Naturally, arsenic is found in different oxidation states: V (arsenate), III (arsenite), 0 (arsenic), and -III (arsine) [2, 3]. Arsenic (As) is one of the elements that occur naturally and commonly found as an impurity in metal ores, and it is in abundance. It can be found in the soil, water, and living organisms. It is produced commercially for use in wood preservatives, metal alloys, and pesticides.

Both As^{III} and As^V exist in the pH range of 6–9, and when comparing As^{III} and As^V, it is known that As^{III} is more toxic than As^V and also in terms of mobility [4]. Depending on the pH, Arsenite (As^{III}) exists in four forms in aqueous solution, such as H₃AsO₃, H₂AsO₃⁻, HAsO₃²⁻, and AsO₃³⁻. In a reductive environment, below pH 9.1 As(III) exists in the form of inorganic arsenite (H₃AsO₃) and is thermodynamically stable [5].

Since arsenic is one the most well-known poisonous elements in the periodic table, it is known to be carcinogenic in many parts of the world [6]. Long-term exposure to arsenic, through water and food, can lead to serious health problems like neurological effects, hypertension and cardiovascular diseases, and skin and lung cancer [7]. The kidney is the major source for regulation of water and electrolytes, waste, and chemical compounds, and arsenic(III) can affect the role of the proximal tubules and glomerulus of the kidney [8].

Arsenic(III) is the one that is known to be toxic [4]. The World Health Organization (WHO) recommended a more rigid limit of 10 μ g/L as the maximum acceptable arsenic level [9]. Commercial methods for removing arsenic involve technologies such as precipitation, membranes, and adsorption. But adsorption is the most easy, flexible, inexpensive method to be applied by using mineral oxides [10], polymer resins [11], and activated carbons [12]. According to literature, waste materials such as rice husks, tea, and agricultural waste have been applied as inexpensive adsorbents [13].

It is well known that South Africa is a developing country with limited resources for water purification; therefore, the aim of this work is to develop a cheaper, easy-to-use method of treating water especially in the rural areas where the water treatment stations are not yet established.

The most crucial aim of the work is that the bio-adsorbent must be manufactured from a locally available material that is reusable in order to save the rural area's people from daily expenses.

2. Materials and experimental method

2.1. Reagents and standards

Potassium carbonate and arsenic standard employed in the synthetic application procedures of this work were of analytical grade and obtained from Sigma-Aldrich (St. Louis, MO, USA). Millipore water (Merck, Darmstadt, Germany) of 18 M Ω cm⁻¹ was used throughout the experiments. Concentrated nitric acid (HNO₃) (70%) was also purchased from (St. Louis, MO,

USA, www.sigmaaldrich.com). All materials especially plastics and glassware prior to use were cleansed by soaking in dilute HNO_3 and rinsed with copious deionized water. The stock standard solutions of As(III) at a concentration of 1000 mgL⁻¹ was obtained by dissolving an appropriate amount of arsenic oxide. The working standards were prepared daily by stepwise dilution of stock solution. Avocado fruit waste seeds (AFWS) were locally sourced from fruit and vegetable shop outlet around the city of Johannesburg (Gauteng Province, South Africa).

2.2. Instrumentation

The As quantification was performed using inductively coupled plasma optical emission spectroscopy (ICPOES) (iCAP 6500 Duo, Thermo Fisher Scientific, UK) equipped with a charge injection device (CID) detector. The sample injection application was done through a concentric nebulizer and a cyclonic spray chamber. A Mettler Toledo pH meter model 120 (Greifensee, Switzerland) was employed for all pH measurements. The active carbon material production, i.e., activation, was performed in a tubular furnace (Gallenkamp, Germany). The AFWS and ACM were characterized for porosity, pore structures, surface area, and pore volume using N₂ gas adsorption BET (Brunauer, Emmett, and Teller) method for surface area, while the crystallinity of the material was determined by X-ray diffraction (XRD, Rigaku, UHMa IV, Japan). Surface morphology and surface functional groups were determined by scanning electron microscopy (EDS) (TECAN VEGA 3 XMU, Czech Republic) coupled with energy dispersive spectroscopy (FTIR, PerkinElmer FTIR, UK), respectively.

2.3. Adsorbent preparation and application

The precursor for the active carbon material was acquired by collecting avocado seeds. The avocado fruit waste seeds (AFWS) were air-dried and thoroughly washed before rinsing with deionized water. The washed seed residues were then oven-dried overnight at 100°C. The seeds were then pulverized by ball milling it with laboratory hammer mill (Janke and Kunkel Micro-hammer Mill, Staufen IM Breisgau, Germany) to obtain fine powder. The bulky powdered material was later fractionated to diverse particle size using laboratory sieves. The resultant particles of different miniature diameters ranging from 38 to 150 μ m were obtained in which 75 μ m particle size was subsequently employed in production of active carbon material. The powdered form of avocado seed was then stored inside desiccator until application.

The adsorption studies were carried out to evaluate the efficiency of the avocado peel (bioadsorbent) for the removal of As^{III} from the aqueous solution using the batch adsorption method. The batch adsorption experiments were carried out in 50 mL plastic bottles by shaking a constant mass of a predetermined size of adsorbent with arsenic standard solutions. The pH of the solutions was adjusted accordingly by adding either ammonium hydroxide or acetic acid solution. Each flask was sealed and kept in a state of agitation (200 rpm) using a mechanical laboratory shaker for the material to reach equilibrium. Upon equilibrium, the samples were filtered and analyzed using inductively coupled plasma optical emission spectroscopy (ICPOES). Parameters such as pH, concentration of solution, mass of adsorbent, contact time, and temperature were optimized. The percentage removal of As(III) in solution was calculated using Eq. (1):

$$R\% = \frac{C_0 - C_e}{C_0} \times 100$$
 (1)

where *R* is the percentage (%) removal and *Co* and *Ce* are the initial and equilibrium concentrations of the analyte, respectively.

The amount of metal adsorbed by adsorbent was calculated from the difference of metal quantity added to the biomass and metal content of the supernatant (Eq. (2) [14, 15]:

$$q_e = \frac{(C_0 - C_e)}{M} \times V \tag{2}$$

where q_e is the metal uptake (mgg⁻¹), C_0 and C_e are the initial and equilibrium metal concentration (mgL⁻¹), *V* is the volume of the solution (mL), and *M* is the mass of the adsorbent (g).

3. Results and discussion

3.1. Characterization of the raw avocado seed and activated carbon material

The FTIR spectrum is an important technique which provides the surface functional groups that significantly contribute in the enhanced adsorption efficiency of the adsorbent. FTIR was used to determine the surface functional groups of raw avocado fruit waste seed. In **Figure 1**, the spectrum of the powdered avocado seed is represented, where the band located at 3259 cm^{-1} corresponds to v (O—H) vibrations in the hydroxyl group, while the strong peaks



Figure 1. FTIR spectrum of avocado fruit waste seed (AFWS).

at 2913 and 2848 cm⁻¹ bands correspond to v(C-H) vibration in the alkane/alkyl aliphatic group which could be methylene [16–20]. The presence of alcohols and carbonyl groups was confirmed by the bond vibrations observed at 1633 cm⁻¹. This confirms that avocado seed is composed of carboxylic group which is responsible for adsorption; similar results were reported in the literature [21, 22].

The surface morphology and the chemical composition of raw avocado seed was studied with scanning electron microscope coupled with energy dispersive spectroscopy (SEM-EDS). The image in **Figure 2(a)** showed that raw avocado seed material had a smooth surface with long ridges and a series of graphitic layers with various pores.

The EDS analyses performed on avocado seed revealed that the surface contained different mineral particles, such as carbon, oxygen, potassium, phosphorus, and chlorine (**Figure 2b**). The highest content of oxygen may assist in adsorption due to electron lone pairs.

3.2. Optimization of adsorption parameters

pH is one of the most important parameters that influence the adsorption of the analyte. In this study, the amount of As^{III} adsorbed on avocado seed was the highest at pH 6 and gradually decreased as the pH increased up to 9 (**Figure 3a**) [7]. However, the highest removal was observed with avocado seed due to the presence of carboxylic group on the surface which increased the affinity toward arsenic to the adsorbent (**Figure 1**). Oxygen of the carbonyl group easily formed the complex with the arsenic [23]. Arsenic(III) adsorption decreased as the pH goes below 6 due to the increasing ionic strength [24].

The effect of the concentration was carried out by increasing the initial concentration from 5 to 30 mg L^{-1} , and the solutions were adjusted to pH 6 at 25°C. It was observed that the percentage removal increased with the increasing concentration of the analyte; this is due to



Figure 2. Avocado seed images of (a) SEM and (b) EDS.



Figure 3. Optimization of (a) pH of the solution, (b) concentration of the analyte, (c) bio-adsorbent dosage, (d) contact time between the bio-adsorbent and the analyte, and (e) temperature of the solution.

the fact that as the concentration increased more ions were available in the solution for adsorption [25]. It was observed from the results in **Figure 3b** that the highest removal (65%) was reached using 20 mg L⁻¹ and after there was no significant increase in the percentage (%) removal of As^{III}.

The amount of adsorbent is one on the important factors that affects the adsorption capacity. The adsorbent amount of raw avocado seed on the efficiency of adsorption was investigated, and adsorbent amount was varied from 0.025 to 0.8 g. The results observed indicated that the adsorption increased with increasing adsorbent dosage till 0.8 g (**Figure 3c**). The increase in the percentage removal is due to the availability of active sites for adsorption [26]. It was found that after the dosage of 0.4 g there is no significant change in the percentage removal of arsenic. Then, 0.8 g was used throughout the experiments.

The effect of contact time is an important factor in adsorption because it affects the adsorption kinetics of an adsorbent at the given initial concentration of the adsorbate [26]. The batch adsorption experiments were carried out to investigate the effect of agitation time on the adsorption of As(III). Adsorption rate initially increased rapidly, and the highest removal was reached at 120 min (**Figure 3d**). Further increase in contact time did not show a significant change in the percentage (%) removal of arsenic.

Temperature is one of the parameters that affect the equilibrium and solubility and can also initiate the chemical reaction. This is because temperature can either increase or decrease the activation energy of the analyte. The effect of temperature on the adsorption of arsenic was investigated from room temperature of 40°C. From the results obtained in **Figure 3e**, the temperature did not have any effects since there is no significant increase or decrease in the percentage (%) removal of arsenic.

Under optimized conditions, 2 mg L^{-1} As^{III} standard solution was adsorbed by the avocado peels, and 75% As^{III} was removed (**Figure 4**). The adsorption capacity was 93.75 mg/g when Eq. (2) was applied.

3.3. Adsorption kinetics

Adsorption is described by the functions which connect the amount of adsorbate on the adsorbent.

The distribution of metal ions between the liquid phase and the solid phase is described by several isotherm models such as Langmuir and Freundlich [27].

The Langmuir equation can be written in the form of Eq. (3):

$$\frac{C_e}{q_e} = \frac{1}{q_{\max}}C_e + \frac{1}{K_L q_{\max}}$$
(3)

where C_e is the equilibrium concentration (mg/L), q_e is the amount of arsenic adsorbed onto the solid phase (mg/g), b is the equilibrium adsorption constant related to the affinity of binding



Figure 4. Determination of percentage (%) removal from 2 mg L^{-1} As^{III} standard solution by ICPOES.

sites (L/mg), and q_{max} is the maximum amount of arsenic per unit weight of adsorbent for complete monolayer coverage.

Freundlich equation is represented as shown in Eq. (4):

$$\log q_e = \log K_f + \frac{1}{n} \log C_e \tag{4}$$

where C_e is the equilibrium concentration (mg/L), q_e is the amount of arsenic adsorbed onto the solid phase (mg/g), K_f is an indicator of the adsorption capacity, and n is the heterogeneity factor.

The results in **Figure 5(a** and **b)** and **Table 1** showed that the correlation coefficient for linear Langmuir model (\mathbb{R}^2 , 0.97) was higher than the Freundlich model (\mathbb{R}^2 , 0.72). The data was best fitted in Langmuir model, and this signified that the adsorbent had high affinity for arsenic(III)



Figure 5. (a) Langmuir isotherm displaying the adsorption of As^{III} onto the surface of the avocado seed by plotting C_e/q_e against equilibrium concentration (C_e). (b) Freundlich isotherm showing the adsorption of As^{III} onto the surface of the avocado seed by plotting ln C_e against equilibrium concentration ln q_e .

due to the carboxylic groups that are the surface of the avocado seed [28], meaning that the chemisorption took place. To prove that the data belonged to Langmuir isotherm, the separation value, R_L value from Eq. (5) was calculated. R_L proves whether the Langmuir adsorption nature is favorable if $R_L > 0$, unfavorable if $R_L > 1$, and irreversible if $R_L = 0$:

$$R_{\rm L} = \frac{1}{1 + (1 + K_{\rm L} \times C_0)}$$
(5)

where C_0 is the initial concentration and K_L is a Langmuir constant obtained from plotting $1/q_e$ versus $1/C_e$. The results in **Table 1** indicated that the equilibrium sorption was favorable for Langmuir isotherm.

3.4. Analytical figures of merit

Analytical figures of merit for the quantitative analysis of arsenic(III) such as limit of detection (LOD), limit of quantification (LOQ), correlation coefficient (\mathbb{R}^2), and the relative standard deviation (RSD) were calculated. In order to determine the LOD, the blank solution was subjected to the optimum experimental conditions, and the signals for ten blank samples were measured (n = 10). The limit of detection (LOD), calculated based on 3S/m (where S is the standard deviation of the blank and m is the slope of the calibration curve) was 0.10 mg L⁻¹. The limit of quantification (LOQ = 10S/m) was 0.20 mg L⁻¹ for arsenic(III). The linear calibration curve was plotted with a correlation coefficient of 0.98.

The precision (repeatability) of the batch adsorption method was studied by measurements of eight replicates of 2.0 mg L^{-1} standard solution of As^{III} as shown in **Table 2**. The precision, expressed in terms of standard deviation (%RSD), was 2.1.

3.5. Application of the avocado seed adsorbent in real water samples

A water sample from East London municipality was adsorbed by the raw avocado seed under the optimized conditions. It is shown in **Figure 6(a** and **b)** that the bio-adsorbent is removed (54 and 55%) from sampling area A and B, respectively. During the adsorption of As^{III} from environmental water samples, an interference can be experienced from metal ions such as Fe^{III}, Fe^{II}, Zn^{II}, Cd^{II}, Ni^{II}, Mn^{II}, Al^{III}, Pb^{II}, and Cu^{II} [10].

This indicated that avocado seed has the great potential in removing heavy metals like As^{III} in environmental water samples without being modified.

Adsorption isotherm	Parameter	Value
Langmuir	K _L	0.0022 L/mg
	R_L	0.17
	R^2	0.97
Freundlich	R^2	0.72

 Table 1. Adsorption isotherms for As^{III} adsorption by a bio-adsorbent.

As ^{III} standard solution adsorbed by avocado seed	Data
Before adsorption	2.0 mg L^{-1}
After adsorption	$(0.50; 0.50; 0.50; 0.50; 0.49; 0.49; 0.49; 0.47) \text{ mg L}^{-1}$
Mean	$0.49 \mathrm{~mg~L^{-1}}$
Standard deviation	\pm 0.010 mg L $^{-1}$
Relative standard deviation	2.1%
Table 2. The repeatability of As ^{III} concentration during the Johannesburg.	he adsorption by avocado seed obtained from a local shop in



Figure 6. The determination of the percentage (%) of As^{III} removed by the bio-adsorbent from (a) Sample A to (b) Sample B using ICPOES.

4. Conclusions

This work focused on removal of arsenic from aqueous solution using a powdered raw avocado seed. Important parameters that affect adsorption were optimized accordingly, pH 6, analyte 2 mg L⁻¹, dosage mass 0.8 g, and contact time 120 min, and temperature was constant from room temperature of 40°C. It was observed that raw avocado fruit seed can remove more than 50% of arsenic(III) from real water sample without any modification. The advantages of this bio-adsorbent is that it requires less preparation time and is readily available. The use of avocado seeds as a bio-adsorbent will also reduce the waste that is normally discarded in the streets, and it does not affect the food security issues since it is not edible. Due to the advantages that it possesses, it is strongly recommended that it should be incorporated in the removal of toxic heavy metals such as As^{III}. The adsorption isotherm data were tested for both Langmuir and Freundlich models. The regression coefficient and R_L values, best fitted Langmuir model ($R^2 = 0.97$), and the adsorption capacity was 93.75 mg/g. The Langmuir model means that chemisorption took place at the monolayer of the bio-adsorbent due to the availability of functional groups such as carboxylic acids that have high affinity for metal ions such As^{III}.

Acknowledgements

This work was supported by the National Research Foundation of South Africa (Thuthuka Grant No. 107066 and CPRR Grant No. 98887); the Centre for Nanomaterials Science Research; the National Nanoscience Postgraduate Teaching and Training Platform; the University of Johannesburg (UJ), South Africa; and the Faculty of Science, University of Johannesburg (UJ), South Africa.

Author details

Khathutshelo Catherine Mqehe-Nedzivhe, Khathutshelo Makhado, Oluwasayo Folasayo Olorundare, Omotayo Ademola Arotiba, Elizabeth Makhatha, Philiswa Nosizo Nomngongo and Nonhlangabezo Mabuba*

*Address all correspondence to: nmabuba@uj.ac.za

University of Johannesburg, Johannesburg, South Africa

References

 [1] James KA, Meliker JR, Nriagu JO. Arsenic. In: Quah SR, Cockerham WC, editors. The International Encyclopedia of Public Health, 2nd ed. vol. 1. Oxford: Academic Press; 2016; 27:170-175

- [2] Bissena M, Frimmel FH. Arsenic—A review. Part II: Oxidation of arsenic and its removal in water treatment. Clean Soil Air Water. 2003;**31**(2):97-107. DOI: 10.1002/aheh.200300485
- [3] Nahar N, Mandal A. Phytoremediation of arsenic from the contaminated soil using transgenic tobacco plants expressing ACR2 gene of Arabidopsis thaliana. Journal of Plant Physiology. 2017;218:121-126. DOI: 10.1016/j.32 jplph.2017.08.00
- [4] Patil-Shinde V, Mulani KB, Donde K, Chanvan NN, Ponrathnam S, Tambe SS. The removal of arsenite [As(III)] and arsenate [As(V)] ions from wastewater using TFA and TAFA resins: Computational intelligence based reaction modeling and optimization. Journal of Environmental Chemical Engineering. 2016;4(4):4275-4286. DOI: 10.1016/j.jece.2016.09.030
- [5] Çiftçi TL, Henden E. Nickel/nickel boride nanoparticles coated resin: A novel adsorbent for arsenic(III) and arsenic(V) removal. Powder Technology. 2015;269:470-480. DOI: 10.1016/j.powtec.2014.09.041
- [6] Banerji T, Chaudhari S. Arsenic removal from drinking water by electrocoagulation using iron electrodes—An understanding of the process parameters. Journal of Environmental Chemical Engineering. 2016;4(2016):3990-4000. DOI: 10.1016/j.jece.2016.09.007
- [7] Vahidnia A, van der Voet GB, de Wolff FA. Arsenic neurotoxicity A review. Human and Experimental Toxicology. 2007;**26**(10):823-832
- [8] Vaezi M, Bahar B, Mousavi A, Yaghmai M, Kasaeian A, Souri M, Jahani M, Alimoghaddam K, Ghavamzadeh A. Comparison of 60 and 80 mg/m² of daunorubicin in induction therapy of acute myeloid leukaemia. Heamatological Oncology. 2017;35(1):101-105. DOI: 10.1002/ hon.2236
- [9] Lakovleva E, Maydannik P, Ivanova TV, Sillanpää M, Tang WZ, Mäkila E, Salonen J, Gubal A, Ganeev AA, Kamwilaisak K, Wang S. Modified and unmodified low-cost iron-containing solid wastes as adsorbents for efficient removal of As(III) and As(V) from mine water. Journal of Cleaner Production. 2016;133:1095-1104. DOI:10.1016/j.jclepro.2016.05.147
- [10] Magoda C, Nomngongo PN, Mabuba N. Magnetic iron–cobalt/silica nanocomposite as adsorbent in micro solid-phase extraction for preconcentration of arsenic in environmental samples. Microchemical Journal. 2016;128:242-247. DOI: 10.1016/j.microc.2016.05.005
- [11] Mohan D, Pittman CU Jr. Arsenic removal from water/wastewater using adsorbents—A critical review. Journal of Hazardous Materials. 2007;142(1–2):1-53. DOI: 10.1016/j. jhazmat.2007.01.006
- [12] Ansari R, Sadegh M. Application of activated carbon for removal of arsenic ions from aqueous solutions. E-Journal of Chemistry. 2007;4(1):103-108. DOI: 10.1155/2007/829187
- [13] Lui Y, Ma S, Chen J. A novel pyro-hydrochar via sequential carbonization of biomass waste: Preparation, characterization and adsorption capacity. Journal of Cleaner Production. 2017;176:187-195. DOI: 10.1016/j.jclepro.2017.12.090
- [14] Moyo M, Chikazaza L, Dekhil AB, Hannachi Y, Ghorbel A, Boubaker T. Bioremediation of lead(II) from polluted wastewaters employing sulphuric acid treated maize tassel biomass. Journal of Chemistry and Ecology. 2013;5:689-695. DOI: 10.4236/ajac.2013.412083

- [15] Pérez-Sirvent C et al. Geochemical background levels of zinc, cadmium and mercury in anthropically influenced soils located in a semi-arid zone (SE, Spain). Geoderma. 2009; 148:307-317. DOI: 10.1016/j.geoderma.2008.10.017
- [16] Olorundare O. Potential application of activated carbon from maize tassel for the removal of heavy metals in water. Physics and Chemistry of the Earth Parts A/B/C. 2012;50:104-110. DOI: 10.1016/j.pce.2012.06
- [17] El-Nabarawy T, Petro NS, Abdel-Aziz S. Adsorption characteristics of coal-based activated carbons. II. Adsorption of water vapour, pyridine and benzene. Adsorption Science & Technology. 1997;15(1):47-57. DOI: 10.1177/026361749701500105
- [18] El-Nabarawy T, Petro NS, Abdel-Aziz S. Adsorption characteristics of coal-based activated carbons. 1. Adsorption of nitrogen and carbon dioxide. Adsorption Science & Technology. 1996;13(3):177-186. DOI: 10.1177/026361749601300304
- [19] Olorundare O. Activated carbon from lignocellulosic waste residues: Effect of activating agent on porosity characteristics and use as adsorbents for organic species. Water, Air, & Soil Pollution. 2014;225(3):1-14
- [20] Olorundare O. Steam activation, characterisation and adsorption studies of activated carbon from maize tassels. Chemistry and Ecology. 2014;**30**(5):473-490
- [21] Bhaumik M. Highly effective removal of toxic Cr(VI) from wastewater using sulfuric acidmodified avocado seed. Industrial & Engineering Chemistry Research. 2014;53(3):1214-1224. DOI: 10.1021/ie402627d
- [22] Díaz-Muñoz LL. Sorption of heavy metal ions from aqueous solution using acid-treated avocado kernel seeds and its FTIR spectroscopy characterization. Journal of Molecular Liquids. 2016;215:555-564. DOI: 10.1016/j.molliq.2016.01.022
- [23] Zhang S. Arsenite and arsenate adsorption on coprecipitated bimetal oxide magnetic nanomaterials: MnFe₂O₄ and CoFe₂O₄. Chemical Engineering Journal. 2010;158(3):599-607. DOI: 10.1016/j.cej.2010.02.013
- [24] Mandal S, Padhi T, Patel R. Studies on the removal of arsenic(III) from water by a novel hybrid material. Journal of Hazardous Materials. 2011;192(2):899-908. DOI: 10.1016/ jhazmat.2011.05.099
- [25] Ren Z, Zhang G, Chen JP. Adsorptive removal of arsenic from water by an iron–zirconium binary oxide adsorbent. Journal of Colloid and Interface Science. 2011;358(1):230-237. DOI: 10.1016//j.jcis.2011.01.013
- [26] Zhu Y. Avocado seed-derived activated carbon for mitigation of aqueous ammonium. Industrial Crops and Products. 2016;92:34-41. DOI: 10.1016/j.indcrop.2016.07.016
- [27] Desta MB. Batch sorption experiments: Langmuir and Freundlich isotherm studies for the adsorption of textile metal ions onto teff straw (*Eragrostis tef*) agricultural waste. Journal of Thermodynamics. 2013;2013(2013):1-6. DOI: 10.1155/2013/375830
- [28] Hall KR, Eagleton LC, Acrivos A, Vermeulan T. Pore and solid kinetics in fixed bed adsorption under constant pattern conditions. Industrial and Engineering Chemistry Fundamentals. 1966;5(2):212-223. DOI: 10.1021/i160018a011



IntechOpen