

We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,900

Open access books available

186,000

International authors and editors

200M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com



Intrinsically Disordered Proteins in Biomineralization

Magdalena Wojtas, Piotr Dobryszewski and Andrzej Ożyhar
Wrocław University of Technology
Poland

1. Introduction

Intrinsically disordered proteins (IDPs) have the potential to play a unique role in the study of proteins and the relationships between structure and function. Intrinsic disorder affects chemical and cellular events such as cell signaling, macromolecular self-assembly, protein removal and crystal nucleation and growth. This chapter explores the structural principles by which IDPs act and reveals the prevalence of IDPs in the field of biomineralization. It has been demonstrated that proteins involved in biomineralization are frequently very extended and disordered. Moreover, the disordered structure is integral to how these proteins fulfill their functions. We have focused on the analysis of polypeptide folding, the role of post-translational modifications, predictions of the structural disorder and the degree of disorder in secondary structures. Computational and biophysical strategies to analyze the secondary structures and evaluate the degree and nature of "disorder" in proteins are described. Biomineralization is the result of the orchestration of a series of protein-protein, protein-mineral and protein-cell interactions. Identifying unfolded functional domains in cell signaling may have a great impact in the study of tissue regeneration and biomineral formation. IDPs are typically organic components of biominerals. It is believed that they could act as a regulatory coordinator for specific interactions of many proteins, and thus many physiological processes such as formation of dentin and bone, the formation of sea urchin and crustacean exoskeletons. Here, we review what is currently understood about the molecular basis of biomineral formation. This includes protein interaction with metal ions, post-translational modifications, interactions with other proteins, or other factors that induce the formation of crystal shape and size along with the proper polymorph selection in relation to the role of IDPs.

2. Intrinsically disordered proteins

The history of IDPs goes back to the 1960s, with Linus Pauling's observation of the existence of regions in proteins with a disordered structure (Pauling & Delbruck, M., 1940). However, only a small group of researchers like Dunker, Uversky, Wright, Dyson, Tompa and others during the next forty years demonstrated that it was possible to depart from the paradigm that a protein's function is closely affiliated with its structure (Dyson & P.E. Wright, 2005; Tompa, 2011; Uversky & Dunker, 2010; P.E. Wright & Dyson, 1999). Currently, it is believed

that 20-50% of eukaryotic proteins contain at least one fragment belonging to the class of IDPs (Babu et al., 2011; Dunker et al., 2000). It is well known that globular proteins decrease their activity in a denatured state when a solution is subjected to high temperatures or chemical denaturants. The "structure-function" paradigm was not contested for many years until experimental data began to show that there was no stable three-dimensional structure for some protein fragments that had been attributed to particular functions. These proteins are in whole or in part, in contrast to globular proteins, heterogeneous ensembles of flexible molecules, unorganized and without a defined three-dimensional structure. According to these properties, the proteins are referred to as natively unfolded, intrinsically unfolded (IUP), intrinsically unstructured or intrinsically disordered (Dunker et al., 2005; Dyson & Wright, 2005; Tompa, 2005; Uversky, 2002). It has been previously shown that structural disorder is characteristic of proteins involved in important biological processes such as signal transmission, regulation of cell cycles, regulation of gene expression, activity of chaperone proteins, neoplastic processes, and biomineral formation (Dyson, 2011; Tompa, 2011; Uversky, 2010).

These processes require a series of dynamic macromolecular interactions and IDPs seem to be specially created for their functions. An IDP's meta-stable conformation allows it to bind to its protein partners as well as interact with high specificity and relatively low affinity. Furthermore, there is some experimental evidence showing that IDPs may interact with multiple partners, changing or adjusting the structures and functions of their partners (Tompa, 2005). Comparative analyses of the amino acid sequences of all currently known IDPs have shown common features. These proteins are characterized by amino acid compositions enriched with residues like A, R, G, Q, S, P, E and K that promote a disordered structure, with the small participation of other residues like W, C, F, I, Y, V, L and N, which simultaneously promote an ordered structure (Dunker et al., 2001). IDPs can be classified into five groups based on their relative functions: entropic chains, effectors, assemblers, scavengers, and display sites. Entropic chains act as flexible linkers between the globular domains of multidomain proteins. Effectors bind and modify the activity of a partner. Assemblers are able to simultaneously bind several ligands as multimolecular assemblies. Scavengers store or neutralize small ligands. Finally, display sites promote specific interactions within the active sites of enzymes that facilitate post-translational modifications (Tompa, 2002).

2.1 Methods for analyzing IDP structure

Based on the amino acid composition of IDPs, a number of algorithms have been proposed that predict regions containing a disordered structure. The most frequently used are PONDR (Romero et al., 2001), DISOPRED 2 (Ward et al., 2004a, 2004b), IUPred (Dosztanyi et al., 2005), GLOBPLOT 2 (Linding et al., 2004) and FoldIndex (Uversky et al., 2000). More algorithms can be found in the DisProt database (Sickmeier et al., 2007). These algorithms operate on the principle of a neuronal network "trained" using amino acid sequences belonging to experimentally confirmed IDPs. It has been observed that sequences that have low complexity or are abundantly charged and/or frequently post-translationally modified (e.g. phosphorylated) usually adopt a stretched, unordered conformation (Romero et al., 2001). IDPs are often characterized by charge-hydropathy

plots. Based on the normalized net charge and mean hydrophobicity, proteins can be categorized into either globular folded proteins or IDPs. IDPs are specifically localized within a unique region of charge-hydrophobicity proteins (Uversky et al., 2000). Figure 1A shows a charge-hydrophobicity plot for experimentally confirmed IDPs and globular proteins, while Figure 1B presents a charge-hydrophobicity plot for proteins involved in biomineralization.




Fig. 1. Charge-hydrophobicity plots. The solid line represents the contractual boundary between disordered and ordered proteins. (A) Comparison of charge-hydrophobicity for IDPs (black dots) and globular proteins (white dots). (B) Proteins involved in biomineralization represented on the charge-hydrophobicity plot. Black triangles show experimentally confirmed IDPs, while white triangles represent proteins whose secondary structure has not been studied.

Even this simple analysis indicates that many proteins involved in biomineralization could be IDPs. However, computer predictions themselves can not be relied on as the sole evidence of the absence of structural order in a protein. Such evidence only invites further experimental study, which could include X-ray diffraction analysis (Dunker & Obradovic, 2001), multidimensional nuclear magnetic resonance spectroscopy (NMR) (Bai et al., 2001), circular dichroism spectroscopy (CD) (Tompa, 2002), differential scanning microcalorimetry (DSC) (Mendoza et al., 2003), X-ray scattering at small angle (SAXS) (Millett et al., 2002).

3. IDPs found in calcium phosphate related mineralization

In bone and dentin, collagen acts as a structural matrix whereas hydroxyapatite (HA) nucleation is regulated by the acidic phosphoproteins (Chen et al., 1992; Glimcher, 1989). These non-collagenous proteins (NCPs) play crucial roles in the organization of the collagen matrix and in the modulation of HA crystal formation (Ganss et al., 1999). NCPs

are often classified as IDPs. Some examples of IDPs engaged in HA formation are presented below.

3.1 SIBLINGs

Small integrin-binding ligand, N-linked glycoproteins (SIBLINGs) with NCPs are involved in the mineralization of bone and dentin (George & Veis, 2008; Qin et al., 2004). Within the family of human SIBLINGs there is limited sequence similarity; however, they share common features, such as: (i) similar gene organization and chromosome localization, (ii) RGD (arginine-glycine-aspartate) motifs mediating cell attachment/signaling *via* their interactions with cell-surface integrins, (iii) extensive post-translational modifications like phosphorylation and glycosylation, (iv) abundance of acidic residues, (v) calcium ions and collagen binding ability (George & Veis, 2008; Qin et al., 2004), (vi) intrinsically disordered molecular character (Tomba, 2002). The SIBLINGs family includes osteopontin (OPN), bone sialoprotein (BSP), dentin matrix protein 1 (DMP1), matrix extracellular phosphoglycoprotein (MEPE) and dentin sialophosphoprotein (DSPP). DSPP gives rise to two mature products, dentin phosphoprotein (also called phosphophoryn) (DPP) and dentin sialoprotein (DSP) (George & Veis, 2008; Qin et al., 2004).

3.1.1 DMP1

The highly acidic protein (D and E constitute 29% of all residues) DMP1 acts as a nucleator for HA deposition *in vitro* (He et al., 2003a). The disordered character of DMP1 has been shown using several methods (Tab. 1). CD and FTIR measurements have shown that DMP1 has a random structure in solution, however upon calcium ions binding DMP1 undergoes a slight conformational change to a more ordered structure. SAXS and DLS confirmed a calcium-induced disorder-to-order transition in DMP1 leading to oligomerization (Gericke et al., 2010; He et al., 2003b). Moreover, it has been shown that the DMP1 molecule assumes an elongated shape (He et al., 2005a). Further studies have revealed that two specific acidic clusters (ESQES and QESQSEQDS) in DMP1 are responsible for the calcium-induced oligomerization and *in vitro* nucleation of apatite crystals (He et al., 2003b). This calcium-induced conformational change of DMP1 could be the structural basis for biocomposite self-assembly (He et al., 2003b).

The lack of a rigid structure enables DMP1 to serve multiple functions, not only in biomineralization, but also in osteoblast differentiation and maturation (Narayanan et al., 2003). Nonphosphorylated DMP1 is localized in the nucleus where it acts as a transcriptional component for the activation of matrix genes involved in mineralized tissue formation (Narayanan et al., 2003). It binds the DSPP gene promoter and activates DSPP gene expression. Calcium ions released from intracellular stores bind DMP1 and induce in DMP1 a conformational change and phosphorylation by casein kinase 2 (CK2). Finally, the phosphorylated protein is exported to the extracellular matrix, where it acts as a nucleator of hydroxyapatite (Narayanan et al., 2003). The DNA binding domain is localized within the C-terminal region of DMP1 (Narayanan et al., 2006). Extracellular DMP1 also has the ability to strongly bind the H factors, integrin $\alpha\beta 3$ and CD44 (Jain et al., 2002), and it is specifically involved in signaling via extracellular matrix-cell surface interaction (Wu et al., 2011).

Organism	Protein	pI	Methods	Reference
Mammals	DMP1	4.0	CD, DLS, FTIR, SAXS	(Gericke et al., 2010; He et al., 2003a, 2003b)
	DPP	2.8	CD, NMR, SAXS	(Cross et al., 2005; Evans et al., 1994; Fujisawa & Kuboki, 1998; George & Hao, 2005; He et al., 2005b; Lee et al., 1977)
	BSP	4.1	CD, NMR, SAXS	(Fisher et al., 2001; Tye et al., 2003, 2005; Wuttke et al., 2001)
	OPN	4.4	CD, NMR, FTIR	(Fisher et al., 2001; Gorski et al., 1995)
	amelogenin	6.6	CD, NMR	(Buchko et al., 2010; Delak et al., 2009b; Ndao et al., 2011;Shaw et al., 2008)
	statherin	8.0	CD, NMR	(Long et al., 2001; Naganagowda et al., 1998; Raj et al., 1992)
	lithostathine	5.7	CD	(Gerbaud et al., 2000)
<i>Haliotis rufescens</i>	AP7	5.2	CD, NMR	(Kim et al., 2004, 2006a; Michenfelder et al., 2003; Wustman et al., 2004)
	AP24	5.3	CD, NMR	(Michenfelder et al., 2003; Wustman et al., 2004)
	Lustrin A	8.1	NMR	(Wustman et al., 2003; Zhang et al., 2002)
<i>Pinctada fucata</i>	n16	7.5	CD, NMR	(Amos et al., 2011; Collino & Evans, 2008; Kim et al., 2004, 2006b)
	ACCBP	4.7	CD	(Amos et al., 2009)
	PFMG1	7.9	CD	(Liu et al., 2007)
<i>Atrina rigita</i>	Asprich	2.7-3.5	CD, NMR	(Collino et al., 2006; Delak et al., 2009a, 2008; Kim et al., 2008; Ndao et al., 2010)
<i>Procambrus clarkii</i>	CAP-1	3.9	CD	(Inoue et al., 2007)
<i>Strongylocentrotus purpuratus</i>	SM50	10.8	CD, NMR	(Xu & Evans, 1999; Zhang et al., 2000)
	PM27	8.1	CD, NMR	(Wustman et al., 2002)
<i>Danio rerio</i>	Stm	4.1	CD, gel filtration	(Kaplun et al., 2008, 2009)

Table 1. IDPs involved in biomineralization of calcium carbonate and phosphate for which a disordered structure has been confirmed experimentally.

3.1.2 DSPP

DSPP undergoes proteolytic cleavage to DPP and DSP. DPP is most abundant in dentin, but also present in bone (George & Hao, 2005; Lee et al., 1977). At least 75% of the DPP sequence (isolated from dentin) is composed of S and D residues and 85-90% of the S residues are phosphorylated (George & Veis, 2008; He et al., 2005b; Huq et al., 2000). In solution DPP isolated from dentin behaves as a fairly extended, random-chain molecule due to electrostatic repulsion (Table 1), as has been shown by CD studies (Lee et al., 1977). The

presence of calcium ions reduces DPP solubility, which indicates aggregation of the protein (Lee et al., 1977). It has been demonstrated that nonphosphorylated DPP has lower calcium binding ability than the phosphorylated form and induces amorphous calcium phosphate formation, while the phosphorylated form promotes plate-like apatite crystals (He et al., 2005b). SAXS studies revealed a calcium-induced conformation change from an extended structure to a more compact one, but only in phosphorylated DPP. Nonphosphorylated DPP was disordered irrespective of the presence of calcium ions at various concentrations (George & Hao, 2005; He et al., 2005b). NMR spectroscopy also confirmed high mobility and flexibility of DPP in the absence of calcium ions, and decreased mobility in the presence of calcium ions (Cross et al., 2005; Evans et al., 1994). Solid-state NMR spectroscopy enabled investigation of the DPP structure when bonded to HA. The secondary structure of DPP bound to crystal was very extended and largely disordered. A majority of DPP residues interacted with crystal. (Fujisawa & Kuboki, 1998). This disordered molecular structure facilitates DPP’s extension across the surface of a crystal and allows it to cover the surface with only a small number of molecules, all of which results in a highly inhibitory effect on crystal growth (Fujisawa & Kuboki, 1998).

While DPP structure has been extensively explored, DSP structural studies are still unavailable. However, bioinformatic predictions strongly suggest that DSP is also an IDP (Table 2).

Organism	Protein	pI	Overall percent disordered		
			IUPred	DISOPRED2	PONDR
Mammals	DSP	4.5	100	100	73
	MEPE	8.6	95	60	64
<i>Picntada fucata</i>	Aspein	1.5	100	100	100
	Prismalin-14	3.9	0	0	9
<i>Patinopecten yessoensis</i>	MSP-1	3.2	97	98	96
<i>Pinna nobilis</i>	Calprismin	4.9	12	0	74
<i>Crassostrea nippona</i>	MPP1	2.2	100	98	97
<i>Nautilus macromphalus</i>	Nautilin-63	9.2	66	4	41
<i>Procambrus clarkii</i>	GAMP	4.2	63	73	63
	CAP-2	4.2	18	2	45
	Casp-2	4.3	33	8	68
<i>Orchestia cavimana</i>	Orchestin	4.5	58	34	69
<i>Cherax quadricarinatus</i>	GAP 65	5.0	2	0	11
	GAP 10	5.5	4	0	37
<i>Penaeus japonicus</i>	Crustocalcin	3.9	45	37	81
<i>Strongylocentrotus purpuratus</i>	SM30	6.2	25	0	28
	SM32	8.3	44	44	47
	SM37	10.4	60	43	56
	phosphodontin	3.9	96	94	94
<i>Oryzias latipes</i>	Stm-like	3.8	100	98	94
<i>Oncorhynchus mykiss</i>	OMM-64	3.5	97	96	92
<i>Gallus gallus</i>	Ovocleidin-116	6.6	91	57	78

Table 2. Bioinformatic predictions of a disordered structure in proteins involved in biomineralization.

All three bioinformatic tools (IUPred, DISOPRED2, and PONDR) predict that DSP is largely or completely disordered. DSP, similarly to DPP, also has a low pI value, which causes electrostatic repulsion that leads to an extended structure. However, this presumption requires experimental confirmation.

3.1.3 BSP

BSP is a multifunctional protein involved in cell attachment, signaling, HA binding, HA nucleation and collagen binding (Ganss et al., 1999). BSP is relatively specific to skeletal tissues and is the most abundant protein in bone (Bianco et al., 1991). NMR, CD and SAXS studies of BSP showed a high level of disordered structure (Table. 1) (Fisher et al., 2001; Tye et al., 2003, 2005; Wuttke et al., 2001). Post-translationally, unmodified BSP has lower rates of migration during SDS-PAGE, as do other IDPs (Stubbs et al., 1997). BSP visualized by electron microscopy after rotary shadowing was an extended monomer possessing a globular structure, probably on the C-terminus of the protein (Wuttke et al., 2001). BSP treated with 6 M Gdm-HCl lost its residual α -helix and β -sheet structure. Structural studies indicated that BSP had IDP-like characteristics, but not a random structure (Wuttke et al., 2001). Calcium ions had a significant effect on BSP conformation, in contrast to DMP1 and DPP (Tye et al., 2003; Wuttke et al., 2001). The flexibility and plasticity of BSP may enable cell attachment to HA. Additionally, BSP has a strong affinity for HA (Fujisawa et al., 1997), while on the other hand, RGD sequences allow integrin binding (Fujisawa et al., 1997; Oldberg et al., 1988). Hence, the extension and flexibility of BSP may be advantageous to its function as a bridge for the cell attachment of HA (Tye et al., 2003). The intrinsic disorder of BSP seems to be important for interacting with type I collagen (Tye et al., 2005).

3.1.4 OPN

While DPP, BSP and DMP1 are relatively specific to bone and teeth, OPN is also present in the brain, kidney, smooth muscle, macrophages, inner ear and body fluids (milk, urine, bile) (George & Veis, 2008; Gericke et al., 2005; Kazanecki et al., 2007). Its ubiquitous expression pattern and variations in phosphorylation, glycosylation and sulphation suggest that OPN fulfills many different functions (George & Veis, 2008). Moreover, OPN controls the formation of calcium phosphate (Goldberg & Hunter, 1995), calcium carbonate (Chien et al., 2008), and calcium oxalate (Grohe et al., 2007) crystals. NMR, CD and FTIR studies demonstrated that OPN is an IDP in solution (Tab.1) (Fisher et al., 2001; Gorski et al., 1995). The addition of calcium ions had little effect on the CD spectrum of OPN, while increasing protein concentration led to a more organized secondary structure (Gorski et al., 1995). Hence, it was suggested that OPN conformation in solution may be different from the conformation of OPN adsorbed to HA, because the local concentration of OPN in the semi-solid matrix might be relatively high (Gorski et al., 1995). This theory is supported by the observation that antibodies do not recognize OPN bound to HA, while they are able to recognize OPN bound to plastic (Gorski et al., 1995). Moreover, the acidic peptide based on the OPN sequence, which was examined by RosettaSurface, was able to adsorb to a calcium oxalate crystal surface in multiple conformations (Chien et al., 2009).

OPN is a substrate of tissue transglutaminase (Prince et al., 1991). Investigations of polymeric OPN showed a 5-fold increase in OPN binding to collagen type I when it was a polymer than when it was a monomer (Kaartinen et al., 1999), which indicates that there is a conformational change in OPN upon cross-linking. CD measurements demonstrated that

cross-linked OPN has a more organized structure than monomeric OPN (Kaartinen et al., 1999). It seems that OPN needs molecular crowding to assume a more ordered structure.

OPN found in non-mineralized tissues may or may not be phosphorylated, while bone OPN is always phosphorylated (George & Veis, 2008; Veis et al., 1997). Low phosphorylated OPN from bone (38%) is an effective HA mineralization inhibitor in contrast to highly phosphorylated OPN from milk (96%), which promotes HA formation and growth. The dephosphorylated form had no significant effect (Gericke et al., 2005). The degree to which OPN affected HA formation depended on the level of phosphorylation (Gericke et al., 2005). It has been suggested that the binding of OPN to HA alters OPN conformation, facilitating recruitment and activation of macrophages that remove pathologic HA deposits (Steitz et al., 2002). It was also shown that dephosphorylated OPN loses its ability to inhibit smooth muscle cell calcification (Jono et al., 2000).

3.2 Enamel proteins

Amelogenins are a protein family derived from a single gene by alternative splicing and controlled, post-secretory processing. They are abundant in tooth enamel, but amelogenin has also been identified in dentin, bone, cartilage and nonmineralizing tissues such as those of the brain, salivary glands and macrophages (Gruenbaum-Cohen et al., 2009; Lyngstadaas et al., 2009). Amelogenin is involved in biomineralization as well as cell signaling events (Gruenbaum-Cohen et al., 2009; Lyngstadaas et al., 2009; Veis, 2003). The primary sequence of amelogenin is highly conserved, especially the N-terminal Tyr-rich and C-terminal charged regions (Delgado et al., 2005). Determination of amelogenin's secondary structure has been hampered by the self-association of the protein (Li et al., 2006). Far UV CD and NMR spectra demonstrated that amelogenin in a monomeric form is largely disordered (Table 1). There is no well-defined, continuous region with an ordered structure, but some residual secondary structure was observed. In addition, amelogenin exists in at least two conformations (Buchko et al., 2010; Delak et al., 2009b; Ndao et al., 2011). Amelogenin can interact with other important proteins engaged in enamel formation (Bartlett et al., 2006). Amelogenin binds to CD63 and LAMP1 receptors, which mediate signal transduction events and endo-, pinocytosis, and phagocytosis, respectively. Both partners interact with the same amelogenin motif, which is largely disordered and accessible to the external environment (Shapiro et al., 2007; Zou et al., 2007).

The large number of alternatively spliced variants, expression in different tissues and the intrinsically disordered character of amelogenin reflect the multifunctionality of the protein, which is probably a common feature among IDPs.

Ameloblastin is also involved in enamel biomineralization, interactions between the ameloblasts and enamel extracellular matrix, and regeneration of hard-tissue. No NMR or CD studies of ameloblastin are available; however, bioinformatic analysis and molecular modeling strongly suggest that the protein is an IDP (Vymetal et al., 2008).

3.3 Statherin

Statherin is an inhibitor of the nucleation and growth of HA in the supersaturated environment of saliva (Hay et al., 1984; Johnsson et al., 1991; Stayton et al., 2003). The N-terminal region of statherin contains highly acidic motifs (DSpSpEE, where Sp indicates a

phosphoserine residue), which are important for adsorption of statherin onto the surface of HA and the inhibition of HA growth (Raj et al., 1992). Statherin was reported as unstructured in solution using NMR techniques (Naganagowda et al., 1998). Far UV CD experiments showed that N-terminal regions of statherin had a strong tendency to adopt an α -helical structure (upon the addition of TFE), while middle and C-terminal portions of this protein were flexible and preferred to adopt an unordered conformation (Naganagowda et al., 1998; Raj et al., 1992). Solid-state NMR applied to examine the structure of statherin bound to HA (Tab. 1) demonstrated, that under biologically relevant conditions, 12 residues of the N-terminus of statherin were in a helical conformation and that they were strongly adsorbed to the HA surface. In contrast, middle and C-terminal regions weakly interacted with HA and were highly mobile. The mobility of statherin on HA surfaces could allow it to effectively block more nucleation sites than a very rigidly bonded protein (Long et al., 2001).

4. IDPs found in calcium carbonate related mineralization

Calcium carbonate biominerals are widespread in nature. They occur in vertebrates as well as invertebrates, where they fulfill various functions. Here, we present the characteristics of IDPs involved in calcium carbonate crystal formation.

4.1 Lithostathine

Pancreatic fluid is supersaturated with calcium and carbonate ions; however, stones are observed only in cases of patients with chronic calcifying pancreatitis (De Caro et al., 1988; Moore & Verine, 1987). Lithostathine, a pancreatic glycoprotein, inhibits the growth and nucleation of calcium carbonate crystals. The C-terminal region of lithostathine is homologous with C-type lectins (Patthy, 1988). The crystal structure of lithostathine has been determined. However, the 13 residues of the N-terminus, including the glycosylation site, are flexible in the crystal (Bertrand et al., 1996). Far UV CD spectra of the N-terminal region are typical for random-coil structures (Table 1) (Gerbaud et al., 2000). Interestingly, the short N-terminal peptide of lithostathine is essential for the inhibition of nucleation and crystal growth. The glycosylated N-terminal peptide generated by limited trypsin hydrolysis inhibited crystal growth similarly to full-length lithostathine, while the C-terminal polypeptide was inactive. A synthetic N-terminal peptide, but not glycosylated was equally active (Bernard et al., 1992). Hence, it was postulated that backbone flexibility is essential for the inhibitory effect of the protein (Gerbaud et al., 2000).

4.2 Mollusk shell proteins

The mollusk shell is a commonly used model system for studying calcium carbonate biomineralization. Some mollusks have developed a bilayer of composite materials. Interestingly, the two layers, prismatic and nacreous, are composed of different forms of calcium carbonate polymorph, calcite and aragonite, respectively (Evans, 2008).

Several acidic proteins from *Haliotis rufescens* have been identified and characterized. AP7, AP8 and AP24 (aragonitic protein of molecular weight 7kDa, 8kDa and 24kDa, respectively) have been identified from the demineralized nacre protein fraction (Fu et al., 2005; Michenfelder et al., 2003). *In vitro* mineralization studies showed that AP7 and AP24 interacted with the step edges of growing calcite, which inhibited growth (Michenfelder et

al., 2003). Analysis of the AP7 and AP24 sequence revealed that the N-terminus of both proteins (1-30 residues of the mature protein) is characterized by calcite binding domains. Both sequences are capable of affecting calcium carbonate crystal growth *in vitro* (Michenfelder et al., 2003). Far-UV CD studies of AP7 showed that the N-terminus of AP7 adopts a random-coil or extended conformation in solution (Tab 1.) (Michenfelder et al., 2003; Wustman et al., 2004), while the C-terminus is α -helical (Kim et al., 2006a). Interestingly, AP7's C-terminus end did not influence crystal growth (Kim et al., 2006a), while AP7's N-terminus was responsible for interactions with calcium ions and led to an inhibition of calcite growth *in vitro* (Kim et al., 2004; Michenfelder et al., 2003). It should be noted that full-length AP7 protein had the highest effect on calcite crystal growth (Kim et al., 2006a). This observation suggests that the flexibility and plasticity of IDPs might be crucial factors which inhibit crystal growth, although the well-defined, ordered secondary structure may also be necessary. It should be noted that high concentrations of calcium ions led to the precipitation of AP7's N-terminus, which may indicate calcium-dependent oligomerization (Kim et al., 2004). Finally, full-length AP7 undergoes a conformational change to an α -helical structure as a function of TFE concentration (Amos & Evans, 2009).

Another protein from *Haliotis rufescens*, Lustrin A, is a component of the intercrystalline organic matrix lying between layers of aragonite tablets. The postulated role of Lustrin A is to enhance nacre layers' resistance to fracture (Shen et al., 1997). NMR studies showed that the N-terminal end of Lustrin A contains loop regions, which behave as entropic springs that endow it with resilience and flexibility (Table 1). This sequence is believed to be one of several putative elastic motifs within Lustrin A (Zhang et al., 2002). Although the sequence adopts a relatively defined secondary structure, the plasticity of Lustrin A's loop regions seems to be crucial to its postulated role in resisting fracture. Further studies of model peptides based on Lustrin A sequences showed two domains (RKS_Y and D4) existing largely in conformationally labile random-coil and extended states (Wustman et al., 2003). Possibly, these features permit side chain accessibility to exposed calcium carbonate crystal surfaces (Wustman et al., 2003). In addition, its D4 domain, which as the name implies contains 4 D residues, inhibits nucleation of calcite crystals *in vitro* (Wustman et al., 2003). The inhibitory effect strongly supports the theory that IDPs control biomineralization processes.

Another mollusk protein, n16, has been isolated from the nacre layer of *Pinctada fucata* (Samata et al., 1999). The analysis of n16's primary sequence revealed the requisite amino acid residues associated with a calcium carbonate modification domain within the C- and N-terminae of the mature protein (n16-C and n16-N, respectively) (Kim et al., 2004). Both sequences modify the morphology of calcium carbonate crystals and induce calcite growth *in vitro* (Kim et al., 2004). Far-UV CD and NMR studies demonstrated that n16 exists as a random-coil molecule; however, increasing the concentration of the peptide led to a conformational equilibrium between random-coil and β -sheet conformers (Tab. 1) (Kim et al., 2004). Interestingly, in the presence of TFE, n16-N adopted a β -sheet conformation, unlike AP7 and AP24, which adopted an α -helical conformation. Thus, AP7, AP24 and n16N are conformationally labile, but exhibit different folding propensities (Collino & Evans, 2008). Moreover, random scrambling of n16-N abolishes its concentration-dependent conformational rearrangement capability, resulting in a decrease of its ability to affect crystal growth (Kim et al., 2006b). It was also shown that n16-N

simultaneously interacted with β -chitin and the nucleating mineral phase, finally leading to aragonite formation *in vitro* (Keene et al., 2010). Also noteworthy, n16-N alone induced calcite formation (Kim et al., 2004). It has been suggested that the binding of n16-N to β -chitin could trigger disorder-to-order transitions. In summary, the intrinsically disordered structure of n16-N facilitates interactions with its partners (like for example β -chitin) and disorder-to-ordered transition seems to be crucial for self-assembly (Amos et al., 2011; Collino & Evans, 2008; Keene et al., 2010).

ACCBP (amorphous calcium carbonate binding protein) was found in the extrapallial fluid of *Pinctada fucata* (Ma et al., 2007), while PFMG1 (*Pinctada fucata* mantle gene protein 1) controls calcium carbonate nucleation and is believed to assist in the formation of pearl nacre (Liu et al., 2007). Based on previously obtained results (Amos et al., 2009; Collino et al., 2006; Keene et al., 2010; Kim et al., 2004; Wustman et al., 2004) and bioinformatic predictions, the C- and N- terminal sequences of both proteins (PFMG1-C, PFMF1-N and ACCN) have been studied to find mineralization activity and conformational disorder (Amos et al., 2009; Liu et al., 2007). Far UV CD spectroscopy confirmed that PFMG1-C, PFMF1-N and ACCN possess a combination of a random-coil conformation and other secondary structures (Table 1). Moreover, the addition of TFE led to disorder-to-order transitions in all peptides (Amos et al., 2009; Liu et al., 2007).

Aspein is another extremely acidic (60.4 % of D) protein from *Pinctada fucata* (Tsukamoto et al., 2004). The extraordinary acidic character of Aspein and the fact that SDS-PAGE overestimated its molecular mass (Takeuchi et al., 2008; Tsukamoto et al., 2004) suggested that Aspein is also an IDP. Bioinformatic tools predicted that Aspein is completely disordered (Table 2). Prismaticin-14 from the prismatic layer of *Pinctada fucata* also contains putative intrinsically disordered regions. Firstly, G/Y-rich regions might form glycine loop motifs, which may contribute to the elasticity of the molecule (Suzuki et al., 2004). This motif is responsible for interaction with chitin (Suzuki & Nagasawa, 2007). Secondly, D-rich regions within the N- and C- terminae of Prismaticin-14, which are responsible for inhibiting calcium carbonate precipitation *in vitro* (Suzuki & Nagasawa, 2007), also might be intrinsically disordered. However, only PONDR predicted short intrinsically disordered regions in Prismaticin-14. IUPred and DISOPRED2 didn't predict any disordered structure (Table 2).

Ten acidic Asprich proteins (51-61% of acidic residues) have been identified from *Atrina rigida* (Gotliv et al., 2005). The Asprich family might be the product of alternative RNA splicing of the same gene and are arbitrarily divided into six domains: (i) N-terminal signal peptide, (ii) basic domain, (iii) the acidic1 domain, identical in all the Asprich proteins, (iv) the variable acidic domain, which differs among Asprich proteins, (v) conserved DEAD repeat domain, (vi) and conserved acidic2 domain (Gotliv et al., 2005). All three conserved acidic domains (acidic1, DAED and acidic2) are intrinsically disordered and they control calcium carbonate crystal growth (Collino et al., 2006; Delak et al., 2009a; Kim et al., 2008). Far UV CD studies of acidic1, DAED and acidic2 domains demonstrated that these peptides exist in a random-coil conformation in equilibrium with other secondary structures. Interestingly, a significant conformational change was not observed at lower pH and in the presence of calcium ions, which suggests that structural lability is a result of more than just electrostatic repulsion (Collino et al., 2006; Delak et al., 2009a; Kim et al., 2008). NMR spectroscopy showed that calcium ions induced local perturbations in conformations of

acidic1, DAED and acidic2, but the structure was still very flexible (Table 1) (Delak et al., 2009a). Asprich proteins are able to adopt a more ordered structure in the presence of TFE, indicating that they might undergo a disorder-to-order transition (Ndao et al., 2010).

Several other acidic proteins have been identified from mollusk shells, for instance: MSP-1 (molluscan shell protein 1) from *Patinopecten yessoensis* (Sarashina & Endo, 2001), Caspartin and Calprismin from *Pinna nobilis* (Marin et al., 2005), moluscan phosphorylated protein 1 (MPP1) from *Crassostrea nippona* (Samata et al., 2008), P95 from *Unio pictorum* (Marie et al., 2008), and Nautilin-63 from *Nautilus macromphalus* (Marie et al., 2011). No secondary structure analyses of these proteins have been published, hence it is unknown if they are IDPs. However, MSP-1 and MPP1 are likely to be largely disordered, while Nautilin-63 probably consists of a combination of disordered and ordered regions (Table 2).

4.3 Crustacean associated IDPs

Most crustaceans possess a calcified exoskeleton that is periodically molted to permit growth. Hence, their calcium metabolism is tightly linked to seasonal molting cycles. Aquatic crustaceans take calcium from the water, whereas terrestrial species have developed several storage strategies (Luquet et al., 1996; Testeniere et al., 2002). During the premolting period, calcium is stored in the hemolymph, the hepatopancreas, sterna plates, gastroliths or posterior caeca, depending on the species (Luquet et al., 1996; Meyran et al., 1984). All calcified deposits correspond to biomineralized structures (Testeniere et al., 2002). After ecdysis, stored calcium is quickly reabsorbed and translocated to harden the new exoskeleton (Ishii et al., 1996). The exoskeleton of crustaceans consists of calcium carbonate and chitin-protein microfibrillar frameworks.

Calcification-associated peptide 1 (CAP-1) is an acidic protein isolated from the exoskeleton of *Procambrus clarkii* (Inoue et al., 2001). The C-terminal region is especially acidic and possesses a phosphoserine residue, which is essential for the inhibition of calcium carbonate precipitation and the calcium-binding activities of CAP-1 (Inoue et al., 2003, 2007). Far UV CD studies demonstrated that CAP-1 has a random-coil conformation in equilibrium with a residual β -sheet (Table 1). The N-terminal region contributes to maintaining the overall conformation of CAP-1 (Inoue et al., 2007). It has been suggested that the N-terminal fragment of CAP-1 inhibits crystal growth less efficiently, because it possesses a more ordered structure than the C-terminal fragment (Inoue et al., 2007). This hypothesis is supported by the observation that CAP-2, which has a sequence similar to CAP-1, but shorter by 17 residues at the C-terminus, is a less active inhibitor of calcium carbonate precipitation (Inoue et al., 2004, 2007).

There are more proteins identified from the calcium storage organs of exoskeleton in crustaceans like CAP-2 (Inoue et al., 2004), Casp-2 (calcification-associated soluble protein-2) (Inoue et al., 2008) and GAMP (gastrolith matrix protein) (Ishii et al., 1996) from *Procambrus clarkii*, orchertin from *Orchestia cavimana* (Hecker et al., 2004; Luquet et al., 1996), gastrolith protein 65 (GAP 65) (Shechter et al., 2008) and gastrolith protein 10 (GAP 10) (Glazer et al., 2010) from *Cherax quadricarinatus*, and crustocalcin (CCN) from *Penaeus japonicus* (Endo et al., 2004). Most of them are acidic; however, no secondary structure analysis has been performed. Bioinformatic predictions indicated that all of these proteins might possess intrinsically disordered regions (Table 2).

4.4 Sea urchin larval spicule matrix protein IDPs

Sea urchins have an elaborate, calcified skeleton, which is a valuable model system for analyzing molecular regulation of biomineralization (Wilt & Etensohn, 2007; 2008). The skeleton is a network of calcified spicules, consisting of calcium and magnesium carbonate (in a 19:1 ratio), a surrounding extracellular matrix and small amounts of occluded matrix proteins (Wilt & Etensohn, 2007; 2008). It has been estimated that about 40-50 different proteins are associated with the spicule (Killian & Wilt, 1996). SM30, SM32, PM27, SM37, and SM50 have been identified in *Strongylocentrotus purpuratus* (Benson et al., 1987; George et al., 1991; Harkey et al., 1995; Katoh-Fukui et al., 1991; Lee et al., 1999). SM32, PM27, SM37, and SM50 are basic, non-glycosylated, closely related proteins. They contain SP, C-type lectin domains and a variable number of proline-rich repeats (Killian & Wilt, 2008; Wilt, 1999; Wilt & Etensohn, 2007; 2008).

SM50 is involved in the depositing initial calcite crystals as well as the elongation of the spicule elements, and it probably interacts with growing calcium carbonate crystals (Killian & Wilt, 2008). The C-terminal domain of SM50 contains two motifs exhibiting traits that are characteristic for IDPs. Firstly, GVGG and GMGGQ repeats are present, which are sequence homologs of elastin and spider silk protein repeats. NMR studies of the C-terminal fragment showed that it exists as a β -sheet with an extended structure (Tab. 1). This structure might play an important role in matrix assembly, protein stability, molecular elasticity and protein-crystal recognition within the spicule's mineralized matrix (Xu & Evans, 1999). Secondly, PNNP repeat motifs are believed to play an important role in mineralization. P-rich sequences often exhibit the extended, flexible structure responsible for protein-protein and/or protein-crystal recognition, while N residues represent putative sites for side chain hydrogen bonding (Zhang et al., 2000). PNNP repeats adopt an extended, twisted conformation consisting of a mixture of turn-like and coil-like regions, most likely interconverting with the coiled-coil state (Zhang et al., 2000). Several possible roles for PNNP have been suggested: (i) as a mineral recognition domain, (ii) as a self-assembly domain, (iii) as a molecular spacer (Zhang et al., 2000).

PM27 contains PGMG repeated motifs, which have been examined by far UV CD, and NMR spectroscopy (Table 1). It has also been shown that this motif exhibits a random-coil or loop-like structure characterized by the ongoing oscillations between different conformational states (Wustman et al., 2002).

Bioinformatic tools also predicted that SM30, SM32, and SM37 might be partially disordered (Tab. 2). SM30, the most abundant spicule matrix protein, an acidic glycoprotein, also contains signal peptide and C-type lectin domains (Killian & Wilt, 1996; Wilt, 1999). It is coded by six genes, which are variously expressed in different mineralized structures (Illies et al., 2002; Killian et al., 2010; Livingston et al., 2006). Another protein isolated from *Strongylocentrotus purpuratus* is phosphodontin. It is the major acidic phosphoprotein of the tooth matrix (Mann et al., 2010). Phosphodontin is probably an IDP. All three predictors indicated that phosphodontin is disordered (Table 2).

4.5 Otolith related IDP

Otoliths are mineral deposits in the inner ear of fish, responsible for sensing gravity and detecting linear acceleration. They are mainly composed of calcium carbonate, but also contain

a small fraction of organic molecules (1-5 % w/w). The organic matrix acts as a template for depositing crystals, promoting crystal growth in certain directions, and inhibiting crystal growth in undesired directions (Allemand et al., 2007; 2008; Ross & Pote, 1984).

Starmaker (Stm) and otolith matrix macromolecule-64 (OMM-64) are acidic proteins from *Danio rerio* and *Oncorhynchus mykiss* otoliths, respectively (Sollner et al., 2003; Tohse et al., 2008). Both proteins have similar gene organization and 25% sequence identity, and because of this, it has been postulated that they are orthologs (Sollner et al., 2003; Tohse et al., 2008). It should also be noted that DSPP is the close human functional analog of Stm (Sollner et al., 2003). Stm is responsible for the size, shape and polymorph selection in otoliths (Sollner et al., 2003). It has been demonstrated by several methods that Stm is an IDP (Tab. 1) (Kaplon et al., 2008, 2009). Far UV CD spectrum of Stm yielded the signatures typical for a disordered protein. The extended conformation of Stm results in the large hydrodynamic radius of the molecule, as was shown by gel filtration and ultracentrifugation. Interestingly, calcium ions led to a lower hydrodynamic radius, probably by decreasing electrostatic repulsion. Also, solvent-induced denaturation of Stm indicated the lack of an ordered structure in the molecule (Kaplon et al., 2008, 2009). Recently, another homolog of *Starmaker* has been identified: *Starmaker-like* from *Oryzias latipes*. The deduced amino acid sequence of *Starmaker-like* is also rich in acidic residues (Bajoghli et al., 2009). No secondary structure analysis of Stm-like, or OMM-64, have been performed; however, bioinformatic predictions strongly suggest that these proteins might be completely disordered (Table 2).

4.6 Egg shell related IDPs

An eggshell is a highly ordered natural, acellular composite bioceramic. It is one of the fastest and also one of the most structurally complicated biomineralizing systems. To produce an eggshell, 5 grams of calcium carbonate must be crystallized within 20 h (Arias et al., 2007; 2008). OPN, which is one of the eggshell proteins, was described above and is characterized as an IDP (3.1.4) (Chien et al., 2008; Panheleux et al., 1999). There are some proteins that are unique to eggshells. Ovocleidin-116 has been isolated and cloned from chickens (Hincke et al., 1999; Mann et al., 2002). Recent studies demonstrated that Ovocleidin-116 is an ortholog of mammalian MEPE, which belongs to the SIBLINGs family (Bardet et al., 2010). Although, structural studies of MEPE have not been available, it's possible that both proteins are IDPs, as was predicted by bioinformatic tools (Tab. 2). Several proteins identified from different avian species are C-type lectin-like proteins (Arias et al., 2007; 2008): ovocleidin-17 (chicken) (Hincke et al., 1995), ansocalcin (goose) (Lakshminarayanan et al., 2003), stuthiocalcin-1 and struthiocalcin-2 (ostrich) (Mann & Siedler, 2004), rheacalcin-1 and rheacalcin-2 (rhea) (Mann, 2004), dromaiocalcin-1 and dromaiocalcin-2 (emu) (Mann & Siedler, 2006). Structural studies of ovocleidin-17 and ansocalcin revealed that their three-dimensional structure is very similar to the structure of lithostathine (Bertrand et al., 1996; Lakshminarayanan et al., 2005; Reyes-Grajeda et al., 2004); however, the three proteins had different effects on calcium carbonate crystals. Lithostathine was an inhibitor, ansocalcin caused the formation of crystal aggregates, and ovocleidin-17 led to the crystals twinning (but not to an extensive aggregation of crystals like with ansocalcin) (Geider et al., 1996; Lakshminarayanan et al., 2005). It should be noted that N-terminal regions of ansocalcin and ovocleidin-17 are well folded, while lithostathine's N-terminus is disordered. Possibly lithostathine, ansocalcin and

ovocleidin-17 influence crystal formation in different ways because of the distinct structure of each of their N-termini. The disordered structure of lithostathine's N-terminus might be directly responsible for its inhibitory effect on crystal formation. Hence, based on the evidence presented in this review, it can be postulated that IDPs are crucial to the inhibition of crystal growth.

5. The innate specialization of IDPs in biomineralization

All of the above-mentioned examples strongly suggest that it is no accident that so many proteins involved in biomineralization exhibit an IDP-like character or are simply IDPs. Conformational instability is a common feature of proteins that bind to inorganic solids (Delak et al., 2009a; Kim et al., 2006a; Michenfelder et al., 2003). Intrinsic disorder provides benefits to these proteins and enables them to fulfill their functions.

Many IDPs involved in biomineralization have an unusual amino acid composition, for instance, they are rich in acidic residues. This unusual composition leads to strong electrostatic repulsion and results in the extended conformation of the IDP molecule.

The extended conformation of IDPs provides a much larger binding surface in comparison to the compact conformation of globular proteins. It is highly advantageous, especially when interacting with crystalline surfaces. Many proteins act as inhibitors of crystal growth by interacting with the crystal lattice and blocking nucleation sites. DPP's larger binding surface enables it to block more nucleation sites, hence one extended molecule can do the work of several molecules with a globular conformation (Fujisawa & Kuboki, 1998). Moreover, CAP-1, statherin and lithostathin structural studies clearly demonstrated that the highly flexible regions of these proteins were directly responsible for the inhibitory effects they had on crystal growth (Gerbaud et al., 2000; Inoue et al., 2007; Long et al., 2001).

Secondly, their extended conformation combined with their acidic character facilitates protein interactions with counter ions (Uversky, 2009). DPP and DMP1 bind relatively large amounts of calcium ions compared to calmodulin, which has a well-defined three-dimensional structure (He et al., 2003b, 2005b). Counter ion-binding seems to be crucial to weakening electrostatic repulsion and permitting the formation of β -sheets that lead to disorder-to-order transitions (He et al., 2005a). Asprich and AP7 proteins can bind calcium ions as well as other ions; however, this does not lead to significant global conformational rearrangement. It has been suggested that both the extended β -strand and coil segments enhance calcium binding and possibly determine the function of these domains (Collino et al., 2006; Delak et al., 2009a).

One of the most significant features of IDPs is their ability to interact with many different partners (Uversky & Dunker, 2010). Proteins involved in biomineralization have to bind many targets to properly fulfill their functions. They are responsible for macromolecular complex assembly, and they are engaged in cell attachment (Fujisawa et al., 1997; Stubbs et al., 1997), cell signaling (Gruenbaum-Cohen et al., 2009) and/or the regulation of gene expression (Narayanan et al., 2003, 2006). Macromolecular complex assemblies are crucial for proper biomineral formation. The extended conformation of IDPs provides a large binding surface for different partners, while the flexibility and plasticity of polypeptide chains permit IDPs to conformationally adapt to different targets (Collino et al., 2006; Delak et al., 2008). Moreover, proteins involved in biomineralization may undergo

disorder-to-order transitions as a result of binding with a partner, molecular crowding or other factors (Amos et al., 2010). Additionally, this disorder-to-order transition promotes macromolecular complex assembly.

Interactions with other macromolecules can also modulate the function of a protein. DPP in solution acts as an inhibitor of HA growth, while DPP bound to collagen acts as a nucleator of HA crystals. This phenomenon might be the result of conformational changes in DPP triggered by interactions with collagen. OPN also exhibits a different conformation when it is bound to HA from that of the solution state (Chien et al., 2009; Gorski et al., 1995). The function of n16 and OMM64 (which is also a putative IDP) is also modulated by interactions with β -chitin. OMM64, n16 and β -chitin in isolation can not induce aragonite formation *in vitro*. However, the combination of OMM46/ β -chitin and n16/ β -chitin molecules result in aragonite formation. Moreover, it has been suggested that the intrinsic disorder of n16 is a key factor allowing this protein to simultaneously interact with β -chitin and mineral face (Keene et al., 2010; Tohse et al., 2009).

Many proteins involved in biomineralization are able to self-assemble (Kaartinen et al., 1999; Lakshminarayanan et al., 2003). Monomer proteins are often IDPs, while the aggregation of a protein leads to the formation of a β -sheet structure. It is very possible that the extended structure of a protein in solution facilitates interactions with other macromolecules. These interactions may trigger disorder-to-order transitions, which enable macromolecular complexes to form (Buchko et al., 2008; Gorski et al., 1995; He et al., 2003b). Random scrambling of n16 led to a lower affinity for β -chitin and the disappearance of disorder-to-order transitions; this resulted in an inability to form aragonite *in vitro* (Keene et al., 2010). Interestingly, aggregation and conformational change is highly associated with ambient conditions; self-assembly of amelogenin depends on protein concentration, ionic strength, pH and temperature (Lyngstadaas et al., 2009), while DMP1 oligomerization is induced by calcium ions (He et al., 2003b).

A fascinating example of IDPs involved in biomineralization is DMP1. This multifunctional protein is able to interact with calcium ions (He et al., 2003a, 2003b), HA crystals (He et al., 2003a), collagen (Qin et al., 2004), DNA (Narayanan et al., 2006), H factors, integrin $\alpha\beta 3$ and CD44 (Jain et al., 2002). Consequently, DMP1 is engaged in biomineralization, cell signaling and regulation of gene expression (He et al., 2003a; Jain et al., 2002; Narayanan et al., 2006). It exhibits different localization (nuclear, extracellular) according to post-translational modifications and its conformational state (Narayanan et al., 2003). This multifunctionality and interactions with numerous target are likely facilitated by the intrinsically disordered character of the protein.

It is known that proteins involved in biomineralization are extensively post-translationally modified, frequently being phosphorylated, glycosylated and proteolytically cleaved (George & Veis, 2008; He et al., 2005b; Hecker et al., 2003; Qin et al., 2004). A susceptibility to post-translational modifications seems to be associated with the extended and flexible structure that is characteristic of IDPs. The lack of a well-packed hydrophobic core and rapid fluctuations in the peptide chain lead to a greater amount of potential phosphorylation sites, more so than in the case of globular proteins. (Bertrand et al., 1996; Iakoucheva et al., 2004).

Using the IDP classifications (2.2), one can classify the proteins involved in biomineralization into several groups. Those most important for biomineralization are

molecular assemblers. This is supported by their ability to interact simultaneously with crystals, scaffold molecules (collagen, β -chitin) and their self-assembling properties. Furthermore, widespread counter ion-binding indicates that they may act as scavengers. We cannot exclude the function of these proteins as effectors, because they are also engaged in processes such as gene expression (Narayanan et al., 2003, 2006). Finally, numerous post-translational modifications suggest the presence of display sites.

It is apparent that intrinsic disorder is characteristic of proteins involved in biomineralization. The structure of many proteins has yet to be established, but there is a considerable likelihood that they are IDPs (Fig. 1B, Table 2).

6. Acknowledgment

This paper was supported in part by the National Science Centre grant 1200/B/H03/2011/40 (to P.D.) and by the Wrocław University of Technology.

7. References

- Allemand, D.; Mayer-Gostan, N.; De Pontual, H.; Boeuf, G. & Payan, P. (2007; 2008). Fish Otolith Calcification in Relation to Endolymph Chemistry, Wiley-VCH Verlag GmbH, 9783527619443
- Amos, F.F. & Evans, J.S. (2009). AP7, a partially disordered pseudo C-RING protein, is capable of forming stabilized aragonite in vitro. *Biochemistry*, Vol. 48, No. 6, pp. 1332-1339, 1520-4995; 0006-2960
- Amos, F.F.; Ndao, M. & Evans, J.S. (2009). Evidence of mineralization activity and supramolecular assembly by the N-terminal sequence of ACCBP, a biomineralization protein that is homologous to the acetylcholine binding protein family. *Biomacromolecules*, Vol. 10, No. 12, pp. 3298-3305, 1526-4602; 1525-7797
- Amos, F.F.; Ponce, C.B. & Evans, J.S. (2011). Formation of framework nacre polypeptide supramolecular assemblies that nucleate polymorphs. *Biomacromolecules*, Vol. 12, No. 5, pp. 1883-1890, 1526-4602; 1525-7797
- Amos, F.F.; Destine, E.; Ponce, C.B. & Evans, J.S. (2010). The N- and C-Terminal Regions of the Pearl-Associated EF Hand Protein, PFMG1, Promote the Formation of the Aragonite Polymorph in Vitro. *Crystal Growth & Design*, Vol. 10, No. 10, pp. 4211-4216
- Arias, J.L.; Mann, K.; Nys, Y.; Ruiz, J.M.G. & Fernández, M.S. (2007; 2008). Eggshell Growth and Matrix Macromolecules, Wiley-VCH Verlag GmbH, 9783527619443
- Babu, M.M.; van der Lee, R.; de Groot, N.S. & Gsponer, J. (2011). Intrinsically disordered proteins: regulation and disease. *Current Opinion in Structural Biology*, Vol. 21, No. 3, pp. 432-440, 1879-033X; 0959-440X
- Bai, Y.; Chung, J.; Dyson, H.J. & Wright, P.E. (2001). Structural and dynamic characterization of an unfolded state of poplar apo-plastocyanin formed under nondenaturing conditions. *Protein Science: A Publication of the Protein Society*, Vol. 10, No. 5, pp. 1056-1066, 0961-8368; 0961-8368
- Bajoghli, B.; Ramialison, M.; Aghaallaei, N.; Czerny, T. & Wittbrodt, J. (2009). Identification of starmaker-like in medaka as a putative target gene of Pax2 in the otic vesicle. *Developmental Dynamics: An Official Publication of the American Association of Anatomists*, Vol. 238, No. 11, pp. 2860-2866, 1097-0177; 1058-8388

- Bardet, C.; Vincent, C.; Lajarille, M.C.; Jaffredo, T. & Sire, J.Y. (2010). OC-116, the chicken ortholog of mammalian MEPE found in eggshell, is also expressed in bone cells. *Journal of Experimental Zoology. Part B, Molecular and Developmental Evolution*, Vol. 314, No. 8, pp. 653-662, 1552-5015; 1552-5007
- Bartlett, J.D.; Ganss, B.; Goldberg, M.; Moradian-Oldak, J.; Paine, M.L.; Snead, M.L.; Wen, X.; White, S.N. & Zhou, Y.L. (2006). 3. Protein-protein interactions of the developing enamel matrix. *Current Topics in Developmental Biology*, Vol. 74, pp. 57-115, 0070-2153; 0070-2153
- Benson, S.; Sucov, H.; Stephens, L.; Davidson, E. & Wilt, F. (1987). A lineage-specific gene encoding a major matrix protein of the sea urchin embryo spicule. I. Authentication of the cloned gene and its developmental expression. *Developmental Biology*, Vol. 120, No. 2, pp. 499-506, 0012-1606; 0012-1606
- Bernard, J.P.; Adrich, Z.; Montalto, G.; De Caro, A.; De Reggi, M.; Sarles, H. & Dagorn, J.C. (1992). Inhibition of nucleation and crystal growth of calcium carbonate by human lithostathine. *Gastroenterology*, Vol. 103, No. 4, pp. 1277-1284, 0016-5085; 0016-5085
- Bertrand, J.A.; Pignol, D.; Bernard, J.P.; Verdier, J.M.; Dagorn, J.C. & Fontecilla-Camps, J.C. (1996). Crystal structure of human lithostathine, the pancreatic inhibitor of stone formation. *The EMBO Journal*, Vol. 15, No. 11, pp. 2678-2684, 0261-4189; 0261-4189
- Bianco, P.; Fisher, L.W.; Young, M.F.; Termine, J.D. & Robey, P.G. (1991). Expression of bone sialoprotein (BSP) in developing human tissues. *Calcified Tissue International*, Vol. 49, No. 6, pp. 421-426, 0171-967X; 0171-967X
- Buchko, G.W.; Tarasevich, B.J.; Bekhazi, J.; Snead, M.L. & Shaw, W.J. (2008). A solution NMR investigation into the early events of amelogenin nanosphere self-assembly initiated with sodium chloride or calcium chloride. *Biochemistry*, Vol. 47, No. 50, pp. 13215-13222, 1520-4995; 0006-2960
- Buchko, G.W.; Tarasevich, B.J.; Roberts, J.; Snead, M.L. & Shaw, W.J. (2010). A solution NMR investigation into the murine amelogenin splice-variant LRAP (Leucine-Rich Amelogenin Protein). *Biochimica Et Biophysica Acta*, Vol. 1804, No. 9, pp. 1768-1774, 0006-3002; 0006-3002
- Chen, Y.; Bal, B.S. & Gorski, J.P. (1992). Calcium and collagen binding properties of osteopontin, bone sialoprotein, and bone acidic glycoprotein-75 from bone. *The Journal of Biological Chemistry*, Vol. 267, No. 34, pp. 24871-24878, 0021-9258; 0021-9258
- Chien, Y.C.; Hincke, M.T.; Vali, H. & McKee, M.D. (2008). Ultrastructural matrix-mineral relationships in avian eggshell, and effects of osteopontin on calcite growth in vitro. *Journal of Structural Biology*, Vol. 163, No. 1, pp. 84-99, 1095-8657; 1047-8477
- Chien, Y.C.; Masica, D.L.; Gray, J.J.; Nguyen, S.; Vali, H. & McKee, M.D. (2009). Modulation of calcium oxalate dihydrate growth by selective crystal-face binding of phosphorylated osteopontin and polyaspartate peptide showing occlusion by sectoral (compositional) zoning. *The Journal of Biological Chemistry*, Vol. 284, No. 35, pp. 23491-23501, 0021-9258; 0021-9258
- Collino, S. & Evans, J.S. (2008). Molecular specifications of a mineral modulation sequence derived from the aragonite-promoting protein n16. *Biomacromolecules*, Vol. 9, No. 7, pp. 1909-1918, 1526-4602; 1525-7797
- Collino, S.; Kim, I.W. & Evans, J.S. (2006). Identification of an Acidic C-Terminal Mineral Modification Sequence from the Mollusk Shell Protein Asprich. *Crystal Growth & Design*, Vol. 6, No. 4, pp. 839-842

- Cross, K.J.; Huq, N.L. & Reynolds, E.C. (2005). Protein dynamics of bovine dentin phosphophoryn. *The Journal of Peptide Research: Official Journal of the American Peptide Society*, Vol. 66, No. 2, pp. 59-67, 1397-002X; 1397-002X
- De Caro, A.; Multigner, L.; Dagorn, J.C. & Sarles, H. (1988). The human pancreatic stone protein. *Biochimie*, Vol. 70, No. 9, pp. 1209-1214, 0300-9084; 0300-9084
- Delak, K.; Collino, S. & Evans, J.S. (2009a). Polyelectrolyte domains and intrinsic disorder within the prismatic Asprich protein family. *Biochemistry*, Vol. 48, No. 16, pp. 3669-3677, 1520-4995; 0006-2960
- Delak, K.; Harcup, C.; Lakshminarayanan, R.; Sun, Z.; Fan, Y.; Moradian-Oldak, J. & Evans, J.S. (2009b). The tooth enamel protein, porcine amelogenin, is an intrinsically disordered protein with an extended molecular configuration in the monomeric form. *Biochemistry*, Vol. 48, No. 10, pp. 2272-2281, 1520-4995; 0006-2960
- Delak, K.; Giocondi, J.; Orme, C. & Evans, J.S. (2008). Modulation of Crystal Growth by the Terminal Sequences of the Prismatic-Associated Asprich Protein. *Crystal Growth & Design*, Vol. 8, No. 12, pp. 4481-4486
- Delgado, S.; Girondot, M. & Sire, J.Y. (2005). Molecular evolution of amelogenin in mammals. *Journal of Molecular Evolution*, Vol. 60, No. 1, pp. 12-30, 0022-2844; 0022-2844
- Dosztanyi, Z.; Csizmok, V.; Tompa, P. & Simon, I. (2005). IUPred: web server for the prediction of intrinsically unstructured regions of proteins based on estimated energy content. *Bioinformatics (Oxford, England)*, Vol. 21, No. 16, pp. 3433-3434, 1367-4803; 1367-4803
- Dunker, A.K.; Cortese, M.S.; Romero, P.; Iakoucheva, L.M. & Uversky, V.N. (2005). Flexible nets. The roles of intrinsic disorder in protein interaction networks. *The FEBS Journal*, Vol. 272, No. 20, pp. 5129-5148, 1742-464X; 1742-464X
- Dunker, A.K.; Lawson, J.D.; Brown, C.J.; Williams, R.M.; Romero, P.; Oh, J.S.; Oldfield, C.J.; Campen, A.M.; Ratliff, C.M.; Hipps, K.W.; Ausio, J.; Nissen, M.S.; Reeves, R.; Kang, C.; Kissinger, C.R.; Bailey, R.W.; Griswold, M.D.; Chiu, W.; Garner, E.C. & Obradovic, Z. (2001). Intrinsically disordered protein. *Journal of Molecular Graphics & Modelling*, Vol. 19, No. 1, pp. 26-59, 1093-3263; 1093-3263
- Dunker, A.K. & Obradovic, Z. (2001). The protein trinity-linking function and disorder. *Nature Biotechnology*, Vol. 19, No. 9, pp. 805-806, 1087-0156; 1087-0156
- Dunker, A.K.; Obradovic, Z.; Romero, P.; Garner, E.C. & Brown, C.J. (2000). Intrinsic protein disorder in complete genomes. *Genome Informatics. Workshop on Genome Informatics*, Vol. 11, pp. 161-171, 0919-9454; 0919-9454
- Dyson, H.J. (2011). Expanding the proteome: disordered and alternatively folded proteins. *Quarterly Reviews of Biophysics*, pp. 1-52, 1469-8994; 0033-5835
- Dyson, H.J. & Wright, P.E. (2005). Intrinsically unstructured proteins and their functions. *Nature Reviews. Molecular Cell Biology*, Vol. 6, No. 3, pp. 197-208, 1471-0072; 1471-0072
- Endo, H.; Takagi, Y.; Ozaki, N.; Kogure, T. & Watanabe, T. (2004). A crustacean Ca^{2+} -binding protein with a glutamate-rich sequence promotes CaCO_3 crystallization. *The Biochemical Journal*, Vol. 384, No. Pt 1, pp. 159-167, 1470-8728; 0264-6021
- Evans, J.S. (2008). "Tuning in" to mollusk shell nacre- and prismatic-associated protein terminal sequences. Implications for biomineralization and the construction of high performance inorganic-organic composites. *Chemical Reviews*, Vol. 108, No. 11, pp. 4455-4462, 1520-6890; 0009-2665

- Evans, J.S.; Chiu, T. & Chan, S.I. (1994). Phosphophoryn, an "acidic" biomineralization regulatory protein: conformational folding in the presence of Cd(II). *Biopolymers*, Vol. 34, No. 10, pp. 1359-1375, 0006-3525; 0006-3525
- Fisher, L.W.; Torchia, D.A.; Fohr, B.; Young, M.F. & Fedarko, N.S. (2001). Flexible structures of SIBLING proteins, bone sialoprotein, and osteopontin. *Biochemical and Biophysical Research Communications*, Vol. 280, No. 2, pp. 460-465, 0006-291X; 0006-291X
- Fu, G.; Valiyaveetil, S.; Wopenka, B. & Morse, D.E. (2005). CaCO₃ biomineralization: acidic 8-kDa proteins isolated from aragonitic abalone shell nacre can specifically modify calcite crystal morphology. *Biomacromolecules*, Vol. 6, No. 3, pp. 1289-1298, 1525-7797; 1525-7797
- Fujisawa, R. & Kuboki, Y. (1998). Conformation of dentin phosphophoryn adsorbed on hydroxyapatite crystals. *European Journal of Oral Sciences*, Vol. 106 Suppl 1, pp. 249-253, 0909-8836; 0909-8836
- Fujisawa, R.; Mizuno, M.; Nodasaka, Y. & Kuboki, Y. (1997). Attachment of osteoblastic cells to hydroxyapatite crystals by a synthetic peptide (Glu7-Pro-Arg-Gly-Asp-Thr) containing two functional sequences of bone sialoprotein. *Matrix Biology: Journal of the International Society for Matrix Biology*, Vol. 16, No. 1, pp. 21-28, 0945-053X; 0945-053X
- Ganss, B.; Kim, R.H. & Sodek, J. (1999). Bone sialoprotein. *Critical Reviews in Oral Biology and Medicine : An Official Publication of the American Association of Oral Biologists*, Vol. 10, No. 1, pp. 79-98, 1045-4411; 1045-4411
- Geider, S.; Baronnet, A.; Cerini, C.; Nitsche, S.; Astier, J.P.; Michel, R.; Boistelle, R.; Berland, Y.; Dagorn, J.C. & Verdier, J.M. (1996). Pancreatic lithostathine as a calcite habit modifier. *The Journal of Biological Chemistry*, Vol. 271, No. 42, pp. 26302-26306, 0021-9258; 0021-9258
- George, A. & Hao, J. (2005). Role of phosphophoryn in dentin mineralization. *Cells, Tissues, Organs*, Vol. 181, No. 3-4, pp. 232-240, 1422-6405; 1422-6405
- George, A. & Veis, A. (2008). Phosphorylated proteins and control over apatite nucleation, crystal growth, and inhibition. *Chemical Reviews*, Vol. 108, No. 11, pp. 4670-4693, 1520-6890; 0009-2665
- George, N.C.; Killian, C.E. & Wilt, F.H. (1991). Characterization and expression of a gene encoding a 30.6-kDa *Strongylocentrotus purpuratus* spicule matrix protein. *Developmental Biology*, Vol. 147, No. 2, pp. 334-342, 0012-1606; 0012-1606
- Gerbaud, V.; Pignol, D.; Loret, E.; Bertrand, J.A.; Berland, Y.; Fontecilla-Camps, J.C.; Canselier, J.P.; Gabas, N. & Verdier, J.M. (2000). Mechanism of calcite crystal growth inhibition by the N-terminal undecapeptide of lithostathine. *The Journal of Biological Chemistry*, Vol. 275, No. 2, pp. 1057-1064, 0021-9258; 0021-9258
- Gericke, A.; Qin, C.; Spevak, L.; Fujimoto, Y.; Butler, W.T.; Sorensen, E.S. & Boskey, A.L. (2005). Importance of phosphorylation for osteopontin regulation of biomineralization. *Calcified Tissue International*, Vol. 77, No. 1, pp. 45-54, 0171-967X; 0171-967X
- Gericke, A.; Qin, C.; Sun, Y.; Redfern, R.; Redfern, D.; Fujimoto, Y.; Taleb, H.; Butler, W.T. & Boskey, A.L. (2010). Different forms of DMP1 play distinct roles in mineralization. *Journal of Dental Research*, Vol. 89, No. 4, pp. 355-359, 1544-0591; 0022-0345
- Glazer, L.; Shechter, A.; Tom, M.; Yudkovski, Y.; Weil, S.; Aflalo, E.D.; Pamuru, R.R.; Khalaila, I.; Bentov, S.; Berman, A. & Sagi, A. (2010). A protein involved in the

- assembly of an extracellular calcium storage matrix. *The Journal of Biological Chemistry*, Vol. 285, No. 17, pp. 12831-12839, 1083-351X; 0021-9258
- Glimcher, M.J. (1989). Mechanism of calcification: role of collagen fibrils and collagen-phosphoprotein complexes in vitro and in vivo. *The Anatomical Record*, Vol. 224, No. 2, pp. 139-153, 0003-276X; 0003-276X
- Goldberg, H.A. & Hunter, G.K. (1995). The inhibitory activity of osteopontin on hydroxyapatite formation in vitro. *Annals of the New York Academy of Sciences*, Vol. 760, pp. 305-308, 0077-8923; 0077-8923
- Gorski, J.P.; Kremer, E.; Ruiz-Perez, J.; Wise, G.E. & Artigues, A. (1995). Conformational analyses on soluble and surface bound osteopontin. *Annals of the New York Academy of Sciences*, Vol. 760, pp. 12-23, 0077-8923; 0077-8923
- Gotliv, B.A.; Kessler, N.; Sumerel, J.L.; Morse, D.E.; Tuross, N.; Addadi, L. & Weiner, S. (2005). Asprich: A novel aspartic acid-rich protein family from the prismatic shell matrix of the bivalve *Atrina rigida*. *Chembiochem : A European Journal of Chemical Biology*, Vol. 6, No. 2, pp. 304-314, 1439-4227; 1439-4227
- Grohe, B.; O'Young, J.; Ionescu, D.A.; Lajoie, G.; Rogers, K.A.; Karttunen, M.; Goldberg, H.A. & Hunter, G.K. (2007). Control of calcium oxalate crystal growth by face-specific adsorption of an osteopontin phosphopeptide. *Journal of the American Chemical Society*, Vol. 129, No. 48, pp. 14946-14951, 1520-5126; 0002-7863
- Gruenbaum-Cohen, Y.; Tucker, A.S.; Haze, A.; Shilo, D.; Taylor, A.L.; Shay, B.; Sharpe, P.T.; Mitsiadis, T.A.; Ornoy, A.; Blumenfeld, A. & Deutsch, D. (2009). Amelogenin in cranio-facial development: the tooth as a model to study the role of amelogenin during embryogenesis. *Journal of Experimental Zoology. Part B, Molecular and Developmental Evolution*, Vol. 312B, No. 5, pp. 445-457, 1552-5015; 1552-5007
- Harkey, M.A.; Klueg, K.; Sheppard, P. & Raff, R.A. (1995). Structure, expression, and extracellular targeting of PM27, a skeletal protein associated specifically with growth of the sea urchin larval spicule. *Developmental Biology*, Vol. 168, No. 2, pp. 549-566, 0012-1606; 0012-1606
- Hay, D.I.; Smith, D.J.; Schluckebier, S.K. & Moreno, E.C. (1984). Relationship between concentration of human salivary statherin and inhibition of calcium phosphate precipitation in stimulated human parotid saliva. *Journal of Dental Research*, Vol. 63, No. 6, pp. 857-863, 0022-0345; 0022-0345
- He, G.; Dahl, T.; Veis, A. & George, A. (2003a). Dentin matrix protein 1 initiates hydroxyapatite formation in vitro. *Connective Tissue Research*, Vol. 44 Suppl 1, pp. 240-245, 0300-8207; 0300-8207
- He, G.; Dahl, T.; Veis, A. & George, A. (2003b). Nucleation of apatite crystals in vitro by self-assembled dentin matrix protein 1. *Nature Materials*, Vol. 2, No. 8, pp. 552-558, 1476-1122; 1476-1122
- He, G.; Gajjeraman, S.; Schultz, D.; Cookson, D.; Qin, C.; Butler, W.T.; Hao, J. & George, A. (2005a). Spatially and temporally controlled biomineralization is facilitated by interaction between self-assembled dentin matrix protein 1 and calcium phosphate nuclei in solution. *Biochemistry*, Vol. 44, No. 49, pp. 16140-16148, 0006-2960; 0006-2960
- He, G.; Ramachandran, A.; Dahl, T.; George, S.; Schultz, D.; Cookson, D.; Veis, A. & George, A. (2005b). Phosphorylation of phosphophoryn is crucial for its function as a mediator of biomineralization. *The Journal of Biological Chemistry*, Vol. 280, No. 39, pp. 33109-33114, 0021-9258; 0021-9258

- Hecker, A.; Quennedey, B.; Testeniere, O.; Quennedey, A.; Graf, F. & Luquet, G. (2004). Orchestin, a calcium-binding phosphoprotein, is a matrix component of two successive transitory calcified biomineralizations cyclically elaborated by a terrestrial crustacean. *Journal of Structural Biology*, Vol. 146, No. 3, pp. 310-324, 1047-8477; 1047-8477
- Hecker, A.; Testeniere, O.; Marin, F. & Luquet, G. (2003). Phosphorylation of serine residues is fundamental for the calcium-binding ability of Orchestin, a soluble matrix protein from crustacean calcium storage structures. *FEBS Letters*, Vol. 535, No. 1-3, pp. 49-54, 0014-5793; 0014-5793
- Hincke, M.T.; Gautron, J.; Tsang, C.P.; McKee, M.D. & Nys, Y. (1999). Molecular cloning and ultrastructural localization of the core protein of an eggshell matrix proteoglycan, ovocleidin-116. *The Journal of Biological Chemistry*, Vol. 274, No. 46, pp. 32915-32923, 0021-9258; 0021-9258
- Hincke, M.T.; Tsang, C.P.; Courtney, M.; Hill, V. & Narbaitz, R. (1995). Purification and immunochemistry of a soluble matrix protein of the chicken eggshell (ovocleidin 17). *Calcified Tissue International*, Vol. 56, No. 6, pp. 578-583, 0171-967X; 0171-967X
- Huq, N.L.; Cross, K.J.; Talbo, G.H.; Riley, P.F.; Loganathan, A.; Crossley, M.A.; Perich, J.W. & Reynolds, E.C. (2000). N-terminal sequence analysis of bovine dentin phosphophoryn after conversion of phosphoserine to S-propylcysteine residues. *Journal of Dental Research*, Vol. 79, No. 11, pp. 1914-1919, 0022-0345; 0022-0345
- Iakoucheva, L.M.; Radivojac, P.; Brown, C.J.; O'Connor, T.R.; Sikes, J.G.; Obradovic, Z. & Dunker, A.K. (2004). The importance of intrinsic disorder for protein phosphorylation. *Nucleic Acids Research*, Vol. 32, No. 3, pp. 1037-1049, 1362-4962; 0305-1048
- Illies, M.R.; Peeler, M.T.; Dechtiaruk, A.M. & Etensohn, C.A. (2002). Identification and developmental expression of new biomineralization proteins in the sea urchin *Strongylocentrotus purpuratus*. *Development Genes and Evolution*, Vol. 212, No. 9, pp. 419-431, 0949-944X; 0949-944X
- Inoue, H.; Ohira, T.; Ozaki, N. & Nagasawa, H. (2004). A novel calcium-binding peptide from the cuticle of the crayfish, *Procambarus clarkii*. *Biochemical and Biophysical Research Communications*, Vol. 318, No. 3, pp. 649-654, 0006-291X; 0006-291X
- Inoue, H.; Ohira, T.; Ozaki, N. & Nagasawa, H. (2003). Cloning and expression of a cDNA encoding a matrix peptide associated with calcification in the exoskeleton of the crayfish. *Comparative Biochemistry and Physiology, Part B, Biochemistry & Molecular Biology*, Vol. 136, No. 4, pp. 755-765, 1096-4959; 1096-4959
- Inoue, H.; Ozaki, N. & Nagasawa, H. (2001). Purification and structural determination of a phosphorylated peptide with anti-calcification and chitin-binding activities in the exoskeleton of the crayfish, *Procambarus clarkii*. *Bioscience, Biotechnology, and Biochemistry*, Vol. 65, No. 8, pp. 1840-1848, 0916-8451; 0916-8451
- Inoue, H.; Yuasa-Hashimoto, N.; Suzuki, M. & Nagasawa, H. (2008). Structural determination and functional analysis of a soluble matrix protein associated with calcification of the exoskeleton of the crayfish, *Procambarus clarkii*. *Bioscience, Biotechnology, and Biochemistry*, Vol. 72, No. 10, pp. 2697-2707, 1347-6947; 0916-8451
- Inoue, H.; Ohira, T. & Nagasawa, H. (2007). Significance of the N- and C-terminal regions of CAP-1, a cuticle calcification-associated peptide from the exoskeleton of the crayfish, for calcification. *Peptides*, Vol. 28, No. 3, pp. 566-573, 0196-9781

- Ishii, K.; Yanagisawa, T. & Nagasawa, H. (1996). Characterization of a matrix protein in the gastroliths of the crayfish *Procambarus clarkii*. *Bioscience, Biotechnology, and Biochemistry*, Vol. 60, No. 9, pp. 1479-1482, 0916-8451; 0916-8451
- Jain, A.; Karadag, A.; Fohr, B.; Fisher, L.W. & Fedarko, N.S. (2002). Three SIBLINGs (small integrin-binding ligand, N-linked glycoproteins) enhance factor H's cofactor activity enabling MCP-like cellular evasion of complement-mediated attack. *The Journal of Biological Chemistry*, Vol. 277, No. 16, pp. 13700-13708, 0021-9258; 0021-9258
- Johnsson, M.; Richardson, C.F.; Bergey, E.J.; Levine, M.J. & Nancollas, G.H. (1991). The effects of human salivary cystatins and statherin on hydroxyapatite crystallization. *Archives of Oral Biology*, Vol. 36, No. 9, pp. 631-636, 0003-9969; 0003-9969
- Jono, S.; Peinado, C. & Giachelli, C.M. (2000). Phosphorylation of osteopontin is required for inhibition of vascular smooth muscle cell calcification. *The Journal of Biological Chemistry*, Vol. 275, No. 26, pp. 20197-20203, 0021-9258; 0021-9258
- Kaartinen, M.T.; Pirhonen, A.; Linnala-Kankkunen, A. & Maenpaa, P.H. (1999). Cross-linking of osteopontin by tissue transglutaminase increases its collagen binding properties. *The Journal of Biological Chemistry*, Vol. 274, No. 3, pp. 1729-1735, 0021-9258; 0021-9258
- Kaplon, T.M.; Michnik, A.; Drzazga, Z.; Richter, K.; Kochman, M. & Ozyhar, A. (2009). The rod-shaped conformation of Starmaker. *Biochimica et Biophysica Acta*, Vol. 1794, No. 11, pp. 1616-1624, 0006-3002; 0006-3002
- Kaplon, T.M.; Rymarczyk, G.; Nocola-Lugowska, M.; Jakob, M.; Kochman, M.; Lisowski, M.; Szewczuk, Z. & Ozyhar, A. (2008). Starmaker exhibits properties of an intrinsically disordered protein. *Biomacromolecules*, Vol. 9, No. 8, pp. 2118-2125, 1526-4602; 1525-7797
- Katoh-Fukui, Y.; Noce, T.; Ueda, T.; Fujiwara, Y.; Hashimoto, N.; Higashinakagawa, T.; Killian, C.E.; Livingston, B.T.; Wilt, F.H. & Benson, S.C. (1991). The corrected structure of the SM50 spicule matrix protein of *Strongylocentrotus purpuratus*. *Developmental Biology*, Vol. 145, No. 1, pp. 201-202, 0012-1606; 0012-1606
- Kazanecki, C.C.; Uzwiak, D.J. & Denhardt, D.T. (2007). Control of osteopontin signaling and function by post-translational phosphorylation and protein folding. *Journal of Cellular Biochemistry*, Vol. 102, No. 4, pp. 912-924, 0730-2312; 0730-2312
- Keene, E.C.; Evans, J.S. & Estroff, L.A. (2010). Matrix Interactions in Biomineralization: Aragonite Nucleation by an Intrinsically Disordered Nacre Polypeptide, n16N, Associated with a β -Chitin Substrate. *Crystal Growth & Design*, Vol. 10, No. 3, pp. 1383-1389
- Killian, C.E.; Croker, L. & Wilt, F.H. (2010). SpSM30 gene family expression patterns in embryonic and adult biomineralized tissues of the sea urchin, *Strongylocentrotus purpuratus*. *Gene Expression Patterns: GEP*, Vol. 10, No. 2-3, pp. 135-139, 1872-7298; 1567-133X
- Killian, C.E. & Wilt, F.H. (2008). Molecular aspects of biomineralization of the echinoderm endoskeleton. *Chemical Reviews*, Vol. 108, No. 11, pp. 4463-4474, 1520-6890; 0009-2665
- Killian, C.E. & Wilt, F.H. (1996). Characterization of the proteins comprising the integral matrix of *Strongylocentrotus purpuratus* embryonic spicules. *The Journal of Biological Chemistry*, Vol. 271, No. 15, pp. 9150-9159, 0021-9258; 0021-9258
- Kim, I.W.; Morse, D.E. & Evans, J.S. (2004). Molecular characterization of the 30-AA N-terminal mineral interaction domain of the biomineralization protein AP7.

- Langmuir: The ACS Journal of Surfaces and Colloids*, Vol. 20, No. 26, pp. 11664-11673, 0743-7463; 0743-7463
- Kim, I.W.; Collino, S.; Morse, D.E. & Evans, J.S. (2006a). A Crystal Modulating Protein from Molluscan Nacre That Limits the Growth of Calcite in Vitro. *Crystal Growth & Design*, Vol. 6, No. 5, pp. 1078-1082
- Kim, I.W.; Darragh, M.R.; Orme, C. & Evans, J.S. (2006b). Molecular Tuning of Crystal Growth by Nacre-Associated Polypeptides. *Crystal Growth & Design*, Vol. 6, No. 1, pp. 5-10
- Kim, I.W.; DiMasi, E. & Evans, J.S. (2004). Identification of Mineral Modulation Sequences within the Nacre-Associated Oyster Shell Protein, n16. *Crystal Growth & Design*, Vol. 4, No. 6, pp. 1113-1118
- Kim, I.W.; Giocondi, J.L.; Orme, C.; Collino, S. & Spencer Evans, J. (2008). Morphological and Kinetic Transformation of Calcite Crystal Growth by Prismatic-Associated Asprich Sequences. *Crystal Growth & Design*, Vol. 8, No. 4, pp. 1154-1160
- Lakshminarayanan, R.; Joseph, J.S.; Kini, R.M. & Valiyaveetil, S. (2005). Structure-function relationship of avian eggshell matrix proteins: a comparative study of two major eggshell matrix proteins, ansocalcin and OC-17. *Biomacromolecules*, Vol. 6, No. 2, pp. 741-751, 1525-7797; 1525-7797
- Lakshminarayanan, R.; Valiyaveetil, S.; Rao, V.S. & Kini, R.M. (2003). Purification, characterization, and in vitro mineralization studies of a novel goose eggshell matrix protein, ansocalcin. *The Journal of Biological Chemistry*, Vol. 278, No. 5, pp. 2928-2936, 0021-9258; 0021-9258
- Lee, S.L.; Veis, A. & Glonek, T. (1977). Dentin phosphoprotein: an extracellular calcium-binding protein. *Biochemistry*, Vol. 16, No. 13, pp. 2971-2979
- Lee, Y.H.; Britten, R.J. & Davidson, E.H. (1999). SM37, a skeletogenic gene of the sea urchin embryo linked to the SM50 gene. *Development, Growth & Differentiation*, Vol. 41, No. 3, pp. 303-312, 0012-1592; 0012-1592
- Li, M.; Liu, J.; Ran, X.; Fang, M.; Shi, J.; Qin, H.; Goh, J.M. & Song, J. (2006). Resurrecting abandoned proteins with pure water: CD and NMR studies of protein fragments solubilized in salt-free water. *Biophysical Journal*, Vol. 91, No. 11, pp. 4201-4209, 0006-3495; 0006-3495
- Linding, R.; Schymkowitz, J.; Rousseau, F.; Diella, F. & Serrano, L. (2004). A comparative study of the relationship between protein structure and beta-aggregation in globular and intrinsically disordered proteins. *Journal of Molecular Biology*, Vol. 342, No. 1, pp. 345-353, 0022-2836; 0022-2836
- Liu, H.L.; Liu, S.F.; Ge, Y.J.; Liu, J.; Wang, X.Y.; Xie, L.P.; Zhang, R.Q. & Wang, Z. (2007). Identification and characterization of a biomineralization related gene PFMG1 highly expressed in the mantle of *Pinctada fucata*. *Biochemistry*, Vol. 46, No. 3, pp. 844-851, 0006-2960; 0006-2960
- Livingston, B.T.; Killian, C.E.; Wilt, F.; Cameron, A.; Landrum, M.J.; Ermolaeva, O.; Sapojnikov, V.; Maglott, D.R.; Buchanan, A.M. & Etensohn, C.A. (2006). A genome-wide analysis of biomineralization-related proteins in the sea urchin *Strongylocentrotus purpuratus*. *Developmental Biology*, Vol. 300, No. 1, pp. 335-348, 0012-1606; 0012-1606

- Long, J.R.; Shaw, W.J.; Stayton, P.S. & Drobny, G.P. (2001). Structure and dynamics of hydrated statherin on hydroxyapatite as determined by solid-state NMR. *Biochemistry*, Vol. 40, No. 51, pp. 15451-15455, 0006-2960; 0006-2960
- Luquet, G.; Testeniere, O. & Graf, F. (1996). Characterization and N-terminal sequencing of a calcium binding protein from the calcareous concretion organic matrix of the terrestrial crustacean *Orchestia cavimana*. *Biochimica et Biophysica Acta*, Vol. 1293, No. 2, pp. 272-276, 0006-3002; 0006-3002
- Lyngstadaas, S.P.; Wohlfahrt, J.C.; Brookes, S.J.; Paine, M.L.; Snead, M.L. & Reseland, J.E. (2009). Enamel matrix proteins; old molecules for new applications. *Orthodontics & Craniofacial Research*, Vol. 12, No. 3, pp. 243-253, 1601-6343; 1601-6335
- Ma, Z.; Huang, J.; Sun, J.; Wang, G.; Li, C.; Xie, L. & Zhang, R. (2007). A novel extrapallial fluid protein controls the morphology of nacre lamellae in the pearl oyster, *Pinctada fucata*. *The Journal of Biological Chemistry*, Vol. 282, No. 32, pp. 23253-23263, 0021-9258; 0021-9258
- Mann, K. (2004). Identification of the major proteins of the organic matrix of emu (*Dromaius novaehollandiae*) and rhea (*Rhea americana*) eggshell calcified layer. *British Poultry Science*, Vol. 45, No. 4, pp. 483-490, 0007-1668; 0007-1668
- Mann, K.; Hincke, M.T. & Nys, Y. (2002). Isolation of ovocleidin-116 from chicken eggshells, correction of its amino acid sequence and identification of disulfide bonds and glycosylated Asn. *Matrix Biology: Journal of the International Society for Matrix Biology*, Vol. 21, No. 5, pp. 383-387, 0945-053X; 0945-053X
- Mann, K.; Poustka, A.J. & Mann, M. (2010). Phosphoproteomes of *Strongylocentrotus purpuratus* shell and tooth matrix: identification of a major acidic sea urchin tooth phosphoprotein, phosphodontin. *Proteome Science*, Vol. 8, No. 1, pp. 6, 1477-5956; 1477-5956
- Mann, K. & Siedler, F. (2006). Amino acid sequences and phosphorylation sites of emu and rhea eggshell C-type lectin-like proteins. *Comparative Biochemistry and Physiology. Part B, Biochemistry & Molecular Biology*, Vol. 143, No. 2, pp. 160-170, 1096-4959; 1096-4959
- Mann, K. & Siedler, F. (2004). Ostrich (*Struthio camelus*) eggshell matrix contains two different C-type lectin-like proteins. Isolation, amino acid sequence, and posttranslational modifications. *Biochimica et Biophysica Acta*, Vol. 1696, No. 1, pp. 41-50, 0006-3002; 0006-3002
- Marie, B.; Luquet, G.; Bedouet, L.; Milet, C.; Guichard, N.; Medakovic, D. & Marin, F. (2008). Nacre calcification in the freshwater mussel *Unio pictorum*: carbonic anhydrase activity and purification of a 95 kDa calcium-binding glycoprotein. *Chembiochem: A European Journal of Chemical Biology*, Vol. 9, No. 15, pp. 2515-2523, 1439-7633; 1439-4227
- Marie, B.; Zanella-Cleon, I.; Corneillat, M.; Becchi, M.; Alcaraz, G.; Plasseraud, L.; Luquet, G. & Marin, F. (2011). Nautilin-63, a novel acidic glycoprotein from the shell nacre of *Nautilus macromphalus*. *The FEBS Journal*, 1742-4658; 1742-464X
- Marin, F.; Amons, R.; Guichard, N.; Stigter, M.; Hecker, A.; Luquet, G.; Layrolle, P.; Alcaraz, G.; Riondet, C. & Westbroek, P. (2005). Caspartin and calprismin, two proteins of the shell calcitic prisms of the Mediterranean fan mussel *Pinna nobilis*. *The Journal of Biological Chemistry*, Vol. 280, No. 40, pp. 33895-33908, 0021-9258; 0021-9258


- Mendoza, C.; Figueirido, F. & Tasayco, M.L. (2003). DSC studies of a family of natively disordered fragments from *Escherichia coli* thioredoxin: surface burial in intrinsic coils. *Biochemistry*, Vol. 42, No. 11, pp. 3349-3358, 0006-2960; 0006-2960
- Meyran, J.; Graf, F. & Nicaise, G. (1984). Calcium pathway through a mineralizing epithelium in the crustacean *Orchestia* in pre-molt: Ultrastructural cytochemistry and X-ray microanalysis. *Tissue and Cell*, Vol. 16, No. 2, pp. 269-286, 0040-8166
- Michenfelder, M.; Fu, G.; Lawrence, C.; Weaver, J.C.; Wustman, B.A.; Taranto, L.; Evans, J.S. & Morse, D.E. (2003). Characterization of two molluscan crystal-modulating biomineralization proteins and identification of putative mineral binding domains. *Biopolymers*, Vol. 70, No. 4, pp. 522-533, 0006-3525; 0006-3525
- Millett, I.S.; Doniach, S. & Plaxco, K.W. (2002). Toward a taxonomy of the denatured state: small angle scattering studies of unfolded proteins. *Advances in Protein Chemistry*, Vol. 62, pp. 241-262, 0065-3233; 0065-3233
- Moore, E.W. & Verine, H.J. (1987). Pancreatic calcification and stone formation: a thermodynamic model of calcium in pancreatic juice. *The American Journal of Physiology*, Vol. 252, No. 5 Pt 1, pp. G707-18, 0002-9513; 0002-9513
- Naganagowda, G.A.; Gururaja, T.L. & Levine, M.J. (1998). Delineation of conformational preferences in human salivary statherin by ¹H, ³¹P NMR and CD studies: sequential assignment and structure-function correlations. *Journal of Biomolecular Structure & Dynamics*, Vol. 16, No. 1, pp. 91-107, 0739-1102; 0739-1102
- Narayanan, K.; Gajjerman, S.; Ramachandran, A.; Hao, J. & George, A. (2006). Dentin matrix protein 1 regulates dentin sialophosphoprotein gene transcription during early odontoblast differentiation. *The Journal of Biological Chemistry*, Vol. 281, No. 28, pp. 19064-19071, 0021-9258; 0021-9258
- Narayanan, K.; Ramachandran, A.; Hao, J.; He, G.; Park, K.W.; Cho, M. & George, A. (2003). Dual functional roles of dentin matrix protein 1. Implications in biomineralization and gene transcription by activation of intracellular Ca²⁺ store. *The Journal of Biological Chemistry*, Vol. 278, No. 19, pp. 17500-17508, 0021-9258; 0021-9258
- Ndao, M.; Dutta, K.; Bromley, K.M.; Lakshminarayanan, R.; Sun, Z.; Rewari, G.; Moradian-Oldak, J. & Evans, J.S. (2011). Probing the self-association, intermolecular contacts, and folding propensity of amelogenin. *Protein Science : A Publication of the Protein Society*, Vol. 20, No. 4, pp. 724-734, 1469-896X; 0961-8368
- Ndao, M.; Keene, E.; Amos, F.F.; Rewari, G.; Ponce, C.B.; Estroff, L. & Evans, J.S. (2010). Intrinsically disordered mollusk shell prismatic protein that modulates calcium carbonate crystal growth. *Biomacromolecules*, Vol. 11, No. 10, pp. 2539-2544, 1526-4602; 1525-7797
- Oldberg, A.; Franzen, A. & Heinegard, D. (1988). The primary structure of a cell-binding bone sialoprotein. *The Journal of Biological Chemistry*, Vol. 263, No. 36, pp. 19430-19432, 0021-9258; 0021-9258
- Panheleux, M.; Bain, M.; Fernandez, M.S.; Morales, I.; Gautron, J.; Arias, J.L.; Solomon, S.E.; Hincke, M. & Nys, Y. (1999). Organic matrix composition and ultrastructure of eggshell: a comparative study. *British Poultry Science*, Vol. 40, No. 2, pp. 240-252, 0007-1668; 0007-1668
- Patthy, L. (1988). Homology of human pancreatic stone protein with animal lectins. *The Biochemical Journal*, Vol. 253, No. 1, pp. 309-311, 0264-6021; 0264-6021

- Pauling, L. & Delbruck, M. (1940). The Nature of the Intermolecular Forces Operative in Biological Processes. *Science (New York, N.Y.)*, Vol. 92, No. 2378, pp. 77-79, 0036-8075; 0036-8075
- Prince, C.W.; Dickie, D. & Krumdieck, C.L. (1991). Osteopontin, a substrate for transglutaminase and factor XIII activity. *Biochemical and Biophysical Research Communications*, Vol. 177, No. 3, pp. 1205-1210, 0006-291X; 0006-291X
- Qin, C.; Baba, O. & Butler, W.T. (2004). Post-translational modifications of sibling proteins and their roles in osteogenesis and dentinogenesis. *Critical Reviews in Oral Biology and Medicine : An Official Publication of the American Association of Oral Biologists*, Vol. 15, No. 3, pp. 126-136, 1544-1113; 1045-4411
- Raj, P.A.; Johnsson, M.; Levine, M.J. & Nancollas, G.H. (1992). Salivary statherin. Dependence on sequence, charge, hydrogen bonding potency, and helical conformation for adsorption to hydroxyapatite and inhibition of mineralization. *The Journal of Biological Chemistry*, Vol. 267, No. 9, pp. 5968-5976, 0021-9258; 0021-9258
- Reyes-Grajeda, J.P.; Moreno, A. & Romero, A. (2004). Crystal structure of ovocleidin-17, a major protein of the calcified *Gallus gallus* eggshell: implications in the calcite mineral growth pattern. *The Journal of Biological Chemistry*, Vol. 279, No. 39, pp. 40876-40881, 0021-9258; 0021-9258
- Romero, P.; Obradovic, Z.; Li, X.; Garner, E.C.; Brown, C.J. & Dunker, A.K. (2001). Sequence complexity of disordered protein. *Proteins*, Vol. 42, No. 1, pp. 38-48, 0887-3585; 0887-3585
- Ross, M.D. & Pote, K.G. (1984). Some Properties of Otoconia. *Philosophical Transactions of the Royal Society of London. B, Biological Sciences*, Vol. 304, No. 1121, pp. 445-452
- Samata, T.; Ikeda, D.; Kajikawa, A.; Sato, H.; Nogawa, C.; Yamada, D.; Yamazaki, R. & Akiyama, T. (2008). A novel phosphorylated glycoprotein in the shell matrix of the oyster *Crassostrea nippona*. *The FEBS Journal*, Vol. 275, No. 11, pp. 2977-2989, 1742-464X; 1742-464X
- Samata, T.; Hayashi, N.; Kono, M.; Hasegawa, K.; Horita, C. & Akera, S. (1999). A new matrix protein family related to the nacreous layer formation of *Pinctada fucata*. *FEBS Letters*, Vol. 462, No. 1-2, pp. 225-229, 0014-5793
- Sarashina, I. & Endo, K. (2001). The complete primary structure of molluscan shell protein 1 (MSP-1), an acidic glycoprotein in the shell matrix of the scallop *Patinopecten yessoensis*. *Marine Biotechnology (New York, N.Y.)*, Vol. 3, No. 4, pp. 362-369, 1436-2228; 1436-2228
- Shapiro, J.L.; Wen, X.; Okamoto, C.T.; Wang, H.J.; Lyngstadaas, S.P.; Goldberg, M.; Snead, M.L. & Paine, M.L. (2007). Cellular uptake of amelogenin, and its localization to CD63, and Lamp1-positive vesicles. *Cellular and Molecular Life Sciences: CMLS*, Vol. 64, No. 2, pp. 244-256, 1420-682X; 1420-682X
- Shaw, W.J.; Ferris, K.; Tarasevich, B. & Larson, J.L. (2008). The structure and orientation of the C-terminus of LRAP. *Biophysical Journal*, Vol. 94, No. 8, pp. 3247-3257, 1542-0086; 0006-3495
- Shechter, A.; Glazer, L.; Cheled, S.; Mor, E.; Weil, S.; Berman, A.; Bentov, S.; Aflalo, E.D.; Khalaila, I. & Sagi, A. (2008). A gastrolith protein serving a dual role in the formation of an amorphous mineral containing extracellular matrix. *Proceedings of the National Academy of Sciences of the United States of America*, Vol. 105, No. 20, pp. 7129-7134, 1091-6490; 0027-8424

- Shen, X.; Belcher, A.M.; Hansma, P.K.; Stucky, G.D. & Morse, D.E. (1997). Molecular cloning and characterization of lustrin A, a matrix protein from shell and pearl nacre of *Haliotis rufescens*. *The Journal of Biological Chemistry*, Vol. 272, No. 51, pp. 32472-32481, 0021-9258; 0021-9258
- Sickmeier, M.; Hamilton, J.A.; LeGall, T.; Vacic, V.; Cortese, M.S.; Tantos, A.; Szabo, B.; Tompa, P.; Chen, J.; Uversky, V.N.; Obradovic, Z. & Dunker, A.K. (2007). DisProt: the Database of Disordered Proteins. *Nucleic Acids Research*, Vol. 35, No. Database issue, pp. D786-93, 1362-4962; 0305-1048
- Sollner, C.; Burghammer, M.; Busch-Nentwich, E.; Berger, J.; Schwarz, H.; Riekel, C. & Nicolson, T. (2003). Control of crystal size and lattice formation by starmaker in otolith biomineralization. *Science (New York, N.Y.)*, Vol. 302, No. 5643, pp. 282-286, 1095-9203; 0036-8075
- Stayton, P.S.; Drobny, G.P.; Shaw, W.J.; Long, J.R. & Gilbert, M. (2003). Molecular recognition at the protein-hydroxyapatite interface. *Critical Reviews in Oral Biology and Medicine : An Official Publication of the American Association of Oral Biologists*, Vol. 14, No. 5, pp. 370-376, 1544-1113; 1045-4411
- Steitz, S.A.; Speer, M.Y.; McKee, M.D.; Liaw, L.; Almeida, M.; Yang, H. & Giachelli, C.M. (2002). Osteopontin inhibits mineral deposition and promotes regression of ectopic calcification. *The American Journal of Pathology*, Vol. 161, No. 6, pp. 2035-2046, 0002-9440; 0002-9440
- Stubbs, J.T., 3rd; Mintz, K.P.; Eanes, E.D.; Torchia, D.A. & Fisher, L.W. (1997). Characterization of native and recombinant bone sialoprotein: delineation of the mineral-binding and cell adhesion domains and structural analysis of the RGD domain. *Journal of Bone and Mineral Research : The Official Journal of the American Society for Bone and Mineral Research*, Vol. 12, No. 8, pp. 1210-1222, 0884-0431; 0884-0431
- Suzuki, M.; Murayama, E.; Inoue, H.; Ozaki, N.; Tohse, H.; Kogure, T. & Nagasawa, H. (2004). Characterization of Prismalin-14, a novel matrix protein from the prismatic layer of the Japanese pearl oyster (*Pinctada fucata*). *The Biochemical Journal*, Vol. 382, No. Pt 1, pp. 205-213, 1470-8728; 0264-6021
- Suzuki, M. & Nagasawa, H. (2007). The structure-function relationship analysis of Prismalin-14 from the prismatic layer of the Japanese pearl oyster, *Pinctada fucata*. *The FEBS Journal*, Vol. 274, No. 19, pp. 5158-5166, 1742-464X; 1742-464X
- Takeuchi, T.; Sarashina, I.; Iijima, M. & Endo, K. (2008). In vitro regulation of CaCO₃ crystal polymorphism by the highly acidic molluscan shell protein Aspein. *FEBS Letters*, Vol. 582, No. 5, pp. 591-596, 0014-5793; 0014-5793
- Testeniere, O.; Hecker, A.; Le Gurun, S.; Quennedey, B.; Graf, F. & Luquet, G. (2002). Characterization and spatiotemporal expression of orchestin, a gene encoding an ecdysone-inducible protein from a crustacean organic matrix. *The Biochemical Journal*, Vol. 361, No. Pt 2, pp. 327-335, 0264-6021; 0264-6021
- Tohse, H.; Takagi, Y. & Nagasawa, H. (2008). Identification of a novel matrix protein contained in a protein aggregate associated with collagen in fish otoliths. *The FEBS Journal*, Vol. 275, No. 10, pp. 2512-2523, 1742-464X; 1742-464X
- Tohse, H.; Saruwatari, K.; Kogure, T.; Nagasawa, H. & Takagi, Y. (2009). Control of Polymorphism and Morphology of Calcium Carbonate Crystals by a Matrix Protein Aggregate in Fish Otoliths. *Crystal Growth & Design*, Vol. 9, No. 11, pp. 4897-4901

- Tompa, P. (2011). Unstructural biology coming of age. *Current Opinion in Structural Biology*, 1879-033X; 0959-440X
- Tompa, P. (2005). The interplay between structure and function in intrinsically unstructured proteins. *FEBS Letters*, Vol. 579, No. 15, pp. 3346-3354, 0014-5793; 0014-5793
- Tompa, P. (2002). Intrinsically unstructured proteins. *Trends in Biochemical Sciences*, Vol. 27, No. 10, pp. 527-533, 0968-0004; 0968-0004
- Tsukamoto, D.; Sarashina, I. & Endo, K. (2004). Structure and expression of an unusually acidic matrix protein of pearl oyster shells. *Biochemical and Biophysical Research Communications*, Vol. 320, No. 4, pp. 1175-1180, 0006-291X; 0006-291X
- Tye, C.E.; Hunter, G.K. & Goldberg, H.A. (2005). Identification of the type I collagen-binding domain of bone sialoprotein and characterization of the mechanism of interaction. *The Journal of Biological Chemistry*, Vol. 280, No. 14, pp. 13487-13492, 0021-9258; 0021-9258
- Tye, C.E.; Ratray, K.R.; Warner, K.J.; Gordon, J.A.; Sodek, J.; Hunter, G.K. & Goldberg, H.A. (2003). Delineation of the hydroxyapatite-nucleating domains of bone sialoprotein. *The Journal of Biological Chemistry*, Vol. 278, No. 10, pp. 7949-7955, 0021-9258; 0021-9258
- Uversky, V.N. (2009). Intrinsically disordered proteins and their environment: effects of strong denaturants, temperature, pH, counter ions, membranes, binding partners, osmolytes, and macromolecular crowding. *The Protein Journal*, Vol. 28, No. 7-8, pp. 305-325, 1875-8355; 1572-3887
- Uversky, V.N. (2002). Natively unfolded proteins: a point where biology waits for physics. *Protein Science: A Publication of the Protein Society*, Vol. 11, No. 4, pp. 739-756, 0961-8368; 0961-8368
- Uversky, V.N. & Dunker, A.K. (2010). Understanding protein non-folding. *Biochimica Et Biophysica Acta*, Vol. 1804, No. 6, pp. 1231-1264, 0006-3002; 0006-3002
- Uversky, V.N.; Gillespie, J.R. & Fink, A.L. (2000). Why are "natively unfolded" proteins unstructured under physiologic conditions?. *Proteins*, Vol. 41, No. 3, pp. 415-427, 0887-3585; 0887-3585
- Veis, A. (2003). Amelogenin gene splice products: potential signaling molecules. *Cellular and Molecular Life Sciences : CMLS*, Vol. 60, No. 1, pp. 38-55, 1420-682X; 1420-682X
- Veis, A.; Sfeir, C. & Wu, C.B. (1997). Phosphorylation of the proteins of the extracellular matrix of mineralized tissues by casein kinase-like activity. *Critical Reviews in Oral Biology and Medicine: An Official Publication of the American Association of Oral Biologists*, Vol. 8, No. 4, pp. 360-379, 1045-4411; 1045-4411
- Vymetal, J.; Slaby, I.; Spahr, A.; Vondrasek, J. & Lyngstadaas, S.P. (2008). Bioinformatic analysis and molecular modelling of human ameloblastin suggest a two-domain intrinsically unstructured calcium-binding protein. *European Journal of Oral Sciences*, Vol. 116, No. 2, pp. 124-134, 1600-0722; 0909-8836
- Ward, J.J.; McGuffin, L.J.; Bryson, K.; Buxton, B.F. & Jones, D.T. (2004a). The DISOPRED server for the prediction of protein disorder. *Bioinformatics (Oxford, England)*, Vol. 20, No. 13, pp. 2138-2139, 1367-4803; 1367-4803
- Ward, J.J.; Sodhi, J.S.; McGuffin, L.J.; Buxton, B.F. & Jones, D.T. (2004b). Prediction and functional analysis of native disorder in proteins from the three kingdoms of life. *Journal of Molecular Biology*, Vol. 337, No. 3, pp. 635-645, 0022-2836; 0022-2836

- Wilt, F.H. (1999). Matrix and mineral in the sea urchin larval skeleton. *Journal of Structural Biology*, Vol. 126, No. 3, pp. 216-226, 1047-8477; 1047-8477
- Wilt, F.H. & Etensohn, C.A. (2007; 2008). The Morphogenesis and Biomineralization of the Sea Urchin Larval Skeleton, Wiley-VCH Verlag GmbH, 9783527619443
- Wright, P.E. & Dyson, H.J. (1999). Intrinsically unstructured proteins: re-assessing the protein structure-function paradigm. *Journal of Molecular Biology*, Vol. 293, No. 2, pp. 321-331, 0022-2836; 0022-2836
- Wu, H.; Teng, P.N.; Jayaraman, T.; Onishi, S.; Li, J.; Bannon, L.; Huang, H.; Close, J. & Sfeir, C. (2011). Dentin matrix protein 1 (DMP1) signals via cell surface integrin. *The Journal of Biological Chemistry*, 1083-351X; 0021-9258
- Wustman, B.A.; Morse, D.E. & Evans, J.S. (2004). Structural characterization of the N-terminal mineral modification domains from the molluscan crystal-modulating biomineralization proteins, AP7 and AP24. *Biopolymers*, Vol. 74, No. 5, pp. 363-376, 0006-3525; 0006-3525
- Wustman, B.A.; Santos, R.; Zhang, B. & Evans, J.S. (2002). Identification of a "glycine-loop"-like coiled structure in the 34 AA Pro,Gly,Met repeat domain of the biomineral-associated protein, PM27. *Biopolymers*, Vol. 65, No. 5, pp. 362-372, 0006-3525; 0006-3525
- Wustman, B.A.; Weaver, J.C.; Morse, D.E. & Evans, J.S. (2003). Structure-function studies of the lustrin A polyelectrolyte domains, RKS and D4. *Connective Tissue Research*, Vol. 44 Suppl 1, pp. 10-15, 0300-8207; 0300-8207
- Wuttke, M.; Muller, S.; Nitsche, D.P.; Paulsson, M.; Hanisch, F.G. & Maurer, P. (2001). Structural characterization of human recombinant and bone-derived bone sialoprotein. Functional implications for cell attachment and hydroxyapatite binding. *The Journal of Biological Chemistry*, Vol. 276, No. 39, pp. 36839-36848, 0021-9258; 0021-9258
- Xu, G. & Evans, J.S. (1999). Model peptide studies of sequence repeats derived from the intracrystalline biomineralization protein, SM50. I. GVGG and GMGG repeats. *Biopolymers*, Vol. 49, No. 4, pp. 303-312, 0006-3525; 0006-3525
- Zhang, B.; Wustman, B.A.; Morse, D. & Evans, J.S. (2002). Model peptide studies of sequence regions in the elastomeric biomineralization protein, Lustrin A. I. The C-domain consensus-PG-, -NVNCT-motif. *Biopolymers*, Vol. 63, No. 6, pp. 358-369, 0006-3525; 0006-3525
- Zhang, B.; Xu, G. & Evans, J.S. (2000). Model peptide studies of sequence repeats derived from the intracrystalline biomineralization protein, SM50. II. Pro,Asn-rich tandem repeats. *Biopolymers*, Vol. 54, No. 6, pp. 464-475, 0006-3525; 0006-3525
- Zou, Y.; Wang, H.; Shapiro, J.L.; Okamoto, C.T.; Brookes, S.J.; Lyngstadaas, S.P.; Snead, M.L. & Paine, M.L. (2007). Determination of protein regions responsible for interactions of amelogenin with CD63 and LAMP1. *The Biochemical Journal*, Vol. 408, No. 3, pp. 347-354, 1470-8728; 0264-6021



Advanced Topics in Biomineralization

Edited by Dr. Jong Seto

ISBN 978-953-51-0045-4

Hard cover, 174 pages

Publisher InTech

Published online 17, February, 2012

Published in print edition February, 2012

Advanced Topics in Biomineralization is a compendium of current topics focusing on processes of formation, organization, as well as mineralization of novel structural materials. From enchondral ossification to the application of biomineralized cement, the subject of biomineralization encompasses a range of diverse disciplines including molecular biology, supramolecular chemistry, materials science and engineering. A common theme in all these areas of research in biomineralization is the ability to utilize strategies from Nature to create functional materials. By understanding Nature's tools to make strong and tough materials, similar properties can be endowed into man-made materials in the near future.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Magdalena Wojtas, Piotr Dobryszycski and Andrzej Ożyhar (2012). Intrinsically Disordered Proteins in Biomineralization, Advanced Topics in Biomineralization, Dr. Jong Seto (Ed.), ISBN: 978-953-51-0045-4, InTech, Available from: <http://www.intechopen.com/books/advanced-topics-in-biomineralization/intrinsically-disordered-proteins-in-biomineralization>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2012 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](https://creativecommons.org/licenses/by/3.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

IntechOpen

IntechOpen