# We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,900

185,000

200M

Downloads

154
Countries delivered to

Our authors are among the

 $\mathsf{TOP}\:1\%$ 

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index in Web of Science™ Core Collection (BKCI)

Interested in publishing with us? Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.

For more information visit www.intechopen.com



# Chapter

# Utilization of Agro-Industrial Wastes as Edible Coating and Films for Food Packaging Materials

Urmila Choudhary, Basant Kumar Bhinchhar, Vinod Kumar Paswan, Sheela Kharkwal, Satya Prakash Yadav and Prity Singh

## **Abstract**

Mostly, food packaging employs synthetic materials obtained from nonrenewable sources. These packaging materials are based on petrochemicals and cause substantial environmental problems by producing massive amounts of nonbiodegradable solid wastes. Edible coatings and films are considered as the potential solution to these problems of non-biodegradable packaging solid wastes for maintaining food-environment interactions, retaining food quality, and extending shelf life. In addition, edible coatings and films offer prevention from microbial spoilage of packed foods by controlling moisture and gas barrier characteristics. Increasing environmental concerns and consumer demands for high-quality eco-friendly packaging have fueled the advancement of innovative packaging technologies, for instance, the development of biodegradable films from renewable agricultural and food processing industry wastes. Therefore, the current chapter presents the application of edible coatings and films as an alternative to conventional packaging, emphasizing the fundamental characterization that these biodegradable packaging should hold for specific applications such as food preservation and shelf life enhancement. The primary employed components (e.g., biopolymers, bioactive, and additives components), manufacturing processes (for edible films or coatings), and their application to specific foods have all been given special consideration in this chapter. Besides, a future vision for the use of edible films and coatings as quality indicators for perishable foods is presented.

**Keywords:** agro-industrial wastes, edible films, edible coatings, food packaging, biopolymers

# 1. Introduction

Majority of food packaging are made of synthetic materials derived from nonrenewable sources and based on petrochemicals, having advantages of being available in large quantities at a low cost and having excellent barrier and resistance properties. Nevertheless, these are causing serious environmental issues due to the


production of large amounts of non-biodegradable solid wastes [1]. Apart from its primary function of containing food, delaying deterioration, and extending shelf life, packaging also plays a critical role in regulating food-environment interactions [2, 3]. Environmental concerns and consumer demands for high-quality eco-friendly products that are similar to those found in nature (natural products), has prompted the development of technologies for novel packaging materials, such as the production of biodegradable films from renewable polymers [1, 3, 4]. As a result, consumer demand for packaging materials has switched to safe and environment friendly biodegradable materials, particularly from renewable agriculture by-products and food processing industry wastes. Polysaccharides including starch, cellulose, sodium alginate, pectin, chitosan, and gums, as well as proteins like whey, soy, gluten, and gelatin, are among the most commonly used biopolymers in the manufacture of biodegradable films [5]. Because of their abundance in nature, biodegradability, and edibility, these natural biopolymers are widely employed. Casting, pressing, and extrusion, followed by blowing, are some of the procedures utilized in the production of these films [6]. Plant-derived bioactive substances, such as essential oils, vitamins, minerals, polyphenols, and carotenoids, are extensively distributed in nature in addition to biopolymers. Because of their biological nature, different parts of plants, such as leaves, flowers, seeds, and roots, can possibly be employed in the manufacture of environment friendly films with functional features [7]. Some bioactive substances have antioxidant and antibacterial properties [8–10]. Bioactive films with new and/or improved properties, such as antioxidant [8, 9] and antimicrobial [10] effects, innovative colors [11, 12], and customized barrier and mechanical properties, have been developed using biopolymers and natural bioactive compounds [8, 11, 13]. Some of the techniques used for their production include the use of inherently bioactive biopolymer-based materials [14, 15], as well as the direct or sprinkling incorporation of free or encapsulated bioactive compounds into the film-forming solutions [8, 12].

Some polymers generated from renewable agro-waste sources are edible and have played important roles in food throughout history as well as in the food, pharmaceutical, and other industries. Biopolymers can be used alone or in combination with other biopolymers to produce an edible coating or film material [16, 17]. In comparison to non-edible polymeric packaging, edible coatings and films offer a number of advantages. They can simplify food packaging and, even if they are not consumed with the packaged product, they can assist to environmental pollution reduction due to their biodegradable nature. Material fragmentation and subsequent mineralization are the mechanisms through which polymers degrade in a bioactive environment. Outer temperature and moisture, as well as the enzyme activity of microorganisms degrade polymer, resulting in fragmented polymer residues. These polymer fragments are only considered biodegradable if they are consumed as food and for energy by microorganisms and converted into carbon dioxide (CO<sub>2</sub>), water (H<sub>2</sub>O), and biomass under aerobic conditions and hydrocarbons, methane, and biomass under anaerobic conditions at the end of the degradation process [18].

# 2. Agro-waste based renewable sources used in development of edible coatings and films

Bio-packaging films are made of materials derived from renewable resources that degrade completely. These can be made directly by biological systems (for example, plants, animals, algae, and microbes) or by polymerizing bio-based monomers (e.g.,

Utilization of Agro-Industrial Wastes as Edible Coating and Films for Food Packaging Materials DOI: http://dx.doi.org/10.5772/intechopen.99786



**Figure 1.**Life cycle of agro-waste based renewable sources used in the development of edible coatings or films with modifications. (Adopted from Giosafatto et al. [19].)

polylactic acid). Classification and life cycle of various agro-waste based renewable sources used in the development of edible coatings or films has been depicted in **Figure 1**. These bio-polymer materials have been classified into four groups based on their origin and manufacturing method [20]. Among the biopolymers utilized in the packaging business include natural polysaccharides, proteins, and their derivatives [21, 22]. Polysaccharides (e.g., cellulose, pectin, gum, starch, chitosan) and proteins (e.g., collagen, casein, whey protein, egg protein, gluten) extracted from biomass, polymers synthesized from bio-derived monomers (e.g., polylactic acid (PLA)), and those produced directly by microorganisms (e.g., polyhydroxyalkanoates (PHA), pullulan, curdlan, bacterial cellulose) are examples of such materials based on renewable resources that are commonly used for food packaging applications [21]. These bio-based materials have good barrier properties and can be mass-produced on a large industrial scale for moderately low costs, making them a viable alternative to petroleum-based plastics. However, due to considerable divergence in respect to plastics, such as weak tensile strength, brittleness, thermal instability, and water sensitivity, commercialization of polymers produced from biomass is still limited [23–26]. As a result, various reinforcing materials and chemicals, such as plasticizers (e.g., glycerol, glycol, sorbitol), are combined with edible films and coatings to enhance their quality [27–31]).

In most circumstances, one of the above-mentioned biomaterials can be used alone or in combination with other biopolymers to create an edible coating or film material [16, 17].

# 3. Preparation of edible coatings and films

Edible coatings and films can be liquid, semi-solid or solid matrix that is wrapped around the surface of a food product and can be used as main packaging without providing any sensory or nutritional benefits. These are intended to be tasteless, colorless, non-toxic and unaffected by the sensory properties of the food product [32]. Trinetta [33] reported that when edible coatings and films are applied to cold or hot beverages, edible film dissolves and releases its contents,

giving customers comfort portion control, and the elimination of solid waste. Recently, consumer awareness of edible, biodegradable, and environment friendly packaging materials has grown; edible films and coatings are increasingly being employed in the food processing industry for a wide range of food products. A comprehensive list of biopolymers used, their properties, functions and processing methods employed for production of edible coatings and films for various food products has been presented in **Table 1**. The coating method chosen has an impact not only on the preservation effect of the coating generated on the food products, but also on the cost of manufacturing and process efficiency. There are two types of edible packagings: (i) edible coatings applied directly to the food products and (ii) premade films wrapped around the food products. Two processes can be used to create edible coatings [54]. Dry-process methods, such as thermoplastic extrusion, rely on the thermoplastic characteristics of polymers when plasticized and heated above their glass-transition temperature in low-water-content circumstances. Extruded films have the drawback of not being able to cover uneven surfaces. On a commercial scale, extrusion and spraying are the predominant procedures for film creation and coating deposition, respectively. On the other hand, at a lab scale, the casting method for film creation and dipping methods for coating deposition, are simple to use and preferred methods.

Bio-polymers	Properties	Functions in edible coatings and films	Food product	Processing methods	References
Starch Cellulose Pectin Gums Chitosan Agar Alginate Dextran	Thickeners Gellants Stabilizers Coatings	They form base structure of a solid polymer matrix. They control physical changes, microbial growth, nutritional qualities and shelf-life.	Mango, Apple, Tomato, Strawberries, Green chilies, Sausage, Water melon, Plums, Bell pepper, Brinjal, Potatoes, Taro corms	Extrusion Solvent casting, co-extrusion, Dipping	[34–40]
Gelatin Pea protein isolate Casein Collagen Blood protein Fish protein Whey protein	Gellants Thickeners Stabilizers Emulsifiers Foaming	They help in transport of antimicrobials and antioxidants. They control transport of gases (mainly O <sub>2</sub> )	Soybean oil Cheese slice, Sausage, Meat slice, Soluble coffee, Walnut kernels, Apple, Blood hake, Beef tenderloins, Pork loins, Salmon fillets Chicken breasts, Rice crisp balls	Solvent casting, Extrusion, Panning, Spraying, Dipping, Compression, Injection Molding, Electrospinning, 3D-printing	[5, 41–48]
Waxes Pullulan esters Chocolates Milk butter Oils (Olive oil and sunflower oil) Paraffin Glycerides	Protectors Coatings	They help to avoid drying or dehydration of the edible films and provide flexibility. They show anti-aging effects.	Strawberry, Fresh-cut apples	Solvent casting, Spreading, Dipping	[49, 50]

Bio-polymers	Properties	Functions in edible coatings and films	Food product	Processing methods	References
Additives (Glycerol, Resins, Polyglycerol Polyricinoleate, Lecithin, Ascorbic acid, Bioactive compounds)	Viscosity resistance Flexibility Antioxidants Stabilizers Anti-fungal Herbicides Fertilizers Antimicrobial Anti- inflammatory	They decrease the intermolecular force, melting temperature in the mixture and modify viscosity and rheological properties. They increase the solubility of polymers in water and work as stabilizers as well as protection for the products.	Pear, Mango, Quail eggs, Fresh- cut apples	Solvent casting, Spreading, Dipping	[49, 51–53]

**Table 1.**List of biopolymers used, their properties, functions and processing methods employed for production of edible coatings and films for various food products.

# 4. Classification of edible coatings and films

Edible coatings and edible films are not the same; edible coatings can be applied directly to the surface of fruits, vegetables, and other food products in liquid form, usually by immersing the product in an edible material solution. Whilst edible films are molded as solid sheets and then utilized to wrap and package the food products [55]. The edible coating and film components are biodegradable and non-toxic. Biopolymer matrixes such as polysaccharides, proteins, lipids, and composite materials are used to create edible materials (**Table 1**). These coatings and films are thin layers created as a coating on a food surface or put (pre-made) between food components. Their goal is to enhance the shelf life of the food product while simultaneously acting as a safety barrier. They can retard moisture migration and the loss of volatile chemicals, as well as inhibit respiration and delay textural changes. In addition, as compared to typical synthetic films, they are good fat and oil barriers and have a high selective gas permeability ratio  $CO_2/O_2$  [56]. They can also serve as carriers for food additives like antioxidants [57] and/or antimicrobial agents [10], as well as improve the product's mechanical integrity and handling properties. For some applications, stand-alone edible films with strong mechanical qualities could replace synthetic packaging films. Composition of biopolymers, their concentration, drainage time, viscosity, and other factors influence the mechanical and barrier properties of edible films and coatings [58].

# 5. Incorporation of bioactive compounds into edible coatings and films

Bioactive chemicals are generally secondary metabolites of plants that have both nutritional value and other functions in their metabolism, such as growth stimulant and protection against biotic and abiotic stress [59]. They are widely distributed in

nature. Fruits and vegetables [11], leaves, blossoms [2], grains, seeds [60], rhizomes and roots [61], of different sorts of plants are important sources of bioactive components including phenols, proteins, essential oils, terpenoids and flavonoids. Plant-determined bioactive compounds are being viewed as fascinating elements for the creation of biodegradable and bioactive films because of their usefulness and natural origin [7]. Plant extracts and fruit pulps as sources of bioactive compounds or isolated bioactive compounds in film-forming solutions have been demonstrated to have antioxidant and antibacterial effects on the subsequent films, prolonging their utility in bioactive and biodegradable films or packaging [2, 3, 24, 62]. Plant derived naturally bioactive compounds are incorporated directly into agro-based polymers or the encapsulated plant-derived bioactive chemicals are integrated into the biopolymers by spraying during the production process [63]. Some edible coatings obtained from plant-derived bioactive compounds along with their methods of incorporation into the coatings, method of development of the edible coatings and films from these phytochemicals and the functional properties of these coatings and films are enlisted in Table 2.

Plant-derived bioactive compounds	Methods for incorporation	Methods of development of edible coatings and films	Functional properties	Reference
Blackberry pulp	Directly by sprinkling into the film-forming solution	Casting	Increased water vapor permeability and solubility in water; Reduced tensile strength; Antioxidant properties	[8, 12]
Curcumin	Directly into the film forming solution	Casting	Antioxidant and antimicrobial activity	[64]
Cranberry extract	Directly into the film forming solution	Casting	Antioxidant	[65]
Vitamin E (α-tocopherol encapsulated in carboxy methyl cellulose)	Directly into the film forming solution	Solution casting	Antioxidant; Decreased water vapor permeability and tensile strength	[66]
Tea Polyphenols	Directly into the film forming solution	Casting	Antioxidant and antimicrobial properties; Improved water barrier properties and tensile strength	[67, 68]
Babassu	Producing the film using inherently bioactive biopolymeric materials from agricultural by-products		Antioxidant	[15]
Essential oils	Directly into the film- forming solution	Casting	Improved barrier properties	[2]

**Table 2.**List of some edible coatings obtained from plant-derived bioactive compounds, their methods of incorporation, method of development of the edible coatings and films and their functional properties.

# 6. Properties of edible coatings and films from agro-waste based polymers

In the food processing industry, edible coating/film provides a consistent quality for food items with market safety, nutritional value, and low manufacturing costs [69]. Control of mass transfers, mechanical protection, and sensory appeal are the most significant functions of an edible film or coating. Preventing desiccation of foods, regulating microenvironments of gases around foods, and controlling migration of ingredients and additives in food systems are all part of mass transfer control. Edible coatings on fresh foods can reduce quality changes and quantity losses by modifying and controlling the internal atmosphere of particular foods, which is an alternative to modified atmosphere storage. Even while penetration of oxygen may degrade food quality due to oxidation of the fragrance components in the food, modification of the internal atmosphere by the application of edible coatings can aggravate disorders associated with high carbon dioxide or low oxygen concentration. For fresh items, edible films with high water vapor permeability is also desired to extend the shelf life, while extremely high water vapor permeability is not, as it might cause significant moisture loss in the fruits during storage. The mechanical strength of an edible film must be sufficient to safeguard the packaging's integrity during distribution. The sensory qualities of an edible coating or film are critical aspects in final product approval.

The selection of ingredients is one of the most crucial aspects of making edible films. Polysaccharide-based edible coatings and films, a type of natural macromolecule with a high bioactivity, are often generated from agricultural feedstock or crustacean shell wastes. Polysaccharides that may form gels in water are found all over the plant kingdom. Some of them have been thoroughly explored, such as pectins in higher plants, carrageenans and agarose in algae, algal and bacterial alginates, and xanthans. Mucilages are heteropolysaccharides derived from plant stems, such as cactus stems. Food, cosmetics, pharmaceuticals, and other businesses may benefit from cactus mucilage [70]. The complex polysaccharide is a type of dietary fiber that can absorb adequate water before dissolving and dispersing and generating viscous or gelatinous colloids. The low cost of cactus mucilage as a coating is an important desirable consideration.

On the other hand, proteins such as casein, whey proteins, and maize zein, have been employed as a moisture barrier in edible coatings since they are numerous, abundant, inexpensive, and readily available. Corn zein, soy protein, wheat proteins (gluten, gliadin), peanut protein, gelatin, casein, and milk whey proteins have all been used in the production of protein-based films [5]. Food protein may act as natural vehicles, adapted to carry vital micronutrients (e.g. calcium and phosphate), building blocks (e.g. amino acids), as well as immune system components (e.g. immunoglobulins and lactoferrin) [71]. Furthermore, food proteins can be employed in coating formulations to create environment friendly packagings that are easily degradable and can be applied to a variety of foods such as vegetables, fruits, poultry, and fish items [72]. Protein-based edible films are appealing because, when compared to lipid- and polysaccharide-based edible films, they have superior gas barrier properties. Protein films' poor water vapor resistance and lower mechanical strength when compared to synthetic polymers, however, limit their use in food packaging.

Further, despite multifunctional potential of polysaccharides and proteins, the hydrophilic nature of these biopolymers limits their capacity to offer the desired edible film capabilities. Incorporation of hydrophobic chemicals, adjustment of

polymer interaction, and production of cross-links are some of the ways to increase the water barrier and mechanical properties of these films. Lipid molecules used in edible coatings include neutral lipids of glycerides, which are esters of glycerol and fatty acids, and waxes, which are esters of long-chain monohydric alcohols and fatty acids. They are used to give hydrophobicity to food coatings [73]. Although protein films have good oxygen barrier and mechanical properties at low and intermediate relative humidity due to their large number of polar groups and extensive polymer inter-chain, the hydrophilic nature of proteins prevents edible protein films from acting as an effective water vapor barrier. However, lipid films have limited water vapor permeability due to their hydrophobic nature, but they are extremely brittle because of their monomeric structure. Furthermore, lipids generate opaque films or coatings and are susceptible to oxidation. These characteristics may affect the organoleptic characteristics of food and reduce their marketability. Natural antioxidants and antibacterial agents have also been added to the edible film to help prevent autoxidation of high-fat foods and boost oil resistance in fried foods [74, 75]. During storage, edible materials acts as barrier against moisture and gases from fresh produce, slowing enzymatic oxidation and protecting the food from browning and texture softening. These may also have the capacity to preserve natural volatile flavor compounds and prevent color components from discoloration [76]. Edible coatings and films aid to preserve phytochemical (phenolic, antioxidants, color) and physicochemical (total soluble solids, weight loss, pH, and respiration rate) attributes in fresh and minimally processed fruits and vegetables over time [77].

# 7. Physiochemical and morphological characterization of edible coatings and films

The main attributes and techniques for characterization of edible coatings and films are given below:

### 7.1 Physicochemical characterization

- Mechanical properties
- Solubility
- Color and transparency
- Thermal properties
- Microscopy
- Barrier properties

### 7.2 Performance evaluation

- Moisture loss, color, film thickness, microbial test
- Sensory properties
- Barrier properties (O<sub>2</sub> permeability, CO<sub>2</sub> permeability, water vapor permeability)


# 7.3 Morphological characterization

- Atomic force microscopy
- Transmission electron microscopy
- Scanning electron microscopy
- Universal tensile machine
- Fourier transform infrared spectroscopy
- Thermal methods
- Differential scanning calorimetry
- Thermogravimetric analysis
- Differential thermal analysis
- Dynamic mechanical analysis
- X-Ray diffraction
- Nuclear magnetic resonance spectroscopy analysis
- Dynamic light scattering
- Rheological analysis
- Zeta potential analysis

# 8. Application of edible coatings and films

Edible coatings and films produced from a variety of biopolymers can effectively preserve the nutritional and organoleptic qualities of various foods (**Figure 2**). Edible coatings and films are known as eco-friendly packaging materials, as they replace synthetic or plastic packaging materials and lower the post-harvest losses of fruits and vegetables [78–81]. The edible coating extends shelf life [76, 82–84], prevent microbiological contamination [85], minimizes lipid oxidation [86], and lowers their degradation effect [87].

Biopolymers-based edible coatings operate as barrier layers against gas diffusion, fragrance alterations, water migration, and various volatile exchange [88, 89]. Because of their great selective permeability to oxygen and carbon dioxide, polysaccharides have mostly been employed for food wrapping. The majority of these low-cost films are made from cellulose and its derivatives, such as ethers and esters, starch, pectins, and gums, which are used in food preservation. Fresh fruit products such as tomatoes, cherries, fresh beans, strawberries, mangoes, and bananas have all been coated with cellulose-based edible coatings to prevent quality loss. Chitosan is a polysaccharide that is commonly used to prevent post-harvest deterioration in fresh fruits and vegetables. Chitosan is made up of chitin, which is found in nature just next to cellulose in quantity [90]. Tahir et al. [91] investigated the efficiency of



**Figure 2.**Application of edible coating and films.

a gum arabic edible coating for increasing total antioxidant content in strawberry fruits during cold storage, with an increase in anthocyanin and phenolic contents. Furthermore, edible coatings containing chitosan and essential oils of oregano or thyme can inhibit the growth of spoilage and pathogen microorganisms while also improving the sensory quality of peeled shrimp [92]. Edible coatings are good transporter of functional ingredients and additives such color, flavor, minerals, vitamins, and antioxidant agents to improve the nutritional value, durability, and functionality of foods [77]. Ebrahimi and Rastegar [93] reported that a guar-based edible coating coated with A. vera and Spirulina platensis was effective in preserving the ascorbic acid content, total phenol, and antioxidant activity of mango maintained at room temperature. In addition, the coating extended the shelf life of mango fruit by reducing respiration and weight loss. Active films offer promising approach for slowly delivering the functional additives to the food surface, which could help to prevent food spoilage. Active packaging – a novel offshoot of the family of edible films - is quite encouraging as it can be carrier for a wide range of food additives, such as vitamins, antioxidants, minerals, colorants, fragrances, and antibacterial agents for the packaged food products [94].

# 9. Conclusions and future prospects

Starch, pectin, collagen, sodium alginate, gelatin, chitin, whey protein, chitosan, soy protein, gluten proteins and lipids are all examples of agro-industrial leftovers based biopolymers that have been widely used in the manufacturing of environment friendly food coatings and films. However, limited mechanical strengths and moisture barrier properties of most biopolymers-based edible coatings and films are the notable drawbacks. Combining agro- industrial leftovers based biopolymers with plant-derived bioactive substances (vitamins, carotenoids, phenolic compounds and phytochemicals, among others) permit the formation of bioactive films with antioxidants, antibacterial action. It is feasible to improve the mechanical and moisture barrier and physical properties of films by combining proteins (e.g., milk proteins, soy protein, collagen, and gelatin) with polysaccharides (e.g., starches, alginates, cellulose, and chitosan) or other polymers and hydrophobic compounds (lipids). Crosslinking procedures, on the other hand, could be a fascinating process that take into consideration chemical, enzymatic, and physical processes to produce biodegradable packaging materials with improved qualities from agroindustrial wastes.

# **Conflict of interest**

The authors declare no conflict of interest.



### **Author details**

Urmila Choudhary<sup>1</sup>, Basant Kumar Bhinchhar<sup>2</sup>, Vinod Kumar Paswan<sup>3\*</sup>, Sheela Kharkwal<sup>4</sup>, Satya Prakash Yadav<sup>3</sup> and Prity Singh<sup>3</sup>

- 1 Department of Food and Biotechnology, Faculty of Agriculture and Veterinary Science, Jayoti Vidyapeeth Women's University, Jaipur, India
- 2 Department of Livestock Production Management, Krishi Vigyan Kendra Bharatpur, Sri Karan Narendra Agriculture University, Jobner, Jaipur, India
- 3 Department of Dairy Science and Food Technology, Institute of Agricultural Sciences, Banaras Hindu University, Varanasi, UP, India
- 4 Department of Agriculture Economics, Sri Karan Narendra Agriculture University, Johner, Jaipur, India

\*Address all correspondence to: vkpaswan.vet@gmail.com

# **IntechOpen**

© 2021 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (http://creativecommons.org/licenses/by/3.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited. CC BY

# References

- [1] Zhao G, Lyu X, Lee J, Cui X, Chen WN. Biodegradable and transparent cellulose film prepared eco-friendly from durian rind for packaging application. Food Packaging and Shelf Life. 2019; 21:100345.
- [2] Mahcene Z, Khelil A, Hasni S, Akman PK, Bozkurt F, Birech K, Goudjil MB, Tornuk F. Development and characterization of sodium alginate based active edible films incorporated with essential oils of some medicinal plants. International Journal of Biological Macromolecules. 2020; 145:124-132.
- [3] Zahan KA, Azizul NM, Mustapha M, Tong WY, Rahman AMS, Sahuri IS. Application of bacterial cellulose film as a biodegradable and antimicrobial packaging material. Materials Today: Proceedings. 2020; 31:83-88.
- [4] Gouveia TIA, Biernacki K, Castro MCR, Gonçalves MP, Souza HKS. A new approach to develop biodegradable films based on thermoplastic pectin. Food Hydrocolloids. 2019; 97:105175.
- [5] Álvarez-Castillo E, Felix M, Bengoechea C, Guerrero A. (2021). Proteins from Agri-Food Industrial Biowastes or Co-Products and Their Applications as Green Materials. Foods. 2021; 10:981. DOI: 10.3390/ foods10050981
- [6] Fakhouri FM, Costa D, Yamashita F, Martelli SM, Jesus RC, Alganer K, Collares-Queiroz FP, Innocentini-Mei LH. (2013). Comparative study of processing methods for starch/gelatin films. Carbohydrate Polymers. 2013; 95:681-689.
- [7] Jafarzadeh S, Jafari SM, Salehabadi A, Nafchi AM, Uthaya Kumar US, Khalil HPSA. (2020).

- Biodegradable green packaging with antimicrobial functions based on the bioactive compounds from tropical plants and their by-products. Trends in Food Science and Technology. 2020. 100:262-277.
- [8] Nogueira GF, Soares CT, Cavasini R, Fakhouri FM, de Oliveira RA. Bioactive films of arrowroot starch and blackberry pulp: Physical, mechanical and barrier properties and stability to pH and sterilization. Food Chemistry. 2019(a); 275:417-425.
- [9] Riaz A, Lagnika C, Luo H, Dai Z, Nie M, Hashim MM, Liu C, Song J, Li D. (2020) Chitosan-based biodegradable active food packaging film containing Chinese chive (*Allium tuberosum*) root extract for food application. International Journal of Biological Macromolecules. 2020; 150:595-604.
- [10] Fu Y, Dudley EG. (2021). Antimicrobial-coated films as food packaging: A review. Comprehensive Review in Food Science and Food Safety. 2021; 1-34. DOI: 10.1111/1541-4337.12769
- [11] Brito TB, Carrajola JF, Gonçalves ECBA, Martelli-Tosi M, Ferreira MSL. Fruit and vegetable residues flours with different granulometry range as raw material for pectin-enriched biodegradable film preparation. Food Research International. 2019; 121:412-421.
- [12] Nogueira GF, Fakhouri FM, de Oliveira RA. Incorporation of spray dried and freeze dried blackberry particles in edible films: Morphology, stability to pH, sterilization and biodegradation. Food Packaging and Shelf Life. 2019(b); 20:100313.
- [13] Zarandona I, Barba C, Guerrero P, de la Caba K, Maté J. Development of chitosan films containing-cyclodextrin

- inclusion complex for controlled release of bioactives. Food Hydrocolloids. 2020; 104:105720
- [14] Maniglia BC, Domingos JR, de Paula RL, Tapia-Blácido DR. (2014). Development of bioactive edible film from turmeric dye solvent extraction residue. LWT:Food Science and Technology. 2014; 56, 269-277.
- [15] Maniglia BC, Tessaro L, Lucas AA, Tapia-Blácido DR. Bioactive films based on babassu mesocarp flour and starch. Food Hydrocolloids. 2017; 70:383-391.
- [16] Shit SC, Shah PM. Edible polymers: Challenges and opportunities. Journal of Polymers. 2014; 427259:1-13.
- [17] Pop OL, Pop CR, Dufrechou M, Vodnar DC, Socaci SA, Dulf FV, et al. Edible films and coatings functionalization by probiotic incorporation: A Review. Polymers. 2020; 12(12):1-15.
- [18] Mohee R, Unmar GD, Mudhoo A, Khadoo P. Biodegradability of biodegradable/degradable plastic materials under aerobic and anaerobic conditions. Waste Management. 2008; 28:1624-1629.
- [19] Giosafatto CVL, Antonio Fusco A, Al-Asmar A, Mariniello L. (2020). Microbial Transglutaminase as a Tool to Improve the Features of Hydrocolloid-Based Bioplastics. International Journal of Molecular Science. 2020; 21:3656. DOI:10.3390/ijms21103656
- [20] DeGruson ML. Biobased polymer packaging. In Reference Module in Food Science; Smithers, G., Ed.; Elsevier Inc.: Amsterdam, The Netherlands. 2016.
- [21] Gruji´c R, Vujadinovi´c D, Savanovi´c D. Biopolymers as food packaging materials. In Advances in Applications of Industrial Biomaterials; Pellicer E, Nikolic D, Sort J, Baró M, Zivic F, Grujovic N, Gruji´c R,

- Pelemis S. Eds.; Springer International Publishing: Cham, Switzerland, 2017; 139-160. ISBN 9783319627663.
- [22] Pellicer E, Nikolic D, Sort J, Baró MD, Zivic F, Grujovic N, Gruji'c R, Pelemis S. Advances in Applications of Industrial Biomaterials, 1st ed.; Springer International Publishing: New York, NY, USA, 2017; ISBN 9783319627670.
- [23] Jabeen N, Majid I, Nayik GA. (2015). Bioplastics and food packaging: A review. Cogent Food and Agriculture. 2015; 1:1117749.
- [24] Chen H, Wang J, Cheng Y, Wang C, Liu H, Bian H, ....., Han W. (2019). Application of protein-based films and coatings for food packaging: A review. Polymers. 2019; 11(12):2039.
- [25] Milani JM, Tirgarian B. (2020). An overview of edible protein-based packaging: Main sources, advantages, drawbacks, recent progressions and food applications. Journal of Packaging Technology and Research. 2020; 4:103-115.
- [26] Zhong Y, Godwin P, Jin Y, Xiao H. Biodegradable polymers and green-based antimicrobial packaging materials: A mini-review. Advanced Industrial and Engineering Polymer Research. 2020; 3:27-35.
- [27] Borges JA, Romani VP, Cortez-Vega WR, Martins VG. Influence of different starch sources and plasticizers on properties of biodegradable films. International Food Research Journal. 2015; 22(6).
- [28] Jeyasubramanian K, Balachander R. Starch bioplastic film as an alternative food-packaging material. Journal of Achievements in Materials and Manufacturing Engineering. 2016; 75:78-84.
- [29] Shendurse A. Milk protein based edible films and coatings—Preparation,

properties and food applications. Journal of Nutritional Health and Food Engineering. 2018; 8:219-226.

- [30] Zakaria NH, Muhammad N, Sandu AV, Abdullah MMAB. Effect of mixing temperature on characteristics of thermoplastic potato starch film. IOP Conference Series: Materials Science and Engineering, 2018; 374:012083.
- [31] Rahman R. Bioplastics for food packaging: A review. International Journal of Current Microbiology and Applied Sciences. 2019; 8:2311-2321.
- [32] Viana RM, Sá NMSM, Barros MO, Borges MDF, Azeredo HMC. Nanofibrillated bacterial cellulose and pectin edible films added with fruit purees. Carbohydrate Polymers, 2018; 196:27-32.
- [33] Trinetta V. Edible packaging. Reference Module in Food Sciences, 2016; 1-4.
- [34] Aly SS, Mohamed EN, Abdou ES. Research Article Effect of Edible Coating on Extending the Shelf Life and Quality of Fresh Cut Taro. American Journal of Food Technology. 2017; 12:24-131.
- [35] Calderón-Castro A, Vega-García MO, de Jesús Zazueta-Morales J, Fitch-Vargas PR, Carrillo-López A, Gutiérrez-Dorado R, ....., Aguilar-Palazuelos E. (2018). Effect of extrusion process on the functional properties of high amylose corn starch edible films and its application in mango (*Mangifera indica* L.) cv. Tommy Atkins. Journal of Food Science and Technology. 2018; 55(3): 905-914.
- [36] Licciardello F, Lombardo S, Rizzo V, Pitino I, Pandino G, Strano MG, Muratore G, Restuccia C, Mauromicale G. Integrated agronomical and technological approach for the quality maintenance of ready-to-fry potato sticks during refrigerated

storage. Postharvest Biology and Technology. 2018; 136:23-30.

- [37] Fitch-Vargas, PR, Aguilar-Palazuelos E, Vega-García MO, Zazueta-Morales JJ, Calderón-Castro A, Montoya-Rodríguez A, et al. Effect of a corn starch coating obtained by the combination of extrusion process and casting technique on the postharvest quality of tomato. Revista Mexicana de Ingeniera Quimica, 2019. 18(3):789-801.
- [38] Zhang W, Li X, Jiang W. Development of antioxidant chitosan film with banana peels extract and its application as coating in maintaining the storage quality of apple. International Journal of Biological Macromolecules. 2019.
- [39] Hilbig J, Hartlieb K, Herrmann K, Weiss J, Gibis M. Influence of calcium on white efflorescence formation on dry fermented sausages with co-extruded alginate casings. Food Research International. 2020; 131(109012):1-8.
- [40] Abral H, Pratama AB, Handayani D, Mahardika M, Aminah I, Sandrawati N, ...., Ilyas RA. Antimicrobial Edible Film Prepared from Bacterial Cellulose Nanofibers/Starch/Chitosan for a Food Packaging Alternative. International Journal of Polymer Science, 2021. DOI: 10.1155/2021/6641284
- [41] Antoniewski MN, Barringer SA, Knipe CL, Zerby HN. Effect of a gelatin coating on the shelf life of fresh meat. Journal of Food Science. 2007; 72(6):382-387.
- [42] Chiu Po-en, Lih-shiuh L. Antimicrobial Activities of Tapioca Starch / Decolorized Hsian-Tsao Leaf Gum Coatings Containing Green Tea Extracts in Fruit-Based Salads, Romaine Hearts and Pork Slices. International Journal of Food Microbiology. 2010; 139:23-30.
- [43] Carrión-Granda X, Fernández-Pan I, Rovira J, Maté J I.

- (2018). Effect of antimicrobial edible coatings and modified atmosphere packaging on the microbiological quality of cold stored hake (merluccius merluccius) fillets. Journal of Food Quality2018; 1-12.
- [44] Fadini AL, Rocha FS, Alvim ID, Sadahira MS, Queiroz MB, Alves RMV, et al. (2013). Mechanical Properties and Water Vapour Permeability of Hydrolysed Collagen-Cocoa Butter Edible Films Plasticised with Sucrose. Food Hydrocolloids. 30:625-631.
- [45] Feng Z, Wu G, Liu C, Li D, Jiang B, Zhang X. Edible coating based on whey protein isolate nanofibrils for antioxidation and inhibition of product browning. Food Hydrocolloids, 2018; 79:179-188.
- [46] Grosso, AL, Asensio CM, Nepote V, Grosso NR. Quality preservation of walnut kernels using edible coatings. Grasas Y Aceites. 2018; 69(4):1-9.
- [47] Puscaselu R, Gutt G, Amariei S. Biopolymer-based films enriched with *Stevia rebaudiana* used for the development of edible and soluble packaging. Coatings. 2019; 9(6).
- [48] Huntrakul K, Yoksan R, Sane A, Harnkarnsujarit N (2020). Effects of pea protein on properties of cassava starch edible films produced by blownfilm extrusion for oil packaging. Food Packaging and Shelf Life. 2020; 24.
- [49] Khan, MKI, Cakmak H, Tavman S, Schutyser M, Schroën K. Anti-browning and barrier properties of edible coatings prepared with electrospraying. Innovative Food Science and Emerging Technologies. 2014; 25:9-13.
- [50] Niu B, Shao P, Chen H, Sun P. Structural and physiochemical characterization of novel hydrophobic packaging films based on pullulan derivatives for fruits preservation. Carbohydrate Polymers, 2019; 208:276-284.

- [51] Dubey PK, Shukla RN, Srivastava G, Mishra AA, Pandey, A. Study on Quality Parameters and Storage Stability of Mango Coated with Developed Nanocomposite Edible Film. International Journal of Current Microbiology and Applied Sciences. 2019; 8(4):2899-2935.
- [52] Yang K, Dang H, Liu L, Hu X, Li X, Ma Z, et al. (2019). Effect of syringic acid incorporation on the physical, mechanical, structural and antibacterial properties of chitosan film for quail eggs preservation. International Journal of Biological Macromolecules. 2019; 141:876-884.
- [53] Rodríguez GM, Sibaja JC, Espitia PJP, Otoni CG. (2020). Antioxidant active packaging based on papaya edible films incorporated with Moringa oleifera and ascorbic acid for food preservation. Food Hydrocolloids, 2020; 103
- [54] Antonio GC, Alves DG, Azoubel PM, Murr FEX, Park KJ. Influence of osmotic dehydration and high temperature short time processes on dried sweet potato (*Ipomoea batatas Lam.*). Journal of Food Engineering. 2008; 84(3):375-382.
- [55] Aguirre-Joya JA, De Leon-Zapata MA, Alvarez-Perez OB, Torres-León C, Nieto-Oropeza DE, Ventura-Sobrevilla JM, ....., Aguilar CN. (2018). Basic and applied concepts of edible packaging for foods. In *Food* packaging and preservation. Academic Press. 2018; pp:1-61. DOI: 10.3390/ foods10050981
- [56] Falguera V, Quintero JP, Jimenez A, Munoz JA, Ibarz A (2011) Edible films and coatings: structures, active functions and trends in their use. Trends in Food Science and Technology 22(6): 292-303.
- [57] Song Y, Liu L, Shen H, You J, Luo Y. Effect of sodium alginate-based edible

- coatings containing different antioxidants on quality and shelf life of refrigerated bream (*Megalobrama amblycephala*). Food Control 2011; 22(3-4): 608-615.
- [58] Lin D, Zhao Y. Innovations in the development and application of edible coatings for fresh and minimally processed fruits and vegetables.

  Comprehensive Reviews in Food Science and Food Safety, 2007; 6(3):60-75.
- [59] Banožić M, Babić J, Jokić S. (2020). Recent advances in extraction of bioactive compounds from tobacco industrial waste-a review. Industrial Crops and Products. 2020; 144:112009.
- [60] Rodsamran P, Sothornvit R. (2018). Bioactive coconut protein concentrate films incorporated with antioxidant extract of mature coconut water. Food Hydrocolloids. 2018; 79:243-252.
- [61] Schaefer EW, Pavoni JMF, Luchese CL, Faccin DJL, Tessaro IC. Influence of turmeric incorporation on physicochemical, antimicrobial and mechanical properties of the cornstarch and chitosan films. International Journal of Biological Macromolecules. 2020; 148:342-350.
- [62] Shirahigue LD, Ceccato-Antonini SR. Agro-industrial wastes as sources of bioactive compounds for food and fermentation industries. Ciência Rural. 2020; 50.
- [63] Nogueira GF, de Oliveira RA, Velasco JI, Fakhouri FM. Methods of Incorporating Plant-Derived Bioactive Compounds into Films Made with Agro-Based Polymers for Application as Food Packaging: A Brief Review. Polymers. 2020; 12:2518. DOI:10.3390/ polym12112518
- [64] Nieto-Suaza L, Acevedo-Guevara L, Sánchez LT, Pinzón MI, Villa CC. (2019). Characterization of Aloe vera-banana starch composite films

- reinforced with curcumin-loaded starch nanoparticles. Food Structure. 2019; 22:100131.
- [65] Wang S, Xia P, Wang S, Liang J, Sun Y, Yue P, Gao X. Packaging films formulated with gelatin and anthocyanins nanocomplexes: Physical properties, antioxidant activity and its application for olive oil protection. Food Hydrocolloids. 2019; 96:617-624.
- [66] Mirzaei-Mohkam A, Garavand F, Dehnad D, Keramat J, Nasirpour A. Physical, mechanical, thermal and structural characteristics of nanoencapsulated vitamin E loaded carboxymethyl cellulose films. Progress in Organic Coatings. 2020; 138:105383.
- [67] Farhan A, Hani NM. Active edible films based on semi-refined κ-carrageenan: Antioxidant and color properties and application in chicken breast packaging. Food Packaging and Shelf Life. 2020; 24:100476.
- [68] Wu H, Lei Y, Zhu R, Zhao M, Lu J, Xiao D, Jiao C, Zhang Z, Shen G, Li S. Preparation and characterization of bioactive edible packaging films based on pomelo peel flours incorporating tea polyphenol. Food Hydrocolloids. 2019; 90:41-49.
- [69] Bhardwaj A, Alam T, Talwar N. Recent advances in active packaging of agrifood products: A review. Journal of Postharvest Technology, 2019; 7(1):33-62.
- [70] Del-Valle V, Hernández-Muñoz P, Guarda A, Galotto MJ. Galotto Development of a cactus-mucilage edible coating (*Opuntia ficus indica*) and its application to extend strawberry (*Fragaria ananassa*) shelf-life. Food Chemistry. 2005; 91:751-756.
- [71] Livney YD. Milk proteins as vehicles for bioactives. Current Opinion in Colloid and Interface Science. 2010; 15(1-2):73-83.

- [72] Rodriguez-Turienzo L, Cobos A, Moreno V, Caride A, Vieites JM, et al. Whey protein-based coatings on frozen Atlantic salmon (Salmo salar): Influence of the plasticiser and the moment of coating on quality preservation. Food Chemistry. 2011; 128(1):187-194.
- [73] Aydin F, Kahve HI, Ardic M. Lipid Based Edible Films. Journal of Scientific and Engineering Research. 2017; 4(9):86-92.
- [74] Daraei GA, Mirzaei HO, Maghsudlo Y, Kashaninejad M, Jafari SM. Production of low fat frenchfries with single and multi-layer hydrocolloid coatings. Journal of Food Science and Technology. 2012; 1(8):660-669.
- [75] Ganiari S, Choulitoudi E, Oreopoulou V. Edible and active films and coatings as carriers of natural antioxidants for lipid food. Trends in Food Science and Technology, 2017; 68:70-82.
- [76] Sapper M, Amparo C. Starch-based coatings for preservation of fruits and vegetables. Coatings. 2018; 8(152):2-20.
- [77] Sharma P, Shehin VP, Kaur N, Vyas P. Application of edible coatings on fresh and minimally processed vegetables: A review. International Journal of Vegetable Science, 2019; 25(3):295-314.
- [78] Campos-Requena VH, Rivas BL, Pérez MA, Garrido-Miranda KA, Pereira ED. Polymer/clay nanocomposite films as active packaging material: Modeling of antimicrobial release. European Polymer Journal. 2015; 71:461-475.
- [79] Medina JC, Gutiérrez TJ, Goyanes S, Bernal C, Famá L. Biodegradability and plasticizing effect of yerba mate extract on cassava starch edible films. Carbohydrate Polymers. 2016; 151:150-159.

- [80] Bashir K, Jan K, Aggarwal M. Thermo-rheological and functional properties of gamma-irradiated whole wheat flour. International Journal of Food Science and Technology. 2017; 52(4):927-935.
- [81] Moghadam M, Salami M, Mohammadian M, Khodadadi M, Emam-Djomeh Z. Development of antioxidant edible films based on mung bean protein enriched with pomegranate peel. Food Hydrocolloids. 2020. 105735.
- [82] Grosso AL, Asensio CM, Grosso NR, Nepote V. Increase of walnuts' shelf life using a walnut flour protein-based edible coating. LWT:Food Science and Technology. 2020; 118.
- [83] Hasan KSM, Ferrentino G, Scampicchio M. Nanoemulsion as advanced edible coatings to preserve the quality of fresh-cut fruits and vegetables: A review. International Journal of Food Science and Technology. 2020; 55:1-10.
- [84] De Pilli T. Development of a vegetable oil and egg proteins edible film to replace preservatives and primary packaging of sweet baked goods. Food Control. 2020; 114.
- [85] Bajpai S, Navin-Chand, Lodhi, R. Water sorption properties and antimicrobial action of zinc oxide nano particles loaded sago starch film. Journal of Microbiology, Biotechnology and Food Sciences. 2020; 2(4):2368-2387.
- [86] Kazemian-Bazkiaee F, Ebrahimi A, Hosseini SM, Shojaee-Aliabadi S, Farhoodi M, Rahmatzadeh B, et al. Evaluating the protective effect of edible coatings on lipid oxidation, fatty acid composition, aflatoxins levels of roasted peanut kernels. Journal of Food Measurement and Characterization. 2020; 14(2):1025-1038.
- [87] Dong C, Wang B, Li F, Zhong Q, Xia X, Kong B. Effects of edible chitosan

coating on Harbin red sausage storage stability at room temperature. Meat Science. 2020; 2020159.

[88] Sabbah M, Di Pierro P, Dell'Olmo E, Arciello, A, Porta R. Improved shelf-life of Nabulsi cheese wrapped with hydrocolloid films. Food Hydrocolloids. 2019; 96:29-35.

[89] Kõrge K, Bajić1 M, Likozar B, Novak U. Active chitosan-chestnut extract films used for packaging and storage of fresh pasta. 2020. DOI: 10.1111/IJFS.14569.

[90] Harish, KV, Prashanth, Tharanathan RN. Chitin/chitosan: modifications and their unlimited application potential-an overview. Trends in Food Science and Technology. 2007; 18(3):117-131.

[91] Tahir HE, Xiaobo Z, Jiyong S, Mahunu GK, Zhai X, Mariod AA. Quality and postharvest-shelf life of cold-stored strawberry fruit as affected by gum arabic (Acacia senegal) edible coating. Journal of Food Biochemistry. 2018; 42(3):12527.

[92] Carrión-Granda X, Fernández-Pan I, Jaime I, Rovira J, Maté JI. Improvement of the microbiological quality of ready-to-eat peeled shrimps (*Penaeus vannamei*) by the use of chitosan coatings. International Journal of Food Microbiology, 2016; 232:144-149.

[93] Ebrahimi F, Rastegar S. Preservation of mango fruit with guar-based edible coatings enriched with Spirulina platensis and Aloe-vera extract during storage at ambient temperature. Scientia Horticulturae. 2020; 265.

[94] Yong H, Liu J. (2021). Active packaging films and edible coatings based on polyphenol-rich propolis extract: A review. Comprehensive Review in Food Science and Food Safety. 2021; 20:2106-2145.