We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Synthesis and Characterization of Dispersion Reinforced Sintered System Based on Ultra Fine and Nanocomposite Cu-Al₂O₃ Powders

Zoran Anđić¹, Aleksandar Vujović¹, Miloš Tasić¹,
Marija Korać² and Željko Kamberović²

*Scientific Research Center, Užice
Faculty of Metallurgy and Technology, Belgrade
Serbia*

1. Introduction

The research in nanocrystal materials has intensified in the last years, primarily due to their attractive potential, i.e. properties which are significantly improved compared to large grain materials [Karch, et al., 1987; Milošević, 1999; Ristić, 2003]. Nanostructure materials rank in the group of ultrafine metastable structures which contain a high defect concentration (spotted defects, dislocations, grain boundaries, interphase boundaries, etc). These materials are structurally different from crystal and amorphous forms, due to the fact that grain boundaries and the interphase represent a specific condition of the solid matter, since the atoms on the boundary are subject to a periodical potential field of crystal from both sides of the boundary [Milošević, 1999]. Nanostructural materials can be synthesized in controlled processes by the following methods: highly energetic reactive milling [Ahn, 1996], solution precipitation (sol-gel [Ruys & Mai, 1999], hydrothermal synthesis [Byrappaa & Adschririb, 2007], electrochemical synthesis [Yuana et al., 2007]), internal oxidation [Afshar & Simchi, 2008] etc. The synthesis of nanoparticles is generally performed by the methods of "from the bottom - to the top approach" ("bottom-up approach"), such as the deposition from the gas or liquid phase, thermal decomposition (evaporation-condensation), and the methods based on "from the top - to the bottom approach" ("top-down approach"), wherein mechanical grinding processes are distinctive. When using the bottom-up method, nanoparticles are formed atom by atom or molecule by molecule, whereas when using the top-down approach, large volumes are gradually reduced in proportion to reach the nanometer dimensions [Hosokawa, 2007].

The synthesis of metal and alloy powders represents the starting stage in the production of sintered metal materials. For obtaining sintered products with the required properties, the starting material, powders of metals or alloys, are of decisive importance. Since the starting structure undergoes certain changes in further processing, but, basically, remains preserved in the structure of the final product [Anđić, 2007; Ristić, 2003], there is an increased necessity for a larger number of methods for producing powders. Although obtaining powders by a thermochemical method, where the input materials are in liquid phase, is not a new

procedure, the interest in this method has intensified recently, due to the development of contemporary materials with pre-set properties, especially in terms of nano-powder production [Jena et al., 2001; Lee et al., 2001; Wu et al., 2001].

This paper presents the synthesis and characterization of Cu-Al₂O₃ nanocomposite systems using a combination of procedures suitable for obtaining sintered materials with nanocrystal structure and homogenous distribution of dispersoids in the basic material matrix, characterized by a good combination of electro-mechanical properties. The obtained sintered materials with nanocrystal structure based on Cu-Al₂O₃ nanocomposite powders have a wide application in the field of electronics and electrical engineering. They are used as electrodes for spot welding, different contact materials, various switches, as well as thermal and electric conductors, microwave tubes, commutators for starting helicopter engines, relays, etc. In addition to this, there is a significant possibility of using these systems as coatings with low porosity and high adhesion degree [Anđić et al., 2006, 2007; Korać et al., 2007].

Disperse reinforcement has recently raised great theoretical and practical interest. It is known that the introduction of finely dispersed particles into a metal matrix could have significant reinforcing effects, which can be maintained at elevated temperatures. Consequently, dispersion reinforced materials of this type show good mechanical properties during exploitation at elevated temperatures and during preservation at room temperature after high temperature exposure. The improvement of mechanical properties is achieved without any significant loss in electric and heat conductivity [Naser et al., 1997; Trian et al., 2006; Trojanová et al., 1999]. For such reinforcement, ultra fine particles and nano particles of oxides are suitable, which, due to their hardness, stability and insolubility in a metal matrix present exceptionally good obstacles to dislocation motion at elevated temperatures. Dispersed phases present in metals before deformation, affect the structural design and behaviour of metals when heated. The deformed material structure created in the presence of secondary phases depends on the size and distance of particles. Small finely dispersed particles which are at a smaller distance cause the high density of evenly distributed dislocations. The borders of subgrains and individual subgrains are vaguely expressed, and the curve of the lattice, i.e. the discrepancy in the orientation of adjacent subgrains is too small for them to become the germs of new recrystallised grains, which consequently leads to the reduction in the speed of grain production, i.e. in recrystallisation speed, which may be totally obstructed. Finely dispersed particles at a smaller distance obstruct, i.e. reduce subgrain moveability so that the subgrains which might transform into germs are activated with great difficulty and they are turned into new recrystallised grains. Finely dispersed particles and their homogenous distribution in the base metal matrix cause stabilization of dislocation substructure formed during deformation and create significant reinforcing effects by a complex action of different mechanisms [Liang et al., 2004; Plascencia & Utigard, 2005]. The third, Cu_xAl_yO_z, phase has a considerable influence since it appears in the structure due to the eutectic reaction on Cu-Al contact surfaces [Jena et al., 2001, 2004; Korać et al., 2010]. Accordingly, it has been concluded that binding mechanisms on Cu/CuAlO₂, Cu₂O/CuAlO₂ and Al₂O₃/CuAlO₂ inter-surfaces are considerably stronger compared to those on Cu/Al₂O₃ and Cu₂O/Al₂O₃ contact surfaces, and indicated that the formed third phase influences the stabilization of dislocation substructure and thereupon the improvement of mechanical properties and the achievement of a good combination of

electro - mechanical properties of the sintered systems [Entezarian & Drew, 1996; Lee & Kim, 2004; Yi et al., 1999; Yoshino & Shibata, 1992].

The characteristics of starting powders significantly determine the later-stage processing and sintering properties and eventually determine the microstructure of the composite. Nano-powders give better performance in sintering due to their high surface area and, therefore, can tremendously improve the sintering process. The parts produced from nano-powders will have high density, hardness and fracture toughness [http://www.nanopowders.com/].

Sintering is an extremely complex process with a complex action of multiple mechanisms of material transfer and the distribution and change of particle shapes, which are all processes that are closely connected with the off-balance condition of the crystal lattice and that have a considerable influence on the properties of the obtained metal materials. The driving force of sintering is the free energy of the system, which is off-balance from the thermodynamic point of view. This results from the highly developed free surface of powder particles and the presence of balance (point defects) and off-balance defects (dislocations) [Anđić, 2007; Ristić, 2003]. Sintering of ultradispersed powders occurs due to particles sliding along their borders and a dislocation mechanism that is responsible for the creation of surplus vacancies. Surplus vacancy concentrations can reach a value which corresponds to the vacancy concentration in the area of temperatures close to the temperatures of material melting. On the basis of this, it can be concluded that diffusion activity during sintering of ultra dispersed particles in the area of really low temperatures (0.1-0.3T_m) is conditioned by the presence of unbalancing 'recrystallization' vacancies. High recrystallization speeds of ultradispersed particles are a subsequence of the process of recrystallization self-activation [Lapovok & Novikov, 1983; Mohorov et al., 1977; Ristić, 2003]. A considerable number of studies have examined fundamental issues related to the mechanism and kinetics of sintering [Lapovok & Novikov, 1983; Mohorov et al., 1977; Ristić, 1993, 2003], by using the existing phenomenological equations which have considerably contributed to the theory and technology of sintering and also enabled numerous technological processes in the production of various ceramic and metal-ceramic materials. On the basis of the kinetic analysis of the process of sintering powders from the Cu-Al₂O₃ system, it was concluded that sintering process occurs in two phases. Given that the volume diffusion requires higher activation energy, the results of the kinetic analysis indicate that the surface diffusion and grain- boundary diffusion occur in the first phase, whereas the mass transfer occurs in the second phase during the process of volume diffusion [Ristić, 1993, 2003]. The kinetic analysis results indicate higher values of activation energy due to the exceptionally small sizes of particles of nano-composite Cu-Al₂O₃ powder, i.e. their large surface and an extremely large surface between individual particles created at the very beginning of the process.

As noted, disperse phases present in the material prior to deformation influence structure designing, whereas uniform dispersion of nanoparticles of Al₂O₃ in a copper matrix provides completely new, improved, even unexpected properties. However, these unique properties essentially depend on the microstructure, which is a direct consequence of the synthesis procedure of Cu-Al₂O₃ nanocomposites. By hydrometallurgy and powder metallurgy along with prognosis of physical-chemical properties, a synthesis of new improved materials can be successfully performed with pre-set properties which are conditioned by the quality of starting powders i.e. by the improvement of their structure. In

addition to the conventional methods of obtaining composites based on Cu-Al₂O₃, the paper shows the synthesis of these composites in a chemical way by liquid phase deposition, with a comparative analysis of the properties of the obtained nano-composite sintered samples characterized by a good ratio of electro - mechanical properties, suitable for operations at high temperatures.

2. The synthesis and characterization of ultrafine and nanocomposite Cu-Al₂O₃ powder

2.1 The synthesis of ultrafine and nanocomposite Cu-Al₂O₃ powder

Soluble nitrates of copper and aluminium were used, Cu(NO₃)₂×3H₂O and Al(NO₃)₃×9H₂O as a transient component, were used for the synthesis of nanocomposite Cu-Al₂O₃ powder by a thermochemical method. The synthesis process developed in five stages (Fig. 1), as follows:

- obtaining 50% of water solution in which Cu(NO₃)₂×3H₂O and Al(NO₃)₃×9H₂O are dissolved up to achieving the requested composition of Cu-Al₂O₃ nanocomposite system with 3 and 5wt.% of alumina,
- drying by spraying, using a modified house sprayer at a temperature of 180°C with the aim of obtaining composite particles of nitrate salts,
- annealing of the obtained loose mixture in air atmosphere at the temperature of 900°C for one hour with the aim of forming copper oxide and phase transformation of Al₂O₃ up to a thermodynamically stable α-Al₂O₃ phase,
- reduction of thermally treated powders in hydrogen atmosphere at the temperature of 400°C for one hour, whereas copper oxide is transformed into elementary copper and α-Al₂O₃ remains unchanged,
- homogenisation in a jar mill, type HM1, milling chamber dimensions with an internal diameter of 180mm, height of 160mm and volume of 4L.

2.2 The characterization of ultrafine and nanocomposite Cu-Al₂O₃ powder

The characterization of the produced powders consisted of determining the particle specific area, the pouring density and fluidness by the differential thermal and thermogravimetric analysis (DT-TGA), X-ray diffraction (XRD) and analytical electron microscopy (AEM) coupled with energy dispersive spectroscopy (EDS).

The fluidness and pouring density were determined by the standard method, using a Hall apparatus, and in accordance with the appropriate standards (ASTM B13 and ASTM B212). The specific area of the particles was determined by the gas absorption method (BET).

DTA-TGA was performed using a NETZCH STA model 409EP up to 1100°C. A Pt-Pt-Rd alloy S-type thermocouple was utilized. α-Al₂O₃ was used as the reference material.

The quantitative X-ray diffraction analysis of the powder was performed using a Siemens D500 PC diffractometer, CuK_α radiation, in the range 2θ = 0-100° with a step of (2θ) 0.02°.

The analytical electron microscopy (AEM) coupled with energy dispersive spectroscopy (EDS) was carried out on a JEOL 200CX microscope on powders spread on conductive carbon tape.

The results of the determination of fluidness, pouring density and specific area of the nanocomposite Cu-Al₂O₃ powder particles, with different dispersoid contents, obtained by

Fig. 2. DT-TGA curves of the Cu-5wt.%Al₂O₃ powder obtained by the thermochemical procedure

Fig. 3. XRD of the Cu-3wt.%Al₂O₃ powder after spray-drying

The X-ray diffraction analysis after annealing the dried powder is shown in Fig 4. The detected peaks correspond to CuO and Al₂O₃. An unidentified peak was also detected. According to previous studies, [Entezarian & Drew, 1996; Jena et al., 2001, 2004], this peak

corresponds to the third phase, Cu_xAl_yO_z, which appears in the structure due to the eutectic reaction of (Cu+Cu₂O) with Al₂O₃. The formation of this phase is thermodynamically possible on Cu-Al contact surfaces. During the eutectic joining of copper and Al₂O₃, the eutecticum formed by heating up to the eutectic temperature expands and reacts with Al₂O₃ also forming Cu_xAl_yO_z, which is compatible with both phases on the intersurface. The formed third phase influences the nature of the dislocation structure and also the improvement of the mechanical properties and the creation of a good combination of mechanical and electrical properties of the sintered systems.

Fig. 4. XRD of the dried Cu-3wt.%Al₂O₃ powder after thermal treatment

XRD of powder after the reduction (Fig. 5) shows the presence of peaks which correspond to the elementary copper and Al₂O₃.

Fig. 5. XRD pattern of the Cu-3wt.%Al₂O₃ powder after reduction

The obtained powders were analyzed at the National Center for Electron Microscopy, University of California, Berkeley, by Analytical Electron Microscopy (AEM) with a suitable EDX (at the marked spot), as presented in Figure 6.

Particles of 20-50nm in size are clearly noticeable. The shape of particles is irregular, with the presence of individual particles of nodular shape. The surface morphology is rough. The agglomerates of the size >100nm, formed by the individual particles of the stated size are also observed. The agglomerates are of a spongy shape. Since the powders with exceptionally fine particles are obtained by the previously described procedure, the basic "condition" for the appearance of agglomerates is fulfilled. Namely, agglomeration of finer particles is a consequence of their large surface and high surface energy, respectively, and of the effect of attracting forces acting between them. The creation of attracting strains, the magnitude of which depends directly on the surface energy of the particles which are in contact, occurs on contact surfaces due to the atomic connections in the interface.

With the EDS composition of nanocomposite Cu-5wt.% Al₂O₃ powder is determined as shown in Figure 6. The EDS analysis of the spot marked in Figure 6. shows that the identified peaks correspond to Cu, Al and O. The intensity of peaks corresponds to the required composition of the examined systems. Therefore, the peak corresponding to copper is considerably higher than the peaks corresponding to aluminum and oxygen. The obtained results of the examinations are statistically processed and shown in Table 2.

The characterization of the obtained powder indicates a possibility of the synthesis of a nanocomposite Cu-Al₂O₃ system by a thermochemical method, starting from water solutions Cu(NO₃)₂ and Al(NO₃)₃.

Element	Weight%	Atom. %	Measurement discrepancy	Detection correction	k - factor	Absorption correction
O	6,087	20,191	0.189	0.376	2,702	1,000
Al	1,224	2,408	0.047	0.952	1,044	1,000
Cu	92,687	77,399	0.502	0.996	1,743	1,000

Table 2. Statistical data for the EDS analysis

3. Dispersion reinforced sintered system based on ultra fine and nanocomposite Cu-Al₂O₃ powders

After the characterization of powders, cold pressing by pressing force was performed from both sides with an appropriate tool with the dimensions of 8×32×2mm under compaction pressure of 500MPa. The hydraulic lab power press "ZIM", Russia, was used for pressing.

Sintering of the obtained samples was carried out in hydrogen atmosphere in isothermal conditions at two different temperatures, 800 and 900°C, for 30, 60, 90 and 120 minutes. Sintering was performed in a laboratory electric resistance tube furnace, with the power of 3kW and thermoregulation of ±1°C. The internal diameter of the furnace was 45mm and length 100cm. The maximum temperature in the working area (55cm) was 1,300±1°C.

The characterization of the Cu-Al₂O₃ sintered system included examinations of density, relative volume change, electrical and mechanical properties, examination of microstructure by the scanning electronic microscopy (SEM), the energetic dispersion spectroscopy (EDS), the transmission electron microscopy (TEM) and the high-resolution transmission electron microscopy (HRTEM), examinations by the focused ion beam (FIB) method and examinations of the selected area diffraction pattern (SADP).

The values of density, relative volume change, hardness and specific electrical resistance were determined by the standard methods in the above-mentioned examinations. The

Fig. 6. AEM analysis of Cu-Al₂O₃ powder with 5wt.% of Al₂O₃

scanning electron microscopes, types JEOL JSM-T20 and JEOL 5300, as well as the analytical electron microscope (AEM), type JEOL 200CX with the ability to work in TEM and STEM modes between 80 and 200kV, were used for the examination of the microstructure of sintered systems. The contents of the examined systems were determined qualitatively by the energy dispersive spectroscopy (EDS – JEOL Superprobe 733, 20kV). HRTEM analysis was performed using Philips CM200/FEG.

The results of density examination, relative volume change, specific electric resistance and hardness are shown in Table 3..

The results of the research show that the density of the sintered samples at certain temperatures and times decrease with the increasing Al₂O₃ content. However, the density of the sintered samples increases with the increase in temperature. In the area of higher temperatures, when diffusion mobility of atoms is high enough, a complex action of all diffusion mechanisms of mass transfer occurs and they are responsible for the sintering process. With the increase in sintering temperature, the action of these mechanisms is more intensive, which directly affects the formation of contacts between certain particles, growth of contact surfaces, formation of closed pores and grain growth. What follows from this is that, after some time, the sintered density increases with temperature increase.

Temperature, °C	Time, min	Density $\bar{d}_s$, g/cm ³	$\Delta V/V_0$ (average)	Specific electric resistance ρ , 10 ⁻⁶ Ωm	Hardness HRB 10/40 (average)
Cu-3wt.%Al ₂ O ₃					
800	15	5,58	0,1042	0,07413	88,2
	30	5,62	0,1194	0,07128	94,1
	60	5,70	0,1442	0,06581	102,1
	120	5,68	0,1448	0,06232	107,1
900	15	5,84	0,1821	0,06127	96,2
	30	6,14	0,1932	0,04027	101,9
	60	6,42	0,1933	0,03971	102,7
	120	6,44	0,1929	0,03927	102,3
Cu-5 wt.%Al ₂ O ₃					
800	15	5,28	0,0612	0,08941	89,1
	30	5,34	0,0982	0,08827	101,2
	60	5,52	0,1191	0,08146	107,5
	120	5,58	0,1332	0,08007	109,1
900	15	5,94	0,1763	0,07413	99,1
	30	5,98	0,1824	0,06981	108,4
	60	6,14	0,1894	0,06218	118,5
	120	6,20	0,1888	0,06127	124,7

Table 3. Average density, $\Delta V/V_0$, specific electric resistance and hardness for sintered samples of Cu-Al₂O₃ with different alumina content

The relative volume change, as a measure of the system activity increases with the growth of the sintering temperature. The values of the relative volume change, at a certain temperature and sintering time, decrease with the increase in the Al₂O₃ content. Starting from general kinetic equations, and with the aim of an analysis of the sintering kinetics, the obtained results are in accordance with other research results and certainly confirm earlier investigations of the possibility of the use of existing phenomenological equations of sintering [Ristić, 2003].

The dependence of hardness and specific electric resistance on the temperature, time of sintering and alumina content are presented in Figs. 7 and 8, respectively.

The results of the examination of hardness of the sintered samples, as a measure of reinforcement of the highly conducting copper matrix, show that the growth of hardness value is a function of the decrease of specific electric resistance, i.e. of structural stabilization of the system. The results also point to the growth of hardness with Al₂O₃ content increasing, at a certain temperature and sintering time. The obtained results of hardness examination are the consequence of a relatively even distribution of Al₂O₃ dispersoids in the copper matrix. The relatively even distribution of alumina in the nanocomposite system, achieved during synthesis of powder by depositing from a liquid phase, causes stabilization of the dislocation structure and achievement of significant reinforcing effects by a complex action of several mechanisms. Thereby, reinforcement of the material with a small-grain

structure can be caused by the reinforcement of the grain boundaries, dissolving reinforcement and by Orowan's mechanism. Additionally, dislocations can disappear in the grain boundaries or cease to multiply, since the Frenk-Read source of dislocations cannot be activated in small-grained multi-phase materials, which represents an additional mechanism of reinforcement [Morris, D.G. & Morris M.A., 1992].

Fig. 7. Dependence of hardness on the sintering time at different temperatures and different alumina contents

With Al₂O₃ content increasing, the duration of the sintering process is increased. However, with increasing of the sintering temperature for a period of time, the value of specific electric resistance after sintering is decreased. In accordance with the stated and having in mind that the change of specific electric resistance represents a measure of structural stabilization of the system, it can be ascertained that at certain temperatures the structural stabilization of the system has not occurred, i.e. the structural stabilization process is not completed. Also, with the sintering temperature increasing, the duration of the sintering process is shortened (Fig. 8). Based on the value of specific electric resistance, as a measure of structural stabilization, for the system with 3wt.% Al₂O₃ during sintering at 800°C, sintering lasts 120 minutes, whereas for the same system during sintering at 900°C the sintering process lasts 30 minutes.

The analysis of the mechanical and electrical properties of Cu-Al₂O₃ sintered systems showed that for the system with 3wt.%Al₂O₃ structural stabilization had finished after 30 min of sintering at 900°C, with significant reinforcement effects. For the other systems, structural stabilization was not completed even after 120 min. The optimal solution for the production of dispersed reinforced Cu-Al₂O₃ is the process conducted at 900°C for 30 min with 3wt.%Al₂O₃, which was confirmed by microstructural analysis, presented in Figs. 9-11. Considering the fact that the structure takes a central place in the complex of the materials science as a parameter through which the connection between the properties and synthesis of new materials is expressed i.e. since it directly determines mechanical as well as electrical

Fig. 8. Dependence of specific electric resistance on sintering time at different temperatures and different alumina contents

properties, the following development of microstructural constituents through all individual stages of the technological process is of an exceptional importance. The analysis of the microstructure of the corresponding sintered samples confirms the stated stipulations. In Fig. 9 a microstructure survey of the sample sintered at 800°C for 30 minutes is given, and it is clearly seen that the structural stabilization process is not completed. The microstructure is characterized by the formation of closed pores, which is typical of a medium stage of sintering, and also, in certain areas, by achieving contacts between certain particles, which is typical of the starting sintering stage. In Figs. 10 and 11. a survey of the microstructure of samples sintered at 900o°C for 15 and 30 minutes is given. The shown microstructures are characteristic of the medium (Fig. 10), i.e. final stages (Fig. 11) of sintering, which is confirmed by the analysis of the structural stabilization of the system based on the value of specific electric resistance of the sintered samples. Apart from that, a relatively even distribution of pores can be seen in the examined samples, which, among other things, significantly contributes to the reinforcement of the highly conductive copper matrix.

Fig. 9. SEM of the sintered Cu-3wt.%Al₂O₃ system (800°C, 30 min)

Fig. 10. SEM of the sintered Cu-3wt.%Al₂O₃ system (900°C, 15 min)

Fig. 11. SEM of the sintered Cu-3wt.%Al₂O₃ system (900°C, 30 min)

In order to determine the distribution of elements in the structure, the surface analysis of the sample was performed by EDS. The SEM microphotograph of the examined sample with the surface on which the surface scanning was performed is shown in Fig. 12, and the results of the examination of the sample of the sintered Cu-3wt.%Al₂O₃ system by EDS are given in Fig. 13.

The results of surface scanning show a homogeneous distribution of elements in the structure. In Fig. 13.a it can be seen that copper covers almost the entire surface of the sample. The results of surface scanning of aluminium (Fig. 13.b) and oxygen (Fig. 13.c) show that these two elements are present less in the structure of the sintered sample and that the surfaces they occupy are inter-lapping, which corresponds to the existence of an Al₂O₃ dispersoid in the structure. Beside aluminium and oxygen, an inter-lapping of all three elements is also noticeable, which leads to the assumption of the presence of a Cu_xAl_yO_z phase [Jena, et al., 2004]. Finally, an apparatus with an exceptionally high resolution is necessary for the detailed characterization of the third. Cu_xAl_yO_z phase.

Fig. 12. SEM of the sintered Cu-3wt.%Al₂O₃ sample with the surface scanning area marked

Fig. 13. Surface scanning of the sintered Cu-3wt.%Al₂O₃ sample by EDS for: a) copper, b) aluminium, c) oxygen

The characterization of the Cu-Al₂O₃ sintered systems based on the powders obtained by the thermochemical procedure, apart from the stated examination, has included examinations by the Focused Ion Beam (FIB), examinations with Transmission Electronic Microscopy (TEM), examinations of selected diffractive fields (SADP) and High Resolution Transmission Electronic Microscopy Examinations (HRTEM), which were carried out at the National Center for Electronic Microscopy, University of California, Berkeley (USA).

The FIB analysis of the sintered Cu-Al₂O₃ system based on the powders obtained by the thermochemical procedure at different magnifications (Fig. 14) did not indicate, even at considerably higher magnifications, the existence of a phase rich in alumina. In accordance with [Jena et al., 2001], bright fields are identified, i.e. a phase rich in copper, as well as gray fields, which lead us to the possibility of the existence of the third, Cu_xAl_yO_z phase. In addition to this, the stated examinations by Scanning Electronic Microscopy [Jena, et al., 2001] are in accordance with the results of the surface EDS analysis showing that the peaks are identified and correspond to copper, aluminum and oxygen, and finally, having in mind that their intensity corresponds to the demanded composition, this additionally points to the

Fig. 14. FIB of the sintered Cu-5wt.% Al₂O₃ system (900°C, 120 nm)

possibility of the existence of the third, Cu_xAl_yO_z phase. The formation of this phase is thermodynamically possible on Cu-Al contact surfaces. During the eutectic joining of copper and Al₂O₃, the eutecticum formed by heating up to the eutectic temperature expands and reacts with Al₂O₃ creating Cu_xAl_yO_z, which is compatible with both phases on the inter-surface. In accordance with [Entezarian & Drew, 1996; Jena et al., 2001], the process of formation of the third phase is developed through the following reactions: CuO + H₂O → Cu₂O + H₂O, Cu₂O + Al₂O₃ → 2CuAlO₂ and/or CuO + Al₂O₃ → CuAl₂O₄, whereas Misra and Chaklader [Misra & Chaklader, 1963] have published that CuAlO₂ is stable in the air with the temperature range from 800°C to 1000°C, whereas CuAl₂O₄ is transformed into CuAlO₂ at the temperature of app. 1,000 °C.

Additionally, from microphotographs of the examined samples, homogenous distribution of the present phase is clearly noticeable as well as the size of microstructural constituents in the range of 50 – 250nm (Fig. 14).

As noted, finely dispersed particles and their homogenous distribution in the base metal matrix cause stabilization of dislocation substructure formed during deformation and the achievement of significant reinforcing effects by a complex action of different mechanisms [Liang et al., 2004; Plascencia & Utigard, 2005]. The third, Cu_xAl_yO_z phase has a considerable influence since it appears in the structure due to the eutectic reaction on Cu-Al contact surfaces [Jena et al., 2001, 2004; Korać et al., 2010]. Consequently, it has been concluded that the binding mechanisms on Cu/CuAlO₂, Cu₂O/CuAlO₂ and Al₂O₃/CuAlO₂ inter-surfaces are considerably stronger compared to Cu/Al₂O₃ and Cu₂O/Al₂O₃ contact surfaces, indicating that the formed third phase has an influence on the stabilization of dislocation substructure and thereupon the improvement of mechanical properties and achievement of a good combination of electro - mechanical properties of the sintered systems [Entezarian & Drew, 1996; Lee & Kim, 2004; Yi et al., 1999; Yoshino & Shibata, 1992].

A typical TEM pair bright field (BF) – the centered dark field (CDF) of nanocomposite Cu-5wt.%Al₂O₃ sintered system based on powders synthesized by the thermochemical procedure are shown in Figure 15 (a and b).

The TEM characterization of nanocomposite Cu-5wt.%Al₂O₃ sintered system based on powders synthesized by the thermochemical procedure reveals a microstructure with several interesting characteristics. In Fig. 15a and 15b, a typical TEM pair bright field (BF) – centered dark field (CDF) of nanocomposite Cu-5wt.% Al₂O₃ sintered system is shown, with the well developed crystals of copper of 100 nm size exposed to twinning despite their small size. The conditions for twinning are achieved when a great number of obstacles are created in the crystal, which hamper the moving of dislocations, dislocation plaits or already present twins. Since dislocations are piled up at the obstacles, internal tension is increased in the local regions, and this, along with external tension, causes the creation of twins. Having in mind that the decrease in dislocations mobility represents a condition for creating a twin embryo, the clearly noticeable presence of twins in Fig. 15a and 15b, indicates a decreased mobility of dislocations, i.e. stabilization of dislocation substructure, which is an elementary precondition for improving mechanical properties. i.e. for the reinforcement of metal materials. Additionally, when the deformed metal material is heated up to the sufficiently high temperature, recrystallization and grain growth occur, whereas in the stated processes and especially for the grain growth, grain boundaries movement is a basic mechanism which causes a relieved formation of twins.

Typical models of selected diffractive fields (SADP) of the examined nanocomposite Cu-5wt.% Al₂O₃ sintered systems based on the powders synthesized by the thermochemical procedure are shown in Figure 15c - at the point (marked by arrow in Fig. 15a) and Fig. 15d - from the overall area.

Fig. 15. (a and b) TEM BF – CDF pair of the nanocomposite Cu-5wt.%Al₂O₃ sintered system, (c) SADP centered at the point (marked by arrow in Fig. 15a), (d) SADP taken from the overall area

SADP clearly shows spots and rings, where spots refer to the individual crystals of copper, and sharp circles (rings) originate from nanocrystals of alumina dispersed in the copper matrix. Except for copper and alumina, diffractive fields are not identified, which is typical of some other phenomena (e.g. appearance of the third phase). The reason for that could be the common limitations of the technique, i.e. the determined critical value below which the phases cannot be identified. The presence of nano twins within the crystals of copper is partially confirmed by the selected diffractive fields taken from the overall surface (Figure 15d). Finally, apart from the stated, the obtained results of the examinations confirm the crystal nature of copper and dispersed alumina.

The high resolution transmission electron microscopy (HRTEM) of nano composite Cu-5wt.% Al₂O₃ sintered system based on powders synthesised by the thermochemical method is shown in Figure 16.

The HRTEM photos of sintered samples indicate a change in the lattice parameter on the grain boundary, where 'raster' and 'fingerprint' variations can be detected. This leads to the conclusion that, due to the presence of alumina, the eutectic reaction (Cu+Cu₂O) with Al₂O₃ occurred and the third, Cu_xAl_yO_z phase was formed, which is possible on Cu-Al contact surfaces from the thermodynamic point of view.

Bearing in mind the results of all of the above-mentioned examinations, the reinforcement of the copper matrix occurs due to the mechanisms: dispersion and reinforcement due to the dispersion of the fine particles of Al₂O₃ in the matrix, and the reinforcement of grain boundaries due to the appearance of the third phase.

Fig. 16. HRTEM of nanocomposite Cu-5wt.% Al₂O₃ sintered system

4. Conclusion

Characterization of the obtained powder indicates a possibility of the synthesis of nanocomposite Cu-Al₂O₃ system by the thermochemical procedure, starting from water solutions Cu(NO₃)₂ and Al(NO₃)₃. AEM analysis indicates the presence of individual particles of 20-50 nm size. The shape of particles is irregular, with the presence of individual particles of nodular shape. The surface morphology is rough. Apart from that, the presence of an agglomerate with the magnitude of >100nm and of a sponge shape is noticeable. The obtained nanocomposite powders, with the structure basically preserved together with the final product, provided a significant reinforcement effect in the obtained sintered system. This is a consequence of the homogenous distribution of the elements in the structure, accomplished during the synthesis of powder and presence of the third phase which causes stabilization of dislocation substructure and achieves the relevant reinforcing effect.

The analysis of the mechanical and electric properties of the sintered Cu-Al₂O₃ systems based on powders obtained by the thermochemical method shows that in the system with 3wt.% Al₂O₃, sintered at 900°C, structural stabilisation occurs only after 30 minutes with considerable reinforcement effects. Since in other systems, the structural stabilisation process was not completed even after 120 minutes, the system with 3wt.% of dispersoids sintered at 900°C for 30 minutes seems to be the optimum solution for the production of dispersively reinforced Cu-Al₂O₃ systems. This statement is confirmed by the corresponding analysis of the microstructure.

In accordance with the previous statements, the EDS analysis of the sintered systems surface as well as FIB analysis show a homogenous distribution of elements, i.e. present phases. FIB analysis also indicates the size of microstructural constituents within the range of 50-250nm. TEM analysis of the sintered systems reveals the presence of copper crystals of 100 nm in size exposed to twinning, thus pointing to stabilization of the dislocation substructure. SADP of the examined nanocomposite Cu-Al₂O₃ sintered system shows spots and rings, where spots refer to the individual crystals of copper, and sharp circles (rings) originate from nanocrystals of alumina dispersed in the copper matrix. HRTEM analysis indicates the changes in the lattice parameter, which leads to the conclusion that the eutectic reaction occurred and the third, Cu_xAl_yO_z phase was formed on the grain boundary, which will be the subject of future studies based on a more precise approach to physical chemistry of system surfaces and of thermodynamic examinations of the influences of finely dispersed Al₂O₃ on the formation of the third phase and the increase in the system surface energy.

In the end, all the above-mentioned examinations show that the reinforcement of Cu-Al₂O₃ system occurs via two mechanisms, which are: dispersion and reinforcement mechanism due to the homogenous dispersion of fine particles of Al₂O₃ in the matrix, and the mechanism of grain boundary reinforcement due to the appearance of the third phase.

5. Acknowledgement

The authors wish to thank Ministry of Science and Technological development of Republic of Serbia for financial support, projects TR19032 "Synthesis of nanostructured powders designed for production of the new dispersion strengthened sintered materials in system Cu-Al₂O₃" and TR34033 "Innovative synergy of by-products, waste minimization and cleaner technologies in metallurgy" and Prof. dr Velimir Radmilović, National Center for Electron Microscopy, Lawrence Berkley National Laboratory, Berkley for help with instrumental techniques and interpretation of results.

6. References

- Afshar, A. & Simchi, A., (2008). *Scripta Materialia*, 58, 966.
- Ahn, J., Song, I. & Hahn, Y., (1996). *Mater. Trans. JIM*, 37, 733
- Anđić, Z., Korać, M., Tasić, M., Raić, K. & Kamberović, Ž. (2006). The synthesis of ultra fine and nanocomposite powders based on copper, silver and alumina, *Kovove Mater.*, 44, pp. 145-150
- Anđić, Z., Korać, M., Kamberović, Ž., Vujović A. & Tasić, M. (2007). Analysis of the Properties of a Cu-Al₂O₃ Sintered System based on Ultra Fine and Nanocomposite Powders, *Science of Sintering*, 39, pp. 145-152

- Anđić, Z., (2007). D. Sc. Thesis, Faculty of Technology and Metallurgy, University of Belgrade, Serbia
- Byrappaa, K. & Adschirib, T., (2007). Hydrothermal technology for nanotechnology, *Prog. Cryst. Growth Charact. Mater.*, 53, pp. 117-166
- Entezarian, M. & Drew, R., (1996). Direct bonding of copper to aluminum nitride, *Materials Science and Engineering, A: Structural Materials: Properties, Microstructure and Processing*, A212(2), pp. 206-212
- Hosokawa, M., Nogi, K., Naito, M. & Yokoyama, T., (2007). *Nanoparticle Technology Handbook*, Elsevier, ISBN 978-0-444-53122-3, Oxford, UK
- Jena, P., Brocchi, E. & Motta, M., (2001). In-situ formation of Cu-Al₂O₃ nano-scale composites by chemical routes and studies on their microstructures, *Materials Science and Engineering*, A313m, pp. 180-186
- Jena, P., Brocchi, E. & Motta, M., (2001). Characterization of Cu-Al₂O₃ nano-scale composites synthesized by in situ reduction, *Materials Science and Engineering*, C15, pp. 175-177
- Jena, P., Brocchi, E., Solórzano, I. & Motta, M., (2004). Identification of a third phase in Cu-Al₂O₃ nanocomposites prepared by chemical routes, *Materials Science and Engineering*, A317, pp. 72-78
- Karch, J., Birringer, R. & Gleiter, H., (1987). Ceramics ductile at low temperature, *Nature*, 330, pp. 556-558
- Korać, M., Anđić, Z., Tasić, M., & Kamberović, Ž. (2007). Sintering of Cu-Al₂O₃ nanocomposite powders produced by a thermochemical route, *J. Serb. Chem. Soc.*, 72(11), pp. 1115-1125
- Korać, M., Kamberović, Ž., Anđić, Z., Filipović, M. & Tasić, M., (2010). Sintered Materials Based on Copper and Alumina Powders Synthesized by a Novel Method, *Science of Sintering*, 42(1), pp. 81-90
- Lapovok, V., & Novikov, V., (1983). *Fizika tverdogo tela*, 25, 1848, Russia
- Lee, D. & Kim, B., (2004). Nanostructured Cu-Al₂O₃ composite produced by thermochemical process for electrode application *Materials Letters*, *Materials Letters*, 58, pp. 378-383
- Lee, D., Ha, G. & Kim, B., (2001). Synthesis of Cu-Al₂O₃ nano composite powder, *Scripta mater.*, 44, pp. 2137-2140
- Liang, S., Fana, Z., Xua, L. & Fangb, L., (2004). Kinetic analysis on AlO/Cu composite prepared by mechanical activation and internal oxidation, *Composites Part A Applied Science and Manufacturing*, 35(12), pp. 1441-1446
- Milošević, O., (1999). Nanostructured materials and their development in light of the triad "synthesis - structure - properties", *Sintering and sintered materials in the light of the triad "synthesis - structure - properties"*, Monograph of material science, SANU, 38, pp. 55-65
- Misra, S. & Chaklader A., (1963). System Copper Oxide-Alumina, *J. Am. Ceram. Soc.*, 46, 509
- Mohorov, I., Trusov L. & Chiszhnik, S., (1977). *Ultradispersnoe metallicheskie sredoe*, Atomizdat, Moskva, Russia
- Morris, D.G. & Morris M.A., (1992). In *Structural Applications of Mechanical Alloying*, F.H. Froes, J.J. DeBarbadillo, (Ed.), ASM, Metals Park, Ohio
- Naser, J., Ferkel, H. & Riehemann, W., (1997). Grain stabilisation of copper with nanoscaled Al₂O₃-powder, *Materials Science and Engineering, A* 234-236, pp. 470-473

- Plascencia, G. & Utigard, T., (2005). High temperature oxidation mechanism of dilute copper aluminium alloys, *Corros. Sci.*, 47, pp. 1149-1163
- Ristić, M., (1993). Principles of materials science, P. Miljanić, Eds., Serbian academy of science and arts, Department of technical science, Monographs, Vol. DCXVII, No. 36, Belgrade
- Ristić, M., (2003). Fundamental problems of material science, TFČ and SANU, Čačak
- Ruys, A. & Mai, Y., (1999). The nanoparticle-coating process: a potential sol-gel route to homogeneous nanocomposites, *Mater. Sci. Eng.*, A 265, pp. 202-207
- Trian, B., Liua, P., Songa, K., Lia, Y., Liua, Y., Rena, F. & Sua, J., (2006). Microstructure and properties at elevated temperature of a nano- Al_2O_3 particles dispersion-strengthened copper base composite, *Mater. Sci. Eng.*, A 435-436, pp. 705-710
- Trojanová, Z., Ferkel, H., Luká, P., Naser, J. & Riehemann, W., (1999). Thermal stability of copper reinforced by nanoscaled and microscaled alumina particles investigated by internal friction, *Scripta Materialia*, 40(9), pp. 1063-1069
- Wu, Y., Zhang, Y., Huang, X. & Guo, J., (2001). Preparation of platelike nano alpha alumina particles, *Ceramics International*, 27, pp. 265-268
- Yi, S., Trumble, K. & Gaskell, D., (1999). Thermodynamic analysis of aluminate stability in the eutectic bonding of copper with alumina, *Acta. Mater.*, Vol. 47, No. 11, pp. 3221-3226
- Yoshino, Y. & Shibata, T., (1992). Structure and Bond Strength of a Copper-Alumina Interface, *J. Amer. Ceramic Soc.*, 75 (10), pp. 2756-2760
- Yuana, G., Jiang, H., Lina, C. & Liaoa, S., (2007). Shape and size controlled electrochemical synthesis of cupric oxide nanocrystals, *J. Cryst. Growth*, 303(2), pp. 400-406
- Nano Powder Industries, <http://nanopowders.com/applications.htm>

IntechOpen

Nanocrystal

Edited by Dr. Yoshitake Masuda

ISBN 978-953-307-199-2

Hard cover, 494 pages

Publisher InTech

Published online 28, June, 2011

Published in print edition June, 2011

We focused on cutting-edge science and technology of Nanocrystals in this book. “Nanocrystal” is expected to lead to the creation of new materials with revolutionary properties and functions. It will open up fresh possibilities for the solution to the environmental problems and energy problems. We wish that this book contributes to bequeath a beautiful environment and valuable resources to subsequent generations.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Zoran Andić, Aleksandar Vujović, Miloš Tasić, Marija Korać and Željko Kamberovic (2011). Synthesis and Characterization of Dispersion Reinforced Sintered System Based on Ultra Fine and Nanocomposite Cu-Al₂O₃ Powders, Nanocrystal, Dr. Yoshitake Masuda (Ed.), ISBN: 978-953-307-199-2, InTech, Available from: <http://www.intechopen.com/books/nanocrystal/synthesis-and-characterization-of-dispersion-reinforced-sintered-system-based-on-ultra-fine-and-nano>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2011 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the [Creative Commons Attribution-NonCommercial-ShareAlike-3.0 License](https://creativecommons.org/licenses/by-nc-sa/3.0/), which permits use, distribution and reproduction for non-commercial purposes, provided the original is properly cited and derivative works building on this content are distributed under the same license.

IntechOpen

IntechOpen