We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Histopathological Effect Characteristics of Various Biomaterials and Monomers Used in Polymeric Biomaterial Production

Serpil Ünver Saraydin¹ and Dursun Saraydin²

¹*Cumhuriyet University, Faculty of Medicine, Department of Histology and Embryology Sivas,*

²*Cumhuriyet University, Faculty of Science, Department of Chemistry Sivas, Turkey*

1. Introduction

When a synthetic material is placed within the human body, tissue reacts towards the implant in a variety of ways depending on the material type. The mechanism of tissue interaction (if any) depends on the tissue response to the implant surface. In general, there are three terms in which a biomaterial may be described in or classified into representing the tissues responses. These are bioinert, bioresorbable, and bioactive.

Biomaterials are often used and/or adapted for a medical application, thus comprises whole or part of living structures or biomedical devices which performs, augments, or replaces biological functions. Biomaterials are used in dental and surgical applications, in controlled drug delivery applications. A biomaterial may be an autograft, an allograft or a xenograft used as a transplant material.

Biomaterials are mostly polymers produced by monomers, and are used in artificial organ production in contemporary medicine. They are prepared by the polymerization reaction of certain monomers.

In several previous studies, we investigated whether acrylamide, methacrylamide, N-isopropylacrylamide, acrylic acid, 2-hydroxyethyl methacrylate, 1-vinyl-2-pyrrolidone and ethylene glycol had cytotoxic effects and induced apoptosis or not in spinal cord. Immunolocalization of glial fibrillary acidic protein (GFAP) was also determined, and it was evaluated by using semi-quantitative morphometrical techniques. The cytotoxicity of monomers on cultured fibroblastic cell lines was also examined *in vitro*.

Acrylic acid had the most cytotoxic effect when compared to the methacrylamide and the ethylene glycol groups. GFAP immunoreactivity was found to be rather stronger in the methacrylamide than the other monomers application groups. The methacrylamide, acrylic acid, N-vinyl pyrrolidine, acrylamide, N-isopropylacrylamide and 2-hydroxyethyl methacrylate application groups had TUNEL positive cells when compared to the other groups. While some monomers used in biomaterial production seemed not to affect the cell viability and GFAP immunoreactivity, some other monomers had adverse effects on those features. This in turn may contribute to the pathological changes associated to the monomer type.

In our previous other works, *in vitro* swelling and *in vivo* biocompatibility of radiation crosslinked acrylamide and its co-polymers such as acrylamide (AAm) and acrylamide/crotonic acid (AAm/CA), acrylamide/itaconic acid (AAm/IA), and acrylamide/maleic acid (AAm/MA) hydrogels were investigated.

The radiation crosslinked AAm, AAm/CA, AAm/IA and (AAm/MA) co-polymers were found to be well tolerated, non-toxic and highly biocompatible.

On the other hand, calcium phosphate ceramics and xenografts have been used in different fields of medicine and dentistry. We demonstrated the effects of calcium phosphate ceramics (Ceraform) and xenograft (Unilab Surgibone) in the field of experimentally created critical size parietal bone defects in rats. Although Ceraform was less resorptive and not osteoconductive properties, it could be considered as a biocompatible bone defect filling material having a limited application alternative in dentistry and medicine. However, xenograft seems biocompatible, osteoconductive, and could be used in a limited manner as a filling material in osseous defects in clinical practice.

2. Toxicological effect of the water-soluble monomers

2.1 Monomers

Monomer is a molecule of any of a class of compounds, mostly organic, that can react with other molecules of the same or other compound to form very large molecules, or polymers. The essential feature of a monomer is polyfunctionality, the capacity to form chemical bonds to at least two other monomer molecules. Bifunctional monomers can form only linear, chainlike polymers, but monomers of higher functionality yield cross-linked, network polymeric products. Toxicological effects of the monomers are changing from very low (zero) to very high.

Some polymeric biomaterials such as hydrogels are produced by the effect of initiator such as chemical initiator, heat, light or high energy radiation from the water soluble-monomers.

2.2 Cytotoxic effects

Biomaterial suitable for a biomedical application must be biocompatible at least on its surface. In several previous studies, we investigated whether acrylamide, methacrylamide, N-isopropylacrylamide, acrylic acid, 2-hydroxyethyl methacrylate, 1-vinyl-2-pyrrolidone and ethylene glycol used in polymeric biomaterial production had cytotoxic effects (Unver Saraydin et al., 2011). The cytotoxicity of xenograft (one of the alternative graft materials) was also examined *in vitro* (Unver Saraydin et al., 2011).

The viability of cultured fibroblastic cell lines following all monomer applications except for the ethylene glycol group were found to be decreased in all time intervals (Figure 1, 2), and differences were statistically significant ($p < 0.05$). In addition, the cell viability was significantly ($p < 0.05$) lower in the acrylamid application group when compared to the control group. Acrylic acid demonstrated the maximum cytotoxic effect when compared to the methacrylamide and ethylene glycol groups. On the other hand, the ethylene glycol group showed no cytotoxicity for cells (Graphic 1).

In our study of the xenograft cytotoxic activities, the xenograft showed no cytotoxicity for the cells (Figure 3). There was no decolorization zone around the samples. Although the cells were directly in contact with the xenograft in the culture media, they did not show any signs of injury and preserved their morphological characteristics and wholeness like those seen in the controls.

Fig. 1. Fibroblast viability %100 after 12 h incubation period with ethylene glycol

Fig. 2. Fibroblast viability % 0 after 12h incubation period with N-isopropyl acrylamide

Graphic 1. Shows the cell viability alterations between groups in the fibroblastic cell lines by the time.

Fig. 3. There is no cytotoxicity for the cells.

2.3 Neurotoxic effects

Several studies revealed neurotoxic effects as well as ataxi and muscle weakness caused by biomaterials on humans and on laboratory animals. It has been suggested that they cause axonal degeneration in central and peripheric nervous system (Barber et al., 2001).

Astrocytes are the stellate glial cells in the central nervous system, which play a major role in supporting neurons, scar formation and development and maintenance of the blood-brain barrier. The physiological and metabolic properties of astrocytes indicate that those cells are involved in the regulation of water, ions, neurotransmitters, and pH of the neuronal milieu (Montgomery 1994). They are also implicated in protection against toxic insults such as excitotoxicity and oxidative stress (Lamigeon et al., 2001). Glial fibrillary acidic protein (GFAP) is an intermediate filament protein found predominantly in astrocytes (McLendon 1994). Therefore it is important to determine the glial fibrillary acidic protein (GFAP) immunoreactivity in astrocytes for the evaluation of biomaterials.

In our study, immunolocalization of glial fibrillary acidic protein (GFAP) was determined, and it was evaluated by using semi-quantitative morphometrical techniques (Unver Saraydin et al., 2011). GFAP immunoreactivity was found to be very strong in the methacrylamide, N-isopropylacrilamid, ethylene glycol and N-vinyl pyrrolidine application groups whereas it was weak in acrylic acid, acrylamide and 2-hydroxyethyl metacrylad applied groups (Table 1, Figure 4-10). Changes in GFAP immunoreactivity could be due to following conditions; astrocyte dysfunction, astrocyte loss accompanied by astroglial cell proliferation, de-differentiation, and changes in functional state of neuronal cell types, thus altering the neuron-glial homeostasis. The over-expression of GFAP could probably indicate the protective strategy of these tissues.

Although the neurotoxicity of acrylamide and many monomers has been known since 1950s, its' mechanisms have remained obscure (Lee et al., 2005, Gold and Schaumburg, 2000). Acrylamide increases p53 protein (Okuno et al., 2006), recent studies indicate that it plays a role in apoptotic cell death in neurons (Morrison et al., 2003). Acrylamide can activate caspase- 3 and cause apoptosis in neuronal cells (Sumizawa and Igisu, 2007). The cellular process of apoptosis is an important component of tissue and organ development as well as the natural response to disease and injury (David et al., 2003). DNA fragmentation in neurons was characterized by double staining with terminal deoxynucleotidyl transferase-mediated deoxyuridine triphosphate-biotin nick end labeling (TUNEL) (Bao and Liu, 2004). To our knowledge, however, it has not been determined whether acrylamide and other

Fig. 4. Control group GFAP immunoreactivity. GFAP40X

Fig. 5. GFAP immunoreactivity 6 week after Acrylic acid exposure. GFAP 40X

Fig. 6. GFAP immunoreactivity 2 week after Acrylamide exposure. GFAP 40X

Fig. 7. GFAP immunoreactivity 6 week after 2-hydroxyethyl methacrylate exposure GFAP 40X

Fig. 8. GFAP immunoreactivity 4 week after methacrylamide exposure GFAP 40X

Fig. 9. GFAP immunoreactivity 6 week after N-isopropylacrylamide exposure GFAP 40X

Fig. 10. GFAP immunoreactivity 4 week after N-vinyl pyrrolidone exposure. GFAP 40X

Monomer	1st week	2nd week	4th week	6 th week	12 th week
Ethylene glycol	++	++	+++	++	++
N-vinyl pyrrolidone	+++	+++	+++	+++	++
2-hydroxyethyl methacrylate	+	++	+++	++	++
Acrylamide	++	++			
Methacrylamide	+++	+++	++	++	+
N-isopropylacrylamide	+++	+++	+++	+++	
Acrylic acid	+	++		++	++
Control	+++	+++	+++	+++	+++

Table 1. Demonstrates the semi-quantitative scoring findings of GFAP immunolocalization in rat medullaspinalis following 1, 2, 4, 6 and 12 weeks of particular monomer applications

monomers cause apoptosis in neuronal cells. We therefore examined apoptosis by using terminal deoxynucleotidyl transferase dUTP nick and labelling (TUNEL) method in spinal cord (Unver Saraydin et al., 2011).

While TUNEL positive cells has been detected rarely in the control and in the ethylen glycol application groups, numerous TUNEL positive cells were intensively observed in the spinal cord of the methacrylamide, acrylic acid, N-vinyl pyrrolidine, acrylamide, N-isopropylacrylamide and 2-hydroxyethyl metacrylate application groups (Figure 11-14).

Fig. 11. TUNEL-positive apoptotic cells in the control group. TUNEL 100X

Fig. 12. TUNEL positive cells 6 week after 2-hydroxyethyl methacrylate. TUNEL 100X

Fig. 13. TUNEL positive cells 6 week after N-isopropylacrylamide. TUNEL 100X

Fig. 14. TUNEL positive cells 6 week after N-vinyl pyrrolidone. TUNEL 100X

3. Polymeric biomaterials

Some polymeric biomaterials such as hydrogels are made of water-soluble molecules, connected usually by covalent bonds, forming a three-dimensional insoluble network. The space between chains is accessible for diffusion of solutes and this space is controllable by the level of cross-linked (connected) molecules. They usually show good biocompatibility in contact with blood, body fluids, and tissues. Therefore, they are very often used as biomaterials for medical purposes, for instance contact lenses, coating of catheters, etc.

Biomaterials are defined as materials that can be interfaced with biological systems in order to evaluate, treat, augment, or replace any tissue, organ, or function of the body.

The clinical application of a biomaterial should not cause any adverse reaction in the organism and should not endanger the life of the patient; any material to be used as part of a biomaterial device has to be biocompatible. The definition of biocompatibility includes that the material has to be nontoxic, non-allergenic, noncarcinogenic, and non-mutagenic, and that it does not influence the fertility of a given patient. Preliminary use of *in vitro* methods is encouraged as screening tests prior to animal testing. In order to reduce the number of animals used, these standards use a step-wise approach with review and analysis of test results at each stage. Appropriate *in vitro* investigations can be used for screening prospective biomaterials for estimations of toxic effect. Cytotoxicity *in vitro* assay is the first test to evaluate the biocompatibility of any material for use in biomedical devices (Rogero et.al. 2003).

Hydrogels can be synthesized by accomplishing crosslinking via γ -irradiation (Güven, O; et.al. 1999, Saraydın et.al. 1995, 2002, Karadağ et. al. 2004). However, little work is done on the biomedical applications of the hydrogels prepared by crosslinking of a homo- or copolymer in solution with γ -irradiation. It is well known that the presence of an initiator and a crosslinking agent affects the macromolecular structure and phase behavior of hydrophilic polymers in solution and contributes to inhomogeneity of the network structure. It is argued that more homogeneous network structures can be synthesized, if crosslinking is accomplished with γ -irradiation in the absence of an initiator and a crosslinking agent. The structural homogeneity of the network affects the swelling behavior and mechanical properties that improved the biological response of materials and subsequently the performance of many medical devices (Benson 2002). Thus, looking to the significant consequences of biocompatibility of biomaterials, we, in the present study, are reporting the results on the biocompatibility with the copolymeric hydrogels prepared with acrylamide (AAm) and crotonic acid (CA) or itaconic acid (IA) or maleic acid (MA) via radiation technique. The selection of AAm as a hydrophilic monomer for synthesizing hydrogel rests upon the fact that it has low cost, water soluble, neutral and biocompatible, and has been extensively employed in biotechnical and biomedical fields. On the other hand, CA monomer consists of single carboxyl group, while IA and MA monomers are consisting of double carboxyl groups. These carboxylic acids could provide the different functional characteristics to acrylamide-based hydrogels. So, these monomers were selected for the preparation of the hydrogels and their biocompatibility studies.

In our previous other works, *in vitro* swelling and biocompatibility of blood *in vivo* biocompatibility of radiation crosslinked acrylamide co-polymers such as acrylamide (AAm), acrylamide/crotonic acid (AAm/CA), acrylamide/itaconic acid (AAm/IA) and

acrylamide/maleic acid (AAm/MA) hydrogels were investigated (Saraydin et al., 1995, Karadağ et. al. 1996, Saraydin et al., 2001, 2004).

3.1 In vitro swelling of the hydrogels in the simulated body fluids

In this stage of the study, the swelling of the hydrogels in the simulated physiological body fluids was investigated (Saraydin et al., 1995, Karadağ et. al. 1996). The phosphate buffer at pH 7.4 (pH of cell fluid, plasma, edema fluid, synovial fluid, cerebrospinal fluid, aqueous humour, tears, gastric mucus, and jejunal fluid), glycine-HCl buffer at pH 1.1 (pH of gastric juice), human sera, physiological saline and distilled water intake of initially dry hydrogels were followed for a long time until equilibrium (Saraydin et al., 2001, 2002). The fluid absorbed by the gel network is quantitatively represented by the EFC (equilibrium body fluids content), where: $EFC\% = [\text{mass of fluid in the gel} / \text{mass of hydrogel}] \times 100$. EFCs of the hydrogels for all physiologically fluids were calculated. The values of EFC% of the hydrogels are tabulated in Table 2.

Simulated body fluid	AAm	AAm /CA	AAm /MA	AAm /IA
Distilled Water	86.3	93.9	94,7	92.0
Isoosmotic phosphate buffer	87.5	93.8	89,7	92.2
Gastric fluid	87.7	93.6	92,4	88.7
physiological saline	87.8	92.9	89,7	88.7
Human Sera	88.6	92.5	89.8	86.4
In rat	89.0	93.1	91.9	91.7

Table 2. EFC values of the hydrogels

All EFC values of the hydrogels were greater than the percent water content values of the body about 60%. Thus, the AAm and AAm/CA, AAm/MA and AAm/IA hydrogels were exhibit similarity of the fluid contents with those of living tissues.

3.2 In vitro blood biocompatibility

In the second stage of this study, the biocompatibility of the hydrogels was investigated against some biochemical parameters of human sera at 25 °C. The mean and standard deviation values of control and test groups for biochemical parameters of human sera are listed in Table 3. Table 3 shows that the values of means of control and test groups are in the range of normal values and there is no significant difference in values before and after contacting these sera with the hydrogels. On the other hand, Student's t-test is applied to control and test groups. No significant difference in values of biochemical parameters was found.

3.3 In vivo tissue biocompatibility

In this part, hydrogels based on copolymer of AAm, AAm/MA, AAm/CA and AAm/IA with capacity of absorbing a high water content in biocompatibility with subcutaneous tissues of rats were examined. After one week implantation, no pathology such as necrosis, tumorigenesis or infection were observed in the excised tissue surrounding the hydrogels and in skin, superficial fascia and muscle tissues in distant sites. After 2–4 weeks, thin fibrous capsules were thickened. A few macrophage and lymphocyte were observed in

Biochemical parameters of human serum / Unit	Normal values	Control	AAm	AAm/CA	AAm/MA	AAm/IA
Glucose/mg dl ⁻¹	70-110	87.0±8.2	91.0± 6.1	88.1±3.99	88.8±6.0	88.4±5.30
Triglyceride/mg dl ⁻¹	40-160	127.3±24.6	127.0±25.8	130.6±19.9	127.2±25.1	125.6±20.7
Cholesterol/mg dl ⁻¹	125-350	158.6±10.9	160.6±14.3	159.8±11.3	157.8±10.8	160.6±14.3
BUN/mg dl ⁻¹	8-25	14.8±1.27	15.2±4.56	14.6±3.73	15.2±4.10	15.6±3.84
Creatinin/mg dl ⁻¹	0.8-1.6	0.98±0.14	1.06±0.17	1.02±0.14	0.98±0.18	1.00±0.18
Total protein/g dl ⁻¹	6.0-8.4	6.52±0.15	6.72±0.15	6.70±0.13	6.60±0.22	6.48±0.30
Albumin/mg dl ⁻¹	3.5-5.6	4.02±0.15	3.88±0.15	3.98±0.18	3.96±0.20	3.94±0.10
Alkaline phosphatase/U	35-125	53.6± 13.1	54.5±12.3	54.0±14.9	52.6±12.6	52.6± 10.3
Alanine transaminase/U	7-56	14.6±2.12	16.0±2.63	15.7±3.23	15.9±2.47	16.0±2.63
Aspartate transaminase/U	5-40	16.2±5.33	15.2±3.19	16.5±3.03	17.2±5.16	15.2±3.19
Direct bilirubin/mg dl ⁻¹	0.0-0.3	0.12±0.04	0.12±0.04	0.11±0.03	0.11±0.03	0.12±0.04
Indirect bilirubin/mg dl ⁻¹	0.1-1.1	0.45±0.05	0.35±0.09	0.35±0.09	0.45±0.05	0.40±0.07
Chlorine/meq dl ⁻¹	95-107	98.5±2.17	98.8±2.3	98.6±2.12	97.8±1.75	98.2±2.10
Sodium/meq dl ⁻¹	137-146	142.7±1.4	142.8± 0.9	143.0±1.6	142.7±1.4	142.0±1.6
Potassium/meq dl ⁻¹	3.5-5.5	4.80±0.28	4.68±0.36	4.94±0.39	4.87±0.35	4.70±0.35
Calcium/mg dl ⁻¹	8.5-10.8	9.40±0.39	9.47±0.28	9.42±0.28	9.63±0.42	9.47±0.28
Phosphorus/mg dl ⁻¹	2.5-4.5	3.60±0.41	3.60±0.32	3.68±0.42	3.60±0.36	3.56±0.38

Table 3. Means and standard deviations of biochemical parameters of human sera

these fibrous capsules consisting of fibroblasts, and a grouped mast cells and lymphocyte were observed between tissues and capsule in the some samples (Figure 15, 16).

Fig. 15. After one week, the implan-tation site of AAm hydrogel, H-E, 20X

After 6–10 weeks, the adverse tissue reaction, giant cells and necrosis of cells, inflammatory reaction such as deposition of foamed macrophage were not observed in the implant site, however, it is observed to increase in the collagen fibrils due to proliferation and activation of fibroblasts (Fig. 17). No chronic and acute inflammation, adverse tissue reaction were observed in the all test groups. It is no determination related to the loss of activation and liveliness of cells in the capsule cells and in distant sites. No pathology were observed in the skin and the tissues of straight muscle in the close to implant sites.

Fig. 16. After 4 week, the implantation site of AAm hydrogel, H-E, 20X

Fig. 17. 10 week postimplantation of AAm/CA hydrogel. H-E, 20X

The thickness of the fibrous capsules were measured in the optical microscope using a micrometer scale. The means of five measurements for each the sample and each time point were calculated. The thickness of fibrous capsules are gradually increased to 6 weeks, and then these values are becomed a constant value. The thickness of fibrous capsule occurred due to AAm/CA, AAm/MA and AAm/IA hydrogels implant are high from the values of AAm and hydrogels. The carboxyl groups on the chemical structure and ionogenic character of AAm/CA, AAm/MA and AAm/IA hydrogels can be caused to the high thickness of the fibrous capsule (Smetana et al., 1990). The thickness of the fibrous capsules were measured in the optical microscope using a micrometer scale. The means of five measurements for each the sample and each time point were calculated and shown in Graphic 2. The thickness of fibrous capsules are gradually increased to 6 weeks, and then these values are becomed a constant value. The thickness of fibrous capsule occurred due to AAm/CA, AAm/MA and AAm/IA hydrogels implant are high from the values of AAm and hydrogels. The carboxyl groups on the chemical structure and ionogenic character of AAm/CA, AAm/MA and AAm/IA hydrogels can be caused to the high thickness of the fibrous capsule (Smetana et al., 1990). On the other hand, Student's *t* test was applied to the all constant values of thickness of fibrous capsules of the hydrogels, and no significant differences ($p > 0.05$) was

found. These thickness of fibrous capsule indicated well within the critical tissue tolerance range. It was given by the some reporters that the threshold capsule thickness should not exceed 200–250 μm for an implanted biomaterial (Jeyanthi and Rao, 1990). Our results clearly indicated that the capsule thickness of the excised tissue were well within these stipulated threshold limits. On the basis of the findings we can conclude that the biological response against the tested hydrogels was very similar to the biocompatibility of very low swollen of poly(2-hydroxyethyl methacrylate) hydrogel, which considered as a biologically inert polymer (Smetana et al., 1990). However, it is important that the swelling of acrylamide based hydrogels are very high than the swelling of poly(2-hydroxyethyl methacrylate) hydrogels for the biomedical uses.

Graphic 2. The curves of thickness of fibrous capsule – implantation time.

4. Bioactive ceramic biomaterials

Bioactive refers to a material, which upon being placed within the human body interacts with the surrounding bone and in some cases, even soft tissue. This occurs through a time – dependent kinetic modification of the surface, triggered by their implantation within the living bone. An ion – exchange reaction between the bioactive implant and surrounding body fluids – results in the formation of a biologically active carbonate apatite (CHAp) layer on the implant that is chemically and crystallographically equivalent to the mineral phase in bone. Prime examples of these materials are synthetic hydroxyapatite, glass ceramic and bioglass.

Calcium phosphate ceramics and xenografts have been used in different fields of medicine and dentistry. We demonstrated the effects of calcium phosphate ceramics (Ceraform) and xenograft (Unilab Surgibone) in the field of experimentally created critical size parietal and mandibular bone defects in rats (Develioglu et al., 2006, 2007, 2009, 2010).

Many researches are currently conducted to find out the ideal material to support bone repair or regeneration. The limitations of autogenous grafts and allogeneic bankbone have led to a search for synthetic alloplast alternatives. Calcium phosphate ceramics have been

widely used because the mineral composition of these implants materials does fully biocompatible (Rey C. 1990, LeGeros. 2002). The porous structure of the ceramics is claimed to enhance bone deposition and implant stabilization in the recipient bone. The optimal pore size is still debated to be ranging from 50 and 565 μm (Gauthier et al., 1998, Chang et al., 2000). However, porosity of the material is inversely proportional to the mechanical stability of these calcium phosphate based ceramics (Le Huec et al., 1995). This loss of stability is often cited as a limitation in the use of calcium phosphate-based ceramics in clinical practice. A convenient compromise to overcome this problem is to use a biphasic ceramic, which maintains its mechanical resistance until the resorption is achieved (Gauthier et al., 1998).

Various types of xenografts are used in medicine, dentistry, and also in periodontology. One of the xenografts is Unilab Surgibone, which is currently being used successfully in medicine and implantology. Moreover, osteoconductive properties are also known (Zhao et al., 1999). Unilab Surgibone is obtained from freshly sacrificed calves which is partially deproteinized and processed by the manufacturers. It is available in various shapes like tapered pins, blocks, cubes, granules, circular discs and pegs (Balakrishnan et al., 2000). Xenograft materials, bovine bones have been the most preferred ones, basically because they are easily obtainable and there are no great ethical considerations. Additionally they have the great advantage of practically unlimited availability of source/raw material. Partially deproteinized and defatted preparations (e.g. Unilab Surgibone) was indicated reduce antigenity and mild immune response (William et al., 2008).

Generally, xenografts are one of the alternative graft materials used in different fields for filling osseous defects Slotte and Lundgren, 1999, Salama 1983). Nonetheless, an interesting alternative to xenografts is Biocoral® (natural coral), which has been shown to exhibit osteoconductive and biocompatible properties whereby gradual replacement with newly formed bone occurred after its resorption (Guillemin et al., 1989, Doherty et al., 1994, Yilmaz and Kuru, 1996, Yukna Ra and Yukna CN, 1998).

Another xenogeneic, bone-derived implant material is Bio-Oss, which is similar to the xenograft investigated in our studies (Develioglu et al. 2009, 2010). Bio-Oss has been proposed as a biocompatible graft material for bony defects for it has shown osteoconductive properties – that is, it was replaced with newly formed bone after grafting (Yildirim et al, 2001, Sculean et al., 2002, Carmagnola et al., 2002). However, regarding the resorption of Bio-Oss, contradicting reports have emerged. On one hand, a previous study revealed that the bovine bone mineral underwent resorption (Pinholt et al., 1991). On the other hand, numerous researchers claimed that the resorption process of Bio-Oss® was very slow (Skoglund et al., 1997, Jensen et al 1996, Klinge et al., 1992).

In our previous studies with Ceraform (calcium phosphate ceramics) and xenograft (Unilab Surgibone), multinuclear giant cells (MNGC) were observed in the implantation region on 1st, 3rd, 6th ve 18th months.

The observed MNGCs are featured morphologic characteristics of foreign body giant cell (FBGC). These cells are osteoclast-like cells. Both cell types develop from a common precursor (Anderson, 2000) Since foreign body giant cell (FBGC) are the fusion products of monocytic precursors, which are also the precursors of macrophages, (Brodbeck et al., 2002, Matheson et al., 2004) the presence of such leukocytes in the wound healing compartment may be of central importance in driving the tissue reaction to the material. No necrosis, tumorigenesis, or infection was observed at the implant site up to 18 months (Figure 18-20).

Fig. 18. Remnants of the Xenograft (*) surrounded by fibrous tissue at 30 days. A-T 4X.

Fig. 19. A dense, fibrovascular tissue (*) in the side of ceraform implantation at 12th month M-T, 4X.

Fig. 20. Multinuclear giant cell (↔)in the implantation site. H-E, 40X

A long-term study would be useful to evaluate the biological degradation behavior of the material utilized in this study. BCP ceramics are well known to be biodegradable due both to body fluid dissolution and bio resorption cellular activity Nery et al., 1990, Piatelli et al., 1996). It might indicate that the implants utilized in our studies are progressively resorbed, but the size of the particle might be big (Handsichel et al., 2002) The studies reveal that Ceraform and xenograft are biocompatible. However, the materials did not promote bone formation.

5. Conclusion

In conclusion, while some vinyl monomers had cytotoxic effects on tissues, their polymers, Ceraform and Unilab Surgibone were found to be biocompatible in soft and hard tissues and they seem only to be beneficial bone filler materials in treatment of the bone defects. Unilab Surgibone and xenograft could be used as bone filler materials in the treatment of traumatic and post-traumatic skeletal complications (e.g delayed unions, non-unions), defects due to bone removal (e.g. bone tumors, congenital diseases) or low bone quality (e.g. osteoporosis, osteopenia) and in other medical fields.

6. References

- Anderson JM. (2000). Multinucleated giant cells. *Current Opinion in Hematology*, Vol. 7, pp. 40–47, ISSN 1065-6251.
- Balakrishnan, M.; Agarwal DC, Kumar SA (2000). Study of efficacy of heterogeneous bone graft (Surgibone) in orthopaedic surgery. *Medical Journal Armed Forces India*, Vol. 56, pp. 21-23, ISSN 0377-1237.
- Bao F., Liu D. (2004). Hydroxyl radicals generated in the rat spinal cord at the level produced by impact injury induce cell death by necrosis and apoptosis: Protection by a metalloporphyrin. *Neuroscience*, Vol. 126, pp. 285-295, ISSN 0306-4522.
- Barber DS, Hunt JR, Ehrich MF, Lehning EJ, Lo-Pachin RM (2001). Metabolism, Toxicokinetics and Hemoglobin Adduct Formation in Rats Following Subacute and Subchronic Acrylamide Dosing. *Neuro Toxicology*, Vol. 22, pp. 341-353, ISSN 0161-813.
- Benson RS. (2002) . Use of radiation in biomaterials science. *Nuclear Instruments & Methods In Physics Research Section B–Beam Interactions With Materials And Atoms*; Vol. 191, pp. 752-757, ISSN 0168-583.
- Brodbeck WG, Nakayama Y, Matsuda T, Colton E, Ziats NP, Anderson JM. (2002). Biomaterial surface chemistry dictates adherent monocyte/macrophage cytokine expression *in vitro*. *Cytokine*, Vol. 18, pp. 311–319, ISSN 1043-4666.
- Carmagnola D, Berglundh T, Lindhe J. (2002). The effect of a fibrin glue on the integration of Bio-Oss with bone tissue. An experimental study in Labrador dogs. *Journal of Clinical Periodontology*, Vol. 29, pp. 377-383, ISSN 1600-051.
- Chang BS, Lee CK, Hong KS, Youn HJ, Ryu HS, Chung SS, Park KW. (2000). Osteoconduction at porous hydroxyapatite with various pore configurations. *Biomaterials*, Vol. 21, pp. 1291–1298, ISSN 0142-9612.
- David H. Kim, Alexander R. Vaccaro, Fraser C. Henderson, Edward C. Benzel. (2003). Molecular biology of cervical myelopathy and spinal cord injury: role of oligodendrocyte apoptosis. *The Spine Journal*. Vol. 3, pp. 510-519, ISSN 1529-9430.

- Develioğlu H, Ünver Saraydın S, G. Bolayır, L. Dupoirieux. (2006). Assessment of the effect of a biphasic ceramic on bone response in a rat calvarial defect model. *Journal of Biomedical Materials Research*, Vol. 77, pp. 627-631, ISSN 1549-3296.
- Develioğlu H, Ünver Saraydın S, Laurent Duopoirieux, Zeynep Deniz Şahin. (2007). Histological findings of long-term healing of the experimental defects by application of a synthetic biphasic ceramic in rats. *Journal of Biomedical Materials Research*, Vol. 80, pp. 505-508, ISSN 1549-3296.
- Develioğlu H, Ünver Saraydın S, Ünal Kartal. (2009). The bone healing effect of a xenograft in arat calvarial defect model. *Dental Materials Journal*, Vol. 28, pp. 396-400, ISSN 0287-4547.
- Develioğlu H, Ünver Saraydın S, Ünal Kartal, Levent Taner. (2010). Evaluation of the long term results of rat cranial bone repair using a particular xenograft. *Journal of Oral Implantology*. Vol. 36, pp. 167-173, ISSN 0160-6972.
- Doherty MJ, Schlag G, Schwarz N, Mollan RA, Nolan PC, Wilson DJ. (1994). Biocompatibility of xenogeneic bone, commercially available coral, a bioceramic and tissue sealant for human osteoblasts. *Biomaterials* Vol. 15, pp. 601-608, ISSN 0142-9612.
- Gauthier O, Bouler JM, Aguado E, Pilet P, Daculsi G. (1998). Macroporous biphasic calcium phosphate ceramics: Influence of macropore diameter and macroporosity percentage on bone ingrowth. *Biomaterials*; Vol. 19, pp. 133-139, ISSN 0142-9612.
- Gold BG, Schaumburg HH. (2000). Acrylamide. In: Spencer PS, Schaumburg HH (eds) *Experimental and clinical neurotoxicology*, 2nd edn. ISBN 0195084772, Oxford University Pres, New York pp 124-132.
- Guillemin G, Meunier A, Dallant P, Christel P, Pouliquet JC, Sedel L. (1989). Comparison of corals resorption and bone apposition with two natural corals of different porosities. *Journal of Biomedical Materials Research*, Vol. 23, pp. 767-779, ISSN 1549-3296.
- Güven O, Sen M, Karadağ E, Saraydın D. (1999). A review on the radiation synthesis of copolymeric hydrogels for adsorption and separation purposes. *Radiation Physics And Chemistry*, Vol. 56, No. 4, pp. 381-386, ISSN 0969-806.
- Handschel J, Wiesmann HP, Sratmann U, Kleinheinz J, Meyer U, Joos U. (2002). TCP is hardly resorbed and not osteoconductive in a nonloading calvarial model. *Biomaterials*; Vol. 23, pp. 1689 -1695, ISSN 0142-9612.
- Jensen SS, Aaboe M, Pinholt EM, Hjorting-Hansen E, Melsen F, Ruyter IE. (1996). Tissue reaction and material characteristics of four bone substitutes. *The International Journal of Oral & Maxillofacial Implants*, Vol. 11, pp. 55-56, ISSN 0882-2786.
- Jeyanthi R., Rao KP. (1990). *In vivo* biocompatibility of collagen poly(hydroxyethyl methacrylate) hydrogels. *Biomaterials*, Vol. 11, pp. 238-243, ISSN 0142-9612.
- Karadağ E; Saraydın, D; Cetinkaya, S; Güven, O. (1996). In vitro swelling studies and preliminary biocompatibility evaluation of acrylamide-based hydrogels *Biomaterials*, Vol. 17, pp. 67-70, ISSN 0142-9612.
- Karadağ E; Saraydın, D; Güven, O. (2004). Water absorbency studies of gamma-radiation crosslinked poly (acrylamide-co-2,3-dihydroxybutanedioic acid) hydrogels. *Nuclear Instruments & Methods In Physics Research Section B-Beam Interactions With Materials And Atoms*. Vol. 225, No. 4, pp. 489-496, ISSN 0168-583.

- Klinge B, Alberius P, Isaksson S, Jönsson J. (1992). Osseous response to implanted natural bone mineral and synthetic hydroxyapatite ceramic in the repair of experimental skull bone defects. *Journal Oral Maxillofacial Surgery* Vol. 50, pp. 241-249, ISSN 02782391.
- Lamigeon C, Bellier JP, Sacchettoni S, Rujano M, Jacquemont B. (2001). Enhanced neuronal protection from oxidative stress by coculture with glutamic acid decarboxylase-expressing astrocytes. *Journal of Neurochemistry*, Vol. 77, pp. 598-606, ISSN 1471-4159.
- LeGeros RZ. (2002). Properties of osteoconductive biomaterials: Calcium phosphates. *Clinical Orthopaedics*, Vol. 395, pp. 81-98, ISSN 0009-921.
- Le Huec JC, Schaefferbeke T, Clement D, Faber J, Le Rebeller A. (1995). Influence of porosity on the mechanical resistance of hydroxyapatite ceramics under compressive stress. *Biomaterials*, Vol. 16, pp. 113-118, ISSN 0142-9612.
- Lee K-Y, Shibutani M, Kuroiwa K, Takagi H, Inoue K, Nishikawa H, Miki T, Hirose M. (2005). Chemoprevention of acrylamide toxicity by antioxidative agents in rats-effective suppression of testicular toxicity by phenylethyl isothiocyanate. *Arch Toxicol*, Vol. 79, pp. 531-541, ISSN 0340-5761.
- Matheson MA, Santerre JP, Labow RS. (2004). Changes in macrophage function and morphology due to biomedical polyurethane surface undergoing biodegradation. *Journal of Cell Physiology*, Vol. 199, pp. 8 -19, ISSN 0021-9541.
- McLendon, R.E, Bigner, D.D. (1994). Immunohistochemistry of the glial fibrillary acidic protein: basic and applied considerations. *Brain Pathology*, Vol. 4, pp. 221-228, ISSN 1015-6305.
- Montgomery D. L. (1994). Astrocytes: form, functions, and roles in disease. *Veterinary Pathology*, Vol. 31, pp. 145-167, ISSN 0300-9858.
- Morrison RS, Kinoshita Y, Johnson MD, Guo W, Garden GA. (2003). P53-Dependent cell death signaling in neurons. *Neurochemistry Research*, Vol. 28, pp. 15-27, ISSN 0364-3190.
- Nery EB, Eslami A, Van SR. (1990). Biphasic calcium phosphate ceramic combined with fibrillar collagen with and without citric acid conditioning in the treatment of periodontal osseous defects. *Journal of Periodontology*, Vol. 61, pp. 166 -172, ISSN 0022-3492.
- Okuno T, Matsuoka M, Sumizawa T, Igisu H. (2006). Involvement of the extracellular signal-regulated protein kinase pathway in phosphorylation of p53 protein and exerting cytotoxicity in human neuroblastoma cells (SH-SY5Y) exposed to acrylamide. *Archives of Toxicology*, Vol. 80, pp. 146-153, ISSN 0340-5761.
- Piatelli A, Scarano A, Mangano C. (1996). Clinical and histologic aspects of biphasic calcium phosphate ceramic (BCP) used in connection with implant placement. *Biomaterials*, Vol. 17, pp. 1767-1770, ISSN 0142-9612.
- Pinholt EM, Bang G, Haanes HR. (1991). Alveolar ridge augmentation in rats by Bio-Oss. *Scandinavian Journal of Dental Research*, Vol. 99, pp. 154-161, ISSN 0029-845.
- Rey C. (1990). Calcium phosphate biomaterials and bone mineral. Differences in composition, structures and properties. *Biomaterials*, Vol. 11, pp. 13-15, ISSN 0142-9612.

- Rogero S. O., Malmonge S. M., Lugão A. B., Ikeda T. I., Miyamaru L., and Cruz Á. S. (2003). Biocompatibility Study of Polymeric Biomaterials. *Artificial Organs*, Vol. 27, No. 5, pp. 424-427, ISSN 1525-1594.
- Salama R. (1983). Xenogenic bone grafting in humans. *Clinical Orthopaedics and Related Research*, Vol. 174, pp. 113-121, ISSN 0009-921.
- Saraydın, D; Karadag, E; Guven, O. (1995). Acrylamide/maleic acid hydrogels. *Polymers For Advanced Technologies*, Vol. 6, No. 12, pp. 719-726, ISSN 1042-7147.
- Saraydın, D; Karadag, E; Çetinkaya, S; Guven, O. (1995). Preparation of acrylamide maleic-acid hydrogels and their biocompatibility with some biochemical parameters of human serum. *Radiation Physics And Chemistry*, Vol. 46, No. 4-6, pp. 1049-1052, ISSN 969-806.
- Saraydın, D; Koptagel, E; Unver-Saraydın, S; Karadag, E; Guven, O. (2001). In vivo biocompatibility of radiation induced acrylamide and acrylamide/maleic acid hydrogels. *Journal of Materials Science* Vol. 36, No. 10, pp. 2473-2481, ISSN 0022-2461.
- Saraydın, D; Caldiran, Y. (2001). In vitro dynamic swelling behaviors of polyhydroxamic acid hydrogels in the simulated physiological body fluids. *Polymer Bulletin* Vol. 46, No. 1, pp. 91-98, ISSN 0170-0839.
- Saraydın, D; Isikver, Y; Karadag, E; Sahiner, N; Guven, O. (2002). In vitro dynamic swelling behaviors of radiation synthesized polyacrylamide with crosslinkers in the simulated physiological body fluids. *Nuclear Instruments & Methods In Physics Research Section B-Beam Interactions With Materials And Atoms*, Vol. 187, No. 3, pp. 340-344, ISSN 0168-583.
- Saraydın, D; Karadag, E; Sahiner, N; Guven, O. (2002). Incorporation of malonic acid into acrylamide hydrogel by radiation technique and its effect on swelling behaviour. *Journal Of Materials Science* Vol. 37, No. 15, pp. 3217-3223, ISSN 0022-2461.
- Saraydın, D; Unver-Saraydın, S; Karadag, E; Koptagel, E; Guven, O. (2004). In vivo biocompatibility of radiation crosslinked acrylamide copolymers. *Nuclear Instruments & Methods In Physics Research Section B-Beam Interactions With Materials And Atoms* Vol. 217, No. 2, pp. 281-292, ISSN 0168-583.
- Sculean A, Chiantella GC, Windisch P, Gera I, Reich E. (2002). Clinical evaluation of an enamel matrix protein derivate (Emdogain®) combined with a bovine-derived xenograft (Bio-Oss®) for the treatment of intrabony periodontal defects in humans. *International Journal of Periodontics Restorative Dentistry*, Vol. 22, pp. 259-267, ISSN 0198-7569.
- Skoglund A, Hising P, Young C. (1997). A clinical and histologic examination in humans of the osseous response to implanted natural bone mineral. *International Journal of Oral Maxillofacial Implants* Vol. 12, pp. 194-199, ISSN; 0882-2786.
- Slotte C, Lundgren D. (1999). Augmentation of calvarial tissue using non-permeable silicone domes and bovine bone mineral. An experimental study in the rat. *Clinical Oral Implants Research*, Vol. 10, pp. 468-476, ISSN 0905-7161.
- Smetana Jr. K, Vacík J., Součková D., Krčová Z., Šulc J. (1990). The influence of hydrogel functional groups on cell behavior *Journal of Biomedical Materials Research*, Vol. 24, pp. 463-470, ISSN 1549-3296.
- Sumizawa T, Igisu H. (2007). Apoptosis induced by acrylamide in SH-SY5Y cells. *Archives of Toxicology*, Vol. 81, pp. 279-282, ISSN 0340-5761.

- Ünver Saraydın S, Develioğlu H. (2011). Evaluation of the bone repair capacity and the cytotoxic properties of a particular xenograft: An Experimental study in rats *Turkiye Klinikleri Journal of Medical Sciences*, Vol.31, No.3, pp.541-547, ISSN 1300-0292.
- Ünver Saraydın S, H. Eray Bulut, Ünal Özüm, Z. Deniz Şahin İnan, Zübeyde Akin Polat, Yücel Yalman, Dursun Saraydın. (2011). Evaluation of the Cytotoxic effects of various monomers, In vitro also their effects on Apoptosis and GFAP immunolocalization in rat spinal cord In vivo. *HealthMED*. Vol. 5, No. 1, pp. 17-28, ISSN 1840-2291.
- William S. Pietrzak, Charles A. Vacanti, (2008). *Musculoskeletal Tissue Regeneration: Biological Materials and Methods*, Publisher: Totowa, NJ : Humana Press, p:121, ISSN 0895-8696.
- Yılmaz S, Kuru B. (1996). A regenerative approach to the treatment of severe osseous defects: report of an early onset periodontitis case. *Periodontal Clinical Investigation* Vol. 18, pp. 13-16, ISSN 1065-2418.
- Yukna RA, Yukna CN. (1998). A 5-year follow-up of 16 patients treated with coralline calcium carbonate (BIOCORAL®) bone replacement grafts in infrabony defects. *Journal of Clinical Periodontology*, Vol. 25, pp. 1036-1040, ISSN 0303-6979.
- Yıldırım M, Spiekermann H, Handt S, Edelhoff D. (2001). Maxillary sinus augmentation with the xenograft Bio-Oss® and autogenous intraoral bone for qualitative improvement of the implant site: a histologic and histomorphometric clinical study in humans. *International Journal of Oral Maxillofacial Implants*, Vol. 16, pp. 23-33, ISSN 0882-2786.
- Zhao YF, Mendes M, Symington JM. Listrom RD, Pritzker KP. (1999) Experimental study of bone growth around a dental implant after Surgibone grafting. *International Journal of Oral Maxillofacial Implants*, Vol. 14, pp. 889-897, ISSN 0882-2786.

IntechOpen

Biomaterials - Physics and Chemistry

Edited by Prof. Rosario Pignatello

ISBN 978-953-307-418-4

Hard cover, 490 pages

Publisher InTech

Published online 14, November, 2011

Published in print edition November, 2011

These contribution books collect reviews and original articles from eminent experts working in the interdisciplinary arena of biomaterial development and use. From their direct and recent experience, the readers can achieve a wide vision on the new and ongoing potentialities of different synthetic and engineered biomaterials. Contributions were selected not based on a direct market or clinical interest, but based on results coming from very fundamental studies. This too will allow to gain a more general view of what and how the various biomaterials can do and work for, along with the methodologies necessary to design, develop and characterize them, without the restrictions necessarily imposed by industrial or profit concerns. The chapters have been arranged to give readers an organized view of this research area. In particular, this book contains 25 chapters related to recent researches on new and known materials, with a particular attention to their physical, mechanical and chemical characterization, along with biocompatibility and histopathological studies. Readers will be guided inside the range of disciplines and design methodologies used to develop biomaterials possessing the physical and biological properties needed for specific medical and clinical applications.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Serpil Ünver Saraydin and Dursun Saraydin (2011). Histopathological Effect Characteristics of Various Biomaterials and Monomers Used in Polymeric Biomaterial Production, *Biomaterials - Physics and Chemistry*, Prof. Rosario Pignatello (Ed.), ISBN: 978-953-307-418-4, InTech, Available from:
<http://www.intechopen.com/books/biomaterials-physics-and-chemistry/histopathological-effect-characteristics-of-various-biomaterials-and-monomers-used-in-polymeric-bioma>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2011 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](https://creativecommons.org/licenses/by/3.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

IntechOpen

IntechOpen