We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Nobel Metal Nanoparticles in Bio-LED

Yen-Hsun Su¹, Sheng-Lung Tu² and Wei-Min Zhang³

¹*Department of Material Science and Engineering*

National Dong Hwa University, Tainan

²*Department of Resource Engineering, National Cheng Kung University, Tainan*

³*Department of Physics, National Cheng Kung University, Tainan
Taiwan*

1. Introduction

Nanomaterials are well known for their interesting physical chemical properties [1-7]. Recently, noble metal nanoparticles have attracted attention [9-15] due to their optical property of surface plasmon resonance. Surface plasmon resonance produces hot light spots due to a stronger electromagnetic field. Because of their low toxicity, ease of delivery, and strong and tunable surface plasmon resonance, noble metal nanoparticles are used in the field of the photothermal ablation therapy to treat cancer [10]. Plants help people confront the global warming by absorbing CO₂ in the photosynthesis process. If plants were able to do the photosynthesis process day and night, absorbing CO₂ will act in day and night.

In this paper, we investigate the life time of noble metal nanoparticle colloids on plants specifically. The buds of Floppers, *Bryophyllum pinnatum* (Lam.) Kurz., are watered the noble metal cluster colloids. The buds are recorded for six weeks. The results show that noble metal nanoparticle colloids exit plant growth, with the Pt nanoparticles aggregating on the leaf. We expect that this research has potential applications in the fields of biosensing, bio-LED, bioimaging, nanophotonics, photothermal ablation therapy, and nanotoxicity.

2. Experimental produre

Chemicals and materials. We prepared 10 L standard solution by adding MgCl= 10.0 ppm, KCl=0.5 ppm, NaCl= 8 ppm, and FeCl₃= 0.04 ppm in Milli-Q water. Trisodium citrate (99%) and HAuCl₄, AgNO₃, and H₂PtCl₆ were purchased from Showa Chemical Co. (Tokyo, Japan) and Alfa Aesar Chemical Co. (Lancashire, England) and used as supplied, respectively. Milli-Q water was obtained from the Milli-Q Element system (Massachusetts, USA), which employs ultra-clean materials and a succession of optimized water purification technologies to produce 18.2 MΩ/cm resistivity ultrapure water (at 25 °C), ideal for trace analysis methods. The solution used in this work was freshly prepared and deoxygenated by bubbling nitrogen gas for at least 30 min prior to use. All materials and apparatus were sterile.

Preparation of noble nanoparticles. Au NPs were prepared by a chemical-reduction method with Au, Pt, Ag-salt and Na-cit standard solutions. 1.5 ml of freshly prepared 0.34 M trisodium citrate_(aq) solution was added to 15 ml of 0.5 mM HAuCl_{4(aq)} solution, AgNO_{3(aq)}

solution, and $\text{H}_2\text{PtCl}_{6(\text{aq})}$ solution at room temperature and under vigorous stirring for 48 hours. These solutions were stirred for 30 min to control the reaction rate of Au, Ag, and Pt nanoparticles, respectively. All materials and apparatus were sterile.

Preparation of Floppers, *Bryophyllum pinnatum* (Lam.) Kurz. We cut 40 leaves from the plant *Bryophyllum pinnatum* (Lam.) Kurz., and these were then placed in a 50 ml glass bottom and watered with standard solution. The environment was controlled at 300 K, with 100mW/square-cm radiation with sun lamps and 60% humidity. Buds grew at the edges of the leaves, and when the length of a bud reached 5.980 mm, it was cut, and put at the bottom of a 3 ml glass bottom. The cut buds were hold in a 300 K environment with 100mW/square-cm radiation with sun lamps and 60% humidity. A total of 697 buds were tested using either standard solution or noble metal colloids. The buds were watered with 0.5 ml of the standard solution or noble metal colloids. And all materials and apparatus were sterile.

Instruments and Measurements. Dark-field spectroscopy, zetasizer, and TEM were used in the analysis. The morphology of the noble metal nanoparticles was observed by TEM. The as-grown product was observed with a Hitachi model HF-2000 transmission electron microscope operating at 200 kV. The sample was directly dispersed onto a 200-mesh holey carbon film on a Cu grid for TEM analysis. After being watered with standard solution or noble metal colloids for six weeks, the leaves and roots of the buds were observed via dark-field spectroscopy.

3. Results

3.1 Morphology of Au, Ag, and Pt nanoparticles

The concentration of the citric acid group modifies the noble metal nanoparticles to control their size. The average size for Au, Ag, and Pt nanoparticles was measured with a zetasizer, and was 6.3 nm, 3.2 nm, and 5.8 nm, respectively. From the TEM observation in Fig. 1, the size of the Au, Ag, and Pt nanoparticles is in good agreement with the zetasizer measurements.

(a)

(b)

(c)

Fig. 1. Morphology of (a) Au, (b) Ag, and (c) Pt nanoparticles under TEM observation.

3.2 Buds watered with standard solution or noble metal colloids for six weeks

After being watered with standard solution or noble metal colloids for six weeks, dark-blue masses on the leaves are seen under the dark-field microscopic observation in Fig. 2. The leaves scatter green light, as shown in Fig. 2 (a). Metal clusters usually scatter strong light due to surface plasmon resonance [9,14]. And as the size of the particles (clusters) increases, so does the damping factor and the absorption. On the other hand, the light scattering gets weaker, as the size of particles (clusters) increases [14,15]. Thus, the metal cluster presents the dark-blue masses. In addition, the nanoparticles aggregate on the surface of leaves, and Fig. 2 shows that Pt nanoparticles aggregate together the most.

(a)

(b)

(c)

(d)

Fig. 2. Dark-field microscopic image of leaf on the bud watered with (a) standard solution, (b) Au colloids, (c) Pt colloids, and (d) Ag colloids for six weeks.

In Fig. 3, the dark-field microscopic observation shows the roots scatter the weak light, while the metal clusters scatter stronger light. As the size of the metal clusters decreases, the surface plasmon resonance increases, as does the scattering of light [14,15]. Therefore, the particles (clusters) size on the roots are smaller than these on the leaves. However, the light scattering of Pt clusters is weaker than that of the Au or Ag clusters, and Pt nanoparticles also aggregate together more seriously than the others on the roots.

(a)

(b)

(c)

(d)

Fig. 3. Dark-field microscopic image of roots on the bud watered with (a) standard solution, (b) Au colloids, (c) Pt colloids, and (d) Ag colloids for six weeks.

According to Fig. 2~3, we observe the noble will not be corroded in leaves and roots. Install, noble metal nanoparticle will aggregate together in vein of leaves or the surface of roots.

4. Conclusions

We found that noble metal colloids significantly exit Floppers, *Bryophyllum pinnatum* (Lam.) Kurz. for several weeks. Future detailed studies should be performed to understand how the mechanism of nanoparticle leaves the plant body.

5. Acknowledgments

This work was financially supported by the National Science Council of Taiwan, No. 100-2218-E-259-003-MY3, which is gratefully acknowledged.

6. References

- [1] Pedano ML, Li S, Schatz G C, Mirkin CA 2010 *Angew. Chem. Int. Ed.* 49 78-82.
- [2] Camden J P, Dieringer J A, Wang Y, Masiello DJ, Marks LD, Schatz GC, Van Duyne RP 2008 *J. Am Chem. Soc.* 130 12616.
- [3] Khlebtsov B, Khlebtsov N 2008 *Nanotechnology* 19 435703.
- [4] Hao F, Sonnefraud Y, Van Dorpe P, Maier SA, Halas N J, Nordlander P 2008 *Nano Lett.* 8 983.
- [5] Longo A, Pepe GP, Carotenuto G., Ruotolo A, De Nicola S, Belotelov VI, Zvezdin, AK 2007 *Nanotechnology* 18 365701.
- [6] Maly J, Lampova H, Semeradtova A, Stofik M, Kovacik L 2009 *Nanotechnology* 20 385101.
- [7] Mutombo P, Kiss AM, Berko A, Chab V 2006 *Nanotechnology* 17 4112.
- [8] Bouhelier A, Bachelot R, Lerondel G, Kostcheev S, Royer P, Wiederrecht1 GP 2005 *Phys. Rev. Lett.* 95 267405.
- [9] Schatz G.C 2010 *J. Phys. Chem. Lett.* 1 802.
- [10] Zhang J Z 2010 *J. Phys. Chem. Lett.* 1 686.
- [11] Guo PF, Wu S, Ren QJ, Lu J, Chen Z, Xiao SJ, Zhu YY 2010 *J. Phys. Chem. Lett.* 1 315.
- [12] Wang C, Zhang M, Wang H, Zou S 2010 *J. Phys. Chem. Lett.* 1 79.
- [13] Su YH, Chang SH, Teoh LG, Tu ST, Hon MH 2009 *J. Nanosci. Nanotechnol.* 9 1181.
14. Su YH, Teoh LG, Lai WH, Chang SH, Yang HY, Hon MH 2007 *Appl. Spectrosc.* 61, 1007.
- [14] Su YH, Chang SH, Teoh LG, Chu WH, Tu SL 2009 *J. Phys. Chem. C*, 113 3923.
- [15] Skirtach AG, Javier AM, Kreft O, Kohler K, Alberola AP, Mohwald H, Parak WJ, Sukhorukov GB 2006 *Angew. Chem.. Int. Ed.* 45 4612.
- [16] Troutman TS, Barton JK, Romanowski M 2008 *Adv. Mater.* 20 2604.
- [17] Alkilany AM, Nagaria PK, Hexel CR, Shaw TJ, Murphy CJ, Wyatt MD 2009 *Small* 5 701.
- [18] Male KB, Lachance B, Hrapovic S, Sunahara G., Luong JHT 2008 *Anal. Chem.* 80 5487.
- [19] Gobin AM, Moon JJ, West J, Ephrin L, Int. 2008 *J. Nanomed.* 3 351.
- [20] Bernardi RJ, Lowery AR, Thompson PA, Blaney SM, West J L 2008 *J. Neuro-Oncol.* 86 165.
- [21] Lal S, Clare SE, Halas NJ 2008 *Acc. Chem. Res.* 41 1842.

- [22] Huang XH, El-Sayed IH, Qian W, El-Sayed MA 2006 J. Am. Chem. Soc. 128 2115.
- [23] von Maltzahn G, Park JH, Agrawal A, Bandaru NK, Das SK, Sailor MJ, Bhatia SN 2009 Cancer Res. 69 3892.
- [24] Letfullin RR, Joenathan C, George TF, Zharov V P 2006 Nanomedicine 1 473.
- [25] Mironava T, Hadjiargyrou M, Simon M, Jurukovski V, Rafailovich MH 2010 Nanotoxicology 4 120.

IntechOpen

IntechOpen

Noble Metals

Edited by Dr. Yen-Hsun Su

ISBN 978-953-307-898-4

Hard cover, 426 pages

Publisher InTech

Published online 01, February, 2012

Published in print edition February, 2012

This book provides a broad spectrum of insights into the optical principle, resource, fabrication, nanoscience, and nanotechnology of noble metal. It also looks at the advanced implementation of noble metal in the field of nanoscale materials, catalysts and biosystem. This book is ideal not only for scientific researchers but also as a reference for professionals in material science, engineering, nonascience and plasmonics.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Yen-Hsun Su, Sheng-Lung Tu and Wei-Min Zhang (2012). Nobel Metal Nanoparticles in Bio-LED, Noble Metals, Dr. Yen-Hsun Su (Ed.), ISBN: 978-953-307-898-4, InTech, Available from:
<http://www.intechopen.com/books/noble-metals/nobel-metal-nanoparticles-in-bio-led>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2012 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](https://creativecommons.org/licenses/by/3.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

IntechOpen

IntechOpen