We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

The Effects of Tree-Alfalfa Intercropped Systems on Wood Quality in Temperate Regions

Hamid Reza Taghiyari¹ and Davood Efhami Sisi²

¹*Shahid Rajaee Teacher Training University,*

²*The University of Tehran
Iran*

1. Introduction

Agroforestry is a dynamic, ecologically based, natural resource management system that, through the integration of trees in farm and rangeland, diversifies and sustains production for increased social, economic and environmental benefits (Leakey, 1996). Apart from the social and cultural advantages of growing trees, recreational benefits for human being, as well as improvement in wildlife, there are other advantages associated with planting trees with crops. There are five mechanisms through which trees contribute to the agricultural environment (Yin, 2004). These include reducing wind velocity and wind erosion, controlling sheet and rill erosion, mediating solar radiation and regulating soil and air temperatures, increasing field moisture, and improving soil nutrients.

In low forest cover countries, development of tree-based intercropping is necessary to reduce the dependence on natural forests. Such an agroforestry system can encourage farmers to produce wood along with annual crops (Efhami Sisi et al., 2010). However, a tree plantation is usually considered a long-rotation activity in comparison with agricultural crops. This discouraged farmers from adopting tree farming (Asadi, 1994). Agroforestry encompasses several systems; among which alley intercropping is considered a common practice in this regard. More than 40% of research projects in international agroforestry research institutes focus on this practice (Singh et al. 2001).

Alley cropping is an agroforestry management system that permits the production of a variety of crops in alleys between widely spaced rows of trees (Asadi et al., 2005). Alley cropping (hedged agroforestry) increase tree cover, fuelwood supplies and infiltration of rain, provide protection against wind, and reduce runoff (Otengi et al., 2000). In alley cropping systems where timber is a major ecosystem service, initial spacing between the trees is of great importance because it influences anatomical, physical, and morphological characteristics of wood. For woody components in agroforestry systems, there are some desirable characteristics, such as adaptability, straight bole, thin crown, appropriate leafing phenology, deep root, little or no negative effect on crop, and economical and social traits (Muthuri et al., 2005; Singh et al., 2001). Interplanting of trees with crops requires management practices, which affect wood characteristics of timber trees in alley cropping.

However, little is known about the properties of timber sourced from agricultural lands (Shanavas & Kumar, 2006).

In agroforestry systems, farmers are interested in increasing initial spacing between trees to achieve higher crop yields. Two factors are considered of vital importance in an alley agroforestry to study the quality of the wood cultivated: the crops and their effects on the soil fertility and tree growth, and the initial spacing between the trees. DeBell et al. (2002) found that interplanting nitrogen-fixing *Albizia* spp. increased the mean stem diameter of *Eucalyptus saligna* by 37% but did not alter wood density. Similarly, growth rate of trees generally increases with wider initial-spacing because of the decreased competition with surrounding trees for soil moisture and nutrients (Wodzicki, 2001). The goal of silvicultural practices such as thinning, spacing, interplanting, weeding, and fertilizing is to increase tree height and diameter growth (Chen et al., 1998). In turn, any change in the growth pattern and growth rate of a tree may result in wood property variation (Zobel & van Buijtenen, 1989).

All forestry practices may influence tree growth in one way or another, and consequently, wood properties would also be altered (Fig. 1). It should be justified if the changes in wood properties such as the size of log, proportion of juvenile wood, density, fiber length, etc., are technically accepted by the wood industry. The economical aspects of the silvicultural practices should also be taken into account (Bowyer et al .2007).

Fig. 1. Relationship between silvicultural practices and its effects on wood quality (Bowyer et al., 2007)

The influence of growth rate on wood quality is very complicated. In many cases, a tree species may be positively affected by a certain forestry practice that shows a completely opposite effect on another species (Kollmann & Côté, 1968). For example, increase in growth rate of a tree may cause some changes in tree ring structures (Fig. 2). In softwoods, increase in tree ring width does not have any effect on dense latewood width; it would therefore be predicted that the density of wood would naturally decrease. In ring-porous hardwoods such as oak, this effect would be quite the opposite; that is, increase in tree ring width does

not have any effect on porous early wood width; therefore, the density would naturally increase. In diffuse-porous hardwoods such as poplar, however, no clear relationship between ring width and wood density is observed (Kollmann & Côté, 1968). Similarly, growth rate may have significant effects on wood anatomy (Efhami Sisi et al. 2010, 2011a), physical and mechanical properties (Taghiyari & Sarvari Samadi, 2010; Taghiyari, 2011; Taghiyari et al., 2010, 2011; Taghiyari & Efhami Sisi, 2011; Shanavas & Kumar, 2006). Some researchers believe that, regardless of the cause of increase in growth rate, it may have similar effects on wood quality (DeBell et. al., 1998).

Fig. 2. Schematic diagram of growth rate effects on tree ring structure

There are many complicated interactions between wood properties and technical acceptance that need to be taken into account when studying growth rate effects on wood quality. Improvement in tree growth properties should not necessarily have similar results on technical acceptance of the wood (Fig. 3). In ring-porous species for instance, increase in density by higher growth rates would ultimately improve mechanical properties; while increase in diameter and the number of branches showed negative effect on it (Zobel & van Buijtenen, 1989).

Fig. 3. Effects of tree growth characteristics on wood quality and technical acceptance (Zobel & van Buijtenen, 1989)

Based on the above literature review, alley cropping and N-fixing crops improve the growth rate of trees. Changes in growth rate by forestry management variables (Fig. 1) are reported to alter wood properties. However, not many studies have so far assessed the extent to which alley cropping would affect wood properties from anatomical, physical, and mechanical points of view. Therefore, this chapter evaluates the effects of initial spacing and intercropping on growth rate and wood quality.

2. Effects of agroforestry on growth rate and bole form

Increases in soil organic matter and total organic nitrogen are reported to explain the increase in growth rate of trees in agroforestry systems (Eaglesham et al. 1981; Sea-Lee et al. 1992). DeBell et al. (2002a) evaluated the effects of chemical fertilizer, spacing, and interplanted nitrogen-fixing trees on diameter growth of 15-year-old *Eucalyptus saligna* trees and concluded that diameter growth (hence, productivity) can be increased substantially through supplemental nitrogen and increased growing space. In a separate study, 8 years after establishment, *P. deltooides* intercropped with wheat-fodder maize had larger diameter, crown width and wood volume (m³/ha) than pure tree stands (Chaudhry et al., 2003). Other studies have also shown that (i) an intercropped agroforestry system was more economical at the rotations of 4 and 6 years compared to pure stands (Chaudhry et. al., 2003), (ii) there was more growth in poplar trees under agroforestry conditions than that of forest conditions (Singh et al., 1988), and (iii) *Acacia auriculiformis*, *Acacia mangium*, and *Grevillea robusta* trees grown in agroforestry systems had better growth rate (Shanavas & Kumar, 2006).

Efhami Sisi et al. (2008) studied the effects of *Populus nigra*-alfalfa intercropping and initial spacing on growth rate of poplar trees. They found that (i) tree diameter in tree-crop intercropped systems was greater than in pure tree stands, and (ii) tree diameter increased with decreasing tree density. General trends of diameter growth in relation to age were similar for all treatments (Fig. 4), but the greatest difference in diameter growth values occurred from age 3 to about age 7.

Fig. 4. Diameter growth as a function of ring number from pith to bark
◇ = 3 m × 4 m without alfalfa; □ = 3 m × 4 m with alfalfa; Δ = 3 m × 6.7 m with alfalfa;
○ = 3 m × 8 m with alfalfa; × = 3 m × 10 m with alfalfa

With regard to the early rising and the consequent falling trend of tree growth (Fig. 4), in any plantation, the ring width generally decreases with age because of the increased competition with the surrounding trees (Wodzicki, 2001); in poplar plantations, this decrease in ring width is usually observed in rings 3 to 5. The pointer year at age 6 found only in trees of the treatments with alfalfa might be due to the termination of alfalfa cultivation at age 5 which could be beneficial to trees (Fig. 4).

Alfalfa, a nitrogen(N)-fixing plant, has the capacity of fixing about 230 kg N ha⁻¹ yr⁻¹ and does not need annual plowing and sowing (Tisdal & Nelson, 1974). In tropical and sub-tropical forests, trees of legume family such as *Albizia*, *Pterocaria*, and *Gleditchia* spp are the main source for N-fixing in the soil (Tisdal & Nelson 1974).. Use of N-fixing plants is one of the methods for fertilizing plantation trees (Zobel and van Buijtenen, 1989). Legumes have the synergistic effect of improving soil health through biological N-fixation and adding nutrient-rich residues to the soil (Skelton, 2002). Intercropping trees with alfalfa may increase in soil N content and fertility resulting in an increase in tree diameter (Saarsalmi et al., 2006; Skelton, 2002; Tisdal & Nelso, 1974). Moreover, a wider initial-spacing would decrease competition among individual trees (Wodzicki, 2001) and consequently increase growth rate. Overall wood production and basal area can decrease although wider initial spacing increases growth rate. While intercropping trees with alfalfa can increase basal area, wider initial spacing could decrease it (Fig. 5).

Fig. 5. Basal area of poplar trees influenced by initial spacing and alfalfa-intercropping (Efhami Sisi et al., 2008)

Although the trees in plantations with wide initial spacing grew at a significantly rapid rate and quickly reached merchandisable diameter, the increase in growth rate of trees did not compensate for low tree density (Lundgren, 1981). There is always an optimum initial spacing for a certain tree species - given specific climatic conditions and stand quality in which biomass does not change with initial spacing. Sjolte-Jorgensen (1967) presented data showing quality trends for Norway spruce (Table 1). The biomass of 47-year-old Norway spruce did not change between 2 m and 3 m spacing regimes while mean diameter of trees increased. In fact, this is an optimum initial spacing in which rapid growth rate and wider initial spacing may compensate for a lower tree-density. Finding this optimum point is of great importance in agroforestry system. Larger diameter logs yield significantly more revenue than smaller logs (Barbour and Kellogg's, 1988).

Spacing (m)	Mean Diameter (cm)	Taper Whole stem (cm/m)	Percentage of Knots	Total Production (Tones/ha)
1.25 × 1.40	20.1	0.98	0.191	261
1.40 × 1.65	20.5	1.02	0.236	240
2.00 × 2.00	24.1	1.04	0.260	218
3.00 × 3.00	26.0	1.13	0.340	218
3.50 × 3.50	28.3	1.26	0.335	166

Table 1. Stand characteristics of 47-year-old *Picea abies* as influenced by initial spacing (Data cited in Sjolte-Jorgensen 1967)

Table 1 shows that initial spacing could influence bole quality; that is, an increase in initial spacing could decrease bole quality because of a higher percentage of knots and taper. Trees with significant taper have relatively low lumber yields and they are unacceptable for manufacturing some of the specialty products such as poles. Knot size is an important factor for poles and lumber. The greater the proportion of knots, the lower the strength and the lower the value of clear wood produced (Zobel & van Buijtenen, 1989).

Fig. 6. Schematic diagram of the effects of initial spacing on crown and branch expansion

Taper is largely a crown effect. Since the cambium activates first within the crown, growth rings tend to be widest here, and maximum diameter growth often occurs. Thus, trees with large crowns tend to have highly conical stems, while stems of trees whose crowns have receded gradually become more cylindrical (Fig. 6). High-taper trees have smaller scaling diameters (because diameter is measured at the log’s small end). Knot size is directly impacted by crown size. Persistent, live crowns give branches more time to grow, and knot size increases. Receding crowns limit branch size, thus limiting knot size (Ballard & Long, 1988).

Efhami Sisi et al. (2008) studied the effects of initial spacing and intercropping (with alfalfa) on bole form factors such as taper, eccentric, roundness and number, diameter, length and angle of branches, as well as height of trees (Table 2).

Treatments	Taper (cm/m)	Eccentric	Roundness (%)	Branches				height
				Number	Diameter (cm)	Length (m)	Angle	
3 m × 4 m without alfalfa	1.37	6.17	1.10	11	3	3.4	40	10.8
3 m × 4 m with alfalfa	1.34	8.9	1.09	12	4	4.2	40	11.8
3 m × 6.6 m with alfalfa	1.42	8.63	1.10	12	4	4.3	45	11.8
3 m × 8 m with alfalfa	1.59	13.63	1.38	12	4.6	5	45	12.1
3 m × 10 m with alfalfa	1.76	11.83	1.28	13	5.6	6	47	12.9

Table 2. Bole form of poplar trees influenced by initial spacing and alfalfa-intercropping (Efhami Sisi et al., 2008)

There was no significant difference in tree height across treatments. Taper, eccentric and roundness increased with increasing inter-tree spacing, while integration of alfalfa did not. Number, length, diameter and angle of branches increased in widely spaced and intercropped treatments. Roundness is also considered as an important and influential parameter of yield in veneer and plywood industries (Mäkinen, 1998). Stand density and thinning accounted for 2 – 9% of roundness (Mäkinen, 1998). Also, eccentricity is considered a sign of reaction wood formation in tree stem. Its measurement was based on maximum radius and minimum radius at breast height, showing an increase by initial spacing (Efhami Sisi et al., 2008).

At a close spacing, the sample trees had somewhat less branches in a whorl than more in widely spaced plots. The most pronounced effect of initial spacing was the increase in branch diameter with increasing initial spacing (Mäkinen & Hein, 2006; Ulvcrona et al., 2007). The effects of initial spacing on straightness of tree bole, diameter, and number of branches in each inter-node, are more pronounced than on intrinsic wood properties (Malinauskas, 1999). Planting trees in widely spaced plots reduces establishment costs and accelerates diameter growth of individual trees, resulting in larger, but fewer, trees at any given age with lower bole quality. The more trees established per acre, the higher the total cubic-foot volume yield. However, this increased volume must be harvested from more and smaller trees (Lundgren, 1981).

3. Effects of agroforestry on wood anatomy

3.1 Vessel properties

Vessel diameter and frequency in trees affect wood quality traits such as permeability which in turn determines, among other variables, wood preservation, wood drying, pulp and paper making (Chen et al., 1998). Efhami Sisi et al. (2010) studied the effects of intercropping *Populus nigra* with alfalfa and initial tree spacing on vessel element attributes by measuring the proportion of each ring relative to the whole disc area to obtain weighting coefficient for every growth ring. The study showed that intercropping *Populus nigra* with alfalfa and increasing initial spacing increased vessel diameter and frequency; while wider initial

spacing decreased the vessel frequency (VF), and to some extent the vessel lumen area percentage (VLA %), but increased vessel lumen diameter (VLD) (Table 3; Figs. 7 & 8).

Fig. 7. Microscopic images of cross-section of the third tree-ring in trees harvested in 3 × 4 and 3 × 10 meter inter-tree spacing in tree- alfalfa intercropping (scale bar: 300μ). **A:** 3 × 10 with alfalfa: vessels with low frequency but more diameters resulting in lower vessel lumen area. **B:** 3 × 4 with alfalfa: vessels with more frequency but lower diameter resulting in high vessel lumen area

Vessel lumen diameter increased more or less linearly from pith to bark in all treatments (Fig. 8-A). The rate of increase of VLD in the outer rings was comparatively lower in tree stands without alfalfa than in tree-alfalfa intercropped systems. Vessel Frequency per unit area (mm²) decreased as cambial age increased (Fig. 8-B), but rates were similar across treatments. Vessel Lumen Area (%) increased consistently from pith to bark in treatments with alfalfa (Fig. 8-C). Zobel and van Buijtenen (1989) reported that N fertilization increases the period of juvenile wood production. Considering the definition of juvenile wood as the part of wood that shows severe radial change in wood properties (Zobel & Sprague, 1998), it may be expected that intercropping trees with alfalfa may increase the period to reach wood maturity.

Treatments	Annual Diameter Growth (mm)	Based on the area of tree rings		
		Vessel Diameter (μm)	Vessel frequency per mm	Vessel lumen area percentage
3 m × 4 m without alfalfa	12.2 (d)	62 (c)	94 (b)	28 (b)
3 m × 4 m with alfalfa	13.8 (cd)	67 (b)	103 (ab)	35 (a)
3 m × 6.7 m with alfalfa	14.9 (bc)	69 (ab)	90 (ab)	33 (ab)
3 m × 8 m with alfalfa	16.4 (b)	68 (ab)	89 (ab)	33 (ab)
3 m × 10 m with alfalfa	19.3 (a)	72 (a)	79(a)	32 (ab)

() Duncan's separation grouping results

Table 3. Mean values for annual diameter growth rate and vessel properties of poplar trees

Fig. 8. Radial dimensions of vessel lumen diameter, vessel frequency, and vessel lumen area as a function of ring number from pith to bark in young poplar trees after different treatments; $\diamond = 3 \times 4$ without alfalfa; $\square = 3 \times 4$ with alfalfa; $\Delta = 3 \times 6.7$ with alfalfa; $\circ = 3 \times 8$ with alfalfa; $\times = 3 \times 10$ with alfalfa; A= Vessel lumen diameter; B= Vessel frequency in mm^2 ; C= Vessel lumen area percentage

Although agroforestry systems were found to have positive effects on growth rate, no correlation was found between growth rate and wood properties of six-month-old poplar stems (Jourez *et al.* 2001). However, Doungpet (2005) reported a positive correlation between growth rate (ring width) and vessel lumen diameter (VLD), but negative correlations with VF. Peszlen (1993) investigated three different clones of 10- to 15-year-old poplars and reported that wood properties had no consistent and significant relationship with growth rate. Arnold and Mauseth (1999) reported that low N fertilizer caused reduction of VLD and VF in the cactus species *Cereus peruvianus*. In *Populus deltoides*, deficiencies of nitrogen and sulfur resulted in reduced fiber and vessel diameter (Zobel & van Buijtenen, 1989). These studies suggest that agroforestry systems have the potentiality to significantly affect wood properties.

3.2 Fiber properties

Fiber attributes in trees determine, to some extent, the final quality of pulp and paper (Dinwoodie, 1965). Efhami Sisi *et al.* (2011a), studying the effects of intercropping *Populus*

nigra with alfalfa and initial tree spacing on fiber element attributes, found that fiber diameter and wall thickness significantly increased in tree harvested from tree-alfalfa intercropped plots (Table 4). However, initial-spacing had no significant effect on fiber properties.

Cluster analysis on fiber wall thickness and fiber diameter showed that all three trees of treatment without alfalfa are clustered together (Fig. 9). Although results of Duncan test on fiber length showed the treatment without alfalfa is grouped quite separately, individual trees of this treatment were clustered differently. Also, different trees of treatments with alfalfa were clustered separately. Fiber lumen diameter was not significantly different among treatments. Consequently, fiber wall thickness was the main source of fluctuations in fiber diameter (Table 4).

Table 4 shows that (i) tree diameter and fiber morphological properties of poplar trees in poplar-alfalfa intercropped plots were significantly greater than those in pure poplar stand at all initial tree spacings, (ii) properties of trees in intercropped systems were not significantly different across different initial inter-tree spacings. Therefore, tree-alfalfa intercropping, rather than initial spacing, determined fiber properties in these agroforestry systems.

Treatments	Tree Diameter (cm)	Fiber length (μm)	Fiber wall thickness (μm)	Fiber lumen diameter (μm)	Fiber diameter (μm)
3 m × 4 m without alfalfa	11.4 (c)	895.3 (b)	3.19 (b)	16.8 (ab)	22.2 (b)
3 m × 4 m with alfalfa	14.5 (b)	936.7(ab)	3.91 (a)	17.1 (a)	24.4(a)
3 m × 6.7 m with alfalfa	17.2 (ab)	958.9 (a)	3.88 (a)	17.1 (a)	24.8 (a)
3 m × 8 m with alfalfa	17.5 (ab)	961.0 (a)	3.87 (a)	16.5 (a)	24.9 (a)
3 m × 10 m with alfalfa	18 (a)	957.8(a)	3.93 (a)	16.4 (a)	24.7 (a)

Table 4. Mean values for diameter and fiber morphological parameters of poplar

Fiber length in all treatments increased rapidly from pith to bark. However, fiber diameter and wall thickness showed mild fluctuation (Figs. 10-A & B). The treatment without alfalfa showed a slightly less steep, but still significant, increase in fiber attributes, especially in fiber length. As to the milder changes of fiber attributes in treatment without alfalfa, and considering the definition of juvenile wood as the part of wood that shows severe radial changes in wood properties (Zobel & Sprague, 1989), it may be concluded that intercropping with alfalfa may increase the period to reach wood maturity. However, final decision would be made when older trees are studied. Similar results were also found in vessel attributes of the same treatments (Efhami Sisi et al. 2010). Zobel & Van Buijtenen (1989) reported that nitrogen fertilization increases the period of juvenile wood production. Therefore, it is expected that those trees obtaining more nitrogen would show a more intensified increase in their fiber-length trend.

Fig. 9. Cluster analysis of all 15 trees based on wall thickness of fibers

Fig. 10. Mean characteristics as a function of ring number from pith to bark. A: Fiber length; B: Fiber diameter; C: Fiber wall thickness; D: Ring area. ◇ = 3 m × 4 m without alfalfa; □ = 3 × 4 with alfalfa; Δ = 3 × 6.7 with alfalfa; ○ = 3 × 8 with alfalfa; × = 3 × 10 with alfalfa

Efhami Sisi et al. (2011) observed that the whole-disk fiber length increased with growth rate caused by agro-silvicultural practices as correlated by stem diameter (Fig. 11-A).

Furthermore, weighted fiber diameter and wall thickness showed an increasing trend by stem diameter (Fig. 11-B and C).

Focusing on a positive relationship between whole-disk fiber attributes and growth rate, DeBell et al. (1998) and Doungpet (2005) found that fast-growing trees have more of their basal area concentrated in rings further from the pith than do slower growing trees, and these rings have longer and thicker fibers compared with rings closer to the pith. Thus, whole-disk fiber attributes increased with overall growth rate. Therefore, under similar conditions and with the same age and species, fast-growing young trees have longer and thicker fibers.

A negative effect of growth rate on fiber length was expected, given the existing knowledge about lateral divisions and how they may affect the length of cambial initials, i.e., high rate of anticlinal division is accompanied by short cells (Bannan, 1967). It has been proposed that the cell length in juvenile wood is related to age (Fujiwara & Yang, 2000). However, most of relationships between growth rate and fiber length were not significant at the earlier ages; at the older ages, although some significant relationships were observed, but there were not outstanding (Table 5).

Fig. 11. Mean whole-disk fiber attributes as a function of stem diameter

	Ring 1	Ring 2	Ring 3	Ring 4	Ring 5	Ring 6	Ring 7	Ring 8	Ring 9	Ring 10
Significance level	0.128 NS	0.154 NS	0.018 NS	0.012 NS	0.046 S(+)	0.278 NS	0.008 S (+)	0.076 NS	0.030 S(-)	0.461 NS
R square	0.169	0.150	0.209	0.193	0.273	0.190	0.326	0.222	0.315	0.046

S Statistically significant at the 5% level.
NS Not significant at the 5% level.
() positive (+) or negative (-) correlation

Table 5. Regressions analysis results for correlations between ring width and fiber length (Efhami Sisi et al., 2011a)

The effect of growth rate on shortening the cambial initials would be overshadowed by the subsequently greater elongation of daughter cells in the fast-growing trees (Fujiwara & Yang, 2000; Debell et al. 1998). For example, daughter-cell elongation of fibers in hardwoods averages 140% (Panshin & deZeeuw 1980). It was reported that fiber length was not influenced by growth rate in poplar plantations that are cultivated under different silvicultural practices and had dissimilar growth rates (Snook et al., 1986; DeBell et al., 2002a). Although intercropping and initial spacing have significant effects on fiber dimensions, their effects on tree growth are more influential (Efhami Sisi et al., 2011a). Also, agro-silvicultural practices increase growth rate; but considering the existing knowledge on lateral divisions and how they may affect the length of cambial initials, this increase in growth rate should not necessarily end up in shorter fiber length in young poplar trees as was previously believed.

Debell *et al.* (1998) found that growth rate under different initial spacing had no consistent effect on fiber length within rings of the same age for rings 2-6 of young poplar hybrids although for ring 7 there were positive correlation. They believed that this general relationship will hold for most cultural practices (e.g., increased growing space and supplemental nutrition) that are applied to enhance growth rate. Fujiwara and Yang (2000) reported that there was a positive relationship between fiber length and ring width in mature wood of *Populus tremuloides* Michx. Koubba et al. (1998) reported the correlation between fiber length and growth rate in poplar hybrids varied over the age of the tree. At early ages, correlation between ring width and fiber length was not significant; at older ages, slight negative but significant correlation was found between these two traits. Other studies reported in cultured poplars have concluded that growth rate have no effect on fiber length (Snook et al. 1986; DeBell et al. 2002b). Despite several studies undertaken to assess the effects of growth rate on fiber dimension, the results have been inconclusive.

Under high-nitrogen exposure, xylem fibers were 17% wider and 18% shorter compared to the low nitrogen treatment, and very significant thickening of the fiber cell walls was also observed throughout the stem of trees receiving the high-N treatment (Pitre et al. 2007). Zoble and Van Buijtenen (1989) concluded that N may reduce cell size, wall thickness and specific gravity in hardwoods and increase volume growth, but no generalizations can be made due to interspecific variations especially in the diffuse porous hardwoods.

4. Effects of agroforestry on wood physical properties

4.1 Density and shrinkage of wood

Concerns regarding the physical and mechanical properties of timber harvested from fast growing tree species have been articulated, still more studies should be done because such data from the agroforestry systems are scarce (Shanavas & Kumar, 2006). Evaluation of the effects of chemical fertilizer, spacing, and interplanted nitrogen-fixing trees on wood density of 15-year-old *Eucalyptus saligna* trees showed that (i) wider spacing increased mean diameter by 34%, (ii) the level of chemical fertilization did not affect wood density, and mean diameter of trees, (iii) interplanting of N-fixing *Albizia* trees increased mean diameter by 37%, but did not alter wood density (DeBell et al., 2002). Pith-to-bark profiles of wood density revealed that trees with rapid growth had more uniform wood density patterns across the radius. They conclude that diameter growth (hence, productivity) can be increased substantially through supplemental N and increased growing space without decreasing wood density. Moreover, rapid growth - whether associated with improved nutrition or increased growing space - will result in wood with a more uniform density from pith to bark.

Shanavas & Kumar (2006) evaluated physical and mechanical properties of *Acacia auriculiformis*, *Acacia mangium*, and *Grevillea robusta* trees grown in agroforestry systems and suggested that agroforestry practices per se do not exert any negative impact on wood properties. In another experiment, in older pine and spruce trees, wood density was about the same after as before planting lupines. More growth with more earlywood was obtained but also more latewood was formed. In young pine and spruce though, intercropped with lupines, specific gravity of the wood produced declined (Pechmann and Wutz, 1960). Seven years after establishment of Eucalyptus-Leucaena mixtures, in Brazil, showed that there were no major differences in wood density or holocellulose yields of the eucalypts in the mixture although there was growth response (De Jesus et al., 1988).

The effects of intercropping with alfalfa as well as initial tree spacing on physical variations of *Populus betulifolia* wood were also reported (Efhami Sisi et al., in press). Trees were harvested from an agroforestry trial described in details in Efhami Sisi et al. (2010). Wood density and shrinkage were decreased with alfalfa- *Populus nigra* intercropping while increased by initial spacing (Figs. 12 & 13; Efhami Sisi et al., 2011b). In another study, alfalfa-*Populus nigra* intercropping and initial spacing increased vessel lumen diameter (VLD) and vessel lumen area (VLA), resulting in lower density in this treatment. On the other hand, VLA decreased with increase in initial spacing resulting in higher density. Decrease in wood density caused by direct N-fertilizer was also reported in *Eucalyptus globules* and *P. deltoides* (Raymond & Muneri, 2000). Arnold and Mauseth (1999) reported that low nitrogen fertilizer caused reduction of VLD and VF in the cactus species *Cereus peruvianus*. In *Populus deltoides*, deficiencies of nitrogen and sulfur resulted in reduced fiber and vessel diameter (Zobel & van Buijtenen, 1989). Thus, it can be concluded that the decrease in wood density by alfalfa-intercropping resulted in increase in woody cell-lumen and the consequent wood porosity.

Density had a decreasing trend from pith to bark at breast height, showing similarity with the results of other researcher on different poplar species (Karki, 2001; Doungpet, 2005). Low lumen area of fibers and vessels in the early years of tree growth (Peszlén, 1994; Efhami Sisi et al. 2011a, 2010; Efhami Sisi & Sarayeian, 2009), as well as more extractives in this

section of the stem, may have caused this decrease in density from pith to bark (Zobel & van Buijtenen, 1989).

Fig. 12. Density and volumetric shrinkage variations in wood for 3 × 4 meters treatments with and without alfalfa

Fig. 13. Density and volumetric shrinkage variations in wood for different initial spacings intercropped with alfalfa

4.2 Permeability of wood

Wood permeability, as a physical property, is of vital importance and has great impact on wood and its utilization in different industries (Chen et al., 1998). Permeability is a critical property of porous materials that have continuous-porosity. Many industries need to know how permeable their porous material is so that they could use permeability values in decision-making processes for impregnation, drying, filtration, as well as other purposes. In hardwoods, longitudinal permeability is more important than transversal (radial and tangential) values because of vessel elements orientation along longitudinal axis of trees (Siau, 1971).

Intercropping and initial spacing significantly influences the vessel properties and capillary structures of wood (Efhami Sisi et al., 2010). Permeability is itself influenced by porosity and capillary structure of wood (Siau, 1995). Thus, the effects of agroforestry practices on permeability were investigated on the same treatments (Efhami Sisi et al., 2010).

Fig. 14. Specific longitudinal gas permeability values ($\times 10^{-13} \text{ m}^3 \text{ m}^{-1}$) for the two treatments of 3 $\times$ 4 meters with and without alfalfa

Longitudinal gas permeability values for tree stands with, and without, alfalfa were 1,220.4 and $840.2 \times 10^{-13} \text{ (m}^3 \text{ m}^{-1}\text{)}$ (Fig. 14), respectively. There were no significant differences ($p < 0.05$) in longitudinal gas permeability between tree stands with and without alfalfa which is characteristic of permeability in solid woods (Taghiyari et al., 2010) (Fig. 14). As to the increase in vessel lumen area and vessel lumen diameter caused by intercropping with alfalfa (Table 3), the increase in permeability could have been expected. Furthermore, wider initial spacing showed an increasing effect on both longitudinal and radial gas permeability (Fig. 15).

Fig. 15. Specific longitudinal (left) and radial (right) gas permeability values ($\times 10^{-13} \text{ m}^3 \text{ m}^{-1}$) for the four initial spacings intercropped with alfalfa

A study of longitudinal gas permeability at different tree densities in intercropped treatments (Fig. 15) showed significant growth, caused by increase in initial-spacing, increased VLD and naturally gas permeability would be expected to improve. Longitudinal gas permeability increased by as much as 55% from 3×4 to 3×10, but VLD increased by only 7.2%. Poiseuille's law of viscous flow, which applies to gases through hardwood vessels, proves that there is positive relationship between permeability value and the fourth exponent of the radius of capillary (radius of vessels) (Equation 1) (Siau, 1971).

$$k_l = \frac{n\pi R^4}{8\eta} \times 1.013 \times 10^6 \quad (1)$$

Where:

k_l = longitudinal permeability [cm^3 (fluid) $\text{cm}^{-1} \text{atm}^{-1} \text{sec}^{-1}$]

1 atm = 1.013×10^6 [dyne cm^{-2}]

R = radius of vessels [cm]

$n = N/A$ = number of vessels per cm^2 of cross section

η = viscosity of fluid [dyne sec cm^{-2}]

The fourth exponent of the radius implies that a slight increase or decrease in vessel radius may have a high impact on gas permeability. A similar conclusion was made for longitudinal gas permeability values in *Populus deltoides* (69/55) and 5 trees of *Populus × euroamericana* (cv. I-214) (Taghiyari et al., 2010). However, VLA decreased by 10.2% from 3×4 to 3×10. But, there is a considerable increase in specific gas permeability (55%). Therefore, VLD had a greater effect on gas permeability than VLA.

Chen et al. (1998) studied correlation between different diameter growth rates caused by tree-tree competition and percentage of vessel lumen area (VLA%) in hardwoods, and found no significant correlation in three hardwoods (northern red oak, black walnut, and yellow poplar). However, they still found an increase in permeability in yellow poplar as growth rate increased. They concluded that other factors may also be involved in the increase in longitudinal sapwood permeability. These factors might include VLD and the type of perforation plates between vessel elements. Doungpet (2005) reported correlation coefficient between growth rate and VLA%, vessel frequency (VF), and VLD in six-year old *Populus deltoides* trees to be -0.137, -0.426, and 0.338 respectively. Therefore, an increase in growth rate may eventually result in more vessel diameter and consequently increases permeability values.

5. Conclusion

Current agroforestry practices (intercropping and initial spacing) may significantly influence the growth rate of trees rather than internal wood properties. In agroforestry systems, wider initial spacings are usually used to provide better sunlight for the agricultural crops. However, the wider spacings may have negative effects on the bole form of trees. In order to prevent this negative effect, narrower spacing may be used at the time of stand establishment; while the stand grows and crown of the trees expand, thinning and/or pruning may be used to provide enough sunlight for the agricultural crops. More growth rate induced by intercropping systems may influence wood properties. As to poplar-based

agroforestry systems intercropped with alfalfa in particular, this increase in growth rate should not necessarily end up in shorter fiber length in young poplar trees as was previously believed. In the meantime, intercropping with alfalfa and wider initial spacing may alter the capillary structure of poplar wood in a way that its permeability is increased leading to some improved technical acceptance of wood.

6. Acknowledgment

Authors are grateful to all the contributing people helping us in the compiling of this chapter; Prof. Ali Karimi from UPM for his scientific support; Dr. Farhad Asadi for procurement of the sample trees; Prof. Peter Baas from IAWA journal, Prof. Roshafiza Mohamad and KA Sarifah from The Journal of Tropical Forest Science, Prof. Hubert Hasenauer from The Austrian Journal of Forest Science, and Prof. Ulrich Lüttge and Rob Guy From Trees – Structure and Function Journal for their great help. Also, we would like to deeply thank Dr. Hamid Reza Azemati and Dr. Mohammad Shams from Shahid Rajaei Teacher Training University for their intellectual support.

7. References

- Arnold, D. H. & Mauseth, J.D. (1999). Effect of Environment Factors on Development of Wood. *American Journal of Botany*, Vol.86, No.3, pp. 367-371, ISSN 0002-9122
- Asadi, F. (1994). Investigation of economic-society reasons on decline area cultivated of Poplar in marginal of Zanjan-rood River. M.Sc thesis. Natural Resources College, University of Tehran. 109 pp.
- Asadi, F., Calagari, M., Ghasemi, R., & Bagheri, R. (2005). Investigation of Spacing Effect on Production of Poplar and Alfalfa in Intercropping. *Iranian Journal of Forest and Poplar Research*, Vol.12, No.4, pp. 455-480, ISSN 0883-1735
- Ballard, L.A. & Long, J.N. (1988). Influence of Stand Density on Log Quality of Lodgepole Pine. *Canadian Journal of Forest Research*, Vol.18, No. 7, pp 911-916, ISSN 0045-5067
- Bannan, M.W. (1967). Sequential Changes in Rate of Anticlinal Division, Cambial Cell Length, and Ring Width in the Growth of Coniferous Trees. *Canadian Journal of Botany*, Vol. 45, pp 1359-1369, ISSN 0008-4026
- Barbour, R. J. & Kellogg, R. M. (1990) Forest management and end-product quality: a Canadian perspective. *Canadian Journal of Forest Research*. Vol.20, No. 4, pp 405-417, ISSN 0045-5067
- Barna, M. (2011) Natural regeneration of *Fagus sylvatica* L.: a Review. *Austrian Journal of Forest Science*, Vol.128, No.2, pp 71-91, ISSN 03795292
- Bowyer, J., Shmulsky, R. & Haygreen, J.G. (2007). *Forest products and wood science: an introduction*. Blackwell Publishing Ltd, ISBN-13: 978-0813820361, Oxford, UK.
- Chaudhry, A.K. (2003). Comparative Study of Different Densities of Poplar in Wheat Based Agroforestry System in Central Punjab. PhD thesis, University of Agriculture, Faisalabad, Pakistan.
- Chaudhry, A.K., Khan, G. S., Akhtar, M & Aslam, Z. (2003). Effect of Arable Crops on the Growth of Poplar (*Populus deltoides*) Tree in Agroforestry System. *Palestinian Journal of Agricultural Science*, Vol. 40, No.(1-2), pp 82-85, ISSN 0552-9034

- Chen, P.Y.S., Zhang, G., & Van Sambeek, J.W. (1998). Relationships Among Growth Rate, Vessel Lumen Area, and Wood Permeability for Three Central Hardwood Species. *Forest Products Journal*. Vol.48, No.3, pp 87-90. ISSN: 0015-7473
- De Jesus, R. M., Dias, G. B. N & Cardoso, E.M. (1988). Eucalyptus/Leucaena Mixture Experiment – Growth and Yeild. *IPEF journal*. Vol.39, No.2, pp 41-46, ISSN 0100-4557
- DeBell, J.D.; Gartner, B.L. & DeBell, D.S. (1998). Fiber Length in Young Hybrid *Populus* Stems Grown at Extremely Different Rates. *Canadian Journal of Forest Resource*, Vol.28, No.4, pp 603-608, ISSN 0045-5067
- DeBell, D.S., Christopher R.K. & Barbara L.G. (2002a). Wood density of *Eucalyptus saligna* Grown in Hawaiian Plantations: Effects of Silvicultural Practices and Relation to Growth Rate. *Australian Forestry*, Vol. 64, No. 2, pp. 106-110, ISSN 0004-9158
- DeBell D.S., Singleton, R., Harrington, A. & Gartner, L.B. (2002b). Wood Density and Fiber Length in Young *Populus* Stems: Relation to Clone, Age, Growth rate, and Pruning. *Wood and Fiber Science*, Vol.34, No. 4, pp 529-539, ISSN 0735-6161
- Dinwoodie, J.M. (1965). The Relationship between Fiber Morphology and Paper Properties: A Review of Literature. *Tappi*, Vol.48, pp 440– 447, ISSN 0039-8241
- Doungpet, M. (2005). Environment and Genetic Effects on Wood Quality of *Populus*. PhD thesis. NCS University. Department of wood and paper science. USA.
- Eaglesham, A. R. J.; A. Ayanaba; V. R. Rao & Eskew, D. L. (1981). Improving the Nitrogen Nutrition of Maize by Intercropping With Cowpea. *Soil Biology & Biochemistry*, Vol.13, pp 169-171, ISSN 0038-0717
- Efhami Sisi D., Asadi F., Karimi A., & Pourthamasi K. (2008). Study on the Initial Spacing and Intercropping of Alfalfa on Bole Form and Annual Growth Rate of *Populus nigra betulifolia*. *Proceedings of The 1st Iranian Conference on supplying raw materials and development of Wood and Paper Industries*, Gorgan University of Natural Resources & Agriculture, Iran, December 3-4, 2008
- Efhami Sisi, D & Saraeyan, A.R. (2009). Evaluation of Anatomical and Physical Properties of Juvenile/Mature Wood of *Populus alba* and *Populus × euramericana*. *Iranian Journal of Wood and Paper Science Research*, Vol.24, No.1, pp. 138-151, ISSN 1735-0913
- Efhami Sisi, D.; Karimi, A.N.; Pourtahmasi, K.; Taghiyari, H.R & Asadi, F. (2010). The Effects of Agroforestry Practices on Vessel Properties in *Populus nigra* var. *betulifolia*. *IAWA Journal*, Vol.31, No.4, pp. 781-487, ISSN 0928-1541
- Efhami Sisi D.; Karimi A.N.; Pourtahmasi K.; Taghiyari H.R. (2011a). The Effects of Agroforestry Practices on Fiber Attributes in *Populus nigra* var. *betulifolia*. *Trees-Structure and Function*. DOI 10.1007/s00468-011-0604-4. ISSN 0931-1890
- Efhami Sisi, D.; Karimi, A.N.; Pourtahmasi, K.; Asadi, F. & Mohamadzadeh, M. (2011b). The Effect of agroforestry practices on wood physical properties in Radial and Longitudinal Axis of *Populus nigra*. *Iranian Journal of Scientific Association of Wood & Paper*, (Accepted In Press)
- Fujiwara, S. & Yang, K. C. (2000). The Relationship between Cell Length and Ring Width and Circumference Growth Rate in Five Canadian Species. *IAWA Journal*, Vol. 21, No.3, pp.335-345, ISSN 0928-1541
- Jourez, B., A. Riboux & A. Leclercq. 2001. Anatomical Characteristics of Tension Wood and Opposite Wood in Young Inclined Stems of Poplar (*Populus euramericana* cv 'Ghoy'). *IAWA Journal*. Vol. 22, No. 2, pp 133-157, ISSN 0928-1541

- Karki, T. (2001). Variation of Wood Density and Shrinkage in European Aspen, *Holz als Roh- und Werkstoff*, Vol.59, No. 1/2, pp 13-25. ISSN 0018-3768
- Kollmann F.F.P, Côté W.A. (1968). *Principles of Wood Science and Technology*. I. Solid Wood. Springer, ISBN-10 0387042970, Berlin Heidelberg, New York, 592 pp
- Koubaa, A., R. E. Hernandez, M. Beaudoin & Poliquin, J. (1998). Interclonal, Intraclonal, and Within-Tree Variation in Fiber Length of Poplar Hybrid Clones. *Wood and Fiber Science*. Vol.30, No.1, pp 40-47, ISSN 0735-6161
- Leakey, R. 1996. Definition of Agroforestry Revisited. *Agroforestry Today*, Vol. 8, No.1, pp 5-7, ISSN 1013-9591
- Lundgren, A. L.1981. The Effect of Initial Number of Trees Per Acre and Thinning Densities on Timber Yields From Red Pine plantations the Lake States. Research Paper NC-193. St. Paul, MN: U.S. Dept. of Agriculture, Forest Service, North Central Forest Experiment Station
- Mäkinen, H. (1998). Effect of thinning and natural variation in bole roundness in Scots Pine (*Pinus sylvestris*). *Forest Ecology and Management*, Vol.107, pp 231-239, ISSN: 0378-1127
- Mäkinen, H. & Hein, S. (2006). Effect of Wide Spacing on Increment and Branch Properties of Young Norway Spruce. *European Journal of Forest Research*, Vol.125, No.3, pp 239-248, ISSN 1612-4669
- Malinauskas, A. (1999). The Influence of the Initial Density and Site Conditions on Scots Pine Growth and Wood Quality. *Baltic Forestry*, Vol.5, No.2, pp 8-19, ISSN 1392 - 1355
- Muthuri, C.W., Ong, C.K., Black, C.R., Ngumi, V.W., Mati B.M. (2005). Tree and Crop Productivity in *Grevillea*, *Alnus* and *Paulownia*-Based Agroforestry Systems in Semi-Arid Kenya. *Forest Ecology and Management*, Vol.212, No.1-3, pp 23-39, ISSN 0378-1127
- Otengi, S.B.B., Stigter, C.J., N'ganga, J.K. & Mungai, D.N. (2000). Wind Protection in a Hedged Agroforestry System in Semi-Arid Kenya. *Agroforestry Systems*. Vol.50, No.2, pp 137-156, ISSN 0167-4366
- Panshin, A.J. & C. DeZeeuw. (1980). *Text book of wood technology*, 4th edition, Mc Graw -Hill Publishing Co., ISBN ISBN 0-942391-04-7, New York
- Pechmann, H. Von & Wutz, A. (1960). Haben Mineraldüngung und lupinenaubau einen Kiefernholz? (Do Mineral fertilizer and Planting of Lupines Have any Effect on the Properties of wood of Spruce and Pine?). *Forestwiss. CBL*. Vol.79, No.2, pp 91-105, ISSN 1104-2877
- Peszlen, I. (1993). Influence of site, clone, age, and growth rate on wood properties of three *Populus* × *euramericana* clones. PhD dissertation. Virginia Polytechnic Institute and State University, Blacksburg, Virginia.
- Peszlen, I. (1994). Influence of Age on Selected Anatomical Properties of *Populus* clones. *IAWA Journal*, Vol.15, No.3, pp 311-321, ISSN 0928-1541
- Pitre, E.F., Cooke, J. E. K., & Mackay, J. J. (2007). Short-Term Effects of Nitrogen Availability on Wood Formation and Fiber Properties in Hybrid Poplar. *Trees- Structure & function*, Vol.21, No. 2, pp 249-259, ISSN 0928-1541
- Raymond, C.A. & Muneri, A. (2000). Effect of Fertilizer on Wood Properties of *Eucalyptus globules*. *Canadian Journal of Forest Resource*. Vol.30, No, pp 136-144, ISSN 0045-5067

- Saarsalmi, A., Kukkola, M., Moilanen, M. & Arola, M. (2006). Long-Term Effects of Ash and N Fertilization on Stand Growth, Tree Nutrient Status and Soil Chemistry in a Scots Pine Stand. *Forest Ecology Management*, Vol.235, pp 116–128, ISSN: 0378-1127
- Sea-Lee, S.; P. Vityakon & Prachaiyo, B. (1992). Effects of Erees on Paddy Bunds on Soil Fertility and Rice Growth in Northeast Thailand. *Agroforestry Systems*. Vol.18, No.3, pp 213-223, ISSN: 0167-4366
- Shanavas, A. & Kumar, B.M. (2006). Physical and Mechanical Properties of Three Agroforestry Tree Species from Kerala, India. *Journal of Tropical Agriculture*, Vol.44, No.1-2, pp 23-30, ISSN 0973-5399
- Siau, J.F. (1971). *Flow in Wood*, Syracuse University Press, ISBN 0815650280, New York, pp. 131.
- Siau, J.F. (1995). Wood: Influence of Moisture on Physical Properties; Blacksburg, VA, Department of Wood Science and Forest Products Virginian Polytechnic Institute and State University, 1-63.
- Singh, H. P., Kohli, R. K., & Batish, D. R. (2001) Allelopathic Interference of *Populus deltoides* With Some Winter Season Crop. *Agronomie*, Vol.21, No. 2, pp 139-146, ISSN 0249-5627
- Singh, K., Ram, P., Singh, A. K. & Hussain, A. (1988). Poplar (*Populus deltoides* Batram Ex. Marshall) in forest and agroforestry systems. *Indian Forester*. Vol.114, No.11, pp 814-818, ISSN 0019-4816
- Sjolte-Jorgensen, J. (1967). The Influence of Spacing on the Growth and Development of Coniferous Plantations. *International Revieve of Forest Research*. Vol.2, pp 43-94, ISSN 1465-5489
- Skelton, L. E. (2002). A Comparison of Conventional and Alternative Cropping System Using Alfalfa (*Medicago sativa*) and Winter Wheat (*Triticum aestovim*): An Agroecosystem Analysis. M.S thesis. The University of Georgia.
- Snook, S.K., Labosky, P.L., Bowersox, T.W. & Blankenhorn, P.R. (1986). Pulp and Paper Making Properties of a Hybrid Poplar Clone Grown Under Four Management Strategies and Two Soil Sites. *Wood and Fiber Science*, Vol.18, No.1 , pp 157-167, ISSN 0735-6161
- Taghiyari, H.R. & Sarvari Samadi, Y. (2010). Ultimate Length for Reporting Gas Permeability of *Carpinus betulus* Wood; *Special Topics & Reviews in Porous Media*, Vol.1, No.4, pp 345 – 351, ISSN Print: 2151-4798, ISSN Online: 2151-562X.
- Taghiyari, H.R., Karimi, A.N., Parsapajouh, D. & Pourtahmasi, K. (2010). Study on the Longitudinal Gas Permeability of Juvenile Wood and Mature Wood; *Special Topics & Reviews in Porous Media*, Vol.1, No.1, pp 31 – 38, ISSN Print: 2151-4798, ISSN Online: 2151-562X
- Taghiyari H.R., Efhami Sisi, D., Karimi, A. & Pourtahmasi, K. (2011) The Effect of Initial Spacing on Gas Permeability of *Populus nigra*. *Journal of Tropical Forest Science*, Vol.23, No.3, pp 305-310, ISSN 0128-1283
- Taghiyari HR (2011) Effects of nano-silver on gas and liquid permeability of particleboard. *Digest Journal of Nanomaterials and Bioresources*, Vol. 6, No 4, October-December, pp 1509 – 1517; ISSN 1842 – 3582
- Taghiyari HR, Talaei A., Karimi A. (2011) A correlation between th gas and liquid permeabilities of beech wood heat-treated in hot water and steam mediums. *Maderas. Ciencia y tecnologia*, 13(3): 329 – 336, ISSN 0717-3644 and e-ISSN 0718-221X

- Taghiyari, H.R., Efhami Sisi, D. (2011) Diameter Increment Response of *Populus nigra* var. *betulifolia* Induced by Alfalfa. *Austrian Journal of Forest Science*, Vol.128, No.2, pp 113–127, ISSN 03795292
- Taghiyari HR (2012) Correlation between Gas and Liquid Permeabilities in some Nano-Silver-Impregnated and Untreated Hardwoods. *Journal of Tropical Forest Science*, Accepted: JTFS 24(2): in press on April, 2012 issue, ISSN 0128-1283
- Tisdal L. S., & Nelson L. W. (1974). *Soil Fertility & Fertilizers. Third edition*. Collier Macmillan. pp 402.
- Ulvcrona, K.A., Claesson, S., Sahlen, K. & Lundmark, T. (2007). The Effects of Timing of Pre-Commercial Thinning and Stand Density on Stem Form and Branch Characteristics of *Pinus sylvestris*. *Forestry Advance Access*, Published May 21
- Wodzicki, T.J. (2001). Natural Factors Affecting Wood Structure. *Wood Science and Technology*, Vol.35, No.1-2, pp 5-26, ISSN 0043-7719
- Yin, R.S. (2004). Valuing the Impacts of Agroforestry in Northern China. *Valuing Agroforestry Systems*. pp. 259-280. The Netherlands: Kluwer Academic Publishers.
- Zobel, B.J. & Spargue, J. R. (1998). *Juvenile Wood in Forest Trees*. Springer-Verlag, ISBN-10: 3540640320, New York. 300 pp.
- Zobel, B.J., van Buijtenen, J.P., (1989). *Wood Variation: Its Causes and Control*, Springer-Verlag, ISBN-10: 038750298X, New York, 363 p

IntechOpen

Agroforestry for Biodiversity and Ecosystem Services - Science and Practice

Edited by Dr. Martin Kaonga

ISBN 978-953-51-0493-3

Hard cover, 164 pages

Publisher InTech

Published online 04, April, 2012

Published in print edition April, 2012

Agroforestry has great potential for reducing deforestation and forest degradation, providing rural livelihoods and habitats for species outside formally protected land, and alleviating resource-use pressure on conservation areas. However, widespread adoption of agroforestry innovations is still constrained by a myriad of factors including design features of candidate agroforestry innovations, perceived needs, policies, availability and distribution of factors of production, and perception of risks. Understanding the science, and factors that regulate the adoption, of agroforestry and how they impact the implementation of agroforestry is vitally important. Agroforestry for Biodiversity and Ecosystem Services: Science and Practice examines design features and management practices of some agroforestry practices and their impact on biodiversity and the ecosystem services it delivers. It also identifies policy issues for facilitating adoption of desirable agroforestry practices and gradual diminution of undesirable policies.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Hamid Reza Taghiyari and Davood Efhami Sisi (2012). The Effects of Tree-Alfalfa Intercropped Systems on Wood Quality in Temperate Regions, Agroforestry for Biodiversity and Ecosystem Services - Science and Practice, Dr. Martin Kaonga (Ed.), ISBN: 978-953-51-0493-3, InTech, Available from:
<http://www.intechopen.com/books/agroforestry-for-biodiversity-and-ecosystem-services-science-and-practice/the-effects-of-agroforestry-practices-on-wood-quality>

INTeCH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2012 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](https://creativecommons.org/licenses/by/3.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

IntechOpen

IntechOpen