We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Space Charge–Limited Current Model for Polymers

Syed A. Moiz, Iqbal. A. Khan, Waheed A. Younis and
Khasan S. Karimov

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/63527>

Abstract

Polymers have exceptional charge transport mechanism as a combination of delocalization and localization of charge carriers with intramolecular and intermolecular charge interaction, respectively, and most of the time, it is interpreted with Mott-Gurney space charge–limited current model. As polymers are full of traps, therefore, Mott-Gurney space charge–limited model is modified with various trap distributions as trapped space charge–limited model. The most crucial parameter affected by the nature and distribution of traps is the carrier mobility, and it is argued that space charge–limited model is an acceptable choice for the mobility measurement for polymer. Similarly, in order to account the commonly observed lowering of trap barrier height at higher electric field, the Mott-Gurney space charge–limited current is further modified with little variations, which are evaluated and discussed in detail.

Keywords: polymer electronics, organic semiconductor/polymer, space charge–limited current, charge transport, child's law

1. Introduction

From last few decades, polymer semiconductor-based electronic devices have attracted an enormous deal of interest due to their great achievements both in laboratory and as well as in commercial products [1–10]. Lightweight, flexibility, low-cost, wide-area application, deposition on various substrates, tunability, and many other advantages make these materials an excellent choice for many electronic applications such as light-emitting diode, solar cell, thin-film transistor, laser diode, etc. [11–20]. Another remarkable area of interest for conducting and semiconducting polymer is their application towards highly responsive and low-cost temperature, pressure, humidity, chemical, biochemical, and other types of sensors [21–30].

Despite all of these successes, the complete picture of charge-transport mechanism, which is highly crucial for further achievements, is still not clear [31–40]. Due to such ambiguity, different charge transport models are reported to validate the experimental results performed on various polymer devices [41–54]. Among these charge transport models, space charge–limited current model is counted as highly recited and unanimously accepted charge transport model for disorder organic/polymer semiconductor. In this chapter, we discuss the brief overview of space charge–limited current model with recent development especially for polymer semiconductors.

This chapter starts with the brief discussion of space charge–limited current model and its applications to polymer, especially for conducting and semiconducting polymer. Firstly, the concise overview of historical evaluation and charge transport mechanism of polymer will be discussed. Later on the Child’s Law, Mott-Gurney space charge–limited current model, and trapped space charge–limited current model with single-trap, exponential, and Gaussian distribution of traps and then effects of shallow and deep traps on space charge–limited current are reviewed. Mobility measurement from space charge–limited current and its comparison with other mobility measuring methods such as time-of-flight and different carrier extraction by linearly increasing voltage characteristics are evaluated in the next section. Finally, the application of Poole-Frenkel on space charge–limited equation with other modifications is reviewed before conclusion.

2. Charge transport mechanism of conducting polymer

Before 1977, it was generally considered that polymers are electrically insulator. Most of these insulating polymers such as polyethylene, polystyrene, and polypropylene have almost

Figure 1. (a) Chemical structure of polyacetylene. (b) Comparison of improved conductivity of doped polyacetylene with other conventional materials.

negligible free charge carriers for electrical conductivity. But at the same time, three well-known scientists Heeger, MacDiarmid, and Shirakawa reported a series of great works on the doping of polymer and demonstrated that the proper doping of conjugate polymer improves its conductivity just like as usual semiconductor or metal and they referred it as semiconducting/conducting polymer [3]. They reported first time in the history that the conductivity (10^{-5} S/m) of insulating polyacetylene (molecular structure shown in **Figure 1a**) thin film can be increased by doping it with iodine up to a metallic polyacetylene (10^5 S/m) just like as Cu metal as shown in **Figure 1b**. No doubt, it was a great turning point in the discipline of polymer engineering and caused to initiate a new field as “Organic Electronics” or “Polymer Electronics”. On the basis of their land-mark achievements, Heeger, MacDiarmid, and Shirakawa were awarded Nobel Prize for chemistry in 2000 [2–4].

Figure 2. (a) Sigma (Single bond) hybridization for ethylene, (b) pi (Single bond) hybridization for ethylene and (c) both sigma and pi bond hybridization which give de-localization of pi-electron.

Broadly speaking, conjugate polymers cover the extensive portion of conducting polymers. Conjugate polymers are defined as such polymer which has a combination of alternating double bonds (π bonds) and single bonds (σ bonds) as their backbone structure. As compare to the σ bond, the π bonds are usually unstable in nature and easily ionized or removed. This special combination of single and double bond for conjugate polymer offers a unique arrangement for the de-localization of charge carriers from one end to the other end of polymer chain as extended p-orbital system [19, 55]. This p-orbital overlapping supported with contiguous single bonds allows a de-localization of π -electrons (double-bond electrons are called π -electron offers P_x , P_y , and P_z hybridization for carbon atoms) throughout the double and single-bond combination just as an ethylene as shown in **Figure 2**. Such de-localization of free carriers is the main reason for the charge transport within the molecular chain (intra-molecule) of a conducting polymer [56]. Just for the discussion of σ bond and π bond a simple ethylene (IUPAC name ethene $\text{H}_2\text{C} = \text{CH}_2$) molecular structure is shown here in **Figure 2**. Each carbon makes $\text{sp}^2\text{-sp}^2$ hybridization for π bond and the σ bond is formed between carbon and hydrogen atom. The overall hybridization of σ and π bond is shown in **Figure 2c** for ethylene.

Conducting polymers offer a large number of topological defects as disorder. These defects, such as breaking of bonds in molecular chain, torsion, addition of both internal and external impurity, are produced during the synthesis of polymerization and cause to provide electrical traps for conductivity between molecular chains. Such disorder in conducting polymer presents localization of free carriers inside a molecular chain. Therefore, intermolecular chain transport requires hopping of free carries from one molecular chain to the other molecular chain. So overall, we can say that charge transport in polymer is the combination of both intermolecular and intramolecular charge transport process. Due to the hopping conductivity for intermolecular charge transport, the overall mobility of free carriers for most of polymer is very small as compared to the conventional inorganic semiconductors at normal operating conditions. From charge-transport point of view, there is no fundamental inconsistency between insulating, semiconducting, and conducting polymer except the difference between energy bandgaps, which is larger for insulating polymer semiconductor as compared to semiconducting polymer.

3. Metal-polymer interface

For electronic devices, metal-polymer interface plays a vital role to define the electrical response for conducting polymer. **Figure 3** demonstrates the differences between typical metal-vacuum and metal-polymer interface energy band diagrams for further discussion. Apparently both energy band diagrams look same, but actually different charge injection mechanism is observed in both cases. The Fermi-energy level (E_F) of metal is coincide with E_i of vacuum and as well as with polymer. But the barrier height between E_F of metal and vacuum energy level for metal-vacuum interface is very high as compared to the barrier height between E_F of metal and polymer interface. The barrier height difference between metal E_F and

Figure 3. (a) Metal work function and (b) metal-polymer interface. Energy to inject electron from metal to vacuum is much higher than the required energy to inject electron from metal to polymer/insulator.

vacuum level is defined as metal work function [56]. On the basis of these facts, Mott and Gurneys proposed metal-insulator barrier height reduction theory and justified the low metal-insulator barrier height as compared to the metal work function, which causes space charge–limited current in insulating materials [57]. It is unanimously accepted that Mott and Gurney's proposed space charge–limited current is also valid for most of insulating, semiconducting, and even conducting polymers [31].

4. Bulk-limited and injection-limited current flow

The limitation of current by a polymer can be classified as either (i) injection-limited or (ii) bulk-limited current flow. For injection-limited, the limitation of current through polymer is imposed by non-ohmic metal-polymer interfaces, while for bulk-limited, the limitation is imposed by the bulk properties of polymer. If conducting polymer is sandwiched between two electrodes and any one electrode offers low barrier height ($\sim$ ohmic response) to the polymer-metal interface then the injected carriers from electrode forms a space charge region consisting of a large number of injected carriers and equilibrium free carriers inside polymer. As the mobility of carriers is very small, therefore, before traversing of injected carriers from one to the other electrode, more and more charges are injected. When an external electric field is applied, further charges are injected from low-barrier electrode to the polymer, and an equilibrium stage is reached when injected carriers are comparable or even higher than the free carriers concentration; at this stage, the flow of current is referred as space charge–limited current [57, 58].

5. Child-Langmuir space charge model

Space charge–limited current is a hot topic of research due to their great application for conducting/semiconducting polymers. The origin of space charge theory was founded by C.D. Child and I. Langmuir from 1911 to 1913, when they reported the derivation of space charge–limited current in a parallel-plane vacuum diode as [59, 60]

$$J = \frac{4 \epsilon_0}{9} \sqrt{\frac{2e}{m_e}} \frac{V_a^{\frac{3}{2}}}{d^2} \quad (1)$$

where J is space charge–limited current for vacuum diode, ϵ_0 is the dielectric constant for free space, e is the coulomb charge of electron, m_e is the mass of electron, V_a is the applied (anode) voltage, and d is vacuum spacing between two electrodes. The above equation is reported in the literature with different names such as three-halves power law, Langmuir-Child law. From the equation, it is clear that the space charge current is directly proportional to the three-halves power of the applied voltage and inversely proportional to the square of the displacement between electrodes.

6. Mott-Gurney space charge model

Apparently, Child-Langmuir space charge equation did not find any application for insulator or semiconducting materials due to the presence of vacuum and hence no scattering between electrodes. Therefore, Mott-Gurney proposed another space charge-limited current equation for polymer diode, which is similar to the Child-Langmuir equation with the following assumptions [57].

1. Active layer is trap-free for charge injection
2. Diffusion of carrier is negligible in active layer
3. Electric field at the injecting electrode is zero.

Generally, the assumptions 2 and 3 are still valid for most of organic/polymer semiconducting materials. But for assumption 1, space charge-limited current is further modified with new version as trapped space charge-limited current model and will be discussed in the later section.

When a voltage is applied to an active layer, sandwich between two electrodes as diode, then an electric field (E) is established inside the active layer. Such electric field forces the charges to move with velocity (v) toward another electrode, and therefore, the mobility (μ) of free carrier is defined as

$$v = \mu E \quad (2)$$

Similarly, the current density (J) passing through a semiconductor with conductivity (σ) under the influence of applied electric field E can be defined as

$$J = \sigma E \quad (3)$$

where σ is direct function of both mobility and carrier density of electron $n(x)$ and hole $p(x)$ and can be define as

$$\sigma = e n(x) \mu_n + e p(x) \mu_p \quad (4)$$

If we assume single-carrier devices, then Eq. (4) is simplified as

$$\sigma = e n(x) \mu \quad (5)$$

By incorporating Eq. (5), Eq. (3) becomes as

$$J = en(x)\mu E \quad (6)$$

The injected carriers forms space charge with the distribution of electric field inside insulator and can be defined mathematically by Poisson equation as

$$\frac{dE}{dx} = \frac{en(x)}{\epsilon} \quad (7)$$

By solving all above equation for one-dimension path with boundary conditions $V(0) = V$ and $V(L) = 0$, the pure space charge–limited current without any traps will be obtained as

$$J = \frac{9}{8} \epsilon \epsilon_0 \mu \frac{V^2}{L^3} \quad (8)$$

It is important to note that logarithmic graph ($\log(J) - \log(V)$) of above Eq. (8) yield a straight line with slope 2, which shows trap-free space charge–limited current behavior of polymer between electrodes as sown in **Figure 4**.

Figure 4. Space charge–limited current behavior for polymer semiconductor with only ohmic and trap-free space charge–limited current regions.

Figure 4 shows the ideal current-voltage characteristics of conducting polymer diode, where there are only two regions, one is ohmic region and other is space charge region and both regions can be differentiated with the order of slope. The transition of both ohmic and space charge regions is taken place at specific voltage termed as threshold voltage V_T . At low voltage,

polymer diode offers ohmic behavior ($J \propto V$) with slope at order 1, while at higher voltage, polymer exhibits space charge–limited current ($J \propto V^2$) with slope of an order 2. In other words, there is direct transition is observed from ohmic to space charge–limited region, which is not true in the presence of traps distribution inside polymer.

7. Trapped space charge–limited current model

Generally, an intermediate region is also observed between ohmic to space charge–limited region and this region is termed as trapped space charge region as shown in **Figure 5**. The charge transport inside polymer within this region is controlled by the trapping and de-trapping of carriers at both energetic and positional distribution. Traps are nothing just as impurity and/or structural defects which provide localized states between HOMO (highest occupied molecular orbital) and LUMO (lowest unoccupied molecular orbital) energy bandgap of polymer. These localized states trap the free carriers and avoid them to take any role for charge transport process and degraded the electrical properties of polymer and hence device [61]. When applied voltage is higher than the average energy associated with traps density, then polymer behaves trap-free space charge–limited current as shown in **Figure 5**.

Figure 5. Typical space charge–limited current behavior for polymer semiconductor. Four charge-transport regions are clearly visible (i) ohmic region ($J \propto \mu V$), (ii) trap-SCLC region ($J \propto \mu V^n$) region, (iii) VTFL region ($J \propto \mu N_t d^2$), and (iv) SCLC region ($J \propto \mu V^2$) [31].

The trapped space charge–limited current depends on the distribution of traps state at the energy bandgap of the given polymer. Generally three distributions of electronic traps are reported for conducting polymers. These distributions are as follows:

1. Single energy level trap density.
2. Exponential distribution of trap density.
3. Gaussian distribution of trap density.

7.1. Single energy level trap density

For single energy level trap density (E_T , also called transport energy), the current for trapped space charge–limited current can be little modified as [62]

$$J = \frac{9}{8} \varepsilon \varepsilon_0 \mu \theta \frac{V^2}{L^3} \quad (9)$$

where θ is defined as trap factor and can be correlated with free and trapped carrier density as [63–67]

$$\theta = \frac{n_f}{n_f + n_t} \quad (10)$$

where n_f and n_t are defined as free carrier and trapped carrier density, respectively. The trapped carrier density n_t can be defined with single energy level E_T as

$$n_t = N_T \exp\left(-\frac{(E_T - E_F)}{kT}\right) \quad (11)$$

where N_T , E_F , k , and T can be defined as trap density, Fermi energy level, Boltzmann constant, and ambient temperature, respectively.

7.2. Exponential distribution of traps

Exponential distribution of traps ($g(E)$) with characteristics width of trap energy distribution (E_c) between HOMO and LUMO energy bandgap of polymer can be identified as

$$g(E) = \frac{N_T}{E_c} \exp\left(-\frac{E}{E_c}\right) \quad (12)$$

E_c is correlated with characteristic temperature (T_c) as $E_c = k T_c$. Now, the trapped space charge–limited current for a polymer having exponential distribution of traps can be described as [68–70]

$$J = q^{1-l} \mu_p N_v \left(\frac{2l+1}{l+1}\right)^{l+1} \left(\frac{l\varepsilon_s}{(l+1)N_t}\right)^l \frac{V^{l+1}}{d^{2l+1}}, \quad (13)$$

where $l = T_c / T$ and T is the absolute temperature.

7.3. Gaussian distribution of traps

Bassler proposed Gaussian density of states for polymer material, which are broadened by both energetic and positional disorder [41]. Therefore, many researchers apply Gaussian density of traps ($D_T(E)$) for trapped space charge-limited current as [71].

$$D_t(E) = \frac{N_T}{\sigma\sqrt{2\pi}} \exp\left(-\frac{(E - (E_c - E_T))^2}{2\sigma_T^2}\right) \quad (14)$$

where σ_T is the width of Gaussian distribution traps and $E_c - E_T$ is the trap energy. Similarly Steiger and his workers proved that the Gaussian trapped space charge-limited current follow the same exponential distribution of traps Eq. (13), where l can be redefined as [72]

$$l = \left[1 + \frac{2\pi\sigma^2}{16k^2T^2}\right]^{\frac{1}{2}} \quad (15)$$

If $2\pi\sigma^2 \gg k^2T^2$, then Eq. (15) is further simplified as

$$l = \sqrt{\frac{2\pi}{16}} \frac{\sigma}{kT} \quad (16)$$

8. Photocurrent space charge-limited current model

When light falls on conjugate polymer, huge number of electron and holes are uniformly generated throughout the polymer as free carriers and these carriers move to their respective electrodes as photocurrent under the influence of internal electric field generated by the difference of electrode work-function. If G is the generation rate, L is the length, and q is the electric charge of free carriers, then the photocurrent (J_{ph}) can be defined as [17, 34, 73]

$$J_{ph} = q G L \quad (17)$$

By incorporating the effective thickness of polymer (L) for photocurrent, Eq. (17) can be modified as

$$J_{ph} = q G (\mu_h \tau_h)^{\frac{1}{2}} V^{\frac{1}{2}} \quad (18)$$

where μ_h and τ_h are the mobility and charge carrier life time. Blom et al. observed that the photo-generated current in this region (L) follows space charge–limited current and he derived the fundamental space charge–limited photocurrent equation as [33]

$$J_{ph} = q \left(\frac{9\epsilon_o\epsilon_r\mu_h}{9q} \right) G^{\frac{3}{4}} V^{\frac{1}{2}} \quad (19)$$

Figure 6. Incident light power (ILP) dependence of the photocurrent (J_{ph}) versus the effective voltage ($V_0 - V$) measured at $T = 210$ K. The solid (thick) lines represent the J_{ph} using $\mu_h = 1.2 \times 10^{-7}$ cm²/V s, $\epsilon_r = 2.6$, and $G \propto$ ILP, where ILP was varied from 80 to 6 mW/cm². The arrow indicates the voltage (V_{sat}) at which J_{ph} shows the transition to the saturation regime [33].

where ϵ_o , ϵ_r are the dielectric constant for free air and polymer, respectively. From above equation, Blom et al. experimentally observed that the space charge–limited photocurrent is directly proportional to the three-quarter power of photo-generation rate and half power of voltage as shown in **Figure 6**.

Figure 6 clearly shows that the space charge–limited photocurrent as calculated by Eq. (19) is in contrast with the square-root region for the given voltage range of the experimental results.

9. Shallow and deep traps for space charge–limited current model

Traps not only decrease the mobility for space charge–limited current but also initiate the thermal and electrical degradation for polymer electronic devices. Traps are generally classified as (i) shallow traps, and (ii) deep traps for both electron and hole. If traps are very close to the conduction band (LUMO) within energy bandgap, then traps are classified as shallow traps for electrons. Similarly if traps are in the vicinity of valence band (HOMO) within energy bandgap, then traps are identified as shallow traps for holes as shown in **Figure 8**. On the other hand, deep traps of electron and holes exist far away (mid of the energy bandgap) from conduction (LUMO) and valence (HOMO) band, respectively, as shown in **Figure 7**.

Figure 7. Symbolic representation of shallow and deep traps for polymer semiconductor.

Figure 8. Model simulations of shallow ($E_c - E_t = 0.1$ eV) and deep ($E_c - E_t = 0.5$ eV) trap configurations represented by blue solid lines and red dashed lines. (a) Current density voltage characteristics for a shallow trap and a deep trap are plotted by blue dots and red triangles. Fittings provide the exponent of the voltage. (b) Fermi level representations at 6 V along the thickness, for a shallow trap (blue solid line) and a deep level (red dashed line) [74].

Conventional space charge and trap space charge–limited current model cannot differentiate between shallow and deep traps for both electron and hole. If space charge–limited current is modeled in frequency domain with single traps, then the dynamic picture of the traps can be obtained. By varying the single-trap energy for frequency-domain analysis of space charge–limited current model, it is possible to differential between shallow and deep traps for both electron and polymer with the condition that polymer is sandwiched between properly selected electrodes [74].

10. Mobility measurement and space charge–limited current

The velocity per unit electric field is defined as the mobility for polymer. Mobility is one of the most important parameter, which comprehensively defined the charge transport mechanism of polymer. The efficiency of many polymer electronic devices depends on mobility; therefore, it is very crucial to determine the exact value of mobility [43, 75]. For polymer, mobility can be measured with different methods; some of them are listed as follows:

1. Time-of-flight method [44].
2. Carrier extraction by linearly increasing voltage (CELIV) method [44] and photo-CELIV method [76, 77].
3. Space charge–limited current method [65–67].

Each of this method has some advantages and disadvantages, but these methods are the most commonly used method to determine the mobility of polymer.

10.1. TOF method

The TOF is the most widely used technique for the measurement of mobility. In these techniques, short pulse of light or laser is stroke over the end surface of polymer sample, which result in the generation of photo carriers from the end surface of sample.

$$\mu = \frac{L}{E.T} \quad (20)$$

These photo carriers are immediately swept away from the end surface toward the other end surface through the influence of external DC volts applied at electrodes and give rise to the transient photocurrent as shown in **Figure 9**. The time (T) taken by the photo carriers from one end to the other end surface is calculated from oscilloscope. If E is the applied electric field, L is the thickness of organic layer then the mobility can be calculated as [78].

Figure 9. Schematic setup for typical TOF system for mobility measurements. Here the laser pulse can be illuminated through ITO electrode as well as a semitransparent metal electrode of polymer sample [43].

Figure 10. The schematic Photo CELIV measurement setup is shown. The measuring process consists of two steps. In first step a laser is shine at transparent electrode of sample which generates excess photo carriers. These carriers are extracted by linearly increasing voltage. The peak-extraction time helps to calculate the mobility.

10.2. CELIEV/photo CELIEV method

The charge extraction by increasing the linear voltage is another technique commonly uses to measure the mobility of polymer sandwiched between electrodes. The measuring process consists of two steps. In first step, a laser is shine at transparent electrode of sample which generates excess photo carriers. These carriers are extracted by linearly increasing voltage. The peak-extraction time helps to calculate the mobility of the polymer sample as shown in **Figure 10**. The detail information about these methods can be found in Ref. [79–81].

10.3. Dark-injection space charge–limited mobility measurement

Dark-injection space charge–limited current (DI-SCL) is another commonly used technique for the measurement of mobility for many amorphous, disorder organic/polymer materials [82–85]. To determine the mobility of hole with DI-SCL method, the polymer sample is sandwiched between electrodes and electrodes are managed in such a way that the cathode behaves as blocking electrode and a strong voltage pulse is derived at ohmic anode. The application of voltage pulse will result a transient hole current observed at oscilloscope as shown in **Figure 11**. Therefore, the hole density μ_h can be calculated as

$$\mu_h = \frac{0.787d^2}{V\tau} \quad (21)$$

where τ is the arrival time for early sheet of holes carriers to reach the respective cathode. The τ is correlated with space charge free carrier transit time (τ_{SCL}) as $\tau = 0.787 \tau_{SCL}$ [86, 87].

Figure 11. (a) A sequence of DI signals of Au (treated with UVO)/2TNATA/Au under different applied voltages. The applied voltage varied in steps of 2 V starting from 6 V. (b) An ideal DI-SCLC transient [82].

For both CELIEV and photo-CELIV mobility measurement method, it is not so simple to differential between electron and hole mobility, specially for bipolar charge-transport polymer. Similarly, the TOF method has two series drawbacks (1) the density of photo-generated carrier

is not adequate (very low) to measure the mobility as compare to the usual carrier density at normal operation of many electronic devices, and another drawback is that (ii) TOF method should requires the thickness of polymer above the absorption length of polymer ($>1 \mu\text{m}$) [78]. In the same way, dark-injection space charge–limited current is required the proper selection of electrode for reliable measurements.

Recently, a comprehensive study was performed by Qiu group to compare and evaluate the performance of different mobility measurement methods reported for polymeric materials. They consider various factors such as applied electric field, injection barrier, and energetic disorder, which are crucial for the performance of polymer electronic devices and finally they concluded that the result of both space charge and TOF mobility measurement methods are very close to each other [88]. Therefore, with proper selection of electrodes, space charge–limited mobility measurement is acceptably reliable for most of the cases.

11. Modification of space charge–limited current model

As we discussed earlier, when the current density passing through the polymer with length (L) under the influence of applied voltage (V) shows directly proportional response with the square of voltage ($J \propto V^2$) and inversely proportional to cube of L ($J \propto L^{-3}$) then the polymer sample is modeled with trap-free space charge–limited current. In order to incorporate the variety of the trap distribution, the space charge–limited current model is modified as trapped space charge–limited current model. Traps are both energetically and positional distributed throughout the energy bandgap and capture the free carriers and offer some energy barrier to release them. Both space charge–limited current and trap space charge–limited currents model assume that barrier height of traps are remain constant for entire operating electric field range of the device, which is not true for some of the reported experimental results. In fact, higher electric field lowers the barrier height of traps which cause to increase the emission rate from traps and hence the current density as expected from trap space charge–limited current model as shown in **Figure 12a**. The lowering of trap barrier height or emission rate from traps at high electric field is identified as Poole-Frenkel effect [89], as shown in schematic energy band diagram (**Figure 12b**). There is some similarity between Poole-Frenkel and Schottky models [90, 91] for the lowering of traps barrier height. Schottky model represent barrier height reduction at metal-polymer interface, while Poole-Frenkel model shows the lowering of trap barrier height inside the polymer thin film. The overall current density (J) passing through the polymer due to Poole-Frenkel emission can be written as

$$J = q \mu N_c \exp \left[\frac{-q \left(\phi_T - \sqrt{\frac{q E}{\pi \epsilon_r \epsilon_o}} \right)}{k T} \right] \quad (22)$$

where $q\phi_T$ is trap energy barrier height, and other variables have already defined earlier. Poole-Frenkel behavior can be justified for any polymer device, if a linear relation is obtained between $\ln\left(\frac{J}{E}\right)$ vs $\sqrt{E}$ data derived from their experimental result for such device.

Murgatroyd was the first who addressed the lowering of trap barrier height by incorporating Poole-Frenkel equation into space charge–limited current equation and drive an approximate equation as [92].

$$J = \frac{9}{8} \epsilon_r \epsilon_0 \mu_h \exp(0.89 \gamma \sqrt{E}) \frac{V^2}{L^3} \quad (23)$$

Figure 12. (a) Lowering of energy barrier height of traps at higher electric fields, (b) Pool-Frenkel Effect

Murgatroyd equation is simple and very handy, but it is an approximate equation. Later on, Barbe determined analytically, the effect of trap barrier height reduction on space charge–limited current model and derived an equation as [93, 94]

$$\frac{Jx}{\mu\epsilon\theta} = \frac{2(kT)^4}{\beta^4} \left[\exp\left(\frac{\beta\sqrt{E}}{kT}\right) \left\{ \left(\frac{\beta\sqrt{E}}{kT}\right)^3 - 3\left(\frac{\beta\sqrt{E}}{kT}\right)^2 + 6\frac{\beta\sqrt{E}}{kT} - 6 \right\} + 6 \right] \quad (24)$$

Barbs equation is used to determine the current density (J) as a function of electric field define at position x . It is reported that both these Murgatroyd and Barbe modifications are also applicable with electrical response for many polymers devices [95–99]. As both insulating and semiconducting polymers share the same charge transport mechanism, therefore, above equations are reasonably valid for both types of polymers.

The fundamental work of Frenkel, Murgatroyd, and Barbe is to modify the space charge–limited current to accommodate the lowering of trap barrier height for only in one-dimension trap distribution. For the three-dimension trap distribution, these models not work very well. In this domain, Hartke modification is reasonably accepted for the accommodation of three-dimensional lowering of the trap barrier height for space charge–limited current model [100].

Similarly, Geurst modified the space charge–limited current model in such a way that the thickness of the semiconductor thin film is insignificant with respect to the electrode separation as 2D model [101–104]. While, Chandra derived Mott-Gurney space charge–limited current equation in two dimensions with exponentially distributed traps and other variety of polymer Schottky diodes [105–107].

12. Summary

Despite great recent achievements for conjugate polymer-based electronic devices, the clear picture of charge transport mechanism is still not available. Polymers have unique charge transport mechanism as a combination of delocalization and localization of charge carriers with intramolecular and intermolecular charge interaction, respectively. But it is unanimously believed that Mott-Gurney space charge–limited model is appreciably accepted for most of the polymers. As polymers are full of traps, therefore, Mott-Gurney space charge–limited model is also modified as trapped space charge–limited model according to the requirements of polymers. The nature of traps distribution inside polymer is varied and depends on many factors such as nature of materials itself, polymerization process, nature of dopants, and solvent. Generally, three types of traps distributions are reported in the literature for polymers named as single trap, exponential, and Gaussian distribution of traps. Therefore, trapped space charge–limited current model is further modified to accommodate all these distribution of traps. Just like as distribution of traps the nature of traps, such as shallow and deep traps, is also important to define the electrical response of polymer. The most crucial parameter affected by the distribution and as well as nature of traps is mobility, and space charge–limited current model with little variation is also used to measure the charge mobility of polymer. Different other methods such as time-of-flight method and charge extraction by linearly increasing voltage (CELIV) with or without light (photo–CELIV) sources are available to measure the charge mobility. By comparing these measuring methods for polymer, it is reported that the simple space charge–limited model is an acceptable choice for mobility measurements. Similarly, it is also observed the trap barrier height is significantly reduced at higher electric field and temperature due to Poole-Frenkel effect. Therefore, Murgatroyd and Barbe incorporated Poole-Frenkel effect and solved Mott-Gurney space charge–limited equation numerically

and analytically, respectively. It is reported that both these modifications are experimentally verified with electrical response of many polymers devices.

Acknowledgements

The authors are thankful to Umm Al Qura University and GIK Institute of Engineering Sciences and Technology for its support to this work and the facility used. Authors are also thankful to our PhD and Master students for their cooperation, valuable information, and thoughtful suggestions. Special thanks are due for An-Zhong Lin, M.A. Turaeva, and Kh. Akhmedov for their technical support and helpful discussions.

Author details

Syed A. Moiz^{1*}, Iqbal. A. Khan¹, Waheed A. Younis¹ and Khasan S. Karimov^{2,3}

*Address all correspondence to: moiz_pak@yahoo.com

1 Faculty of Electrical Engineering, Umm Al Qura University, Makkah, Saudi Arabia

2 Physical Technical Institute, Dushanbe, Tajikistan

3 Faculty of Electrical Engineering, GIKI Institute, Topi, Swabi, Pakistan

References

- [1] Liao, C., Zhang, M., Yao, M.Y., Hua, T., Li, L. and Yan, F., 2015. Flexible organic electronics in biology: materials and devices. *Advanced Materials*, 27(46), pp. 7493–7527.
- [2] Forrest, S., Burrows, P. and Thompson, M., 2000. The dawn of organic electronics. *Spectrum, IEEE*, 37(8), pp. 29–34.
- [3] Inokuchi, H., 2006. The discovery of organic semiconductors. Its light and shadow. *Organic electronics*, 7(2), pp. 62–76.
- [4] Heeger, A.J., 2001. Semiconducting and metallic polymers: the fourth generation of polymeric materials (Nobel lecture). *Angewandte Chemie International Edition*, 40(14), pp. 2591–2611.
- [5] Bronstein, H. and King, F.D., 2016. Energetic tuning in spirocyclic conjugated polymers. *Polymers*, 8(1), p. 9.

- [6] Chen, J.D., Cui, C., Li, Y.Q., Zhou, L., Ou, Q.D., Li, C., Li, Y. and Tang, J.X., 2015. Single-junction polymer solar cells exceeding 10% power conversion efficiency. *Advanced Materials*, 27(6), pp. 1035–1041.
- [7] Brütting, W. ed., 2006. *Physics of Organic Semiconductors*. John Wiley & Sons, Ltd., New Jersey, USA.
- [8] Hush, N.S., 2003. An overview of the first half-century of molecular electronics. *Annals of the New York Academy of Sciences*, 1006(1), pp. 1–20.
- [9] Chen, D., Liang, J. and Pei, Q., Flexible and stretchable electrodes for next generation polymer electronics: a review. *Science China Chemistry*, pp. 1–13.
- [10] Jain, A. and George, S.J., 2015. New directions in supramolecular electronics. *Materials Today*, 18(4), pp. 206–214.
- [11] Walzer, K., Maennig, B., Pfeiffer, M. and Leo, K., 2007. Highly efficient organic devices based on electrically doped transport layers. *Chemical Reviews*, 107(4), pp. 1233–1271.
- [12] Petty, M.C., Bryce, M.R. and Bloor, D., 1995. *An Introduction to Molecular Electronics*. Oxford University Press, New York, USA.
- [13] Ye, L. and Hou, J., 2015. Conjugated Polymer Photovoltaic Materials. In *Organic Optoelectronic Materials* (pp. 195–239). Springer International Publishing, Switzerland.
- [14] Geoghegan, M. and Hadziioannou, G., 2013. *Polymer Electronics*, Oxford University Press, New York, USA.
- [15] MacDiarmid, A.G., 2001. “Synthetic metals”: a novel role for organic polymers (Nobel lecture). *Angewandte Chemie International Edition*, 40(14), pp. 2581–2590.
- [16] Shirakawa, H., 2001. The discovery of polyacetylene film: the dawning of an era of conducting polymers (Nobel lecture). *Angewandte Chemie International Edition*, 40(14), pp. 2574–2580.
- [17] Brabec, C.J., Sariciftci, N.S. and Hummelen, J.C., 2001. Plastic solar cells. *Advanced Functional Materials*, 11(1), pp. 15–26.
- [18] You, J., Dou, L., Yoshimura, K., Kato, T., Ohya, K., Moriarty, T., Emery, K., Chen, C.C., Gao, J., Li, G. and Yang, Y., 2013. A polymer tandem solar cell with 10.6% power conversion efficiency. *Nature Communications*, 4, p.1446.
- [19] Gutman, F. and Lyons, L.E., 1981. *Organic semiconductors Part A*. Robert E. Publishing, Malabar, FL.
- [20] Lewis, J., 2006. Material challenge for flexible organic devices. *Materials Today*, 9(4), pp. 38–45.
- [21] Janata, J. and Josowicz, M., 2003. Conducting polymers in electronic chemical sensors. *Nature Materials*, 2(1), pp. 19–24.

- [22] Moiz, S., Karimov, K.S. and Gohar, N.D., 2004. Orange dye thin film resistive hygrometers. *Eurasian Chemico-Technological Journal*, 6(3), pp. 179–183.
- [23] Karimov, K.S., IBRAHIM, I.N., Tahir, M.M., Khan, T.A. and Shafique, U., 2008. Photo organic field effect transistor's properties. *Turkish Journal of Physics*, 32(1), pp. 13–19.
- [24] Karimov, K.H., Ahmed, M.M., Karieva, Z.M., Saleem, M., Mateen, A. and Moiz, S.A., 2011. Humidity sensing properties of carbon nano-tube thin films. *Sensor Letters*, 9(5), pp. 1649–1653.
- [25] Karimov, K., Ahmed, M.M., Noshin, F., Saleem, M., Mahroof-Tahir, M., Moiz, S.A., Akhmedov, K.M., Zahid, M., Abbas, S.Z. and Rashid, A., 2015. Nickel phthalocyanine based organic photo transistor: effect of semiconductor film thickness. *The European Physical Journal Applied Physics*, 72(2), p. 20202.
- [26] Karimov, K.S., Moiz, S.A., Tahir, M.M., Ahmed, N., Tariq, R., Abbas, S.Z. and Zafar, Q., 2014. Nickel phthalocyanine-metal Schottky diode as photodetector. *Journal of Optoelectronics and Advanced Materials*, 16(11–12), pp. 1430–1435.
- [27] Karimov, K.S., Saeed, M.T., Khalid, F.A. and Moiz, S.A., 2011. Effect of displacement on resistance and capacitance of polyaniline film. *Chinese Physics B*, 20(4), p.040601.
- [28] Karimov, K.S., Sayyad, M.H., Ahmed, M.M., Khan, M.N., Karieva, Z.M., Moiz, S.A., Shah, M., Zakaullah, K. and Turaeva, M.A., 2004. Effect of temperature and humidity on electrical properties of organic orange dye complex films'. *Eurasian Chemical Technological Journal*, 6, pp. 145–149.
- [29] Khan, A., Karimov, K.S., Ahmad, Z., Sulaiman, K., Shah, M. and Moiz, S.A., 2014. Pressure sensitive organic sensor based on CNT-VO₂ (3fl) Composite. *Sains Malaysiana*, 43(6), pp. 903–908.
- [30] Chani, M.T.S., Karimov, K.S., Khalid, F.A. and Moiz, S.A., 2013. Polyaniline based impedance humidity sensors. *Solid state sciences*, 18, pp. 78–82.
- [31] Peter, S., 2009. *Electrical Characterization of Organic Electronic Materials and Devices*, John Wiley and Sons, Ltd., New Jersey, USA.
- [32] Moiz, S.A., Nahhas, A.M., Um, H.D., Jee, S.W., Cho, H.K., Kim, S.W. and Lee, J.H., 2012. A stamped PEDOT: PSS–silicon nanowire hybrid solar cell. *Nanotechnology*, 23(14), p. 145401.
- [33] Mihailetchi, V.D., Wildeman, J. and Blom, P.W.M., 2005. Space-charge limited photocurrent. *Physical review letters*, 94(12), p.126602.
- [34] Blom, P.W., Mihailetchi, V.D., Koster, L.J.A. and Markov, D.E., 2007. Device physics of polymer: fullerene bulk heterojunction solar cells. *Advanced Materials*, 19(12), pp. 1551–1566.
- [35] Sirringhaus, H., Brown, P.J., Friend, R.H., Nielsen, M.M., Bechgaard, K., Langeveld-Voss, B.M.W., Spiering, A.J.H., Janssen, R.A., Meijer, E.W., Herwig, P. and De Leeuw,

- D.M., 1999. Two-dimensional charge transport in self-organized, high-mobility conjugated polymers. *Nature*, 401(6754), pp. 685–688.
- [36] Moiz, S.A., Imran, S.M., Nahhas, A.M., Karimov, K.S. and Kim, H.T., 2014. Effect of solvent on Meyer-Neldel rule for conducting polyaniline thin film. *Journal of Optoelectronics and Advanced Materials*, 16(11–12), pp. 1405–1410.
- [37] Moiz, S.A., Ahmed, M.M. and Karimov, K.S., 2005. Effects of temperature and humidity on electrical properties of organic semiconductor orange dye films deposited from solution. *Japanese Journal of Applied Physics*, 44(3R), p. 1199.
- [38] Ahmed, M.M., Karimov, K.S. and Moiz, S.A., 2004. Temperature-dependent IV characteristics of organic-inorganic heterojunction diodes. *Electron Devices, IEEE Transactions on*, 51(1), pp. 121–126.
- [39] Sayyad, M.H., Karimov, K.S., Ellahi, A. and Moiz, S., 2005. The photo-electrical behavior of n-Si and p-Si/orange dye/conductive glass cells. *Eurasian Chemico-Technological Journal*, 7(2), pp. 133–137.
- [40] Karimov, K.S., Akhmedov, K.M., Dzhuraev, A.A., Khan, M.N., Abrarov, S.M. and Fiodorov, M.I., 2000. Organic-on-inorganic Ag/n-GaAs/p-CuPc/Ag photoelectric sensor. *Eurasian Chemico-Technological Journal*, 2(3–4), pp. 251–256.
- [41] Bässler, H., 1993. Charge transport in disordered organic photoconductors a Monte Carlo simulation study. *Physica Status Solidi(b)*, 175(1), pp. 15–56.
- [42] Taylor, D.M., 2006. Space charges and traps in polymer electronics. *IEEE Transactions on Dielectrics and Electrical Insulation*, 5(13), pp. 1063–1073.
- [43] Kokil, A., Yang, K. and Kumar, J., 2012. Techniques for characterization of charge carrier mobility in organic semiconductors. *Journal of Polymer Science Part B: Polymer Physics*, 50(15), pp. 1130–1144.
- [44] Campbell, A.J., Bradley, D.D. and Antoniadis, H., 2001. Dispersive electron transport in an electroluminescent polyfluorene copolymer measured by the current integration time-of-flight method. *Applied Physics Letters*, 79(14), pp. 2133–2135.
- [45] Wang, Yan-Ping, Jin-Ying Huang, Jiang-Shan Chen, Xian-Feng Qiao, De-Zhi Yang, Dong-Ge Ma, and Li-Song Dong, 2016. “The Hole Transport Characteristics of 1, 4, 5, 8, 9 and 11-Hexaazatriphenylene-Hexacarbonitrile by Blending. *Chinese Physics Letters* 33(2), p. 027302.
- [46] Coropceanu, V., Cornil, J., da Silva Filho, D.A., Olivier, Y., Silbey, R. and Brédas, J.L., 2007. Charge transport in organic semiconductors. *Chemical Reviews*, 107(4), pp. 926–952.
- [47] Brédas, J.L., Calbert, J.P., da Silva Filho, D.A. and Cornil, J., 2002. Organic semiconductors: a theoretical characterization of the basic parameters governing charge transport. *Proceedings of the National Academy of Sciences*, 99(9), pp. 5804–5809.

- [48] Pivrikas, A., Sariciftci, N.S., Juška, G. and Österbacka, R., 2007. A review of charge transport and recombination in polymer/fullerene organic solar cells. *Progress in Photovoltaics: Research and Applications*, 15(8), pp. 677–696.
- [49] Karimov, K.S., Sayyad, M.H., Ali, M., Khan, M.N., Moiz, S.A., Khan, K.B., Farah, H. and Karieva, Z.M., 2006. Electrochemical properties of Zn/orange dye aqueous solution/carbon cell. *Journal of Power Sources*, 155(2), pp. 475–477.
- [50] Karimov, K.S., Ahmed, M.M., Moiz, S.A., Babadzhanov, P., Marupov, R. and Turaeva, M.A., 2003. Electrical properties of organic semiconductor orange nitrogen dye thin films deposited from solution at high gravity. *Eurasian ChemTech J*, 5, pp. 109–113.
- [51] Karimov, K.S., Ahmed, M.M., Moiz, S.A. and Fedorov, M.I., 2005. Temperature-dependent properties of organic-on-inorganic Ag/p-CuPc/n-GaAs/Ag photoelectric cell. *Solar Energy Materials and Solar Cells*, 87(1), pp. 61–75.
- [52] Takeshita, S., Modeling of space-charge limited current injection incorporating an advanced model of the Poole–Frenkel effect, MS thesis, Electrical Engineering Clemson University, 2008, Clemson, USA.
- [53] Laquai, F., Andrienko, D., Mauer, R. and Blom, P.W., 2015. Charge carrier transport and photo generation in P3HT: PCBM photovoltaic blends. *Macromolecular Rapid Communications*, 36(11), pp. 1001–1025.
- [54] Ahmed, M.M., Karimov, K.S. and Moiz, S.A., 2008. Photoelectric behavior of n-GaAs/orange dye, vinyl-ethynyl-trimethyl-piperidole/conductive glass sensor. *Thin Solid Films*, 516(21), pp. 7822–7827.
- [55] Molapo, K.M., Ndangili, P.M., Ajayi, R.F., Mbambisa, G., Mailu, S.M., Njomo, N., Masikini, M., Baker, P. and Iwuoha, E.I., 2012. Electronics of conjugated polymers (I): polyaniline. *International Journal of Electrochemical Science*, 7(12), pp. 11859–11875.
- [56] Salaneck, W.R., Friend, R.H. and Brédas, J.L., 1999. Electronic structure of conjugated polymers: consequences of electron–lattice coupling. *Physics Reports*, 319(6), pp. 231–251.
- [57] Mott, N.F. and Gurney, R.W., 1940. *Electronic Processes in Ionic Crystals*. Oxford University Press, New York.
- [58] Ng, K.K., *Complete Guide to Semiconductor Devices*, 2nd ed., John Wiley & Sons, New York, 2002.
- [59] Child, C.D., 1911. Discharge from hot CaO. *Physical Review (Series I)*, 32(5), p. 492.
- [60] Lau, Y.Y., 2001. Simple theory for the two-dimensional Child–Langmuir law. *Physical Review Letters*, 87(27), p. 278301.
- [61] Schmechel, R. and Von Seggern, H., 2004. Electronic traps in organic transport layers. *Physica Status Solidi (a)*, 201(6), pp. 1215–1235.

- [62] Lampert, M.A., 1964. Volume-controlled current injection in insulators. *Reports on Progress in Physics*, 27(1), p. 329.
- [63] Moiz, S.A., Ahmed, M.M. and Karimov, K.S., 2005. Estimation of electrical parameters of OD organic semiconductor diode from measured IV characteristics. *ETRI Journal*, 27(3), pp. 319–325.
- [64] Moiz, S.A., Ahmed, M.M., Karimov, K. and Mehmood, M., 2007. Temperature-dependent current–voltage characteristics of poly-N-epoxypropylcarbazole complex. *Thin Solid Films*, 516(1), pp. 72–77.
- [65] Moiz, S.A., Ahmed, M.M., Karimov, K.S., Rehman, F. and Lee, J.H., 2009. Space charge limited current–voltage characteristics of organic semiconductor diode fabricated at various gravity conditions. *Synthetic Metals*, 159(13), pp. 1336–1339.
- [66] KARIMOV, K., Qazi, I., Moiz, S.A. and Murtaza, I., 2008. Electrical properties of organic semiconductor copper phthalocyanine thin films deposited from solution at high gravity. *Optoelectronics and Advanced Materials – Rapid Communications*, 2(4), pp. 219–223.
- [67] Moiz, S.A. and Nahhas, A.M., 2013. Temperature Dependent Electrical Response of Orange-Dye Complex Based Schottky Diode. *International Journal of Electronics and Communication Engineering & Technology (IJECEt)*, 4(2), pp. 269–279.
- [68] Mandoc, M.M., De Boer, B. and Blom, P.W.M., 2006. Electron-only diodes of poly (dialkoxy-p-phenylene vinylene) using hole-blocking bottom electrodes. *Physical Review B*, 73(15), p. 155205.
- [69] Van Mensfoort, S.L.M., Billen, J., Vulto, S.I.E., Janssen, R.A.J. and Coehoorn, R., 2009. Electron transport in polyfluorene-based sandwich-type devices: quantitative analysis of the effects of disorder and electron traps. *Physical Review B*, 80(3), p. 033202.
- [70] Mark, P. and Helfrich, W., 1962. Space-charge-limited currents in organic crystals. *Journal of Applied Physics*, 33(1), pp. 205–215.
- [71] Nicolai, H.T., Mandoc, M.M. and Blom, P.W.M., 2011. Electron traps in semiconducting polymers: exponential versus Gaussian trap distribution. *Physical Review B*, 83(19), p. 195204.
- [72] Steiger, J., Schmechel, R. and Von Seggern, H., 2002. Energetic trap distributions in organic semiconductors. *Synthetic Metals*, 129(1), pp. 1–7.
- [73] Goodman, A.M. and Rose, A., 1971. Double extraction of uniformly generated electron-hole pairs from insulators with non injecting contacts. *Journal of Applied Physics*, 42(7), pp. 2823–2830.
- [74] Montero, J.M., Bisquert, J., Garcia-Belmonte, G., Barea, E.M. and Bolink, H.J., 2009. Trap-limited mobility in space-charge limited current in organic layers. *Organic Electronics*, 10(2), pp. 305–312.

- [75] Koo, Y.M., Choi, S.J., Chu, T.Y., Song, O.K., Shin, W.J., Lee, J.Y., Kim, J.C. and Yoon, T.H., 2008. Ohmic contact probed by dark injection space-charge-limited current measurements. *Journal of Applied Physics*, 104(12), p. 123707.
- [76] Juška, G., Arlauskas, K., Viliūnas, M. and Kočka, J., 2000. Extraction current transients: new method of study of charge transport in microcrystalline silicon. *Physical Review Letters*, 84(21), p. 4946.
- [77] Mozer, A.J., Sariciftci, N.S., Lutsen, L., Vanderzande, D., Österbacka, R., Westerling, M. and Juška, G., 2005. Charge transport and recombination in bulk heterojunction solar cells studied by the photoinduced charge extraction in linearly increasing voltage technique. *Applied Physics Letters*, 86(11), p. 112104.
- [78] Markham, J.P., Anthopoulos, T.D., Samuel, I.D., Richards, G.J., Burn, P.L., Im, C. and Bäessler, H., 2002. Nondispersive hole transport in a spin-coated dendrimer film measured by the charge-generation-layer time-of-flight method. *Applied Physics Letters*, 81(17), pp. 3266–3268.
- [79] Juška, G., Arlauskas, K., Viliūnas, M., Genevičius, K., Österbacka, R. and Stubb, H., 2000. Charge transport in π -conjugated polymers from extraction current transients. *Physical Review B*, 62(24), p. R16235.
- [80] Hanfland, R., Fischer, M.A., Brütting, W., Würfel, U. and MacKenzie, R.C., 2013. The physical meaning of charge extraction by linearly increasing voltage transients from organic solar cells. *Applied Physics Letters*, 103(6), p.063904.
- [81] Neukom, M.T., Reinke, N.A. and Ruhstaller, B., 2011. Charge extraction with linearly increasing voltage: a numerical model for parameter extraction. *Solar Energy*, 85(6), pp. 1250–1256.
- [82] Cheung, C.H., Kwok, K.C., Tse, S.C. and So, S.K., 2008. Determination of carrier mobility in phenylamine by time-of-flight, dark-injection, and thin film transistor techniques. *Journal of Applied Physics*, 103(9), p.093705.
- [83] Abkowitz, M., Facci, J.S. and Stolka, M., 1993. Behavior of an ideal injecting contact on a trap-free polymer. *Applied Physics Letters*, 63(14), pp. 1892–1894.
- [84] Campbell, A.J., Bradley, D.D., Antoniadis, H., Inbasekaran, M., Wu, W.W. and Woo, E.P., 2000. Transient and steady-state space-charge-limited currents in polyfluorene copolymer diode structures with ohmic hole injecting contacts. *Applied Physics Letters*, 76(13), pp. 1734–1736.
- [85] Campbell, I.H., Smith, D.L., Neef, C.J. and Ferraris, J.P., 1999. Consistent time-of-flight mobility measurements and polymer light-emitting diode current-voltage characteristics. *Applied Physics Letters*, 74(19).
- [86] Lampert, M.A. and Mark, P., 1970. *Current Injection in Solids*. Academic Press, New York, USA.

- [87] Kao, K.C. and Hwang, W., 1981. *Electrical Transport in Solids Semiconductors*, Pergamon Press, Oxford, New York, USA.
- [88] Li, H., Duan, L., Zhang, D. and Qiu, Y., 2014. Electric field inside a hole-only device and insights into space-charge-limited current measurement for organic semiconductors. *The Journal of Physical Chemistry C*, 118(19), pp. 9990–9995.
- [89] Frenkel, J., 1938. On pre-breakdown phenomena in insulators and electronic semiconductors. *Physical Review*, 54(8), p.647.
- [90] Moiz, S.A., Jee, S.W., Um, H.D. and Lee, J.H., 2010. Electrical characterization of metal–silicon microwire interface using conductive atomic force microscope. *Japanese Journal of Applied Physics*, 49(4R), p.045003.
- [91] Jee, S.W., Kim, J., Jung, J.Y., Um, H.D., Moiz, S.A., Yoo, B., Cho, H.K., Park, Y.C. and Lee, J.H., 2010. Ni-catalyzed growth of silicon wire arrays for a Schottky diode. *Applied Physics Letters*, 97(4), p.042103.
- [92] Murgatroyd, P.N., 1970. Theory of space-charge-limited current enhanced by Frenkel effect. *Journal of Physics D: Applied Physics*, 3(2), p.151.
- [93] Barbe, D.F., 1971. Space-charge-limited current enhanced by Frenkel effect. *Journal of Physics D: Applied Physics*, 4(11), p.1812.
- [94] Barbe, D.F. and Westgate, C.R., 1970. Bulk trapping states in β -phthalocyanine single crystals. *The Journal of Chemical Physics*, 52(8), pp. 4046–4054.
- [95] Mihailitchi, V.D., Xie, H.X., de Boer, B., Koster, L.A. and Blom, P.W., 2006. Charge transport and photocurrent generation in poly (3-hexylthiophene): methanofullerene bulk heterojunction solar cells. *Advanced Functional Materials*, 16(5), pp. 699–708.
- [96] Malliaras, G.G., Salem, J.R., Brock, P.J. and Scott, C., 1998. Electrical characteristics and efficiency of single-layer organic light-emitting diodes. *Physical Review B*, 58(20), p. R13411.
- [97] Goh, C., Kline, R.J., McGehee, M.D., Kadnikova, E.N. and Fréchet, J.M., 2005. Molecular-weight-dependent mobilities in regioregular poly (3-hexyl-thiophene) diodes. *Applied Physics Letters*, 86(12), p. 122110.
- [98] Schwartz, G., Pfeiffer, M., Reineke, S., Walzer, K. and Leo, K., 2007. Harvesting triplet excitons from fluorescent blue emitters in white organic light-emitting diodes. *Advanced Materials*, 19(21), pp. 3672–3676.
- [99] Gao, W. and Kahn, A., 2002. Electronic structure and current injection in zinc phthalocyanine doped with tetrafluoro tetracyano quino di methane: interface versus bulk effects. *Organic Electronics*, 3(2), pp. 53–63.
- [100] Hartke, J.L., 1968. The three-dimensional Poole-Frenkel effect. *Journal of Applied Physics*, 39(10), pp. 4871–4873.

- [101] Geurst, J.A., 1966. Theory of space-charge-limited currents in thin semiconductor layers. *Physica Status Solidi(b)*, 15(1), pp. 107–118.
- [102] Grinberg, A.A., Luryi, S., Pinto, M.R. and Schryer, N.L., 1989. Space-charge-limited current in a film. *Electron Devices, IEEE Transactions on*, 36(6), pp. 1162–1170.
- [103] Jurchescu, O.D. and Palstra, T.T., 2006. Crossover from one-to two-dimensional space-charge-limited conduction in pentacene single crystals. *Applied Physics Letters*, 88(12), p. 122101.
- [104] Fraboni, B., Fraleoni-Morgera, A. and Cavallini, A., 2010. Three-dimensional anisotropic density of states distribution and intrinsic-like mobility in organic single crystals. *Organic Electronics*, 11(1), pp. 10–15.
- [105] Chandra, W., Ang, L.K., Pey, K.L. and Ng, C.M., 2007. Two-dimensional analytical Mott–Gurney law for a trap-filled solid. *Applied Physics Letters*, 90(15), p. 153505.
- [106] Chandra, W., Ang, L.K. and Koh, W.S., 2009. Two-dimensional model of space charge limited electron injection into a diode with Schottky contact. *Journal of Physics D: Applied Physics*, 42(5), p. 055504.
- [107] Chandra, W. and Ang, L.K., 2010. Space charge limited current in a gap combined of free space and solid. *Applied Physics Letters*, 96(18), p. 183501.

IntechOpen