We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Controlled Thiolate-Protected Gold and Alloy Clusters

Bharat Kumar, Yoshiki Niihori,
Wataru Kurashige and Yuichi Negishi

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/67833>

Abstract

Small metal clusters exhibit physical and chemical properties that differ substantially from those of corresponding bulk metals. Furthermore, the properties of clusters vary greatly depending on the number of constituent atoms. Metal clusters with these characteristics currently attract great attention in a wide range of fields as new nanoscale functional materials. In recent years, the techniques to precisely synthesize metal clusters protected with organic ligands and polymers with atomic precision have advanced dramatically. In addition, substantial knowledge of the size-specific physical/chemical properties exhibited by these metal clusters has been accumulated. In this chapter, we describe the precise synthesis methods of the most studied thiolate (SR)-protected gold clusters $\text{Au}_n(\text{SR})_m$ and their heteroatom-substituted clusters (alloy clusters).

Keywords: gold clusters, alloy clusters, precise synthesis, fractionation, size focusing, metal exchange

1. Introduction

Substances in our surroundings are composed of assemblies of atoms. For example, a metal is a conglomerate of a nearly infinite number of metal atoms. By contrast, certain substances are made up of a countable number of metal atoms. These substances are called “metal clusters” because their shape resembles grape clusters. Although no clear definition of metal clusters has been established, the term generally refers to an aggregate of two to several hundred metal atoms (**Figure 1**); most such aggregates have a superfine size of 2 nm or less.

The proportion of surface atoms in metal clusters differs substantially from that in bulk metals. Taking a metal cluster with an icosahedral structure as an example, a metal cluster with

Figure 1. Relation of metal clusters discussed in this chapter to a single atom and the bulk metal.

55 atoms (**Figure 1**) has 42 surface atoms, corresponding to 76.3% of the total atom number. In the case of a 13-atom metal cluster (**Figure 1**), 12 atoms are on the surface, corresponding to 92.3% of the total atoms. In bulk metals (**Figure 1**), the proportion of surface atoms is only approximately 0.00001% in a cube of 1 cm³. Thus, compared with bulk metals, metal clusters have a much higher proportion of surface atoms available to react with other substances. Moreover, in addition to these geometric features, metal clusters also exhibit particular characteristics related to their electronic structures. Bulk metals have an electronic structure in which the valence and conduction bands are connected. Conversely, discretization of the electronic structure occurs in metal clusters because of the small number of constituent atoms.

Because of these geometric and electronic features, metal clusters exhibit physical and chemical properties that differ from those of the corresponding bulk metals. For example, although bulk gold (Au) is an inactive metal, as its size decreases to the cluster level, Au exhibits high catalytic activity in various oxidation and reduction reactions [1, 2]. Furthermore, the size-specific properties of clusters greatly vary depending on the number of constituent atoms. **Figure 2** shows a photograph of aqueous solutions of thiolate (SR)-protected Au clusters (approximately 1 nm in size) with 10–39 gold atoms [3]. The color of the cluster solutions differs substantially depending on the number of constituent atoms in the clusters. This diversity of colors can be attributed to the aforementioned discrete electronic structure of clusters.

As illustrated above, metal clusters exhibit physical and chemical properties that differ substantially from those of bulk metals despite being composed of the same elements. Furthermore, the properties of clusters vary greatly depending on the number of constituent atoms. Because of their very small size, clusters contribute to the miniaturization of materials and conservation of resources. Thus, metal clusters currently attract great attention in a wide range of fields as new nanoscale functional materials.

Figure 2. Photograph of aqueous solutions of glutathionate-protected Au_n clusters [3].

In recent years, the atomically precise synthesis of metal clusters protected with organic ligands [4–19] and polymers [20, 21] has advanced dramatically. In addition, substantial knowledge about the size-specific physical/chemical properties exhibited by these metal clusters has been gathered. In this chapter, we describe the precise synthesis methods of the most-studied SR-protected Au clusters, $\text{Au}_n(\text{SR})_m$, and their heteroatom-substituted clusters, which are called alloy clusters.

2. Gold clusters

As described in Section 1, the properties of metal clusters vary greatly depending on the number of constituent atoms (**Figure 2**). Therefore, it is important to synthesize clusters with atomic precision to produce clusters with controlled functions. Typically, $\text{Au}_n(\text{SR})_m$ clusters with a defined number of constituent atoms are synthesized by one of the following four methods [22]:

- (i) High-resolution separation of a mixture of clusters of various sizes according to the number of constituent atoms (**Figure 3(a)**).
- (ii) Exposure of a mixture of clusters of various sizes to extreme conditions followed by the collection of only those clusters stable under such conditions (**Figure 3(b)**).

Figure 3. Typical methods for the precise synthesis of $\text{Au}_n(\text{SR})_m$ clusters [22]: (a) fractionation, (b) size focusing, (c) slow reduction, and (d) transformation from one stable size to another.

- (iii) Controlling the growth rate of the clusters to obtain a uniform chemical composition (**Figure 3(c)**).
- (iv) Replacing the ligands of the cluster with ligands having different bulkiness to render clusters with a different chemical composition stable (**Figure 3(d)**).

Hereafter, each of these methods is explained in detail.

2.1. Fractionation

$\text{Au}_n(\text{SR})_m$ clusters are generally prepared by adding a reducing agent to a solution containing a thiol and Au ions [23]. The aggregation of the resultant Au atoms leads to the formation of $\text{Au}_n(\text{SR})_m$ clusters, and the products obtained by this method normally have a distribution in their number of constituent atoms [3, 4, 24–29]. The high-resolution separation of such a mixture according to the number of atoms is one of the most efficient methods of obtaining $\text{Au}_n(\text{SR})_m$ clusters with well-defined numbers of constituent atoms (**Figure 3(a)**).

Polyacrylamide gel electrophoresis is a highly effective technique for separating hydrophilic SR-protected $\text{Au}_n(\text{SR})_m$ clusters [3, 25, 26, 30, 31]. Using this method, clusters, such as $\text{Au}_{10}(\text{SG})_{10}$, $\text{Au}_{15}(\text{SG})_{13}$, $\text{Au}_{18}(\text{SG})_{14}$, $\text{Au}_{22}(\text{SG})_{16}$, $\text{Au}_{22}(\text{SG})_{17}$, $\text{Au}_{25}(\text{SG})_{18}$, $\text{Au}_{29}(\text{SG})_{20}$, $\text{Au}_{33}(\text{SG})_{22}$, and $\text{Au}_{39}(\text{SG})_{24}$ (SG = glutathionate), have been isolated with high purity (**Figure 4(a)**) [3]. Fractional precipitation [32] and fractional extraction [33–35] have been primarily employed to separate hydrophobic RS-protected $\text{Au}_n(\text{SR})_m$ clusters. In addition to these frequently used conventional methods, reverse-phase high-performance liquid chromatography has also recently proved very effective for the high-resolution separation of both types of $\text{Au}_n(\text{SR})_m$ clusters [27–29, 36–38]. $\text{Au}_n(\text{SC}_{12}\text{H}_{25})_m$ clusters with a wide range of sizes, from $\text{Au}_{38}(\text{SC}_{12}\text{H}_{25})_{24}$ to $\text{Au}_{\sim 520}(\text{SC}_{12}\text{H}_{25})_{\sim 130}$, have been systematically isolated by this method (**Figure 4(b)**) [28]. Thus, several methodologies have been established to date for the fractionation of $\text{Au}_n(\text{SR})_m$ clusters, and precise systematic isolation can be now achieved for $\text{Au}_n(\text{SR})_m$ clusters protected with either hydrophilic or hydrophobic SR using these techniques.

Figure 4. Examples of the precise synthesis of $\text{Au}_n(\text{SR})_m$ clusters by fractionation: (a) separation of $\text{Au}_n(\text{SG})_m$ clusters by polyacrylamide gel electrophoresis and (b) separation of $\text{Au}_n(\text{SC}_{12}\text{H}_{25})_m$ clusters by reverse-phase high-performance liquid chromatography. Figures were adapted from Refs. [3, 28], respectively.

2.2. Size focusing

The fractionation methods noted above are suitable for the systematic isolation of a series of $\text{Au}_n(\text{SR})_m$ clusters. However, these methods are not suitable for mass production. To synthesize $\text{Au}_n(\text{SR})_m$ clusters with a specific chemical composition on a large scale (~ 100 mg), it is necessary to conduct selective synthesis, and size focusing is an effective means of doing so (**Figure 3(b)**). Several $\text{Au}_n(\text{SR})_m$ clusters show higher resistance to deterioration in solution [3] or thiol etching [39–42] than other clusters of the same type. The less stable clusters can be converted into stable clusters when exposed to extreme conditions [39–42]. As an example, when $\text{Au}_n(\text{SR})_m$ clusters ($\text{SR} = \text{SC}_2\text{H}_4\text{Ph}$; $25 \leq n < 102$, $\text{SR} = \text{SG}$; $25 \leq n < 38$) are exposed to extreme conditions, unstable $\text{Au}_n(\text{SR})_m$ clusters are transformed into stable $\text{Au}_{25}(\text{SR})_{18}$ cluster. Stable clusters can be precisely synthesized on a large scale with this size-focusing method (**Figure 5(a)** and **(b)**).

2.3. Slow reduction

Typically, NaBH_4 is employed as the reducing agent to generate Au atoms. However, CO can also be used as the reducing agent. Au atoms are generated more slowly using CO than using NaBH_4 and so the $\text{Au}_n(\text{SR})_m$ clusters are formed at a slower rate [43]. This slower synthesis rate tends to produce more uniform clusters (**Figure 3(c)**). The precise and size-selective synthesis of $\text{Au}_n(\text{SR})_m$ clusters up to $\text{Au}_{25}(\text{SG})_{18}$ has been realized by this method (**Figure 6(a)**). Even when using NaBH_4 as the reducing agent, slow reduction can be achieved by controlling the pH of the solution. $\text{Au}_{76}(\text{4-MEBA})_{44}$ (4-MEBA = 4-(2-mercaptoethyl) benzoic acid) has been synthesized in this manner (**Figure 6(b)**) [44]. However, this method is only applicable to small hydrophilic $\text{Au}_n(\text{SR})_m$ clusters. It is expected that size-selective synthetic methods based on this principle will be established for $\text{Au}_n(\text{SR})_m$ clusters protected by hydrophobic SR as well as for large hydrophilic $\text{Au}_n(\text{SR})_m$ clusters.

2.4. Transformation from one stable size to another

The chemical composition of stable clusters varies depending on the bulk of the SR functional group [45]. Therefore, when the ligand of a stable cluster is replaced with a bulkier

Figure 5. Examples of the precise synthesis of $\text{Au}_n(\text{SR})_m$ clusters by size focusing: (a) synthesis of hydrophobic $\text{Au}_{25}(\text{SC}_2\text{H}_4\text{Ph})_{18}$ and (b) synthesis of hydrophilic $\text{Au}_{25}(\text{SG})_{18}$. Figures were adapted from Refs. [40–42], respectively.

Figure 6. Examples of the precise synthesis of $\text{Au}_n(\text{SR})_m$ clusters by slow reduction: (a) $\text{Au}_n(\text{SG})_m$ clusters synthesized by CO reduction and (b) $\text{Au}_{76}(4\text{-}(2\text{-mercaptoethyl})\text{benzoic acid})_{44}$ synthesized by controlling the pH of the solution. Figures were adapted from Refs. [43, 44], respectively.

SR, distortion of the metal core is induced, resulting in the formation of clusters with a different composition (**Figure 3(d)**) [46]. An example is the reaction of phenylethanethiolate ($\text{SC}_2\text{H}_4\text{Ph}$)-protected $\text{Au}_{38}(\text{SC}_2\text{H}_4\text{Ph})_{24}$ with 4-*tert*-butylbenzenthioi ($\text{HSPH-}^t\text{Bu}$) in solution, which generates $\text{Au}_{36}(\text{SPh-}^t\text{Bu})_{24}$ as the primary product (yield of ~90%) (**Figure 7(a)**). This technique enables the synthesis of stable clusters with different chemical compositions from $\text{Au}_n(\text{SC}_2\text{H}_4\text{Ph})_m$ or $\text{Au}_n(\text{SC}_{x-2x+1})_m$ (SC_{x-2x+1} = alkanethiolate) clusters. Clusters such as $\text{Au}_{28}(\text{SPh-}^t\text{Bu})_{20}$ (**Figure 7(b)**), $\text{Au}_{36}(\text{SPh-}^t\text{Bu})_{24}$ and $\text{Au}_{133}(\text{SPh-}^t\text{Bu})_{52}$ have been synthesized by this method [46].

Figure 7. Examples of the precise synthesis of $\text{Au}_n(\text{SR})_m$ clusters by transformation from one stable size to another: (a) from $\text{Au}_{38}(\text{SC}_2\text{H}_4\text{Ph})_{24}$ to $\text{Au}_{36}(\text{SPh-}^t\text{Bu})_{24}$ and (b) from $\text{Au}_{25}(\text{SC}_2\text{H}_4\text{Ph})_{18}$ to $\text{Au}_{28}(\text{SPh-}^t\text{Bu})_{20}$. Figures were adapted from Ref. [46].

3. Alloy clusters

The physical and chemical properties of metal clusters also strongly depend on the chemical composition as well as on the size of the metal core. For example, the catalytic activity of polymer-stabilized Pd_{147} clusters is remarkably improved when the Pd at the surface is partially substituted by Au [47]. In addition, alloy nanoclusters composed of Pd and Ru exhibit markedly different catalytic activities compared with those of their monometallic nanocluster counterparts. The catalytic activity obtained by mixing these two metals is higher than that of monometallic nanoclusters of Rh, which is located between these two elements in the periodic table [48]. As illustrated by these examples, synergistic effects caused by mixing different

elements generate physical and chemical properties that differ from those of monometallic clusters. Thus, the composition control of metal clusters is very interesting from the viewpoint of modification of the physical and chemical properties of clusters, and results in new applications for clusters.

It is well known that SR forms strong bonds with Au (Section 2). Furthermore, stable $\text{Au}_n(\text{SR})_m$ clusters can be produced, and a large number of methods have been established for their isolation (Section 2). Therefore, in the synthesis of alloy clusters protected by SR ligands, Au is often employed as one of the main metal elements, and the cluster size is controlled using a method similar to that used for $\text{Au}_n(\text{SR})_m$ clusters. The important point in these syntheses is how to successfully mix other metallic elements with Au. In this section, we describe three typical procedures used to address this issue (**Figure 8**).

3.1. Co-reduction of multiple kinds of metal ions

The most common method for mixing other metallic elements with Au is the simultaneous reduction of the other metal ions with Au ions using a reducing agent (**Figure 8(a)**). This approach is called the co-reduction method. For example, to synthesize SR-protected alloy clusters, Au and other metal ions are mixed in solution, followed by the addition of thiol. A strong reducing agent (NaBH_4) is then added, resulting in the simultaneous reduction of all of the metal ions present. Examples of alloy clusters synthesized using this method include $\text{Au}_{25-x}\text{Ag}_x(\text{SR})_{18}$ ($\text{R} = \text{C}_{12}\text{H}_{25}$ or $\text{C}_2\text{H}_4\text{Ph}$; $x = 1-11$; **Figure 9(a)**), $\text{Au}_{25-x}\text{Cu}_x(\text{SR})_{18}$ ($\text{R} = \text{C}_8\text{H}_{17}$ or $\text{C}_2\text{H}_4\text{Ph}$; $x = 1-5$; **Figure 9(b)**), $\text{Au}_{24}\text{Pt}(\text{SC}_2\text{H}_4\text{Ph})_{18}$ (**Figure 9(c)**), $\text{Au}_{24}\text{Pd}(\text{SR})_{18}$ ($\text{R} = \text{C}_{12}\text{H}_{25}$ or $\text{C}_2\text{H}_4\text{Ph}$; **Figure 9(d)**), $\text{Au}_{38-x}\text{Ag}_x(\text{SC}_2\text{H}_4\text{Ph})_{24}$ ($x = 1-12$), $\text{Au}_{36}\text{Pd}_2(\text{SC}_2\text{H}_4\text{Ph})_{24}$, $\text{Au}_{144-x}\text{Ag}_x(\text{SC}_2\text{H}_4\text{Ph})_{60}$ ($x \sim 30, 34, 52, 53$), $\text{Au}_{143/144/145-x}\text{Cu}_x(\text{SC}_2\text{H}_4\text{Ph})_{59/60/61}$ ($x = 1-23$), $\text{Au}_{144}\text{Cu}(\text{SC}_6\text{H}_{13})_{60'}$ and $\text{Au}_{144-x}\text{Pd}_x(\text{SC}_2\text{H}_4\text{Ph})_{60}$ ($x = 1-7$) [49–59]. Using the co-reduction method, it is also possible to synthesize $\text{Au}_{12}\text{Ag}_{32}(\text{SR})_{30}$ ($\text{R} = \text{PhF}$, PhF_2 , or PhCF_3) or $\text{Au}_{12+x}\text{Cu}_{32}(\text{SPhCF}_2)_{30+x}$ ($x = 0, 2, 4, 6$) alloy clusters, in which Ag or Cu is the base metal element [19, 60]. However, in this method, two or more types of metal atoms need to be generated simultaneously by reduction to successfully form alloy clusters.

Figure 8. Representative synthesis methods of thiolate-protected alloy clusters: (a) co-reduction of multiple kinds of metal ions, (b) metal exchange with metal complexes, and (c) deposition of metal atoms onto metal clusters.

Figure 9. Thiolate-protected alloy clusters synthesized by the co-reduction method: (a) $\text{Au}_{25-x}\text{Ag}_x(\text{SC}_2\text{H}_4\text{Ph})_{18}$, (b) $\text{Au}_{25-x}\text{Cu}_x(\text{SC}_2\text{H}_4\text{Ph})_{18}$, (c) $\text{Au}_{24}\text{Pt}(\text{SC}_2\text{H}_4\text{Ph})_{18}$, and (d) $\text{Au}_{24}\text{Pd}(\text{SC}_2\text{H}_4\text{Ph})_{18}$. Ag/Au indicates Ag or Au. R groups are omitted for clarity. Figures were adapted from Refs. [50, 51, 54].

Therefore, it is difficult to form an alloy cluster using this method when there is a large difference in redox potential between the precursor metal ions. As a result, alloy clusters synthesized by this method are presently limited to those containing Au, Ag, Cu, Pt, and Pd.

3.2. Metal exchange with metal complexes

Metal clusters can exchange metal atoms with metal complexes (**Figure 8(b)**). This reaction enables heteroelements to be introduced into metal clusters to synthesize alloy clusters [61]. Although there are some exceptions [62], the number of constituent atoms of the metal core generally does not change during this exchange [63–71]. Therefore, this reaction enables some of the atoms in a cluster to be replaced with other elements while maintaining the original number of constituent atoms and geometry. In addition, this reaction allows heteroelements to be mixed more easily than the co-reduction method. The metal exchange reaction enables the synthesis of alloy clusters composed of metal elements with very different redox potentials, and a larger number of heteroatoms can be replaced than that achieved by the co-reduction method. Using this type of exchange reaction, alloy clusters such as $\text{Au}_{25-x}\text{Ag}_x(\text{SR})_{18}$ ($x = 1-8$), $\text{Au}_{25-x}\text{Cu}_x(\text{SR})_{18}$ ($x = 1-9$), $\text{Au}_{24}\text{Cd}(\text{SR})_{18}$ (**Figure 10(a)**), $\text{Au}_{24}\text{Hg}(\text{SR})_{18}$ (**Figure 10(b)**), $\text{Au}_{24-x}\text{Ag}_x\text{Cd}(\text{SR})_{18}$ ($x = 2-6$), $\text{Au}_{24-x}\text{Ag}_x\text{Hg}(\text{SR})_{18}$ ($x = 1-8$; **Figure 10(c)**), $\text{Au}_{24-x-y}\text{Ag}_x\text{Cu}_y\text{Pd}(\text{SR})_{18}$ ($x = 1-3$, $y = 1, 2$; **Figure 10(d)**), $\text{Ag}_{25-x}\text{Au}_x(\text{SR})_{18}$ ($x = 1, 2$), $\text{Ag}_{24-x}\text{Au}_x\text{Pt}(\text{SR})_{18}$ ($x = 1, 2, 4-9$), and $\text{Au}_{38-x}\text{Ag}_x(\text{SR})_{24}$ ($x = 1-11$) have been synthesized to date [63–71].

Figure 10. Thiolate-protected alloy clusters synthesized by the metal exchange method: (a) $\text{Au}_{24}\text{Cd}(\text{SC}_2\text{H}_4\text{Ph})_{18}$, (b) $\text{Au}_{24}\text{Hg}(\text{SC}_2\text{H}_4\text{Ph})_{18}$, (c) $\text{Au}_{24-x}\text{Ag}_x\text{Hg}(\text{SC}_2\text{H}_4\text{Ph})_{18}$, and (d) $\text{Au}_{22}\text{AgCuPd}(\text{SC}_{12}\text{H}_{25})_{18}$. Hg/Au indicates Hg or Au. R groups are omitted for clarity. Figures were adapted from Refs. [64, 66, 68, 71].

3.3. Deposition of metal atoms onto metal clusters

When $\text{Au}_n(\text{SR})_m$ clusters with fine metal cores (<2 nm) react with Ag ions, the Ag ions are reduced by Au, and Ag is deposited on the cluster surface (**Figure 8(c)**). This type of reaction has been used to synthesize $\text{Au}_{25}\text{Ag}_2(\text{SC}_2\text{H}_4\text{Ph})_{18}$ by depositing two Ag atoms on the surface of an $\text{Au}_{25}(\text{SC}_2\text{H}_4\text{Ph})_{18}$ (**Figure 11**) [72, 73]. A particular feature of this synthesis is that the substrate clusters maintain their chemical composition while the other metal atoms are deposited on the cluster surface. However, the metal clusters and metal ions used for this reaction were the same as those used in the aforementioned metal exchange method (Section 3.2). In the future, it is expected that the reason why the reaction changes from metal exchange to metal deposition under slightly different experimental conditions will be elucidated.

Figure 11. $\text{Au}_{25}\text{Ag}_2(\text{SC}_2\text{H}_4\text{Ph})_{18}$ synthesized by the metal deposition method. R groups are omitted for clarity. This figure was adapted from Ref. [72].

4. Conclusions and prospects

In this chapter, we focused on $\text{Au}_n(\text{SR})_m$ and related alloy clusters as examples of metal nano-clusters and described the latest techniques and knowledge regarding their precise synthesis. The study of $\text{Au}_n(\text{SR})_m$ clusters has progressed with spectacular speed in recent years. Consequently, the associated synthetic techniques have also advanced dramatically, and a greater understanding of their characteristics has been obtained [74–76]. These clusters are now expected to be applied in various fields such as sensing, imaging, cancer radiation therapy, catalysis, photocatalysis, solar cells, fuel cells, photosensitizers, and single-electron devices. If these $\text{Au}_n(\text{SR})_m$ clusters can be regularly assembled [77], further new functions could be induced and their fields of application might be further expanded. In the future, it is expected that intensive investigations will be conducted regarding the formation of various nanoarchitectures using $\text{Au}_n(\text{SR})_m$ clusters as structural units in addition to research on the $\text{Au}_n(\text{SR})_m$ clusters themselves.

Acknowledgements

The authors thank all the coauthors whose names appear in the cited references. This work was supported by JSPS KAKENHI (grant numbers JP15H00763, JP15H00883, JP16H04099, 16K17480, and 16K21402). Funding from the Nippon Sheet Foundation for Materials Science and Engineering, the Sumitomo Foundation, the Takahashi Industrial and Economic Research Foundation, the Tanaka Kikinzoku Memorial Foundation, and the Futaba Electronics Memorial Foundation is also gratefully acknowledged.

Author details

Bharat Kumar¹, Yoshiki Niihori¹, Wataru Kurashige¹ and Yuichi Negishi^{1,2*}

*Address all correspondence to: negishi@rs.kagu.tus.ac.jp

¹ Department of Applied Chemistry, Faculty of Science, Tokyo University of Science, Shinjuku-ku, Tokyo, Japan

² Photocatalysis International Research Center, Tokyo University of Science, Noda, Chiba, Japan

References

- [1] Taketoshi A, Haruta M. Size- and structure-specificity in catalysis by gold clusters. *Chemistry Letters*. 2014;**43**:380-387. DOI: 10.1246/cl.131232
- [2] Tsukuda T, Tsunoyama H, Sakurai H. Aerobic oxidations catalyzed by colloidal nano-gold. *Chemistry – An Asian Journal*. 2011;**6**:736-748. DOI: 10.1002/asia.201000611
- [3] Negishi Y, Nobusada K, Tsukuda T. Glutathione-protected gold clusters revisited: Bridging the gap between gold(I)–thiolate complexes and thiolate-protected gold nanocrystals. *Journal of the American Chemical Society*. 2005;**127**:5261-5270. DOI: 10.1021/ja042218h
- [4] Negishi Y. Toward the creation of functionalized metal nanoclusters and highly active photocatalytic materials using thiolate-protected magic gold clusters. *Bulletin of the Chemical Society of Japan*. 2014;**87**:375-389. DOI: 10.1246/bcsj.20130288
- [5] Whetten RL, Shafigullin MN, Khoury JT, Schaaff TG, Vezmar I, Alvarez MM, Wilkinson A. Crystal structures of molecular gold nanocrystal arrays. *Accounts of Chemical Research*. 1999;**32**:397-406. DOI: 10.1021/ar970239t
- [6] Parker JF, Fields-Zinna CA, Murray RW. The story of a monodisperse gold nanoparticle: Au₂₅L₁₈. *Accounts of Chemical Research*. 2010;**43**:1289-1296. DOI: 10.1021/ar100048c

- [7] Luo Z, Nachammai V, Zhang B, Yan N, Leong DT, Jiang D, Xie J. Toward understanding the growth mechanism: Tracing all stable intermediate species from reduction of Au(I)-thiolate complexes to evolution of Au₂₅ nanoclusters. *Journal of the American Chemical Society*. 2014;**136**:10577-10580. DOI: 10.1021/ja505429f
- [8] Qian H, Zhu M, Wu Z, Jin R. Quantum sized gold nanoclusters with atomic precision. *Accounts of Chemical Research*. 2012;**45**:1470-1479. DOI: 10.1021/ar200331z
- [9] Dass A. Nano-scaling law: Geometric foundation of thiolated gold nanomolecules. *Nanoscale*. 2012;**4**:2260-2263. DOI: 10.1039/c2nr11749e
- [10] Zhang P. X-ray spectroscopy of gold-thiolate nanoclusters. *The Journal of Physical Chemistry C*. 2014;**118**:25291-25299. DOI: 10.1021/jp507739u
- [11] Udayabhaskararao T, Pradeep T. New protocols for the synthesis of stable Ag and Au nanocluster molecules. *The Journal of Physical Chemistry Letters*. 2013;**4**:1553-1564. DOI: 10.1021/jz400332g
- [12] Knoppe S, Wong OA, Malola S, Häkkinen H, Bürgi T, Verbiest T, Ackerson CJ. Chiral phase transfer and enantioenrichment of thiolate-protected Au₁₀₂ clusters. *Journal of the American Chemical Society*. 2014;**136**:4129-4132. DOI: 10.1021/ja500809p
- [13] Dolamic I, Knoppe S, Dass A, Bürgi T. First enantioseparation and circular dichroism spectra of Au₃₈ clusters protected by achiral ligands. *Nature Communications*. 2012;**3**:798. DOI: 10.1038/ncomms1802
- [14] Jadzinsky PD, Calero G, Ackerson CJ, Bushnell DA, Kornberg RD. Structure of a thiol monolayer-protected gold nanoparticle at 1.1 Å resolution. *Science*. 2007;**318**:430-433. DOI: 10.1126/science.1148624
- [15] Kwak K, Kumar SS, Pyo K, Lee D. Ionic liquid of a gold nanocluster: A versatile matrix for electrochemical biosensors. *ACS Nano*. 2014;**8**:671-679. DOI: 10.1021/nn4053217
- [16] Dainese T, Antonello S, Gascón JA, Pan F, Perera NV, Ruzzi M, Venzo A, Zoleo A, Rissanen K, Maran F. Au₂₅(SEt)₁₈, a nearly naked thiolate-protected Au₂₅ cluster: Structural analysis by single crystal X-ray crystallography and electron nuclear double resonance. *ACS Nano*. 2014;**8**:3904-3912. DOI: 10.1021/nn500805n
- [17] Konishi K, Iwasaki M, Sugiuchi M, Shichibu Y. Ligand-based toolboxes for tuning of the optical properties of subnanometer gold clusters. *The Journal of Physical Chemistry Letters*. 2016;**7**:4267-4274. DOI: 10.1021/acs.jpcllett.6b01999
- [18] Desiredy A, Conn BE, Guo J, Yoon B, Barnett RN, Monahan BM, Kirschbaum K, Griffith WP, Whetten RL, Landman U, Bigioni TP. Ultrastable silver nanoparticles. *Nature*. 2013;**501**:399-402. DOI: 10.1038/nature12523
- [19] Yang H, Wang Y, Huang H, Gell L, Lehtovaara L, Malola S, Häkkinen H, Zheng N. All-thiol-stabilized Ag₄₄ and Au₁₂Ag₃₂ nanoparticles with single-crystal structures. *Nature Communications*. 2013;**4**:2422. DOI: 10.1038/ncomms3422

- [20] Zheng J, Petty JT, Dickson RM. High quantum yield blue emission from water-soluble Au₈ nanodots. *Journal of the American Chemical Society*. 2003;**125**:7780-7781. DOI: 10.1021/ja035473v
- [21] Yamamoto K, Imaoka T, Chun WJ, Enoki O, Katoh H, Takenaga M, Sono A. Size-specific catalytic activity of platinum clusters enhances oxygen reduction reactions. *Nature Chemistry*. 2009;**1**:397-402. DOI: 10.1038/nchem.288
- [22] Kurashige W, Niihori Y, Sharma S, Negishi Y. Precise synthesis, functionalization and application of thiolate-protected gold clusters. *Coordination Chemistry Reviews*. 2016;**320-321**:238-250. DOI: 10.1016/j.ccr.2016.02.013
- [23] Brust M, Walker M, Bethell D, Schiffrin DJ, Whyman R. Synthesis of thiol-derivatised gold nanoparticles in a two-phase liquid-liquid system. *Journal of the Chemical Society, Chemical Communications*. 1994:801-802. DOI: 10.1039/c39940000801
- [24] Tsukuda T. Toward an atomic-level understanding of size-specific properties of protected and stabilized gold clusters. *Bulletin of the Chemical Society of Japan*. 2012;**85**:151-168. DOI: 10.1246/bcsj.20110227
- [25] Negishi Y, Takasugi Y, Sato S, Yao H, Kimura K, Tsukuda T. Magic-numbered Au_n clusters protected by glutathione monolayers ($n = 18, 21, 25, 28, 32, 39$): Isolation and spectroscopic characterization. *Journal of the American Chemical Society*. 2004;**126**:6518-6519. DOI: 10.1021/ja0483589
- [26] Negishi Y, Takasugi Y, Sato S, Yao H, Kimura K, Tsukuda T. Kinetic stabilization of growing gold clusters by passivation with thiolates. *The Journal of Physical Chemistry B*. 2006;**110**:12218-12221. DOI: 10.1021/jp062140m
- [27] Negishi Y, Sakamoto C, Ohyama T, Tsukuda T. Synthesis and the origin of the stability of thiolate-protected Au₁₃₀ and Au₁₈₇ clusters. *The Journal of Physical Chemistry Letters*. 2012;**3**:1624-1628. DOI: 10.1021/jz300547d
- [28] Negishi Y, Nakazaki T, Malola S, Takano S, Niihori Y, Kurashige W, Yamazoe S, Tsukuda T, Häkkinen H. A critical size for emergence of nonbulk electronic and geometric structures in dodecanethiolate-protected Au clusters. *Journal of the American Chemical Society*. 2015;**137**:1206-1212. DOI: 10.1021/ja5109968
- [29] Niihori Y, Uchida C, Kurashige W, Negishi Y. High-resolution separation of thiolate-protected gold clusters by reversed-phase high-performance liquid chromatography. *Physical Chemistry Chemical Physics*. 2016;**18**:4251-4265. DOI: 10.1039/c5cp04660b
- [30] Schaaff TG, Knight G, Shafigullin MN, Borkman RF, Whetten RL. Isolation and selected properties of a 10.4 kDa gold:Glutathione cluster compound. *The Journal of Physical Chemistry B*. 1998;**102**:10643-10646. DOI: 10.1021/jp9830528

- [31] Schaaff TG, Whetten RL. Giant gold–glutathione cluster compounds: Intense optical activity in metal-based transitions. *The Journal of Physical Chemistry B*. 2000;**104**:2630-2641. DOI: 10.1021/jp993691y
- [32] Whetten RL, Khoury JT, Alvarez MM, Murthy S, Vezmar I, Wang ZL, Stephens PW, Cleveland CL, Luedtke WD, Landman U. Nanocrystal gold molecules. *Advanced Materials*. 1996;**8**:428-433. DOI: 10.1002/adma.19960080513
- [33] Donkers RL, Lee D, Murray RW. Synthesis and isolation of the molecule-like cluster $\text{Au}_{38}(\text{PhCH}_2\text{CH}_2\text{S})_{24}$. *Langmuir*. 2004;**20**:1945-1952. DOI: 10.1021/la035706w
- [34] Negishi Y, Chaki NK, Shichibu Y, Whetten RL, Tsukuda T. Origin of magic stability of thiolated gold clusters: A case study on $\text{Au}_{25}(\text{SC}_6\text{H}_{13})_{18}$. *Journal of the American Chemical Society*. 2007;**129**:11322-11323. DOI: 10.1021/ja073580+
- [35] Chaki NK, Negishi Y, Tsunoyama H, Shichibu Y, Tsukuda T. Ubiquitous 8 and 29 kDa gold:Alkanethiolate cluster compounds: Mass-spectrometric determination of molecular formulas and structural implications. *Journal of the American Chemical Society*. 2008;**130**:8608-8610. DOI: 10.1021/ja8005379
- [36] Wolfe RL, Murray RW. Analytical evidence for the monolayer-protected cluster $\text{Au}_{225}[(\text{S}(\text{CH}_2)_5\text{CH}_3)]_{75}$. *Analytical Chemistry*. 2006;**78**:1167-1173. DOI: 10.1021/ac051533z
- [37] Choi MMF, Douglas AD, Murray RW. Ion-pair chromatographic separation of water-soluble gold monolayer-protected clusters. *Analytical Chemistry*. 2006;**78**:2779-2785. DOI: 10.1021/ac052167m
- [38] Black DM, Bhattarai N, Bach SBH, Whetten RL. Selection and identification of molecular gold clusters at the nano(gram) scale: Reversed phase HPLC–ESI–MS of a mixture of Au-peth MPCs. *The Journal of Physical Chemistry Letters*. 2016;**7**:3199-3205. DOI: 10.1021/acs.jpcllett.6b01403
- [39] Shichibu Y, Negishi Y, Tsunoyama H, Kanehara M, Teranishi T, Tsukuda T. Extremely high stability of glutathione-protected Au_{25} clusters against core etching. *Small*. 2007;**3**:835-839. DOI: 10.1002/smll.200600611
- [40] Dharmaratne AC, Krick T, Dass A. Nanocluster size evolution studied by mass spectrometry in room temperature $\text{Au}_{25}(\text{SR})_{18}$ synthesis. *Journal of the American Chemical Society*. 2009;**131**:13604-13605. DOI: 10.1021/ja906087a
- [41] Jin R, Qian H, Wu Z, Zhu Y, Zhu M, Mohanty A, Garg N. Size focusing: A methodology for synthesizing atomically precise gold nanoclusters. *The Journal of Physical Chemistry Letters*. 2010;**1**:2903-2910. DOI: 10.1021/jz100944k
- [42] Shichibu Y, Negishi Y, Tsukuda T, Teranishi T. Large-scale synthesis of thiolated Au_{25} clusters via ligand exchange reactions of phosphine-stabilized Au_{11} clusters. *Journal of the American Chemical Society*. 2005;**127**:13464-13465. DOI: 10.1021/ja053915s

- [43] Yu Y, Chen X, Yao Q, Yu Y, Yan N, Xie J. Scalable and precise synthesis of thiolated Au₁₀₋₁₂, Au₁₅, Au₁₈, and Au₂₅ nanoclusters via pH controlled CO reduction. *Chemistry of Materials*. 2013;**25**:946-952. DOI: 10.1021/cm304098x
- [44] Takano S, Yamazoe S, Koyasu K, Tsukuda T. Slow-reduction synthesis of a thiolate-protected one-dimensional gold cluster showing an intense near-infrared absorption. *Journal of the American Chemical Society*. 2015;**137**:7027-7030. DOI: 10.1021/jacs.5b03251
- [45] Nishigaki J, Tsunoyama R, Tsunoyama H, Ichikuni N, Yamazoe S, Negishi Y, Ito M, Matsuo T, Tamao K, Tsukuda T. A new binding motif of sterically demanding thiolates on a gold cluster. *Journal of the American Chemical Society*. 2012;**134**:14295-14297. DOI: 10.1021/ja305477a
- [46] Zeng C, Chen Y, Das A, Jin R. Transformation chemistry of gold nanoclusters: From one stable size to another. *The Journal of Physical Chemistry Letters*. 2015;**6**:2976-2986. DOI: 10.1021/acs.jpclett.5b01150
- [47] Zhang H, Watanabe T, Okumura M, Haruta M, Toshima N. Catalytically highly active top gold atom on palladium nanocluster. *Nature Materials*. 2012;**11**:49-52. DOI: 10.1038/nmat3143
- [48] Kusada K, Kobayashi H, Ikeda R, Kubota Y, Takata M, Toh S, Yamamoto T, Matsumura S, Sumi N, Sato K, Nagaoka K, Kitagawa H. Solid solution alloy nanoparticles of immiscible Pd and Ru elements neighboring on Rh: Changeover of the thermodynamic behavior for hydrogen storage and enhanced CO-oxidizing ability. *Journal of the American Chemical Society*. 2014;**136**:1864-1871. DOI: 10.1021/ja409464g
- [49] Negishi Y, Iwai T, Ide M. Continuous modulation of electronic structure of stable thiolate-protected Au₂₅ cluster by Ag doping. *Chemical Communications*. 2010;**46**:4713-4715. DOI: 10.1039/c0cc01021a
- [50] Kumara C, Aikens CM, Dass A. X-ray crystal structure and theoretical analysis of Au_{25-x}Ag_x(SCH₂CH₂Ph)₁₈⁻ alloy. *The Journal of Physical Chemistry Letters*. 2014;**5**:461-466. DOI: 10.1021/jz402441d
- [51] Negishi Y, Munakata K, Ohgake W, Nobusada K. Effect of copper doping on electronic structure, geometric structure, and stability of thiolate-protected Au₂₅ nanoclusters. *The Journal of Physical Chemistry Letters*. 2012;**3**:2209-2214. DOI: 10.1021/jz300892w
- [52] Negishi Y, Kurashige W, Niihori Y, Nobusada K. Toward the creation of stable, functionalized metal clusters. *Physical Chemistry Chemical Physics*. 2013;**15**:18736-18751. DOI: 10.1039/C3CP52837E
- [53] Qian H, Jiang D, Li G, Gayathri C, Das A, Gil RR, Jin R. Monoplatinum doping of gold nanoclusters and catalytic application. *Journal of the American Chemical Society*. 2012;**134**:16159-16162. DOI: 10.1021/ja307657a

- [54] Tian S, Liao L, Yuan J, Yao C, Chen J, Yang J, Wu Z. Structures and magnetism of mono-palladium and mono-platinum doped $\text{Au}_{25}(\text{PET})_{18}$ nanoclusters. *Chemical Communications*. 2016;**52**:9873-9876. DOI: 10.1039/c6cc02698b
- [55] Negishi Y, Kurashige W, Niihori Y, Iwasa T, Nobusada K. Isolation, structure, and stability of a dodecanethiolate-protected $\text{Pd}_1\text{Au}_{24}$ cluster. *Physical Chemistry Chemical Physics*. 2010;**12**:6219-6225. DOI: 10.1039/b927175a
- [56] Niihori Y, Matsuzaki M, Pradeep T, Negishi Y. Separation of precise compositions of noble metal clusters protected with mixed ligands. *Journal of the American Chemical Society*. 2013;**135**:4946-4949. DOI: 10.1021/ja4009369
- [57] Niihori Y, Matsuzaki M, Uchida C, Negishi Y. Advanced use of high-performance liquid chromatography for synthesis of controlled metal clusters. *Nanoscale*. 2014;**6**:7889-7896. DOI: 10.1039/c4nr01144a
- [58] Kumara C, Dass A. AuAg alloy nanomolecules with 38 metal atoms. *Nanoscale*. 2012;**4**:4084-4086. DOI: 10.1039/c2nr11781a
- [59] Negishi Y, Igarashi K, Munakata K, Ohgake W, Nobusada K. Palladium doping of magic gold cluster $\text{Au}_{38}(\text{SC}_2\text{H}_4\text{Ph})_{24}$: Formation of $\text{Pd}_2\text{Au}_{36}(\text{SC}_2\text{H}_4\text{Ph})_{24}$ with higher stability than $\text{Au}_{38}(\text{SC}_2\text{H}_4\text{Ph})_{24}$. *Chemical Communications*. 2012;**48**:660-662. DOI: 10.1039/c1cc15765e
- [60] Yang H, Wang Y, Yan J, Chen X, Zhang X, Häkkinen H, Zheng N. Structural evolution of atomically precise thiolated bimetallic $[\text{Au}_{12+n}\text{Cu}_{32}(\text{SR})_{30+n}]^{4-}$ ($n = 0, 2, 4, 6$) nanoclusters. *Journal of the American Chemical Society*. 2014;**136**:7197-7200. DOI: 10.1021/ja501811j
- [61] Shon Y-S, Dawson GB, Porter M, Murray RW. Monolayer-protected bimetal cluster synthesis by core metal galvanic exchange reaction. *Langmuir*. 2002;**18**:3880-3885. DOI: 10.1021/la025586c
- [62] Li Q, Wang S, Kirschbaum K, Lambright KJ, Das A, Jin R. Heavily doped $\text{Au}_{25-x}\text{Ag}_x(\text{SC}_6\text{H}_{11})_{18}^-$ nanoclusters: Silver goes from the core to the surface. *Chemical Communications*. 2016;**52**:5194-5197. DOI: 10.1039/c6cc01243d
- [63] Wang S, Song Y, Jin S, Liu X, Zhang J, Pei Y, Meng X, Chen M, Li P, Zhu M. Metal exchange method using Au_{25} nanoclusters as templates for alloy nanoclusters with atomic precision. *Journal of the American Chemical Society*. 2015;**137**:4018-4021. DOI: 10.1021/ja511635g
- [64] Yao C, Lin Y, Yuan J, Liao L, Zhu M, Weng L, Yang J, Wu Z. Mono-cadmium vs Mono-mercury doping of Au_{25} nanoclusters. *Journal of the American Chemical Society*. 2015;**137**:15350-15353. DOI: 10.1021/jacs.5b09627
- [65] Liao L, Zhou S, Dai Y, Liu L, Yao C, Fu C, Yang J, Wu Z. Mono-mercury doping of Au_{25} and the HOMO/LUMO energies evaluation employing differential pulse voltammetry. *Journal of the American Chemical Society*. 2015;**137**:9511-9514. DOI: 10.1021/jacs.5b03483

- [66] Yang S, Wang S, Jin S, Chen S, Sheng H, Zhu M. A metal exchange method for thiolate-protected tri-metal $M_1Ag_xAu_{24-x}(SR)_{18}^0$ ($M = Cd/Hg$) nanoclusters. *Nanoscale*. 2015;**7**:10005-10007. DOI: 10.1039/c5nr01965f
- [67] Yan N, Liao L, Yuan J, Lin Y, Weng L, Yang J, Wu Z. Bimetal doping in nanoclusters: Synergistic or counteractive?. *Chemistry of Materials*. 2016;**28**:8240-8247. DOI: 10.1021/acs.chemmater.6b03132
- [68] Bootharaju MS, Joshi CP, Parida MR, Mohammed OF, Bakr OM. Templated atom-precise galvanic synthesis and structure elucidation of a $[Ag_{24}Au(SR)_{18}]^-$ nanocluster. *Angewandte Chemie International Edition*. 2016;**55**:922-926. DOI: 10.1002/anie.201509381
- [69] Bootharaju MS, Sinatra L, Bakr OM. Distinct metal-exchange pathways of doped Ag_{25} nanoclusters. *Nanoscale*. 2016;**8**:17333-17339. DOI: 10.1039/C6NR06353E
- [70] Kang X, Xiong L, Wang S, Yu H, Jin S, Song Y, Chen T, Zheng L, Pan C, Pei Y, Zhu M. Shape-controlled synthesis of trimetallic nanoclusters: Structure elucidation and properties investigation. *Chemistry – A European Journal*. 2016;**22**:17145-17150. DOI: 10.1002/chem.201603893
- [71] Sharma S, Yamazoe S, Ono T, Kurashige W, Niihori Y, Nobusada K, Tsukuda T, Negishi Y. Tuning the electronic structure of thiolate-protected 25-atom clusters by co-substitution with metals having different preferential sites. *Dalton Transactions*. 2016;**45**:18064-18068. DOI: 10.1039/c6dt03214a
- [72] Yao C, Chen J, Li M-B, Liu L, Yang J, Wu Z. Adding two active silver atoms on Au_{25} nanoparticle. *Nano Letters*. 2015;**15**:1281-1287. DOI: 10.1021/nl504477t
- [73] Tian S, Yao C, Liao L, Xia N, Wu Z. Ion-precursor and ion-dose dependent anti-galvanic reduction. *Chemical Communications*. 2015;**51**:11773-11776. DOI: 10.1039/c5cc03267a
- [74] Chen LY, Wang CW, Yuan Z, Chang HT. Fluorescent gold nanoclusters: Recent advances in sensing and imaging. *Analytical Chemistry*. 2015;**87**:216-229. DOI: 10.1021/ac503636j
- [75] Yang X, Yang M, Pang B, Vara M, Xia Y. Gold nanomaterials at work in biomedicine. *Chemical Reviews*. 2015;**115**:10410-10488. DOI: 10.1021/acs.chemrev.5b00193
- [76] Mathew A, Pradeep T. Noble metal clusters: Applications in energy, environment, and biology. *Particle & Particle Systems Characterization*. 2014;**31**:1017-1053. DOI: 10.1002/ppsc.201400033
- [77] Ariga K, Vinu A, Yamauchi Y, Ji Q, Hill JP. Nanoarchitectonics for mesoporous materials. *Bulletin of the Chemical Society of Japan*. 2012;**85**:1-32. DOI: 10.1246/bcsj.20110162