We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Amino Acids Modification to Improve and Fine-Tune Peptide-Based Hydrogels

Stefan Loic

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/intechopen.68705>

Abstract

Among all the materials used in industry, gels play an increasingly important role. These so-called soft-matter materials are defined by their ability to fix a large amount of solvent, either organic (organogels) or aqueous (hydrogels). The large majority of hydrogels are made of natural or synthetic polymers, or natural proteins. However, a new kind of hydrogel has appeared: the peptide-based hydrogels, developed from short amino acids sequences (<20 amino acids). Due to their exceptional qualities in term of biocompatibility, biodegradability, and atom economy, these peptide-based hydrogels open new horizons in term of applications. They are mainly considered in the biomedical domain as injectable hydrogels, or as an extracellular culture matrix to support cell culture. While important, the possibilities of peptide design can exponentially grow using modified and non-natural amino acids instead of the “only” twenty natural ones. Thus, chemical modifications virtually offer infinite opportunities both to improve applications window and to fine-tune properties of the resulting hydrogels. In this context, this chapter proposes to review peptide and amino acid modifications reported to impact the resulting hydrogel.

Keywords: bioinspired materials, modified amino acids, gelator, peptide-based hydrogel, self-assembly, soft matter, supramolecular chemistry

1. Introduction

1.1. Soft matter and hydrogels as powerful materials

At the tenuous frontier between the solid and the liquid states, soft matter is focusing research interest which has exponentially increased since the beginning of the 1990s (<20 peer-reviewed articles published in 1990 versus >700 for 2014, 2015, and 2016). Interestingly, it is in

perfect accordance with the Nobel Prize in Physics received by Pr. Pierre-Gilles de Gennes in 1991, who merely entitled his Nobel lecture “Soft Matter” [1]. He has definitely contributed to popularize this terminology. Soft matter includes a wide variety of materials, including colloidal suspensions, surfactants, liquid crystals, polymers, or gels. These latter ones constitute the major thread of this chapter.

Interestingly, the gel state can be described both as a solid state, because of the ability of gels to self-support their own weight (which is a solid state characteristic), and as a liquid, on account of the gel composition made of a large majority of a liquid (generally >98% w/w) and only a small amount of solid (<2% w/v) [2–4]. Thus, gels are defined by their ability to fix a large amount of solvent, either organic (organogels) [5] or aqueous (hydrogels) [6, 7]. Hydrogels are of particular interest and find plenty of applications from medical treatments (*e.g.*, wound healing, dental care, cartilage repair, tissue engineering) [8] to cosmetics, agriculture, and water treatments [9]. The commercially available hydrogels are made of several kinds of starting materials, including natural polymers (*e.g.*, xanthan or Arabic gums, agar-agar), synthetic polymers (*e.g.*, polyurethane (PU), polyethylene glycol (PEG), polyacrylic acid (PAA)), or natural proteins (*e.g.*, collagen, silk fibroin, elastin) [10].

Depending on the nature of the interactions inside the matter, hydrogels can be discriminated between both chemical gels and physical gels [11]. For the first one, covalent bonds are created to form a network from the starting building block (also termed “gelator”), while for the latter, dynamic cross-links based on non-covalent interactions (mainly hydrogen bonds, π - π interactions, and Van der Waals interactions) control the supramolecular self-assembly of molecules of gelator [2–4].

Physical hydrogels, also called supramolecular hydrogels, draw scientific community’s attention due to their ability to be, *in theory*, dynamically assembled and disassembled several times, thanks to the formation and break of non-covalent interactions. However, some examples reveal that some hydrogels are too strong to be broken without degradation of the starting gelator. Regardless, the simplicity of the formation of supramolecular hydrogels, consisting of mixing the gelator and water followed by the application of a stimulus to trigger the gelation process, has made these materials of primary interest for a broad range of applications [8, 12, 13]. The stimuli applied are, depending of the system, of different nature including temperature, ultrasound, salt addition, addition of a specific chemical, pH, enzyme, light, electromagnetic field, etc. [2–4].

In the development of high-efficient hydrogels, the place taken by peptide-based hydrogels drastically increased during the last two decades. Based on the self-assembly of peptides, these hydrogels are particularly interesting for applications in biological and medical contexts [14–19]. Great expectations are placed on these innovative materials by the scientific community, and first commercially available systems have emerged, when others are in clinical research trials.

1.2. Peptide-based hydrogelators as innovative and efficient materials

Smaller than proteins, polypeptides and peptides are comprised of amino acids linked by amide bonds, the terminology depending on the length of the chain (respectively ≥ 100 , < 100 , and < 10 amino acids as generally accepted). In a biological context, common natural amino

acids (α -amino acids to be more specific) are 20 and are characterized by their molecular structures and their physicochemical properties including their isoelectric point, hydrophobicity, pKa, etc. (**Table 1**) [20]. As a function of their sequence and conditions, proteins and peptides have the ability to self-assemble in a non-covalent way, forming secondary structures termed β -sheets (parallel and antiparallel), α -helix, 3_{10} helix, or π -helix. These structures are fundamental for physiological process and are mainly due to specific intra- or inter-molecular hydrogen bond interactions between the carbonyls and the protons of the amide groups. Other types of interactions are also crucial for peptide self-assembly, including van der Waals forces, electrostatic forces, π - π interactions, and hydrophobic affinity [2–4].

An overwhelming majority of the peptide-based hydrogels rests on peptide β -sheet assemblies. Indeed, starting gelators (*i.e.*, peptides) mainly self-assemble into fibrils, which subsequently combine each other via supramolecular interactions to form fibers. Altogether, these fibers form a network acting as the frame of the hydrogel, essentially self-supported by hydrogen bonds (**Figure 1**) [21]. This analogy to building construction is shared with numer-

Name	Three-letter code	One-letter code	M (g.mol ⁻¹)	Nature (lateral chain)	Isoelectric point (IP)	pKa (lateral chain)	Hydropathy index	P_{β}
Alanine	Ala	A	89.09	Aliphatic	6.01	N/A	1.8	0.76
Glycine	Gly	G	75.07	Aliphatic	5.97	N/A	−0.4	0.71
Isoleucine	Ile	I	131.17	Aliphatic	6.02	N/A	4.5	1.73
Leucine	Leu	L	131.17	Aliphatic	5.98	N/A	3.8	1.23
Proline	Pro	P	115.13	Aliphatic	6.48	N/A	1.6	0.43
Valine	Val	V	117.15	Aliphatic	5.97	N/A	4.2	1.82
Phenylalanine	Phe	F	165.19	Aromatic	5.48	N/A	2.8	1.48
Tryptophan	Trp	W	204.23	Aromatic	5.89	N/A	−0.9	1.24
Tyrosine	Tyr	Y	181.19	Aromatic	5.66	10.07	−1.3	1.43
Aspartic acid	Asp	D	133.10	Acid	2.77	3.65	−3.5	0.52
Glutamic acid	Glu	E	147.13	Acid	3.22	4.25	−3.5	0.67
Asparagine	Asn	N	132.12	Amide	5.41	N/A	−3.5	0.53
Glutamine	Gln	Q	146.15	Amide	5.65	N/A	−3.5	0.78
Arginine	Arg	R	174.20	Basic	10.76	12.48	−4.5	0.86
Histidine	His	H	155.16	Basic	7.59	6.00	−3.2	1.01
Lysine	Lys	K	146.19	Basic	9.74	10.53	−3.9	0.82
Serine	Ser	S	105.09	Hydroxyl	5.68	N/A	−0.8	0.92
Threonine	Thr	T	119.12	Hydroxyl	5.87	N/A	−0.7	1.19
Cysteine	Cys	C	121.16	Sulfur-containing	5.07	8.18	2.5	1.26
Methionine	Met	M	149.21	Sulfur-containing	5.74	N/A	1.9	1.26

Table 1. Key properties of the main amino acids (with P_{β} for amino acids β -sheet propensity).

Figure 1. Schematic representation of peptide self-assembling to form fibrils.

ous vital biological self-assemblies (*e.g.*, antibody/antigen, RNA/protein, DNA/DNA, etc.), showing the pivotal role of supramolecular assemblies. Because peptides (*i.e.*, short proteins) natively self-assemble each other, peptide-based hydrogels can be considered as Nature-inspired materials [22].

While β -sheet assemblies are the predominant way peptides interact to form hydrogels, a handful of these soft matter materials are based on α -helical coiled-coil structures [23, 24]. Briefly, these architectures involve repeating heptapeptides (or heptads) mainly based on the sequence (HPPHPPP) in which H is a hydrophobic amino acid and P a polar one. Among them, few examples of coiled-coil-based hydrogels can be cited, including the tri heptad repeats (**Ile-Lys-Gln-Leu-Glu-Ser-Glu**)₃ and (**Ile-Ala-Gln-Leu-Glu-Tyr-Glu**)₃ [25], a 34-mer based on the **Gln-Leu-Ala-Arg-Glu-Leu(Gln-Gln-Leu-Ala-Arg-Glu-Leu)**₄ [26], a 19-mer (**Ac-Leu-Lys-Glu-Leu-Ala-Lys-Val-Leu-His-Glu-Leu-Ala-Lys-Leu-Val-Ser-Glu-Ala-Leu-His-Ala-NH₂**) [27], and the hydrogel formed by two 28-residue peptides termed hSAF_{AAA} used as substrate for cell growth [28]. However, these gels based on coiled-coil peptide architecture are limited by both the length of the sequence (from ~20 to 40 amino acid residues) and the concentration of peptide (from 1 to 12% w/v) required. Comparatively, hydrogels based on peptide self-assembling via β -sheet formation can be formed with ultrashort peptides (≤ 7 amino) and with smaller concentrations ($\leq 0.1\%$ w/v), making those indubitably better candidates in terms of efficiency and atom economy. Thus, the large majority of peptide-based hydrogels developed in the last two decades are based on β -sheet assemblies [2–4].

Contrastingly to the use of polymers in hydrogel formation, peptides have indisputable advantages making them remarkably more attractive. In particular, they are both biocompatible and easily metabolized by proteolysis, making them perfect candidates for biomedical and therapeutic applications [15]. Unlike polymers, peptides are chemically defined and synthesized in a high-purity with high reproducibility. Moreover, due to their own structure, peptides are perfectly biodegradable and seem to be an *ad hoc* alternative to polymers when suitable. Nonetheless, it is fair to remind that polymer science still has an indisputable

advantage because of its in-depth knowledge, while peptide-based hydrogels are still at their infancy. Fundamental research strongly supports the interest of these innovative peptide-based materials, trying to decipher the subtle mechanisms of self-assembly and the way(s) to optimize and fine-tune their thermodynamic and kinetic properties. Following this trend, applications have substantially increased and first commercially available peptide-based hydrogels have started to be sold, demonstrating their real interest [29].

1.3. Applications, commercial innovations, and outlook of peptide-based hydrogels

Due to their bioinspired architecture, peptide-based hydrogels are biocompatible, non-immunogenic, and potentially non-inflammatory [30], making them perfect materials for biomedical applications [31]. As a result, several systems were developed:

- as extracellular culture medium (or ECM) for cancer cells [16], stem cells, or neuronal SN4741 cells [32].
- as ECM to control $\alpha_5\beta_1$ integrin expression of endothelial cells [33].
- as injectable hydrogel for controlled-release of opioids [34] or of embryonic stem cell secretome [35].
- as implanted hydrogel-containing stem cells to treat spinal cord injury [36] or for nerve repair after traumatic injury in the nervous system [37]. *In vivo* implantation of RADA-16 peptide derivatives enhances extensive bone regeneration of mice femurs [38].
- as injectable hydrogel incorporating a Gadolinium MRI agent to follow its degradation *in vivo* [35].
- as adjuvant for vaccines, for instance against West Nile virus [39].
- for rapid hemostasis [40].
- for controlled-release of growth factor [41], pindolol, quinine, timolol [42], 5-fluorouracil [43], vancomycin and vitamin B12 [44], tanshinones [45], microRNA [46], or proteins (*e.g.*, BSA, IgG) [47].
- for immobilization of biocatalysts for chemical transformations [48].
- for removal of toxic dyes and heavy metal ions from waste water [49].
- to produce nanostructured silica [50] or to encapsulate carbon nanotubes [51].
- as antibacterial hydrogels [52], like the 20-mer MARG1 against methicillin-resistant *Staphylococcus aureus* [53], or (Lys-Ile-Gly-Ala-Lys-Ile)₃-NH₂, #1 **Figure 2**) against *E. coli* [54].

This laundry list clearly illustrates the potential of peptide-based hydrogels and puts out a new avenue in term of polyvalence, mainly in the biomedical domain. It has not escaped the attention of generalist media, like for instance Times of India [55], Asian Scientist [56], LaboratoryNews [57], Phys Org [58], Medical News Today [59], Medical Daily [60], and so forth.

Figure 2. Chemical structures of peptides forming hydrogels.

Undoubtedly, peptide-based hydrogels are far from the laboratory curiosity, as evidenced by the new commercial market concerning these innovative materials. To the best of our knowledge, five products are commercially available:

- Hydromatrix™, developed by Sigma-Aldrich® (Saint Louis, USA) as medium for cell culture. The average price to prepare a 5 mL solution (0.1% w/v) is around 270 USD [61].
- PuraMatrix®, developed by 3-D Matrix Group (Tokyo, Japan) as medium for cell culture is a 16-mer (sequence **Ac-(Arg-Ala-Asp-Ala)₄-NH₂**, #2 **Figure 2**). The average price to prepare a 5 mL solution (0.1% w/v) is around 230 USD [62].
- Peptigel, developed by PeptiGel Design (Cheshire, UK) as medium for cell culture. The average price to prepare a 1 mL solution is around 130 USD [63].
- PGmatrix™, developed by PepGel LLC (Manhattan, USA) as medium for cell culture. The average price to prepare a 6 mL solution (0.1% w/v) is 375 USD [64].
- Curolox® technology, developed by Credentis (Windisch, Switzerland) as professional dental product for regeneration of enamel. It is not sold as it is, but as both toothpaste and a formulated product. The peptide used is an 11-mer termed P₁₁-4 (sequence **Ac-Gln-Gln-Arg-Phe-Glu-Trp-Glu-Phe-Glu-Gln-NH₂**, #3 **Figure 2**) [65].

It is a good bet that the number of commercially available peptide-based hydrogelator will increase in a near future.

As described hereinbefore, although the 20 natural amino acids offer a multitude of combinations, *i.e.*, a multitude of peptide-based hydrogel designs, the use of modified and non-canonical amino-acids drastically shoots up the possibilities and offers infinite opportunities both to improve the application window and to fine-tune properties of the resulting hydrogels. The next parts of this chapter are dedicated to the modifications developed to this end and illustrate the tremendous modularity of these materials.

2. Addition or insertion of organic moieties at the extremities or inside the amino acids sequences

2.1. Modifications at both N- and C-terminal ends

As discussed hereinbefore, gelation process is due to peptide self-assembly, driven by hydrogen bonds, electrostatic interactions, etc. In particular, π - π interactions and hydrophobic affinity are key parameters to design efficient hydrogelators, along with the subtle ability of the peptide to be partially soluble in water (mainly thanks to the presence of charged amino acids), and partially insoluble to form fibers. Thus, aromatic amino acids, mainly phenylalanine (**Phe**) and tyrosine (**Y**), are perfect candidates to balance these constraints. This is why a large majority of the peptide-based gelators are comprised of either these aromatic amino acids or other aromatic moieties.

Among them, it is not uncommon to observe the presence of a protecting group at the N-terminus. Indeed, protecting groups are widely used in both liquid and solid phase peptide synthesis (SPPS), and the easiest way to have them is simply by skipping the deprotection step at the end of the synthesis. Undoubtedly, Fmoc (fluorenylmethoxycarbonyl) is the more reported one, functionalizing peptide chains from one amino acid (*e.g.*, Fmoc-**Phe**, #4 **Figure 3**), to two (*e.g.*, Fmoc-**Gly-Ser**, #5 **Figure 3**), four (*e.g.*, Fmoc-**Phe-Arg-Gly-Asp**, #6 **Figure 3**), and more. Contrastingly, the other classic Cbz (carboxybenzyl) protecting group has not been well adopted, due to its smaller aromatic area leading to weaker π - π interactions compared to the Fmoc moiety [66, 67]. Another phenyl group was introduced via a cinnamoyl at the N-terminus of a phenylalanine amino acid, but it required higher concentration to form a gel in water, compared to the Fmoc-**Phe** analog (1.0% versus 0.3% w/v, respectively) [67]. Addition of naphthyl (Nap) derivatives (*e.g.*, 6-bromo-naphthyl (**6Br-Nap**) or 6-cyano-naphthyl (**6CN-Nap**)) has demonstrated high efficiency for several dipeptide gelators, like Nap-**Ala-Ala** (#7 **Figure 3**) or Nap-**Phe-Phe** (#8 **Figure 3**), (**6Br-Nap**)-**Phe-Phe** (#9 **Figure 3**), or (**6CN-Nap**)-**Ala-Val** (#10 **Figure 3**) [68]. Interestingly, Nap-**Gly-Ala** (#11 **Figure 3**) is able to form a stable hydrogel at acidic pH (pH = 2) at a concentration as low as 0.07% w/v [69]. Other moieties with larger aromatic areas are reported, even if they are much less common, like phenothiazine (*e.g.*, #12 **Figure 3**) [66], pyrene (*e.g.*, #13 **Figure 3**) [70, 71], spiropyran (*e.g.*, #14 **Figure 3**) [72], or pyridine (#15 **Figure 3**) [73]. In addition, few exotic aromatic groups were used to add specific properties to the peptide, including a fluorescent stilbene chromophore (#16 **Figure 3**) [74] or a photosensitive azobenzene (#17 **Figure 3**) [75]. In this latter, an E conformation leads to hydrogel formation, while the photo-induced isomerization of the double-bond to a Z one triggers a phase change (*i.e.*, a liquid is thus obtained).

Another approach consists to graft a long alkyl chain at the N-terminus to form an amphiphilic hybrid molecule comprised of both a hydrophilic (peptide head) and a hydrophobic parts (alkyl tail). For instance, $\text{CH}_3(\text{CH}_2)_{14}\text{-CO-Gly-Gly-Gly-Ser-Ser-Pro-His-Ser-Arg-Asn-(Ser-Gly)}_5\text{-Arg-Gly-Asp-Ser-Pro}$ forms a stable hydrogel from a minimum gelation concentration of ~1.4% w/v [76]. This latter contains a cell attachment site, the so-called **Arg-Gly-Asp** (or RGD) tripeptide, making the resulting hydrogel a good candidate for long-term human umbilical vein endo-

Figure 3. Chemical structures of hydrogel-forming peptides with N-terminal modifications.

thelial cell adhesion and proliferation. According to this model, other amphiphilic peptides containing alkyl chains were designed [77, 78], including $\text{CH}_3(\text{CH}_2)_{14}\text{-CO-Gly-Thr-Ala-Gly-Leu-Ile-Gly-Gln-Glu-Arg-Gly-Asp-Ser}$ (#18 Figure 4) [79] and $\text{CH}_3(\text{CH}_2)_{14}\text{-CO-Val-Val-Val-Ala-Ala-Ala-Glu-Glu-Glu}$ (#19 Figure 4) [80]. In parallel, innovative antibacterial hydrogels

were developed from peptides in which the nitrogen of the N-terminus was quaternalized, promoting the *in situ* synthesis of gold nanoparticles (#20, 21 **Figure 4**) [78, 81–83]. In order to favor self-assembly of peptides, addition of nucleobases was investigated and demonstrated promising results to develop biocompatible hydrogels (#22, 23 **Figure 4**) [84, 85]. Acetylation of the terminal primary amine is applied in some cases [86], such as for the design of the efficient KLD12 for cartilage tissue repair (#24 **Figure 4**) [87, 88]. Last of all, several hydrogelators are composed of a non-aromatic *tert*-butoxycarbonyl (Boc) protecting group at their N-terminus, annihilating the charge of the amine group. In this case, the resulting peptides are weakly water soluble and often find applications as organogels instead of hydrogels [89–92]. However, Baral et al. show its interest in the formation of stable antibacterial hydrogels (#25 **Figure 4**) [93]. Functionalizations with tetraethylene glycol [94] or polyethylene glycol [95] are also reported and increase significantly the global water solubility of the peptide (#26 **Figure 4**).

Regarding the C-terminus, while neutralization of the carboxylic acid thanks to its substitution by an ester (mostly methyl and ethyl esters) [89–92] is widely used to favor organogels, only few modifications are reported for hydrogels. Indeed, the acidic group plays a pivotal role in the peptide self-assembly and solubilization in aqueous solvent. Conversion of the carboxylic acid to the corresponding amide (*i.e.*, amidation) is well documented and tends toward faster hydrogel formation [96–99], but with weaker rigidity [100]. Peptides P₁₁-I (#27 **Figure 5**) [101] and Ac-Cys-(Phe-Lys-Phe-Glu)₂-Cys-Gly-NH₂ (#28 **Figure 5**) [102] can be cited as examples.

Figure 4. Chemical structures of hydrogel-forming peptides with N-terminal modifications (panel two).

Figure 5. Chemical structures of hydrogel-forming peptides with C-terminal modifications.

Besides, more anecdotal C-terminus modifications were experimented, including pyridinium moieties (*e.g.*, #29 **Figure 5**) [103], thiol ethyl amides (#30 **Figure 5**) [104], tetraethylene glycol [94] or polyethylene glycol [95], kanamycin (an aminoglycoside antibiotic), or glycoside (#31 **Figure 5**) [85].

2.2. Insertion of organic moieties inside the amino acid sequences

Another way to improve hydrogelation and/or to add properties to the resulting gel consists to introduce an organic moiety inside the amino acid sequence. Thus, alkyl chains were inserted between two sequences of one or two amino acids to form a bolaamphiphilic molecule [73]. Indeed, these systems are comprised of a hydrophobic core (*i.e.*, the alkyl chain), twice functionalized at both extremities by hydrophilic amino acids (#32 **Figure 6**) [105]. While several kinds of aggregates are observed for short alkyl chains (*e.g.*, vesicles), longer ones favor hydrogel formation. For instance, with the presence of two histidines on each side (#33 **Figure 6**), optimal length of the alkyl spacer is of 20 methylene groups; in contrast, a length of 10 or 12 methylene leads to too soluble molecules unable to self-assemble to form a gel [106]. Similarly, unsaturated hydrocarbon chains were used, like diacetylene units functionalized by two tetrapeptides on each extremity. This strategy is ingenious because it offers the possibility to add covalent links between the peptide-forming hydrogels (#34, 35 **Figure 6**). Indeed, these materials are simultaneously physical (*i.e.*, by peptide self-assembly) and chemical (*i.e.*, chemical bonds obtained after polymerization) hydrogels, simply obtained by UV radiations (254 nm, 4 W, 30 min) [107].

As described hereinbefore, aromatic moieties play a pivotal role in the peptide self-assembly mechanism and were considered as efficient organic blocks to be inserted inside an amino acid chain. Among them, both naphthalene and perylene (#36 **Figure 6**) diimines demonstrated good results, even if their syntheses were limited by modest yields [108]. However, the same authors described efficient peptide-based hydrogelators comprised of oligophenylenes, oligophenylene vinylenes (#37 **Figure 6**) [109], or oligothiophenes (#38 **Figure 6**).

Figure 6. Chemical structures of hydrogel-forming peptides with organic moieties inserted into.

These systems are also very interesting specimens thanks to their photoluminescence properties due to their large π -conjugated surfaces [108, 110, 111]. Last of all, formation of a disulfide bond inside a sequence, mainly between two cysteines, is an easy way to functionalize hydrogelators. Besides, disulfite bond is often associated with protein and peptide self-assembly [112, 113], which plays a fundamental role in the peptide-based gelation process.

3. Using non-canonical and modified amino acids to tune peptide-based hydrogel properties

3.1. Impact of D-amino acids on the peptide-based hydrogel properties

In biological organism, the overwhelming majority of the natural proteins are exclusively composed of amino acids in their L-enantiomer forms. However, the chiral equivalents, *i.e.*, D-enantiomers with a reverse chemical configuration (**Figure 7A**), are present in several cases. For instance, the D-amino acids are found in bacteria in which D-alanine, D-aspartic, and D-glutamic acids are essential constituents for the synthesis of the peptidoglycan, forming the bacteria cell wall. Several antibiotics also contain a D-amino acid, like penicillin G (δ -(α -aminoadipyl)- $_L$ -Cys- $_D$ -Val), gramicidin, actinomycin, or polymyxins [114]. Not limited to prokaryotes, D-amino acids were also isolated from eukaryotic tissue, including dermorphin from frogs, venom toxins from spiders or platypus, or neurohormones from crustaceans. More recently, these D-amino acids have been discovered in various human tissues, especially due to the presence of D-aspartic acid. It is the case for elastin, β -amyloid, α -synuclein, or AB-crystallin. Interestingly, these proteins are involved in several pathologies: arteriosclerosis, Alzheimer's and Parkinson's diseases, and cataract, respectively, demonstrating the undisputable importance of chirality in physiological process [115]. Research on amino acid role *in vivo* (as signaling molecules in the brain or endocrine glands [116], or in age-related diseases) [117] is a current fascinating hot topic, far from the scope of this chapter, and author incites curious readers to have a look to some reviews cited in this paragraph.

Inspired by the existence of D-amino acids, several groups used them to design efficient peptide-based hydrogels. The shorter one is undoubtedly **Fmoc- $_D$ -Glu**, which forms right-handed helical nanofibers in the presence of $_D$ -Lys (equimolar, #39 **Figure 7B**), while the same mixture with the L-enantiomer equivalents (*i.e.*, **Fmoc- $_L$ -Glu** + $_L$ -Lys) leads to left-handed helical nanofibers. Interestingly, the hydrogel containing D-enantiomers has slightly better viscoelastic properties than the levorotatory one [118]. This example clearly highlights that the organization at the molecular level (*i.e.*, the chirality) impacts the organization at the micro (*i.e.*, the fibers) and macroscopic scales (*i.e.*, the hydrogel). Series of dipeptides containing D-amino acids were also developed, one with Fmoc N-protecting group, and one with a naphthyl group (Nap). For the first instance, **Fmoc- $_D$ -Ala- $_D$ -Ala** (#40 **Figure 7B**) can be cited to be highly efficient to form a hydrogel (>0.13% w/v), slightly better than the corresponding **Fmoc- $_L$ -Ala- $_L$ -Ala** (>0.15% w/v), whereas **Fmoc-Gly- $_D$ -Ala** (#41 **Figure 7B**) required concentration >1.7% w/v [119]. Interestingly, **Nap-Gly- $_D$ -Ala** (#42 **Figure 7B**) displays exceptional properties with a minimum gelation concentration of only 0.07% w/v in water [69]. In this specific case, hydrogel characteristics are similar to the ones obtained with **Nap-Gly-Ala**, but the circular dichroism signature of each other is the perfect reverse, illustrating the opposite helical fibril structure. Tripeptides are also represented in this list with other Fmoc-derivatized structures containing three phenylalanine: **Fmoc-Phe-Phe-Phe** (#43 **Figure 7B**), **Fmoc- $_D$ -Phe- $_D$ -Phe- $_D$ -Phe** (#44 **Figure 7B**), **Fmoc-Phe- $_D$ -Phe- $_D$ -Phe** (#45 **Figure 7B**), and **Fmoc- $_D$ -Phe-Phe-Phe** (#46 **Figure 7B**) [120]. Interestingly, the fibers obtained in water

Figure 7. Chemical structures of L- and D-amino acids (A), and chemical structures of hydrogel-forming peptides incorporating D-amino acid(s) (B).

are right-handed for **Fmoc-Phe-Phe-Phe** and **Fmoc-Phe-D₂-Phe** and left-handed for the two others. Their viscoelastic properties are also improved by the addition of D-enantiomers, with **Fmoc-D₂-Phe-D₂-Phe** about 23% higher than **Fmoc-Phe-Phe-Phe** in terms of storage and loss moduli. Without protecting group at the N-terminus, **Val-Phe-Phe** and **Phe-Phe-Val** peptides were unable to form hydrogels at neutral pH, while the **D₂-Val-Phe-Phe** (#47 Figure 7B) and **D₂-Phe-Phe-Val** (*i.e.*, both with the D-amino acid at the N extremity, #48 Figure 7B) equivalents did [121]. Another tripeptide, protected with an azobenzene moiety at the N-terminus, was developed from the sequence **Azo-Lys-Phe-Ala**, with D-enantiomers in different positions. Contrary to **Azo-Lys-Phe-Ala** which forms a hydrogel from 3.1% w/v, **Azo-Lys-D₂-Phe-D₂-Ala** (#49 Figure 7B) and **Azo-D₂-Lys-Phe-Ala** (#50 Figure 7B) require 6.8% w/v, more than twice. Interestingly, the all D-amino acid-containing peptide gel is a little bit more efficient, with a minimum concentration of 3.0% w/v [75].

The last, but clearly not the least, example of the use of D-amino acids to improve hydrogelation is definitively the introduction of the sequence $_D$ -**Pro-Pro**. Indeed, this latter confers a type II' turn (a β -hairpin), favoring the contact between the two peptide strands on both sides. This decrease of degrees of freedom drastically favors the hydrogel formation efficiency. Thus, plenty of sequences were developed [122, 123], including the 20-mers MAX1 (sequence **(Val-Lys)₄-Val- $_D$ -Pro-Pro-Thr-(Lys-Val)₄-NH₂**, #51 **Figure 8**) [124–129] and MAX8 (**(Val-Lys)₄-Val- $_D$ -Pro-Pro-Thr-Lys-Val-Glu-Val-(Lys-Val)₂-NH₂**) [128, 130], in which the $_D$ -**Pro-Pro** sequence is just in the middle, contrary to SSP1 (**(Val-Lys)₂-Val- $_D$ -Pro-Pro-Thr-(Lys-Val)₆-NH₂**, #52 **Figure 8**) or SSP2 (**(Val-Lys)₃-Val- $_D$ -Pro-Pro-Thr-(Lys-Val)₅-NH₂**) [131, 132]. More complex, a series of three-stranded peptides was developed, including TSS1 (sequence **(Val-Lys)₄-Val- $_D$ -Pro-Pro-Thr-(Lys-Val)₃-Lys- $_D$ -Pro-Pro-(Lys-Val)₄-NH₂**) [133].

Finally, derivatives from EAK-16 (sequence **Ac-(Ala-Glu-Ala-Glu-Ala-Lys-Ala-Lys)₂-NH₂**) incorporating D-amino acids were designed. Interestingly, the enantiomers EAK-16 and $_D$ -EAK-16 (sequence **Ac-($_D$ -Ala- $_D$ -Glu- $_D$ -Ala- $_D$ -Glu- $_D$ -Ala- $_D$ -Lys- $_D$ -Ala- $_D$ -Lys)₂-NH₂**, #53 **Figure 8**) have shown similar hydrogel thermodynamic properties (*e.g.*, storage moduli ≈ 1 kPa at 1% w/v) [134–136]. In contrast, the corresponding diastereoisomers E_D AK-16 (sequence **Ac-($_D$ -Ala-Glu- $_D$ -Ala-Glu- $_D$ -Ala-Lys- $_D$ -Ala-Lys)₂-NH₂**, #54 **Figure 8**) and $_D$ EA $_D$ K (sequence **Ac-(Ala- $_D$ -Glu-Ala- $_D$ -Glu-Ala- $_D$ -Lys-Ala- $_D$ -Lys)₂-NH₂**) appear to have extremely modest capability to form stable hydrogels [137].

Figure 8. Chemical structures of hydrogel-forming peptides incorporating D-amino acid(s).

3.2. Using non-canonical amino acids to design peptide-based hydrogels

As described before, modifications of the peptide may be induced by functionalization of the N- and C-termini, along with the insertion of an organic moiety inside the sequence, or by inversion of the amino acids chirality, using D-amino acids. Furthermore, introduction of non-canonical amino acids (*i.e.*, not from the 20 encoded proteinogenic ones) offers broad new possibilities and has been exploited by researchers to improve and fine-tune hydrogel formation.

Among them, the cyclohexylalanine (**Cha**), a hydrogenated phenylalanine, prevents the formation of π - π interactions and significantly increases the global hydrophobicity of the peptide in which it is inserted. For instance, using the octapeptide **Ac-(Phe-Lys-Phe-Glu)₂-NH₂**, the substitution of both phenylalanine by two cyclohexylalanine (*i.e.*, **Ac-(Cha-Lys-Cha-Glu)₂-NH₂**, #55 **Figure 9**) leads to a less soluble peptide requiring a few percentage of HFIP (for hexafluoroisopropanol) to ensure a gelation. However, while a self-supporting hydrogel was obtained at 0.23% w/v for this latter, the Phe-containing peptide necessitates 0.46% w/v [138]. In parallel, experiments on **Ac-(Cha-Lys-Cha-Lys)₂-NH₂** demonstrate that at the same concentration, **Ac-(Phe-Lys-Cha-Phe)₂-NH₂** (#56 **Figure 9**) forms a more rigid hydrogel ($G' \approx 1800$ kPa versus 76 Pa) [139]. These experiments have illustrated the pivotal role of hydrophobicity in peptide self-assembly and consequently in the gelation process.

Another non-usual amino acid used is the ornithine (**Orn**), comprised of an aminopropyl lateral chain. It can be considered as a lysine but with only three methylenes in the side chain instead of four. Derived from P₁₁ family [101, 140], an 11-mer containing three ornithine, positively charged, was synthesized (sequence **Ac-Gln-Gln-Orn-Phe-Orn-Trp-Orn-Phe-Gln-Gln-Gln-NH₂**, #57 **Figure 9**) and mixed with a close sequence, negatively charged, in which Orn were substituted by glutamic acids (sequence **Ac-Gln-Gln-Glu-Phe-Glu-Trp-Glu-Phe-Gln-Gln-Gln-NH₂**, #58 **Figure 9**). The equimolar mixture revealed both nematic gels and solutions properties. The assembly is favored by electrostatic interactions between charges carried by the primary amines (**Orn**) and the carboxylic acids (**Glu**) [96]. Other Orn-containing hydrogelators were developed from a decapeptide. More specifically, an oligo(p-phenylvinylene) (termed *OPV*) was functionalized by two pentapeptides on both sides: **Ac-Gln-Gln-Orn-Phe-Orn-OPV-Orn-Phe-Gln-Gln-Gln-NH₂** and **Ac-Gln-Gln-Arg-Phe-Glu-OPV-Glu-Phe-Gln-Gln-Gln-NH₂**. They both form a stable hydrogel, the first been more robust than the second one [109]. Working with short sequences of two amino acids without protection either at the N- or at the C-termini, the use of α,β -dehydrophenylalanine (**Δ Phe**) provides distinguished results [141, 142]. Compared to canonical **Phe**, **Δ Phe** has no chirality on its C $^{\alpha}$ and favors π - π stacking due to its extended electron delocalization. Indeed, while **Phe-Phe** lacks to form a hydrogel, **Phe- Δ Phe** is drastically more efficient forming a stiff one with $G' \approx 210,000$ Pa for only 1% w/v. However, after a full study on **Xxx- Δ Phe** (in which **Xxx** = 1 of the 20 canonical amino acids), only 2 dipeptides were reported as able to gelify: **Leu- Δ Phe** (#59 **Figure 9**) and **Phe- Δ Phe** (#60 **Figure 9**). Recently, the first one was applied *in vivo* in a mouse model as a drug delivery platform for mitoxantrone, an anticancer drug, and seems to be very promising [141].

Figure 9. Chemical structures of hydrogel-forming peptides incorporating non-canonical amino acid(s).

Recently, based on the 20-mers MAX1 (sequence **(Val-Lys)₄-Val-_D-Pro-Pro-Thr-(Lys-Val)₄-NH₂**, see hereinbefore) [124–129], other derivatives were synthesized in which eight valines (excluding the **Val** adjacent to the **_D-Pro**) were substituted by non-canonical aminobutyric acid (**Abu**), norvaline (**Nva**, #61 **Figure 9**), or norleucine (**Nle**). Results have highlighted

that, at 1% w/v, only the peptide-containing norvaline forms a stiffer material than the original MAX1, with $G' \approx 3300$ Pa versus 1800 Pa, respectively [143]. The use of cyclodipeptide was also reported as an efficient method. Indeed, **cyclo(L-Tyr-L-Lys)** (#62 **Figure 9**) and **cyclo(L-Phe-L-Lys)** N^ε-acetylated by gluconic acid lead to thixotropic hydrogels, which can be stored for a long period of time as a solution. The gelation is simply triggered by a short and vigorous stirring [144]. In order to increase the aromatic surface available from an ultra-short peptide, Fmoc-β-(2-naphthyl)-L-alanine (#63 **Figure 9**) was evaluated and the resulting hydrogel has exhibited good stability in a large range of pH, from 3 to 12 [145]. Inspired by the pentapeptide fragment **Lys-Leu-Val-Phe-Phe** from the 16 to 20 region of the Aβ protein (involves in Alzheimer's disease) and well-known for its ability to form amyloid fibers, effects of β-2-thienyalanine (**2-Thi**) were evaluated. The obtained **(2-Thi)-(2-Thi)-Val-Leu-Lys-Ala-Ala** (#64 **Figure 9**) has displayed high efficiency in hydrogel formation and liquid crystal properties [146].

Ingenuously, photoleucine, a diazirine-based photo-reactive analog of leucine, was introduced inside a pentapeptide protected with a naphthalene moiety at its N-terminus (#65 **Figure 9**). Thus, the system is applied for protein complex immunoprecipitation (also termed "pull-down" method) and interacts with proteins from 42 to 55 kDa [147].

Derived from the L-proline, the L-4-hydroxyproline (**Hyp**) is one of the amino acids constituting the tropocollagen and, *in fine*, the collagen. Indeed, collagen fibers are composed of the repeating sequence **Gly-Xxx-Hyp** in which **Xxx** = **Lys**, **Glu**, **Ser**, **Ala**, and **Pro** [148]. Based on that, **Nap-Gly-Phe-Phe-Tyr-Gly-Gly-Xxx-Hyp** peptides were studied (#66 **Figure 9**). Depending on the amino acid at the seventh position (*i.e.*, **Xxx**), the minimum gelation concentrations are between 0.04% and 0.10% w/v, demonstrating the assets of this bio-mimicking approach [149].

One of the last categories of modification this part would like to highlight is the functionalization of phenylalanine. Indeed, a convincing body of work has been focused on this pivotal amino acid playing a central role in peptide self-assembly and *in fine*, in hydrogel formation. Thus, working on the short **Fmoc-Phe**, the group of Bradley L. Nilsson studied the impact of the substitution of the hydrogen in the para position by a nitro (**-NO₂**, #67 **Figure 10**), a cyano (**-CN**, #68 **Figure 10**), an amino (**-NH₂**), a hydroxyl (**-OH**, in this case the amino acid corresponds to a tyrosine), a methoxy (**-OMe**, #69 **Figure 10**), a trifluoromethyl (**-CF₃**, #70 **Figure 10**), or a methyl group [100, 150–152]. This modification leads to a redistribution of the electron density of the aromatic ring, influencing the π-π and dipolar interactions between benzyl groups. While **Fmoc-Phe** forms a weak hydrogel at 0.6% w/v ($G' \approx 40$ Pa), all these *para* substitutions improve the mechanical behavior of the resulting gels, especially for **Fmoc-(pNO₂-Phe)**, **Fmoc-Tyr**, and **Fmoc-(pNH₂-Phe)**, with storage moduli of ≈ 410 Pa, 506 Pa, and 527 Pa, respectively. However, the gelation time is not directly linked to the mechanical properties, with $t_{gel} \approx 0.5$ min, 5 min, and 10 min for **Fmoc-(pNO₂-Phe)**, **Fmoc-(pCN-Phe)**, and **Fmoc-(pCH₃-Phe)**, respectively.

The effect of halogenation was also investigated on **Fmoc-Phe**, with substitutions on the *ortho*, *meta*, and *para* positions, by fluorine, chlorine, or bromine [153]. In this work, in terms of gelation time, halogenation on the *para* position is drastically shorter ($t_{gel} \approx 0.5$ min) compared to both *meta* ($t_{gel} \approx 3$ –15 min) and *ortho* ($t_{gel} \approx 30$ –50 min) positions. However, regarding the

Figure 10. Chemical structures of hydrogel-forming peptides incorporating non-canonical amino acid(s) (panel two).

mechanical properties, the presence of a halogen in the *meta* position is the more efficient, followed by the *ortho* and finally the *para* positions. In parallel, the impact of the atom seems to be determined by its polarizability, with the formation of more rigid hydrogels with fluorine, better than chlorine and then bromine. In this way, the use of a pentafluorinated phenylalanine **Fmoc-(F₅-Phe)** (#71 **Figure 10**) was considered [100, 151]. This perfluorination drastically increases the hydrophobicity of the molecule and drops down the minimum gelation concentration to 0.1% w/v. At 0.2% w/v, the gel has good rheological results, with $G' \approx 3100$ kPa and $G'' \approx 320$ Pa, confirming its efficiency compared to the classic **Fmoc-Phe**. Incorporation of (F₅-Phe) in a longer peptide chain was a success, as attested by the studies involving **Ac-[(F₅-Phe)-Lys-(F₅-Phe)-Lys]₂-NH₂** (#72 **Figure 10**) [139].

In the same way was reported the impact of a single-atom replacement of hydrogen with halogen in the human calcitonin-derived amyloidogenic fragment **Asp-Phe-Asn-Lys-Phe**. Mainly, the substitution of phenylalanine(s) by para-X-Phe (X = Cl, Br, I) led to a drastic improvement of the thermodynamic and kinetic properties. Amyloid structures were confirmed by Atomic Force Microscopy (AFM) and cryo-Transmission Electron Microscopy (cryo-TEM) measurement, and by their green birefringence upon staining with Congo Red, highlighting the **Asp-(pI-Phe)-Asn-Lys-(pI-Phe)** derivative (#73 **Figure 10**) as the most fibrillogenic peptide monomer. As reported in the literature, it was attested that these amyloid fibrils had the ability to form hydrogels with more efficiency compared to the wild-type **Asp-Phe-Asn-Lys-Phe**, illustrated by the 30-fold lower concentration required for the gelification of **Asp-(pI-Phe)-Asn-Lys-Phe**. However, best thermal stability ($T = 116^\circ\text{C}$), lowest gelification time (<10 min), and highest stiffness (storage modulus $G' > 10^4$ Pa) were observed for the same bis-iodinated sample (at 15 mM), far better than the bis-bromo and bis-chloro derivatives, respectively. All these results emphasize the positive role of halogenation of peptides, especially iodination, for supramolecular amplification of amyloid self-assembly [154].

3.3. Functionalization of amino acids on their side chain

Among the 20 canonical amino acids, a mere fraction contains a reactive organic group on its lateral chain. These amino acids are mainly the ones with a carboxylic acid: **Asp** and **Glu**, an amine (**Lys**), a guanidine (**Arg**), or a thiol group (**Cys**). Thus, modifications and

post-modifications (*i.e.*, after the peptide synthesis) of the hydrogel-forming peptides can be carried out by chemical reactions between the amino acid cited above and an organic compound.

Following this rule, several structures have been developed, offering a new myriad of possibilities to enhance the versatility of the peptide-based hydrogels. Functionalization of lysine is clearly the more often used method. This amino acid has been grafted to a naphthalene diimine (NDI) moiety to increase the aromatic surface available on the peptide in order to favor π - π interactions and subsequently, hydrogelation. The resulting **Fmoc-Lys-Lys(NDI)** (#74 **Figure 11**) self-assembles at low concentration (<1.5% w/v) and can act as a semiconductor [155]. Similarly, lysines were modified by addition of an azo-benzene moiety, leading to photoswitchable hydrogels (#75 **Figure 11**) [156, 157]. Presence of a sorbamide group on the Lys side chain offers the possibility to photopolymerize the physical hydrogel obtained by non-covalent interactions in order to create chemical bonds rigidifying the network. This second step improves the mechanical rigidity by 2.5 [158]. Using the same approach, an amphiphilic peptide was developed, composed of a lysine functionalized with an alkyl chain containing a diacetylene segment (#76 **Figure 11**). The subsequent polymerization leads to polyacetylene-containing hydrogel applied for cell culture [159]. Furthermore, substituting the primary amine by an acrylamide group to secondly form polyacrylamide is also an adopted approach (#77 **Figure 11**) [160].

Addition of a hydrazine-containing arm to an amphiphilic peptide was proposed to control the release of ketones. Indeed, ketones can react with hydrazine to form a hydrazone. The high hydrolytic stability of this chemical function leads to a slow release of the ketone-containing compound from the hydrogel (#78 **Figure 11**) [161]. The presence of Boc protecting groups at the N $^{\epsilon}$ of **Lys**, originating from the peptide synthesis, definitely improves the hydrogel properties, as described for **Fmoc-Val-Leu-Lys(Boc)** and **Fmoc-Lys(Boc)-Leu-Val** (#79 **Figure 11**). The first one is the weakest with $G' \approx 4000$ Pa (at 2% w/v), while the latter is the stiffest with $G' > 100,000$ Pa [162]. The same approach was reported with Fmoc protecting-group simply using **Lys(N $^{\epsilon}$ -Fmoc)**. However, the hydrogelation was triggered by addition of one equivalent of either **Fmoc-Phe** or **Fmoc-Leu** and both with two equivalents of Na₂CO₃. Comparing the two mixtures, the hydrogel formulated from **Lys(N $^{\epsilon}$ -Fmoc)** + **Fmoc-Phe** (#80 **Figure 11**) is drastically more rigid than the one with **Fmoc-Leu**, with storage moduli of 25,000 Pa and 3000 Pa, respectively [163, 164]. Lastly, a lysine-functionalized peptide reported concerns a linear amphiphilic nonapeptide N $^{\epsilon}$ -functionalized in second and last position by a histine and a palmitoyl (including a C₁₅ alkyl chain). Gelation properties are interesting, with a minimum concentration required of 0.1% w/v and pH > 6.5 [165].

Working on a 20-mer derived from MAX1, an ingenious zinc-triggered hydrogelation was designed using a 3-amidoethoxyaminodiacetoxy-2-aminopropionic acid instead of a valine at the last position of the peptide sequence. Thus, the two incorporated acid groups perfectly fit to bind metals, in particular Zn²⁺. While no gelation occurs for peptide alone in solution, addition of ZnCl₂ triggers the formation of the hydrogel (#81 **Figure 11**) [166]. In order to produce composite materials comprised of peptide fibers mineralized by calcium, an amphiphilic

Figure 11. Chemical structures of hydrogel-forming peptides incorporating functionalized side chains.

molecule of 11 amino acids and a long alkyl chain of 15 methylene groups were designed. The key amino acid is a phosphorylated serine, playing a pivotal role in the formation of calcium phosphate minerals. After the self-assembly of the fibers, cysteine thiol groups are

oxidized to disulfides before being treated by CaCl_2 . After 20 min, the fibers start to be coated by crystalline minerals. These composite materials mimic the collagen fibrils and hydroxyapatite crystals in bone [167]. Concerning the phosphorylated serine, another peptide with the same global structure (alkyl chain and 11-mer) but with a different peptide sequence is able to form hydrogels for which the mechanical properties can be modulated by the cation added (#82 **Figure 12**). Indeed, while a viscous liquid is obtained with Na^+ or K^+ , Mg^{2+} and Ca^{2+} lead to hydrogels with moderate storage moduli (around 500 Pa), while with Zn^{2+} or Cu^{2+} , the gels are drastically stiffer ($G' \approx 10,000$ Pa) [168].

Working on **Fmoc-Phe-Gly-Gly-Gly-Tyr**, an innovative approach was experimented, based on $\text{Ru}(\text{bpy})_3^{2+}$ -catalyzed photo-crosslinking of two tyrosine residues to give dityrosine adduct. The obtained dimer acts as an efficient hydrogelator, while the monomer does not, with an increase of the mechanical stability up to 10,000 times (#83 **Figure 12**) [169]. Interestingly, formation of dityrosine is a strategy used by Nature to improve elastic properties of biomaterials, including the well-known resilin, first identified in *Drosophila melanogaster* [170].

Last of all, some peptide drugs are able of hydrogelating, offering undoubted perspectives for biomedical applications. Among them, analogs of gonadotropin-releasing hormone (or GnRH) were developed. GnRH is a peptide hormone composed of 10 amino acids (sequence **pyro-Glu-His-Trp-Ser-Tyr-Gly-Leu-Arg-Pro-Gly-NH₂**) and discovered by Guillemin [171] and Schally [172] who received the Nobel Prize in Physiology and Medicine in 1977 with Yalow [173]. Analogs have been continuously and slowly releasing during a long period of time, up to 35 days. In particular, both ganirelix and degarelix show efficient gelation properties, and are composed of non-canonical amino acids (#82 **Figure 12**), including a **pCl-Phe**, a **NaI**, a $\text{N}^G, \text{N}^{G'}$ -diethyl arginine, a (3-pyridyl)-alanine, an N^ϵ -isopropyl lysine, a para-urea phenylalanine, and a para-6-amido dihydroxyuracil [174]. Finally, the example of vancomycin,

Figure 12. Chemical structures of hydrogel-forming peptides incorporating functionalized side chains (panel two).

a glycopeptide with antibiotic properties, demonstrates the degree of complexity which can be reached. The minimum concentration of this perplexing molecule is around 0.36% w/v and offers new perspective in term of materials for biomedical applications [175]. However, due to the complexity of the system, it has to be considered as a special case, far from the initial idea to develop short peptide-based hydrogels synthesized in a straightforward and fast way.

4. Development of pseudo-peptides and peptidomimetics

4.1. A brief description of peptide analogs

Research on peptide analogs mainly refers to the development of metabolically stable peptide-like structures for biomedical and therapeutic applications. Indeed, the rapid proteolysis of native peptides and their inability to cross cellular membranes have required modifications of their intrinsic structure. Thus, changes of the peptide bond structure have been deeply studied and have led to efficient drugs commercialized by pharmaceutical company. For instance, Ziconotide (brand name Prialt®, sold by Elan Pharms) is a 25-mer indicated for severe chronic pains, Icatibant acetate (brand name Firazyr®, sold by Jerini AG) is a decapeptide indicated for hereditary angioedema, and Afamelanotide (brand name Scenesse®, sold by Clinuvel Pharmaceuticals) is a 13-mer indicated for erythropoietic prophyries [176].

Thus, two terminologies were introduced. The term “pseudopeptide” proposed by Spatola in 1981 strictly refers to peptide analogs in which the peptide backbone has been modified [177, 178]. Briefly, their nomenclature is quite simple, with the use of the Greek letter psi “ ψ [...]” in which the term under bracket refers to the “new” peptide link introduced. For example, the dipeptide #85 (**Figure 13A**) is represented as **Phe-Leu** (#85 **Figure 13A**), while **Phe- ψ [CH₂O]Leu** represents the pseudopeptide #86 (**Figure 13A**). In parallel, the term “peptidomimetic” refers to any compound able to mimic the specific action of a peptide (*i.e.*, inhibition, activation, etc.) [179]. Thus a “peptidomimetic” can be an organic molecule without any similarities to a peptide. It is the case of morphine, a “non-peptide” molecule mimicking the opioid peptides [177]. However, the word “pseudopeptide” has become obsolete years after years, and the generic term “peptidomimetic” is used to speak about both [180].

4.2. Peptidomimetics as efficient hydrogelators

First and foremost, the most represented peptidomimetics able to form hydrogels are undoubtedly the ones comprised of one or several β -amino acids. These latter differ from the native α -amino acids due to the presence of an additional carbon atom in the amino acid backbone. Besides, two regioisomers exist, depending on the position of the additional methylene group, termed β^2 or β^3 -amino acids (**Figure 13A**, right panel) [181]. With this in mind, a series of β^3 -dipeptides was synthesized, protected at the N-terminus by a naphthalene (**Nap**) derivative. Peptidomimetics #87 (**Nap-OCH₂CO- α Gly- β^3 HALa**, **Figure 13B**) and #88 (**Nap-CH₂CO- β^3 Phg- β^3 Phg**, with **Phg** = phenylglycine, **Figure 13B**) have reasonable mechanical properties,

Figure 13. Chemical structures of peptidomimetics (A), and chemical structures of hydrogel-forming peptides incorporating peptidomimetics (B).

the first one being stiffer than the second one [182]. With the same $\beta^3\text{Phg}$ and naphthalene extremity, a tripeptide ($\text{Nap-CH}_2\text{CO-}\beta^3\text{Phg-}\beta^3\text{Phg-}\alpha\text{Tyr}$, #89 Figure 13B) was studied as injectable hydrogel *in vitro* and *in vivo*, and offers longer biostability than the corresponding all α -containing-amino acids peptide $\text{Nap-CH}_2\text{CO-}\alpha\text{Phe-}\alpha\text{Phe-}\alpha\text{Tyr}$ [183]. Other compounds with a Fmoc N-protected group were developed and demonstrated ability to encapsulate and

release both vitamins B₂ and B₁₂ over a period of more than 48 hours, at physiological pH and temperature. Their structures are **Fmoc-βAla-αVal** (#90 **Figure 13B**) and **Fmoc-βAla-αPhe** and have comparable mechanical properties and release profiles [184]. In parallel, hydrogelation of **Fmoc-βAla-αHis** (#91 **Figure 13B**) is triggered by addition of Zn²⁺ cations [185].

In a peptide, substitution of the native amide function by an ester leads to structures called depsipeptides. The octapeptide Fmoc-DAKA-8 (sequence **Fmoc-Asp-Ala-Asp-Ala-Lys-Ala-Lys-Ala**) was modified, *inter alia*, by the introduction between the first and the second amino acids of an ester bond. Thus, **Fmoc-Asp-ψ[CO-O]Ala-Asp-ψ[CO-O]Ala-Lys-ψ[CO-O]Ala-Lys-Ala** (#92 **Figure 13B**) self-assembles and forms a hydrogel, with hydrolytic susceptibility (hydrolysis at the ester bond sites), which offer opportunities for applications such as tissue scaffold or drug delivery system [186]. Anecdotally, two peptidomimetics containing an oxalyl function are reported for their ability to form organogel as well as hydrogel, including #93 (**Figure 13B**) [187, 188]. As well, a molecule containing a maleic acid-like function is able to gelify in the presence of light and bromine. Indeed, starting with the Z configuration, UV irradiation (330 nm, 400 W, 30 s) and bromine trigger the photochemical isomerization (formation of a fumaryl-like group). The obtained diastereoisomer is then able to self-assemble (#94 **Figure 13B**) [189].

In parallel, a constrained amino acid derived from oxazolidine was used by the group of C. Tomasini, named (4*R*,5*S*)-4-carboxy-5-methyl oxazolidin-2-one (3-letter code **Oxd**). The first hydrogelator including an **Oxd** (#95 **Figure 13B**) was composed of a central alkyl chain, two **Phe** (one on each side), and two terminal **Oxd** (one on each side). However, hydrogelation can only occur in a 50/50 water/MeOH mixture [190, 191] or 90/10 water/EtOH [192]. The second system (#96 **Figure 13B**) is definitively more efficient (cpd xx) and exhibits properties of entrapment of aromatic dyes methylene blue (cationic) and eosin Y (anionic) [193].

Last of all, functionalization of the nitrogen of the amide group was proposed as a way to improve hydrogelation. Because of the high efficiency of phenylalanine, N-benzyl glycine (**Nphe**) derivatives synthesized were the following: **Fmoc-Phe-Phe**, **Fmoc-Phe-Nphe** (#97 **Figure 13B**), **Fmoc-Nphe-Phe** (#98 **Figure 13B**), and **Fmoc-Nphe-Nphe** (#99 **Figure 13B**). While the latter failed to form a hydrogel, the two peptides with one **Nphe** inside turned out to be less stiff than **Fmoc-Phe-Phe** in the same conditions. However, these experiments provide new molecular tools to fine-tune the properties of peptide self-assembly and gelation process [194].

5. Conclusion

Peptide-based hydrogels are innovative materials able to efficiently tackle the challenges of biocompatible and biodegradable soft matter. Mainly, they pave the way to promising medical and biological applications, and it is a safe bet that in the next years, their market share will increase drastically. Furthermore, the first commercially available peptide-based hydrogel has been launched, and new companies have emerged. Nevertheless, all these applications are possible thanks to the plentiful body of work accomplished in fundamental research during the last decades.

In order to improve and fine-tune the hydrogelation process, a critical point to broaden the application window, several strategies have been envisaged, described all along this chapter. Among them, addition of aromatic groups at the N-terminus, mainly via the presence of protecting groups (*e.g.*, Fmoc, Cbz, etc.), clearly favors the hydrogel formation, thanks to the increase of π - π interactions. Introduction of organic moieties inside the peptide sequence is also an efficient strategy, whether they are aromatic or unsaturated. In this latter case, introduction of acetylene groups offers the opportunity to add to the peptide self-assembly polymerization, which reinforces the mechanical properties of the gel. Furthermore, introduction of non-canonical D-amino acids is an efficient approach and leads to more stable hydrogels in term of proteolytic resistance. The development of new amino acids, including α,β -dehydrophenylalanine, β -thienylalanine, or functionalized phenylalanine, especially designed to influence the peptide self-assembly, drastically impacts the final properties of the obtained hydrogel. Functionalization on the lateral chains is another opportunity to support interactions between peptides, and to include new properties, like photoswitchable ones thanks to the introduction of azobenzene moieties. Creation of additional bonds via dityrosine formation or subsequent polymerization is a smart strategy combining both the physical and chemical gels worlds. Last of all, substitution of the inner peptide bond by another one leads to the development of peptidomimetics which are burgeoning and promise a bright future.

This chapter has reviewed the recent advances in peptide-based hydrogel development using modified peptide structures.

Acknowledgements

The author would like to thank Université de Lorraine and the Centre National de la Recherche Scientifique (CNRS) for their support.

Author details

Stefan Loic

Address all correspondence to: dr.stefanloic@gmail.com

Laboratory of Macromolecular Physical Chemistry, University of Lorraine, Nancy, France

References

- [1] De Gennes P-G. Soft matter (Nobel Lecture). *Angewandte Chemie International Edition* [Internet]. 1992;**31**(7):842–845. Available from: <http://doi.wiley.com/10.1002/anie.199208421> [Accessed: January 13, 2017]

- [2] Tomasini C, Castellucci N. Peptides and peptidomimetics that behave as low molecular weight gelators. *Chemical Society Reviews* [Internet]. 2013;**42**(1):156–172. Available from: <http://xlink.rsc.org/?DOI=C2CS35284B> [Accessed: January 23, 2017]
- [3] Dasgupta A, Mondal JH, Das D. Peptide hydrogels. *RSC Advances* [Internet]. 2013;**3**(24): 9117. Available from: <http://xlink.rsc.org/?DOI=c3ra40234g> [Accessed: January 23, 2017]
- [4] De Leon Rodriguez LM, Hemar Y, Cornish J, Brimble MA. Structure-mechanical property correlations of hydrogel forming β -sheet peptides. *Chemical Society Reviews* [Internet]. 2016;**45**(17):4797–4824. Available from: <http://xlink.rsc.org/?DOI=C5CS00941C> [Accessed: January 23, 2017]
- [5] Vintiloiu A, Leroux J-C. Organogels and their use in drug delivery – A review. *Journal of Controlled Release*. 2008;**125**(3):179–192
- [6] Buwalda SJ, Boere KWM, Dijkstra PJ, Feijen J, Vermonden T, Hennink WE. Hydrogels in a historical perspective: From simple networks to smart materials. *Journal of Controlled Release*. 2014;**190**:254–273
- [7] Estroff LA, Hamilton AD. Water gelation by small organic molecules. *Chemical Reviews*. 2004;**104**(3):1201–1217
- [8] Caló E, Khutoryanskiy VV. Biomedical applications of hydrogels: A review of patents and commercial products. *European Polymer Journal*. 2015;**65**:252–267
- [9] Gulrez SK, Al-Assaf S, Phillips GO. Hydrogels: Methods of preparation, characterisation and applications in molecular and environmental bioengineering. *Progress in Molecular and Environmental Bioengineering—From Analysis and Modelling to Technology Applications* [Internet]. 2011;646. Available from: <http://www.intechopen.com/books/progress-in-molecular-and-environmental-bioengineering-from-analysis-and-modelling-to-technology-applications/hydrogels-methods-of-preparation-characterisation-and-applications> [Accessed: January 23, 2017]
- [10] Jonker AM, Löwik DWPM, Van Hest JCM. Peptide- and protein-based hydrogels [Internet]. *Chemistry of Materials*. American Chemical Society. 2012;**24**:759–773. Available from: <http://pubs.acs.org/doi/abs/10.1021/cm202640w> [Accessed: January 23, 2017]
- [11] Sangeetha NM, Maitra U. Supramolecular gels: Functions and uses. *Chemical Society Reviews* [Internet]. 2005;**34**(10):821–836. Available from: <http://xlink.rsc.org/?DOI=b417081b> [Accessed: January 23, 2017]
- [12] Adler-Abramovich L, Gazit E. The physical properties of supramolecular peptide assemblies: From building block association to technological applications. *Chemical Society reviews* [Internet]. 2014;**43**(20):6881–6893. Available from: <http://xlink.rsc.org/?DOI=C4CS00164H> [Accessed: January 23, 2017]
- [13] Eskandari S, Guerin T, Toth I, Stephenson RJ. Recent advances in self-assembled peptides: Implications for targeted drug delivery and vaccine engineering. *Advanced Drug Delivery Reviews*. 2016; in press. DOI: 10.1016/j.addr.2016.06.013

- [14] Ruedinger F, Lavrentieva A, Blume C, Pepelanova I, Scheper T. Hydrogels for 3D mammalian cell culture: A starting guide for laboratory practice. *Applied Microbiology and Biotechnology* [Internet]. 2015;**99**(2):623–636. Available from: <http://link.springer.com/10.1007/s00253-014-6253-y> [Accessed: January 23, 2017]
- [15] Seow WY, Hauser CAE. Short to ultrashort peptide hydrogels for biomedical uses. *Materials Today*. 2014;**17**:381–388
- [16] Worthington P, Pochan DJ, Langhans SA. Peptide hydrogels—Versatile matrices for 3D cell culture in cancer medicine. *Frontiers in Oncology* [Internet]. 2015 ;**5**(April):92. Available from: <http://journal.frontiersin.org/article/10.3389/fonc.2015.00092/abstract> [Accessed: January 11, 2017]
- [17] Hosseinkhani H, Hong P-D, Yu D-S. Self-assembled proteins and peptides for regenerative medicine. *Chemical Reviews* [Internet]. 2013;**113**(7):4837–4861. Available from: <http://pubs.acs.org/doi/abs/10.1021/cr300131h> [Accessed: January 23, 2017]
- [18] Li Y, Qin M, Cao Y, Wang W. Designing the mechanical properties of peptide-based supramolecular hydrogels for biomedical applications [Internet]. *Science China: Physics, Mechanics and Astronomy*. 2014;**57**:849–858. Available from: <http://link.springer.com/10.1007/s11433-014-5427-z> [Accessed: January 23, 2017]
- [19] Jung JP, Gasiorowski JZ, Collier JH. Fibrillar peptide gels in biotechnology and biomedicine. *Biopolymers*. Wiley Subscription Services, Inc., A Wiley Company [Internet]. 2010;**94**:49–59. Available from: <http://doi.wiley.com/10.1002/bip.21326> [Accessed: January 23, 2017]
- [20] Bischoff R, Schlüter H. Amino acids: Chemistry, functionality and selected non-enzymatic post-translational modifications. *Journal of Proteomics*. 2012;**75**:2275–2296
- [21] Knowles TPJ, Buehler MJ. Nanomechanics of functional and pathological amyloid materials. *Nature Nanotechnology* [Internet]. 2011;**6**(8):469–479. Available from: <http://www.nature.com/doi/abs/10.1038/nnano.2011.102> [Accessed: January 23, 2017]
- [22] Petkau-Milroy K, Brunsveld L. Supramolecular chemical biology; bioactive synthetic self-assemblies. *Organic & Biomolecular Chemistry* [Internet]. 2013;**11**(2):219–232. Available from: <http://dx.doi.org/10.1039/C2OB26790J> [Accessed: January 23, 2017]
- [23] Woolfson DN. Building fibrous biomaterials from alpha-helical and collagen-like coiled-coil peptides. *Biopolymers*. Wiley Subscription Services, Inc., A Wiley Company [Internet]. 2010;**94**:118–127. Available from: <http://doi.wiley.com/10.1002/bip.21345> [Accessed: January 23, 2017]
- [24] Kumar VA, Wang BK, Kanahara SM. Rational design of fiber forming supramolecular structures. *Experimental Biology and Medicine* [Internet]. 2016;**241**(9):1–10. Available from: <http://journals.sagepub.com/doi/10.1177/1535370216640941> [Accessed: January 23, 2017]
- [25] Dong H, Paramonov SE, Hartgerink JD. Self-assembly of alpha-helical coiled coil nanofibers_Supporting Info. *Journal of the American Chemical Society* [Internet]. 2008;**130**(41):13691–13695. Available from: <http://pubs.acs.org/doi/abs/10.1021/ja8037323> [Accessed: January 12, 2017]

- [26] Potekhin SA, Melnik TN, Popov V, Lanina NF, Vazina AA, Rigler P, et al. De novo design of fibrils made of short α -helical coiled coil peptides. *Chemistry and Biology*. 2001;8(11):1025–1032
- [27] Fletcher NL, Lockett CV, Dexter AF. A pH-responsive coiled-coil peptide hydrogel. *Soft Matter* [Internet]. 2011;7(21):10210. Available from: <http://xlink.rsc.org/?DOI=c1sm06261a> [Accessed: January 12, 2017]
- [28] Banwell EF, Abelardo ES, Adams DJ, Birchall MA, Corrigan A, Donald AM, et al. Rational design and application of responsive alpha-helical peptide hydrogels. *Nature Materials* [Internet]. 2009;8(7):596–600. Available from: <http://www.nature.com/doi/10.1038/nmat2479> [Accessed: January 12, 2017]
- [29] De Santis E, Ryadnov MG. Peptide self-assembly for nanomaterials: The old new kid on the block. *Chemical Society Reviews* [Internet]. 2015;44(22):8288–8300. Available from: <http://xlink.rsc.org/?DOI=C5CS00470E> [Accessed: January 23, 2017]
- [30] Markey A, Workman VL, Bruce IA, Woolford TJ, Derby B, Miller AF, et al. Peptide hydrogel in vitro non-inflammatory potential. *Journal of Peptide Science* [Internet]. 2016. Available from: <http://doi.wiley.com/10.1002/psc.2940> [Accessed: January 10, 2017]
- [31] Seliktar D. Designing cell-compatible hydrogels for biomedical applications. *Science*. 2012;336(6085):1124–1128
- [32] Motamed S, Del Borgo MP, Kulkarni K, Habila N, Zhou K, Perlmutter P, et al. A self-assembling [small beta]-peptide hydrogel for neural tissue engineering. *Soft Matter* [Internet]. 2016;12(8):2243–2246. Available from: <http://xlink.rsc.org/?DOI=C5SM02902C> [Accessed: January 11, 2017]
- [33] Pashuck ET, Duchet BJR, Hansel CS, Maynard SA, Chow LW, Stevens MM. Controlled sub-nanometer epitope spacing in a three-dimensional self-assembled peptide hydrogel. *ACS Nano* [Internet]. 2016;10(12):11096–11104. Available from: <http://pubs.acs.org/doi/abs/10.1021/acsnano.6b05975> [Accessed: January 10, 2017]
- [34] Martin C, Oyen E, Mangelschots J, Bibian M, Ben Haddou T, Andrade J, et al. Injectable peptide hydrogels for controlled-release of opioids. *MedChemComm* [Internet]. 2016;7(3):542–549. Available from: <http://xlink.rsc.org/?DOI=C5MD00440C> [Accessed: January 11, 2017]
- [35] Bakota EL, Wang Y, Danesh FR, Hartgerink JD. Injectable multidomain peptide nanofiber hydrogel as a delivery agent for stem cell secretome. *Biomacromolecules* [Internet]. 2011;12(5):1651–1657. Available from: <http://pubs.acs.org/doi/abs/10.1021/bm200035r> [Accessed: January 11, 2017]
- [36] Li L-M, Han M, Jiang X, Yin X, Chen F, Zhang T-Y, et al. Peptide-tethered hydrogel scaffold promotes recovery from spinal cord transection via synergism with mesenchymal stem cells. *ACS Applied Materials & Interfaces* [Internet]. 2017. Available from: <http://pubs.acs.org/doi/abs/10.1021/acsaami.6b12829> [Accessed: January 10, 2017]

- [37] Zhang N, He L, Wu W. Self-assembling peptide nanofibrous hydrogel as a promising strategy in nerve repair after traumatic injury in the nervous system. *Neural Regeneration Research* [Internet]. 2016;**11**(5):717–718. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/27335544> [Accessed: January 11, 2017]
- [38] He B, Ou Y, Zhou A, Chen S, Zhao W, Zhao J, et al. Functionalized D-form self-assembling peptide hydrogels for bone regeneration. *Drug Design, Development and Therapy* [Internet]. 2016;**10**:1379–1388. Available from: <https://www.dovepress.com/functionalized-d-form-self-assembling-peptide-hydrogels-for-bone-regen-peer-reviewed-article-DDDT> [Accessed: January 11, 2017]
- [39] Friedrich BM, Beasley DWC, Rudra JS. Supramolecular peptide hydrogel adjuvanted subunit vaccine elicits protective antibody responses against West Nile virus. *Vaccine*. 2016;**34**(46):5479–5482
- [40] Chen C, Zhang Y, Fei R, Cao C, Wang M, Wang J, et al. Hydrogelation of the short self-assembling peptide I3QGK regulated by transglutaminase and use for rapid hemostasis. *ACS Applied Materials & Interfaces* [Internet]. 2016;**8**(28):17833–17841. Available from: <http://pubs.acs.org/doi/abs/10.1021/acsami.6b04939> [Accessed: January 10, 2017]
- [41] Lindsey S, Piatt JH, Worthington P, Sönmez C, Satheye S, Schneider JP, et al. Beta hairpin peptide hydrogels as an injectable solid vehicle for neurotrophic growth factor delivery. *Biomacromolecules* [Internet]. 2015;**16**(9):2672–2683. Available from: <http://pubs.acs.org/doi/10.1021/acs.biomac.5b00541> [Accessed: January 12, 2017]
- [42] Briuglia ML, Urquhart AJ, Lamprou DA. Sustained and controlled release of lipophilic drugs from a self-assembling amphiphilic peptide hydrogel. *International Journal of Pharmaceutics*. 2014;**474**(1–2):103–111
- [43] Liang L, Yang J, Li Q, Huo M, Jiang F, Xu X, et al. A novel targeting drug delivery system based on self-assembled peptide hydrogel. *Journal of Biomaterials and Nanobiotechnology* [Internet]. 2011;**2**(5):622–625. Available from: <http://www.scirp.org/journal/PaperDownload.aspx?DOI=10.4236/jbnb.2011.225074> [Accessed: January 12, 2017]
- [44] Baral A, Roy S, Dehsorkhi A, Hamley IW, Mohapatra S, Ghosh S, et al. Assembly of an injectable noncytotoxic peptide-based hydrogelator for sustained release of drugs. *Langmuir* [Internet]. 2014;**30**(3):929–936. Available from: <http://pubs.acs.org/doi/abs/10.1021/la4043638> [Accessed: January 12, 2017]
- [45] Yin Y, Wu C, Wang J, Song F, Yue W, Zhong W. A simply triggered peptide-based hydrogel as an injectable nanocarrier of tanshinone IIA and tanshinones. *Chemical Communications* [Internet]. 2017;**53**(3):529–32. Available from: <http://xlink.rsc.org/?DOI=C6CC08502D> [Accessed: January 10, 2017]
- [46] Li J, Kooger R, He M, Xiao X, Zheng L, Zhang Y. A supramolecular hydrogel as a carrier to deliver microRNA into the encapsulated cells. *Chemical Communications* [Internet]. 2014;**50**(28):3722–3724. Available from: <http://xlink.rsc.org/?DOI=c4cc00156g> [Accessed: January 12, 2017]

- [47] Koutsopoulos S, Unsworth LD, Nagai Y, Zhang S. Controlled release of functional proteins through designer self-assembling peptide nanofiber hydrogel scaffold. *Proceedings of the National Academy of Sciences* [Internet]. 2009;**106**(12):4623–4628. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/19273853> [Accessed: January 12, 2017]
- [48] Hickling C, Toogood HS, Saiani A, Scrutton NS, Miller AF. Nanofibrillar peptide hydrogels for the immobilization of biocatalysts for chemical transformations. *Macromolecular Rapid Communications* [Internet]. 2014;**35**(9):868–874. Available from: <http://doi.wiley.com/10.1002/marc.201400027> [Accessed: January 12, 2017]
- [49] Nandi N, Baral A, Basu K, Roy S, Banerjee A. A dipeptide-based superhydrogel: Removal of toxic dyes and heavy metal ions from waste-water. *Biopolymers* [Internet]. 2016. Available from: <http://doi.wiley.com/10.1002/bip.22915> [Accessed: January 10, 2017]
- [50] Altunbas A, Sharma N, Lamm MS, Yan C, Nagarkar RP, Schneider JP, et al. Peptide-silica hybrid networks: Biomimetic control of network mechanical behavior. *ACS Nano* [Internet]. 2010;**4**(1):181–188. Available from: <http://pubs.acs.org/doi/abs/10.1021/nn901226h> [Accessed: January 12, 2017]
- [51] Li C, Mezzenga R. The interplay between carbon nanomaterials and amyloid fibrils in bio-nanotechnology. *Nanoscale* [Internet]. 2013;**5**(14):6207–6208. Available from: <http://xlink.rsc.org/?DOI=c3nr01644g> [Accessed: January 12, 2017]
- [52] Ng VWL, Chan JMW, Sardon H, Ono RJ, García JM, Yang YY, et al. Antimicrobial hydrogels: A new weapon in the arsenal against multidrug-resistant infections. *Advanced Drug Delivery Reviews*. 2014;**78**:46–62
- [53] Salick DA, Pochan DJ, Schneider JP. Design of an injectable β -hairpin peptide hydrogel that kills methicillin-resistant staphylococcus aureus. *Advanced Materials* [Internet]. 2009;**21**(41):4120–4123. Available from: <http://doi.wiley.com/10.1002/adma.200900189> [Accessed: January 12, 2017]
- [54] Liu Y, Yang Y, Wang C, Zhao X. Stimuli-responsive self-assembling peptides made from antibacterial peptides. *Nanoscale* [Internet]. 2013;**5**(14):6413–6421. Available from: <http://xlink.rsc.org/?DOI=c3nr00225j> [Accessed: January 12, 2017]
- [55] Chatterjee S. IIT-B has Come up with Hydrogels Mimicking Natural Brain Tissue to Cure Parkinson's Disease via Stem Cell Therapy [Internet]. *Times of India*. 2016. Available from: <http://timesofindia.indiatimes.com/city/bengaluru/IIT-B-has-come-up-with-hydrogels-mimicking-natural-brain-tissue-to-cure-Parkinsons-disease-via-stem-cell-therapy/articleshow/55584718.cms> [Accessed: January 23, 2017]
- [56] Asian Scientist Newsroom. Self-Assembling Peptide Nanogel for Burns [Internet]. *Asian Scientist*. 2014. Available from: <http://www.asianscientist.com/2014/05/in-the-lab/ibn-self-assembling-peptide-nanogel-burns-2014/> [Accessed: January 23, 2017]
- [57] The Wonder Stuff—How Peptide Hydrogels Could Change the Face of Biomedicine [Internet]. *LaboratoryNews*. 2015. Available from: <http://www.labnews.co.uk/features/the-wonder-stuff-how-peptide-hydrogels-could-change-the-face-of-biomedicine-20-01-2015/> [Accessed: January 23, 2017]

- [58] Tuned Gels Reveal Molecules that Drive Stem Cell Differentiation [Internet]. PhysOrg. 2016. Available from: <https://phys.org/news/2016-07-tuned-gels-reveal-molecules-stem.html> [Accessed: January 23, 2017]
- [59] New Antibacterial Gel Could Revolutionize Treatment of Superbug Infections [Internet]. Medical News Today. 2016. Available from: <http://www.medicalnewstoday.com/articles/306299.php> [Accessed: January 23, 2017]
- [60] To Fight Drug-Resistant Superbugs in Hospitals, Researchers Have Developed New Bio-Film Targeting Antibacterial Gel [Internet]. Medical Daily. 2014. Available from: <http://www.medicaldaily.com/fight-drug-resistant-superbugs-hospitals-researchers-have-developed-new-bio-film-targeting-298994> [Accessed: January 23, 2017]
- [61] HydroMatrix™ Peptide Cell Culture Scaffold [Internet]. Sigma Aldrich. 2017. Available from: <http://www.sigmaaldrich.com/catalog/product/sigma/a6982?lang=fr®ion=FR&gclid=CMOP4uWo2NECFQcz0wod1nMD7Q> [Accessed: January 23, 2017]
- [62] Puramatrix [Internet]. 3D Matrix Group. 2017. Available from: <http://puramatrix.com/wp/puramatrix/> [Accessed: January 23, 2017]
- [63] PeptiGel [Internet]. PeptiGel Design. 2017. Available from: <http://www.peptigeldesign.com/> [Accessed: January 23, 2017]
- [64] PGmatrix [Internet]. PepGel LLC. 2017. Available from: http://www.pepgel.com/?page_id=6 [Accessed: January 23, 2017]
- [65] Curolox [Internet]. Credentis. 2017. Available from: <https://www.curodont.com/en/curolox-technology/> [Accessed: January 23, 2017]
- [66] Ou C, Zhang J, Zhang X, Yang Z, Chen M. Phenothiazine as an aromatic capping group to construct a short peptide-based “super gelator”. Chemical Communications [Internet]. 2013;**49**(18):1853–1855. Available from: <http://xlink.rsc.org/?DOI=c3cc38409h> [Accessed: January 11, 2017]
- [67] Shi J, Gao Y, Yang Z, Xu B. Exceptionally small supramolecular hydrogelators based on aromatic-aromatic interactions. Beilstein Journal of Organic Chemistry [Internet]. 2011;**7**(1):167–172. Available from: <http://www.beilstein-journals.org/bjoc/content/7/1/23> [Accessed: January 11, 2017]
- [68] Chen L, Morris K, Laybourn A, Elias D, Hicks MR, Rodger A, et al. Self-assembly mechanism for a naphthalene-dipeptide leading to hydrogelation. Langmuir. 2010;**26**(7):5232–5242
- [69] Yang Z, Liang G, Ma M, Gao Y, Xu B. Conjugates of naphthalene and dipeptides produce molecular hydrogelators with high efficiency of hydrogelation and superhelical nanofibers. Journal of Materials Chemistry [Internet]. 2007;**17**(9):850–854. Available from: <http://xlink.rsc.org/?DOI=B611255B> [Accessed: January 11, 2017]
- [70] Ma M, Kuang Y, Gao Y, Zhang Y, Gao P, Xu B. Aromatic–aromatic interactions induce the self-assembly of pentapeptidic derivatives in water to form nanofibers and supramolecular hydrogels. Journal of the American Chemical Society [Internet]. 2010;**132**(8):2719–2728. Available from: <http://pubs.acs.org/doi/abs/10.1021/ja9088764> [Accessed: January 16, 2017]

- [71] Nanda J, Biswas A, Banerjee A. Single amino acid based thixotropic hydrogel formation and pH-dependent morphological change of gel nanofibers. *Soft Matter* [Internet]. 2013;**9**(16):4198–4208. Available from: <http://xlink.rsc.org/?DOI=c3sm27050e> [Accessed: January 17, 2017]
- [72] Qiu Z, Yu H, Li J, Wang Y, Zhang Y. Spiropyran-linked dipeptide forms supramolecular hydrogel with dual responses to light and to ligand-receptor interaction. *Chemical Communications (Cambridge, England)* [Internet]. 2009;**7345**(23):3342–3344. Available from: <http://xlink.rsc.org/?DOI=b822840j> [Accessed: January 11, 2017]
- [73] Nebot VJ, Armengol J, Smets J, Prieto SF, Escuder B, Miravet JF. Molecular hydrogels from bolaform amino acid derivatives: A structure-properties study based on the thermodynamics of gel solubilization. *Chemistry—A European Journal* [Internet]. 2012;**18**(13):4063–4072. Available from: <http://doi.wiley.com/10.1002/chem.201103193> [Accessed: January 11, 2017]
- [74] Behanna HA, Rajangam K, Stupp SI. Modulation of fluorescence through coassembly of molecules in organic nanostructures. *Journal of the American Chemical Society*. 2007;**129**(2):321–327
- [75] Huang Y, Qiu Z, Xu Y, Shi J, Lin H, Zhang Y. Supramolecular hydrogels based on short peptides linked with conformational switch. *Organic & Biomolecular Chemistry* [Internet]. 2011;**9**(7):2149–2155. Available from: www.rsc.org/obc [Accessed: January 11, 2017]
- [76] Shroff K, Rexeisen EL, Arunagirinathan MA, Kokkoli E. Fibronectin-mimetic peptide-amphiphile nanofiber gels support increased cell adhesion and promote ECM production. *Soft Matter* [Internet]. 2010;**6**(20):5064–5072. Available from: <http://xlink.rsc.org/?DOI=c0sm00321b> [Accessed: January 12, 2017]
- [77] Shome A, Dutta S, Maiti S, Das PK. In situ synthesized Ag nanoparticle in self-assemblies of amino acid based amphiphilic hydrogelators: Development of antibacterial soft nanocomposites. *Soft Matter* [Internet]. 2011;**7**(6):3011–3022. Available from: <http://xlink.rsc.org/?DOI=c0sm01087a> [Accessed: January 12, 2017]
- [78] Dutta S, Shome A, Kar T, Das PK. Counterion-induced modulation in the antimicrobial activity and biocompatibility of amphiphilic hydrogelators: Influence of in-situ-synthesized ag-nanoparticle on the bactericidal property. *Langmuir* [Internet]. 2011;**27**(8):5000–5008. Available from: <http://pubs.acs.org/doi/abs/10.1021/la104903z> [Accessed: January 12, 2017]
- [79] Jun H-W, Yuwono V, Paramonov SE, Hartgerink JD. Enzyme-mediated degradation of peptide-amphiphile nanofiber networks. *Advanced Materials* [Internet]. 2005;**17**(21):2612–2617. Available from: <http://doi.wiley.com/10.1002/adma.200500855> [Accessed: January 12, 2017]
- [80] Greenfield MA, Hoffman JR, De La Cruz MO, Stupp SI. Tunable mechanics of peptide nanofiber gels. *Langmuir* [Internet]. 2010;**26**(5):3641–3647. Available from: <http://pubs.acs.org/doi/abs/10.1021/la9030969> [Accessed: January 12, 2017]

- [81] Roy S, Das PK. Antibacterial hydrogels of amino acid-based cationic amphiphiles. *Biotechnology and Bioengineering* [Internet]. 2008;**100**(4):756–764. Available from: <http://doi.wiley.com/10.1002/bit.21803> [Accessed: January 12, 2017]
- [82] Mitra RN, Das PK. In situ preparation of gold nanoparticles of varying shape in molecular hydrogel of peptide amphiphiles. *Journal of Physical Chemistry C* [Internet]. 2008;**112**(22):8159–8166. Available from: <http://pubs.acs.org/doi/abs/10.1021/jp712106d> [Accessed: January 12, 2017]
- [83] Das D, Maiti S, Brahmachari S, Das PK. Refining hydrogelator design: Soft materials with improved gelation ability, biocompatibility and matrix for in situ synthesis of specific shaped GNP. *Soft Matter*. The Royal Society of Chemistry [Internet]. 2011;**7**:7291–7303. Available from: <http://xlink.rsc.org/?DOI=c1sm05608e> [Accessed: January 12, 2017]
- [84] Li X, Kuang Y, Lin H-C, Gao Y, Shi J, Xu B. Supramolecular nanofibers and hydrogels of nucleopeptides. *Angewandte Chemie International Edition* [Internet]. 2011;**50**(40):9365–9369. Available from: <http://doi.wiley.com/10.1002/anie.201103641> [Accessed: January 13, 2017]
- [85] Li X, Kuang Y, Shi J, Gao Y, Lin HC, Xu B. Multifunctional, biocompatible supramolecular hydrogelators consist only of nucleobase, amino acid, and glycoside. *Journal of the American Chemical Society* [Internet]. 2011;**133**(43):17513–17518. Available from: <http://pubs.acs.org/doi/abs/10.1021/ja208456k> [Accessed: January 13, 2017]
- [86] Ruan L, Zhang H, Luo H, Liu J, Tang F, Shi Y-K, et al. Designed amphiphilic peptide forms stable nanoweb, slowly releases encapsulated hydrophobic drug, and accelerates animal hemostasis. *Proceedings of the National Academy of Sciences of the United States of America* [Internet]. 2009;**106**(13):5105–5110. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/19289834> [Accessed: January 13, 2017]
- [87] Caplan MR, Moore PN, Zhang S, Kamm RD, Lauffenburger DA. Self-assembly of a beta-sheet protein governed by relief of electrostatic repulsion relative to van der Waals attraction. *Biomacromolecules*. 2000;**1**(4):627–631
- [88] Kisiday J, Jin M, Kurz B, Hung H, Semino C, Zhang S, et al. Self-assembling peptide hydrogel fosters chondrocyte extracellular matrix production and cell division: Implications for cartilage tissue repair. *Proceedings of the National Academy of Sciences* [Internet]. 2002;**99**(15):9996–10001. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/12119393> [Accessed: January 13, 2017]
- [89] Maity S, Jana P, Haldar D, Davis ME, Atwood JL, Barbour LJ, et al. Fabrication of nanoporous material from a hydrophobic peptide. *CrystEngComm* [Internet]. 2011;**13**(8):3064–3071. Available from: <http://xlink.rsc.org/?DOI=c0ce00701c> [Accessed: January 13, 2017]
- [90] Maity S, Kumar P, Haldar D, Bowerman CJ, Nilson BL, King KN, et al. Sonication-induced instant amyloid-like fibril formation and organogelation by a tripeptide. *Soft Matter* [Internet]. 2011;**7**(11):5239. Available from: <http://xlink.rsc.org/?DOI=c1sm05277b> [Accessed: January 13, 2017]

- [91] Das AK, Bose PP, Drew MGB, Banerjee A. The role of protecting groups in the formation of organogels through a nano-fibrillar network formed by self-assembling terminally protected tripeptides. *Tetrahedron*. 2007;**63**(31):7432–7442
- [92] Banerjee A, Palui G, Banerjee A. Pentapeptide based organogels: The role of adjacently located phenylalanine residues in gel formation. *Soft Matter* [Internet]. 2008;**4**(7):1430–1437. Available from: <http://xlink.rsc.org/?DOI=b802205b> [Accessed: January 13, 2017]
- [93] Baral A, Roy S, Ghosh S, Hermida-Merino D, Hamley IW, Banerjee A. A peptide-based mechano-sensitive, proteolytically stable hydrogel with remarkable antibacterial properties. *Langmuir* [Internet]. 2016;**32**(7):1836–1845. Available from: <http://pubs.acs.org/doi/abs/10.1021/acs.langmuir.5b03789> [Accessed: January 13, 2017]
- [94] Claussen RC, Rabatic BM, Stupp SI. Aqueous self-assembly of unsymmetric peptide bolaamphiphiles into nanofibers with hydrophilic cores and surfaces. *Journal of the American Chemical Society*. 2003;**125**(42):12680–12681
- [95] Tzokova N, Fernyhough CM, Topham PD, Sandon N, Adams DJ, Butler MF, et al. Soft hydrogels from nanotubes of poly(ethylene oxide)-tetraphenylalanine conjugates prepared by click chemistry. *Langmuir* [Internet]. 2009;**25**(4):2479–2485. Available from: <http://pubs.acs.org/doi/abs/10.1021/la8035659> [Accessed: January 16, 2017]
- [96] Aggeli A, Bell M, Boden N, Carrick LM, Strong AE. Self-assembling peptide polyelectrolyte β -Sheet complexes form nematic hydrogels. *Angewandte Chemie International Edition* [Internet]. 2003;**42**(45):5603–5606. Available from: <http://doi.wiley.com/10.1002/anie.200352207> [Accessed: January 13, 2017]
- [97] Zhang S, Lockshin C, Cook R, Rich A. Unusually stable beta-sheet formation in an ionic self-complementary oligopeptide. *Biopolymers* [Internet]. 1994;**34**(5):663–672. Available from: <http://doi.wiley.com/10.1002/bip.360340508> [Accessed: January 13, 2017]
- [98] Zhang S, Holmes TC, DiPersio CM, Hynes RO, Su X, Rich A. Self-complementary oligopeptide matrices support mammalian cell attachment. *Biomaterials*. 1995;**16**(18):1385–1393
- [99] Holmes TC, de Lacalle S, Su X, Liu G, Rich A, Zhang S. Extensive neurite outgrowth and active synapse formation on self-assembling peptide scaffolds. *Proceedings of the National Academy of Sciences of the United States of America* [Internet]. 2000;**97**(12):6728–6733. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/10841570> [Accessed: January 13, 2017]
- [100] Ryan DM, Doran TM, Anderson SB, Nilsson BL. Effect of C-terminal modification on the Self-Assembly and hydrogelation of fluorinated Fmoc-Phe derivatives. *Langmuir* [Internet]. 2011;**27**(7):4029–4039. Available from: <http://pubs.acs.org/doi/abs/10.1021/la1048375> [Accessed: January 13, 2017]
- [101] Aggeli A, Nyrkova IA, Bell M, Harding R, Carrick L, McLeish TC, et al. Hierarchical self-assembly of chiral rod-like molecules as a model for peptide beta-sheet tapes, ribbons, fibrils, and fibers. *Proceedings of the National Academy of Sciences of the United States of America* [Internet]. 2001;**98**(21):11857–11862. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/11592996> [Accessed: January 13, 2017]

- [102] Bowerman CJ, Nilsson BL. A reductive trigger for peptide self-assembly and hydrogelation. *Journal of the American Chemical Society* [Internet]. 2010;**132**(28):9526–9527. Available from: <http://pubs.acs.org/doi/abs/10.1021/ja1025535> [Accessed: January 13, 2017]
- [103] Debnath S, Shome A, Das D, Das PK. Hydrogelation through self-assembly of fmoc-peptide functionalized cationic amphiphiles: Potent antibacterial agent. *Journal of Physical Chemistry B* [Internet]. 2010;**114**(13):4407–4415. Available from: <http://pubs.acs.org/doi/abs/10.1021/jp909520w> [Accessed: January 13, 2017]
- [104] Ren C, Song Z, Zheng W, Chen X, Wang L, Kong D, et al. Disulfide bond as a cleavable linker for molecular self-assembly and hydrogelation. *Chemical Communications* [Internet]. 2011;**47**(5):1619–1621. Available from: <http://xlink.rsc.org/?DOI=C0CC04135A> [Accessed: January 13, 2017]
- [105] Kogiso M, Hanada T, Yase K, Shimizu T. Intralayer hydrogen-bond-directed nano-fiber formation from dicarboxylic valylvaline bolaamphiphiles. *Chemical Communications* [Internet]. 1998;**(2)**:1791–1792. Available from: <http://xlink.rsc.org/?DOI=a803606c> [Accessed: January 16, 2017]
- [106] Franceschi S, de Viguierie N, Riviere M, Lattes A. Synthesis and aggregation of two-headed surfactants bearing amino acid moieties. *New Journal of Chemistry* [Internet]. 1999;**23**(4):447–452. Available from: <http://xlink.rsc.org/?DOI=a809079c> [Accessed: January 16, 2017]
- [107] Diegelmann SR, Hartman N, Markovic N, Tovar JD. Synthesis and alignment of discrete polydiacetylene-peptide nanostructures. *Journal of the American Chemical Society* [Internet]. 2012;**134**(4):2028–2031. Available from: <http://pubs.acs.org/doi/abs/10.1021/ja211539j> [Accessed: January 16, 2017]
- [108] Vadehra GS, Wall BD, Diegelmann SR, Tovar JD. On-resin dimerization incorporates a diverse array of pi-conjugated functionality within aqueous self-assembling peptide backbones. *Chemical communications* [Internet]. 2010;**46**(22):3947–3949. Available from: <http://xlink.rsc.org/?DOI=c0cc00301h> [Accessed: January 16, 2017]
- [109] Mba M, Moretto A, Armelao L, Crisma M, Toniolo C, Maggini M. Synthesis and self-assembly of oligo(p-phenylenevinylene) peptide conjugates in water. *Chemistry - A European Journal* [Internet]. 2011;**17**(7):2044–2047. Available from: <http://doi.wiley.com/10.1002/chem.201002495> [Accessed: January 16, 2017]
- [110] Wall BD, Tovar JD. Synthesis and characterization of π -conjugated peptide-based supramolecular materials. *Pure and Applied Chemistry* [Internet]. 2012;**84**(4):1039–1045. Available from: <http://dx.doi.org/10.1351/PAC-CON-11-10-24> [Accessed: January 16, 2017]
- [111] Wall BD, Diegelmann SR, Zhang S, Dawidczyk TJ, Wilson WL, Katz HE, et al. Aligned macroscopic domains of optoelectronic nanostructures prepared via shear-flow assembly of peptide hydrogels. *Advanced Materials* [Internet]. 2011;**23**(43):5009–5014.

Available from: <http://doi.wiley.com/10.1002/adma.201102963> [Accessed: January 16, 2017]

- [112] Mossuto MF, Bolognesi B, Guixer B, Dhulesia A, Agostini F, Kumita JR, et al. Disulfide bonds reduce the toxicity of the amyloid fibrils formed by an extracellular protein. *Angewandte Chemie International Edition* [Internet]. 2011;**50**(31):7048–7051. Available from: <http://doi.wiley.com/10.1002/anie.201100986> [Accessed: January 16, 2017]
- [113] Li Y, Yan J, Zhang X, Huang K. Disulfide bonds in amyloidogenesis diseases related proteins. *Proteins: Structure, Function and Bioinformatics* [Internet]. 2013;**81**:1862–1873. Available from: <http://doi.wiley.com/10.1002/prot.24338> [Accessed: January 16, 2017]
- [114] Heck SD, Faraci WS, Kelbaugh PR, Saccomano NA, Thadeio PF, Volkmann RA. Posttranslational amino acid epimerization: Enzyme-catalyzed isomerization of amino acid residues in peptide chains. *Proceedings of the National Academy of Sciences of the United States of America* [Internet]. 1996;**93**(9):4036–4039. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/8633012> [Accessed: January 16, 2017]
- [115] Ollivaux C, Soye D, Toullec JY. Biogenesis of D-amino acid containing peptides/proteins: Where, when and how? *Journal of Peptide Science* [Internet]. 2014;**20**:595–612. Available from: <http://doi.wiley.com/10.1002/psc.2637> [Accessed: January 16, 2017]
- [116] Fuchs SA, Berger R, Klomp LWJ, de Koning TJ. D-amino acids in the central nervous system in health and disease. *Molecular Genetics and Metabolism* [Internet]. 2005;**85**(3):168–180. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/15979028> [Accessed: January 16, 2017]
- [117] Kaji Y, Oshika T, Takazawa Y, Fukayama M, Fujii N. Pathological role of D-amino acid-containing proteins and advanced glycation end products in the development of age-related macular degeneration. *Anti-Aging Medicine*. 2010;**7**(10):107–111
- [118] Adhikari B, Nanda J, Banerjee A, Yashima E, Maeda K, Iida H, et al. Multicomponent hydrogels from enantiomeric amino acid derivatives: Helical nanofibers, handedness and self-sorting. *Soft Matter* [Internet]. 2011;**7**(19):8913. Available from: <http://xlink.rsc.org/?DOI=c1sm05907f> [Accessed: January 16, 2017]
- [119] Zhang Y, Gu H, Yang Z, Xu B. Supramolecular hydrogels respond to ligand-receptor interaction. *Journal of the American Chemical Society*. 2003;**125**(45):13680–13681
- [120] Chronopoulou L, Sennato S, Bordi F, Giannella D, Di Nitto A, Barbetta A, et al. Designing unconventional Fmoc-peptide-based biomaterials: Structure and related properties. *Soft Matter* [Internet]. 2014;**10**(12):1944–1952. Available from: <http://xlink.rsc.org/?DOI=c3sm52457d> [Accessed: January 16, 2017]
- [121] Marchesan S, Easton CD, Kushkaki F, Waddington L, Hartley PG. Tripeptide self-assembled hydrogels: Unexpected twists of chirality. *Chemical Communications* [Internet]. 2012;**48**(16):2195–2197. Available from: <http://xlink.rsc.org/?DOI=C2CC16609G> [Accessed: January 16, 2017]

- [122] Haines LA, Rajagopal K, Ozbas B, Salick DA, Pochan DJ, Schneider JP. Light-activated hydrogel formation via the triggered folding and self-assembly of a designed peptide. *Journal of the American Chemical Society*. 2005;**127**(48):17025–17029
- [123] Larsen TH, Branco MC, Rajagopal K, Schneider JP, Furst EM. Sequence-dependent gelation kinetics of β -hairpin peptide hydrogels. *Macromolecules* [Internet]. 2009;**42**(21):8443–8450. Available from: <http://pubs.acs.org/doi/abs/10.1021/ma901423n> [Accessed: January 17, 2017]
- [124] Schneider JP, Pochan DJ, Ozbas B, Rajagopal K, Pakstis L, Kretsinger J. Responsive hydrogels from the intramolecular folding and self-assembly of a designed peptide. *Journal of the American Chemical Society*. 2002;**124**(50):15030–15037
- [125] Ozbas B, Kretsinger J, Rajagopal K, Schneider JP, Pochan DJ. Salt-triggered peptide folding and consequent self-assembly into hydrogels with tunable modulus. *Macromolecules*. 2004;**37**(19):7331–7337
- [126] Pochan DJ, Schneider JP, Kretsinger J, Ozbas B, Rajagopal K, Haines L. Thermally reversible hydrogels via intramolecular folding and consequent self-assembly of a de novo designed peptide. *Journal of the American Chemical Society*. 2003;**125**(39):11802–11803
- [127] Kretsinger JK, Haines LA, Ozbas B, Pochan DJ, Schneider JP. Cytocompatibility of self-assembled β -hairpin peptide hydrogel surfaces. *Biomaterials*. 2005;**26**(25):5177–5186
- [128] Branco MC, Nettesheim F, Pochan DJ, Schneider JP, Wagner NJ. Fast dynamics of semiflexible chain networks of self-assembled peptides. *Biomacromolecules* [Internet]. 2009;**10**(6):1374–1380. Available from: <http://pubs.acs.org/doi/abs/10.1021/bm801396e> [Accessed: January 17, 2017]
- [129] Yucel T, Micklitsch CM, Schneider JP, Pochan DJ. Direct observation of early-time hydrogelation in β -hairpin peptide self-assembly. *Macromolecules* [Internet]. 2008;**41**(15):5763–5772. Available from: <http://pubs.acs.org/doi/abs/10.1021/ma702840q> [Accessed: January 17, 2017]
- [130] Haines-Butterick L, Rajagopal K, Branco M, Salick D, Rughani R, Pilarz M, et al. Controlling hydrogelation kinetics by peptide design for three-dimensional encapsulation and injectable delivery of cells. *Proceedings of the National Academy of Sciences of the United States of America* [Internet]. 2007;**104**(19):7791–7796. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/17470802> [Accessed: January 17, 2017]
- [131] Hule RA, Nagarkar RP, Hammouda B, Schneider JP, Pochan DJ. Dependence of self-assembled peptide hydrogel network structure on local fibril nanostructure. *Macromolecules* [Internet]. 2009;**42**(18):7137–7145. Available from: <http://pubs.acs.org/doi/abs/10.1021/ma9003242> [Accessed: January 17, 2017]
- [132] Nagarkar RP, Hule RA, Pochan DJ, Schneider JP. De novo design of strand-swapped β -hairpin hydrogels. *Journal of the American Chemical Society*. 2008;**130**(13):4466–4474

- [133] Rughani RV., Salick DA, Lamm MS, Yucel T, Pochan DJ, Schneider JP. Folding, self-assembly, and bulk material properties of a de novo designed three-stranded β -sheet hydrogel. *Biomacromolecules* [Internet]. 2009;**10**(5):1295–1304. Available from: <http://pubs.acs.org/doi/abs/10.1021/bm900113z> [Accessed: January 17, 2017]
- [134] Luo Z, Zhao X, Zhang S. Self-organization of a chiral D-EAK16 designer peptide into a 3D nanofiber scaffold. *Macromolecular Bioscience* [Internet]. 2008;**8**(8):785–791. Available from: <http://doi.wiley.com/10.1002/mabi.200800003> [Accessed: January 17, 2017]
- [135] Luo Z, Yue Y, Zhang Y, Yuan X, Gong J, Wang L, et al. Designer D-form self-assembling peptide nanofiber scaffolds for 3-dimensional cell cultures. *Biomaterials*. 2013;**34**(21):4902–4913
- [136] Luo Z, Zhao X, Zhang S. Structural dynamic of a self-assembling peptide d-EAK16 made of only D-amino acids. *PLoS One* [Internet]. 2008;**3**(5):e2364. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/18509542> [Accessed: January 17, 2017]
- [137] Luo Z, Wang S, Zhang S. Fabrication of self-assembling d-form peptide nanofiber scaffold d-EAK16 for rapid hemostasis. *Biomaterials*. 2011;**32**(8):2013–2020
- [138] Bowerman CJ, Ryan DM, Nissan DA, Nilsson BL. The effect of increasing hydrophobicity on the self-assembly of amphipathic beta-sheet peptides. *Molecular BioSystems* [Internet]. 2009;**5**(9):1058–1069. Available from: <http://xlink.rsc.org/?DOI=b904439f> [Accessed: January 17, 2017]
- [139] Bowerman CJ, Liyanage W, Federation AJ, Nilsson BL. Tuning beta-sheet peptide self-assembly and hydrogelation behavior by modification of sequence hydrophobicity and aromaticity. *Biomacromolecules* [Internet]. 2011;**12**(7):2735–2745. Available from: <http://pubs.acs.org/doi/abs/10.1021/bm200510k> [Accessed: January 17, 2017]
- [140] Aggeli A, Bell M, Boden N, Keen JN, McLeish TCB, Nyrkova I, et al. Engineering of peptide β -sheet nanotapes. *Journal of Materials Chemistry* [Internet]. 1997;**7**(7):1135–1145. Available from: <http://xlink.rsc.org/?DOI=a701088e> [Accessed: January 17, 2017]
- [141] Thota CK, Yadav N, Chauhan VS. A novel highly stable and injectable hydrogel based on a conformationally restricted ultrashort peptide. *Scientific Reports* [Internet]. 2016;**6**:31167. Available from: <http://www.nature.com/articles/srep31167> [Accessed: January 23, 2017]
- [142] Panda JJ, Mishra A, Basu A, Chauhan VS. Stimuli responsive self-assembled hydrogel of a low molecular weight free dipeptide with potential for tunable drug delivery. *Biomacromolecules* [Internet]. 2008;**9**(8):2244–2250. Available from: <http://pubs.acs.org/doi/abs/10.1021/bm800404z> [Accessed: January 23, 2017]
- [143] Micklitsch CM, Medina SH, Yucel T, Nagy-Smith KJ, Pochan DJ, Schneider JP. Influence of hydrophobic face amino acids on the hydrogelation of β -hairpin peptide amphiphiles. *Macromolecules*. 2015;**48**(5):1281–1288
- [144] Xie Z, Zhang A, Ye L, Wang X, Feng Z-G. Shear-assisted hydrogels based on self-assembly of cyclic dipeptide derivatives. *Journal of Materials Chemistry* [Internet].

- 2009;**19**(34):6100–6102. Available from: <http://xlink.rsc.org/?DOI=b912020c> [Accessed: January 17, 2017]
- [145] Orbach R, Adler-Abramovich L, Zigerson S, Mironi-Harpaz I, Seliktar D, Gazit E. Self-assembled Fmoc-peptides as a platform for the formation of nanostructures and hydrogels. *Biomacromolecules*. 2009;**10**(9):2646–2651
- [146] Hamley IW, Brown GD, Castelletto V, Cheng G, Venanzi M, Caruso M, et al. Self-assembly of a designed amyloid peptide containing the functional thienylalanine unit. *Journal of Physical Chemistry B* [Internet]. 2010;**114**(32):10674–10683. Available from: <http://pubs.acs.org/doi/abs/10.1021/jp105508g> [Accessed: January 17, 2017]
- [147] Gao YA, Long MJC, Shi J, Hedstrom L, Xu B. Using supramolecular hydrogels to discover the interactions between proteins and molecular nanofibers of small molecules. *Chemical Communications* [Internet]. 2012;**48**(67):8404–8406. Available from: <http://xlink.rsc.org/?DOI=c2cc33631f> [Accessed: January 17, 2017]
- [148] Brinckmann J, Notbohm H, Müller PK. Collagen: Primer in structure, processing and assembly [Internet]. In: Brinckmann J, Notbohm H, Müller PK, editors. Berlin: Springer; 2005. p. 252. Available from: https://books.google.com/books?id=4jH_SuLShWcC&pgis=1 [Accessed: January 17, 2017]
- [149] Hu Y, Wang H, Wang J, Wang S, Liao W, Yang Y, et al. Supramolecular hydrogels inspired by collagen for tissue engineering. *Organic & Biomolecular Chemistry* [Internet]. 2010;**8**(14):3267–3271. Available from: <http://xlink.rsc.org/?DOI=c002609c> [Accessed: January 17, 2017]
- [150] Liyanage W, Nilsson BL. Substituent effects on the self-assembly/coassembly and hydrogelation of phenylalanine derivatives. *Langmuir* [Internet]. 2016;**32**(3):787–799. Available from: <http://pubs.acs.org/doi/abs/10.1021/acs.langmuir.5b03227> [Accessed: January 18, 2017]
- [151] Ryan DM, Anderson SB, Senguen FT, Youngman RE, Nilsson BL. Self-assembly and hydrogelation promoted by F5-phenylalanine. *Soft Matter* [Internet]. 2010;**6**(3):475–479. Available from: <http://xlink.rsc.org/?DOI=B916738B> [Accessed: January 18, 2017]
- [152] Ryan DM, Doran TM, Nilsson BL. Complementary π – π interactions induce multicomponent coassembly into functional fibrils. *Langmuir* [Internet]. 2011;**27**(17):11145–11156. Available from: <http://pubs.acs.org/doi/abs/10.1021/la202070d> [Accessed: January 18, 2017]
- [153] Ryan DM, Anderson SB, Nilsson BL. The influence of side-chain halogenation on the self-assembly and hydrogelation of Fmoc-phenylalanine derivatives. *Soft Matter* [Internet]. 2010;**6**(14):3220–3231. Available from: <http://xlink.rsc.org/?DOI=c0sm00018c> [Accessed: January 18, 2017]
- [154] Bertolani A, Pirrie L, Stefan L, Houbenov N, Haataja JS, Catalano L, et al. Supramolecular amplification of amyloid self-assembly by iodination. *Nature Communications* [Internet]. 2015;**6**:7574. Available from:

way/Gateway.cgi?GWVersion=2&SrcAuth=ORCID&SrcApp=OrcidOrg&DestLinkType=FullRecord&DestApp=WOS_CPL&KeyUT=WOS:000357181200001&KeyUID=WOS:000357181200001

- [155] Shao H, Parquette JR. A π -conjugated hydrogel based on an Fmoc-dipeptide naphthalene diimide semiconductor. Chemical Communications [Internet]. 2010;**46**(24):4285–4287. Available from: <http://xlink.rsc.org/?DOI=c0cc00701c> [Accessed: January 18, 2017]
- [156] Li X, Gao Y, Kuang Y, Xu B. Enzymatic formation of a photoresponsive supramolecular hydrogel. Chemical Communications [Internet]. 2010;**46**(29):5364–5366. Available from: <http://xlink.rsc.org/?DOI=c0cc00163e> [Accessed: January 18, 2017]
- [157] Li X, Li J, Gao Y, Kuang Y, Shi J, Xu B. Molecular nanofibers of olsalazine form supramolecular hydrogels for reductive release of an anti-inflammatory agent. Journal of the American Chemical Society. 2010;**132**(50):17707–17709
- [158] Rughani RV, Branco MC, Pochan DJ, Schneider JP. *De novo* design of a shear-thin recoverable peptide-based hydrogel capable of intrafibrillar photopolymerization. Macromolecules [Internet]. 2010;**43**(19):7924–7930. Available from: <http://pubs.acs.org/doi/abs/10.1021/ma1014808> [Accessed: January 18, 2017]
- [159] Mata A, Hsu L, Capito R, Aparicio C, Henrikson K, Stupp SI. Micropatterning of bioactive self-assembling gels. Soft Matter [Internet]. 2009;**5**(6):1228–1236. Available from: <http://xlink.rsc.org/?DOI=b819002j> [Accessed: January 13, 2017]
- [160] Zhang Y, Li N, Delgado J, Gao Y, Kuang Y, Fraden S, et al. Post-self-assembly cross-linking of molecular nanofibers for oscillatory hydrogels. Langmuir. 2012;**28**(6):3063–3066
- [161] Matson JB, Stupp SI. Drug release from hydrazone-containing peptide amphiphiles. Chemical Communications [Internet]. 2011;**47**(28):7962–7964. Available from: <http://xlink.rsc.org/?DOI=c1cc12570b> [Accessed: January 18, 2017]
- [162] Cheng G, Castelletto V, Moulton CM, Newby GE, Hamley IW. Hydrogelation and self-assembly of Fmoc-tripeptides: Unexpected influence of sequence on self-assembled fibril structure, and hydrogel modulus and anisotropy. Langmuir [Internet]. 2010;**26**(7):4990–4998. Available from: <http://pubs.acs.org/doi/abs/10.1021/la903678e> [Accessed: January 18, 2017]
- [163] Yang Z, Wang L, Wang J, Gao P, Xu B. Phenyl groups in supramolecular nanofibers confer hydrogels with high elasticity and rapid recovery. Journal of Materials Chemistry [Internet]. 2010;**20**(11):2128–2132. Available from: <http://xlink.rsc.org/?DOI=b922858f> [Accessed: January 18, 2017]
- [164] Yang Z, Xu K, Wang L, Gu H, Wei H, Zhang M, et al. Self-assembly of small molecules affords multifunctional supramolecular hydrogels for topically treating simulated uranium wounds. Chemical Communications [Internet]. 2005;**101**(35):4414–4416. Available from: <http://xlink.rsc.org/?DOI=b507314f> [Accessed: January 18, 2017]
- [165] Guler MO, Stupp SI. A self-assembled nanofiber catalyst for ester hydrolysis. Journal of the American Chemical Society. 2007;**129**(40):12082–12083

- [166] Micklitsch CM, Knerr PJ, Branco MC, Nagarkar R, Pochan DJ, Schneider JP. Zinc-triggered hydrogelation of a self-assembling β -hairpin peptide. *Angewandte Chemie International Edition* [Internet]. 2011;**50**(7):1577–1579. Available from: <http://doi.wiley.com/10.1002/anie.201006652> [Accessed: January 19, 2017]
- [167] Hartgerink JD. Self-assembly and mineralization of peptide-amphiphile nanofibers. *Science* [Internet]. 2001;**294**(5547):1684–1688. Available from: <http://www.sciencemag.org/cgi/doi/10.1126/science.1063187> [Accessed: January 19, 2017]
- [168] Stendahl JC, Rao MS, Guler MO, Stupp SI. Intermolecular forces in the self-assembly of peptideamphiphilenanofibers. *Advanced Functional Materials* [Internet]. 2006;**16**(4):499–508. Available from: <http://doi.wiley.com/10.1002/adfm.200500161> [Accessed: January 19, 2017]
- [169] Ding Y, Li Y, Qin M, Cao Y, Wang W. Photo-cross-linking approach to engineering small tyrosine-containing peptide hydrogels with enhanced mechanical stability. *Langmuir* [Internet]. 2013;**29**(43):13299–13306. Available from: <http://pubs.acs.org/doi/abs/10.1021/la4029639> [Accessed: January 19, 2017]
- [170] Su RSC, Kim Y, Liu JC. Resilin: Protein-based elastomeric biomaterials. *Acta Biomaterialia*. 2014;**10**:1601–1611
- [171] Guillemin R. Peptides in the brain. The new endocrinology of the neuron. *Science*. 1978;**202**(4366):390–402
- [172] Schally AV. Aspects of hypothalamic regulation of the pituitary gland with major emphasis on its implications for the control of reproductive processes. *Materia Medica Polona*. 1980;**12**(1–2):9–27
- [173] Yalow RS. Radioimmunoassays: A probe for fine structure of biologic systems. *Medical Physics*. 1978;**5**(4):247–257
- [174] Maji SK, Schubert D, Rivier C, Lee S, Rivier JE, Riek R. Amyloid as a depot for the formulation of long-acting drugs. In: Weissman JS, editor. *PLoS Biology* [Internet]. 2008;**6**(2):240–52. Available from: <http://dx.plos.org/10.1371/journal.pbio.0060017> [Accessed: January 19, 2017]
- [175] Xing B, Yu CW, Chow KH, Ho PL, Fu D, Xu B. Hydrophobic interaction and hydrogen bonding cooperatively confer a vancomycin hydrogel: A potential candidate for biomaterials. *Journal of the American Chemical Society*. 2002;**124**(50):14846–14847
- [176] Qvit N, Rubin SJS, Urban TJ, Mochly-Rosen D, Gross ER. Peptidomimetic therapeutics: Scientific approaches and opportunities. *Drug Discovery Today*. 2017;**22**(2):454–462
- [177] Venkatesan N, Kim BH. Synthesis and enzyme inhibitory activities of novel peptide isosteres. *Current Medicinal Chemistry* [Internet]. 2002;**9**(24):2243–2270. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/12470245> [Accessed: January 20, 2017]
- [178] Avan I, Hall CD, Katritzky AR. Peptidomimetics via modifications of amino acids and peptide bonds. *Chemical Society Reviews* [Internet]. 2014;**43**(10):3575–3594. Available from: <http://xlink.rsc.org/?DOI=c3cs60384a> [Accessed: January 20, 2017]

- [179] Gante J. Peptidomimetics—Tailored enzyme inhibitors. *Angewandte Chemie International Edition in English* [Internet]. 1994;**33**(17):1699–1720. Available from: <http://doi.wiley.com/10.1002/anie.199416991> [Accessed: January 19, 2017]
- [180] Jones JH. Words derived from the noun peptide. *Journal of Peptide Science* [Internet]. 2006;**12**(2):79–81. Available from: <http://doi.wiley.com/10.1002/psc.724> [Accessed: January 20, 2017]
- [181] Gopalan RD, Del Borgo MP, Mechler AI, Perlmutter P, Aguilar MI. Geometrically precise building blocks: The self-assembly of beta-peptides. *Chemistry and Biology*. 2015;**22**:1417–1423
- [182] Yang Z, Liang G, Xu B. Supramolecular hydrogels based on beta-amino acid derivatives. *Chemical Communications* [Internet]. 2006;**97**(7):738–740. Available from: <http://xlink.rsc.org/?DOI=b516133a> [Accessed: January 20, 2017]
- [183] Yang Z, Liang G, Ma M, Gao Y, Xu B. In vitro and *in vivo* enzymatic formation of supramolecular hydrogels based on self-assembled nanofibers of a beta-amino acid derivative. *Small* [Internet]. 2007;**3**(4):558–562. Available from: <http://doi.wiley.com/10.1002/sml.200700015> [Accessed: January 20, 2017]
- [184] Nanda J, Banerjee A. β -Amino acid containing proteolitically stable dipeptide based hydrogels: Encapsulation and sustained release of some important biomolecules at physiological pH and temperature. *Soft Matter* [Internet]. 2012;**8**(12):3380–3386. Available from: <http://xlink.rsc.org/?DOI=c2sm07168a> [Accessed: January 20, 2017]
- [185] Castelletto V, Cheng G, Greenland BW, Hamley IW, Harris PJF. Tuning the self-assembly of the bioactive dipeptide l-carnosine by incorporation of a bulky aromatic substituent. *Langmuir* [Internet]. 2011;**27**(6):2980–2988. Available from: <http://pubs.acs.org/doi/abs/10.1021/la104495g> [Accessed: January 20, 2017]
- [186] Nguyen MM, Eckes KM, Suggs LJ. Charge and sequence effects on the self-assembly and subsequent hydrogelation of Fmoc-depsipeptides. *Soft matter* [Internet]. 2014;**10**(15):2693–2702. Available from: <http://xlink.rsc.org/?DOI=c4sm00009a> [Accessed: January 20, 2017]
- [187] Makarević J, Jokić M, Perić B, Tomišić V, Kojić-Prodić B, Žinić M. Bis(Amino Acid) oxalyl amides as ambidextrous gelators of water and organic solvents: Supramolecular gels with temperature dependent assembly/dissolution equilibrium. *Chemistry—A European Journal* [Internet]. 2001;**7**(15):3328–3341. Available from: <http://doi.wiley.com/10.1002/1521-3765%2820010803%297%3A15%3C3328%3A%3AAID-CHEM3328%3E3.0.CO%3B2-C> [Accessed: January 20, 2017]
- [188] Jokić M, Makarević J, Žinić M. A novel type of small organic gelators: Bis(amino acid) oxalyl amides. *Journal of the Chemical Society Chemical Communications* [Internet]. 1995;**17**(17):1723–1724. Available from: <http://xlink.rsc.org/?DOI=C39950001723> [Accessed: January 20, 2017]

- [189] Frkanec L, Jokić M, Makarević J, Wolsperger K, Žinić M. Bis(PheOH) maleic acid amide-fumaric acid amide photoisomerization induces microsphere-to-gel fiber morphological transition: The photoinduced gelation system. *Journal of the American Chemical Society*. 2002;**124**(33):9716–9717
- [190] Castellucci N, Angelici G, Falini G, Monari M, Tomasini C. L-Phe-D-Oxd: A privileged scaffold for the formation of supramolecular materials. *European Journal of Organic Chemistry* [Internet]. 2011;**2011**(16):3082–3088. Available from: <http://doi.wiley.com/10.1002/ejoc.201001643> [Accessed: January 20, 2017]
- [191] Castellucci N, Falini G, Angelici G, Tomasini C. Formation of gels in the presence of metal ions. *Amino Acids* [Internet]. 2011;**41**(3):609–620. Available from: <http://link.springer.com/10.1007/s00726-011-0908-0> [Accessed: January 20, 2017]
- [192] Castellucci N, Sartor G, Calonghi N, Parolin C, Falini G, Tomasini C. A peptidic hydrogel that may behave as a “trojan Horse.” *Beilstein Journal of Organic Chemistry* [Internet]. 2013;**9**:417–424. Available from: <http://www.beilstein-journals.org/bjoc/content/9/1/44> [Accessed: January 20, 2017]
- [193] Milli L, Zanna N, Merlettini A, Di Giosia M, Calvaresi M, Focarete ML, et al. Pseudopeptide-based hydrogels trapping methylene blue and eosin Y. *Chemistry—A European Journal* [Internet]. 2016;**22**(34):12106–12112. Available from: <http://doi.wiley.com/10.1002/chem.201601861> [Accessed: January 20, 2017]
- [194] Rajbhandary A, Nilsson BL. Investigating the effects of peptoid substitutions in self-assembly of Fmoc-Diphenylalanine derivatives. *Biopolymers* [Internet]. 2016;**108**. Available from: <http://doi.wiley.com/10.1002/bip.22994> [Accessed: January 20, 2017]

IntechOpen