We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Kinetics of Heterogeneous Self-Propagating High-Temperature Reactions

Christopher E. Shuck and Alexander S. Mukasyan

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/intechopen.70560>

Abstract

In this chapter, we present an overview of experimental techniques utilized and kinetic data collected for exothermic self-sustained noncatalytic heterogeneous reactions. The data focuses on five primary experimental techniques: electrothermal explosion, differential thermal analysis, electrothermography, combustion velocity/temperature analyses, and several advanced in situ diagnostics, including time-resolved X-ray diffraction.

Keywords: self-propagating high-temperature synthesis (SHS), electrothermal explosion, electrothermography, combustion synthesis, mechanical activation, high-energy ball milling, intermetallics, thermites

1. Introduction

Self-propagating high-temperature synthesis (SHS) is a technological approach for fabrication of materials, which involves self-sustained noncatalytic reactions [1–3]. Currently, there exist three major types of SHS systems: (i) gasless; (ii) with gasification of initially solid precursors; (iii) gas-solid. Within gasless systems, there are three major types of chemical reactions that occur: metal-metal, producing intermetallic (e.g., NiAl, NiTi), metal-nonmetal, leading to synthesis of borides, carbides and silicides (e.g., TiB₂, TaC, MoSi₂); nonmetal-nonmetal, producing ceramics (e.g., B₄C, SiC). In the gasification reactions, one of the precursors is volatile, including such elements as S, Se, P, As, Sb. Finally, the gas-solid systems include reactions between metals or nonmetals with different gases, such as nitrogen, oxygen, hydrogen, CO, and CO₂ leading to formation of nitrides, oxides, hydrides and etc. These lists are by no means exhaustive, as different research groups are continually exploring the limits of SHS reactions with different systems, reactants, and conditions. In order to obtain materials with desired

microstructures, and thus properties, one has to precisely control the synthesis conditions during SHS. These conditions are primarily defined by the kinetics of the chemical reactions taking place in the combustion wave.

In order to study and understand the kinetics of SHS reactions, it is important to examine the fundamentals of kinetics and how they relate to SHS itself. Let us start with general definitions. Thus, assuming that the concentrations of any initial reagent, c_i , and the product are uniformly distributed throughout the entire volume (homogeneous or quasi homogeneous cases), the chemical reaction rate can be expressed by the following equation:

$$W_i = \frac{dC_i}{dt} \quad \text{or} \quad W_i = \frac{d\eta_i}{dt} \quad (1)$$

where W_i is the reaction rate for the i^{th} reagent or product, $\eta_i = (c_i^0 - c_i)/c_i^0$ is the degree of conversion for the i^{th} reagent, c_i^0 is the initial concentration of the i^{th} reagent, and t is time.

In the nineteenth century, C.M. Guldberg with P. Waage and N.N. Beketov independently formulated the law of mass action. This essentially states that the chemical reaction rates at a given point are proportional to the concentration (mass) of the reactants raised to a proportional exponent. Thus, for an elementary chemical reaction between two reagents A and B of the following form:

where ν_1, ν_2 are stoichiometric coefficients.

For this reaction, the law of mass action can be written in the form of a kinetic equation:

$$W = k c_A^{\nu_1} c_B^{\nu_2}, \quad (3)$$

where k is the reaction rate constant.

Along with the reactant concentration, the temperature affects the rate of the chemical reaction in a noncatalytic homogeneous reaction. However, the mechanisms of these processes are often unknown or too complicated. This is because the reactions occur in multiple steps, each of which has unique reaction rates. In order to describe the chemical kinetics, a single-step approximation is typically used. This states that the rate of the processes in the condensed state is generally a function of the temperature and degree of conversion:

$$\frac{d\eta}{dt} = F(T, \eta) \quad (4)$$

The single-step approximation employs the assumption that the function in Eq. (4) can be expressed as a product of two separable functions that are independent of each other; the first, $K(T)$, depends solely on the temperature, T , and the second, $\Phi(\eta)$, depends solely on the degree of conversion, η :

$$\frac{d\eta}{dt} = K(T)\Phi(\eta) \quad (5)$$

The temperature function $K(T)$ is generally considered to be the rate constant, while the conversion function $\Phi(\eta)$ is generally considered represent the process mechanism. It is assumed that the reaction mechanism is solely dependent on the conversion, and not the temperature. Eq. (3) resembles a single-step kinetic equation, even though it represents the kinetics of a complex condensed-phase process. The single-step kinetic approximation results in the substitution of a generally complex set of kinetic equations with the sole single-step kinetic equation. Eq. (5) represents a mathematical formulation of the single-step kinetic approximation. With few exceptions, the temperature function is exclusively expressed by the Arrhenius equation:

$$K(T) = A \exp(-E_a/RT) \quad (6)$$

where A and E_a are considered to be the pre-exponential factor and the activation energy, respectively, T is the absolute temperature, and R is the gas constant.

As our knowledge about the atomic and molecular structure of matter increased, coupled with the development of quantum mechanics, new directions in chemical kinetics have emerged. These directions are typically related to the interactions of individual atoms and molecules, which are more fundamental studies. The set of elementary events is called the reaction mechanism. Fundamental studies on the reaction mechanisms allow us to formulate physical explanations to the kinetic parameters (A , E_a , etc.), which were originally introduced as empirical constants. For example, the activation energy E_a is an energy barrier that must be overcome by molecules in the reaction mixture to reach an interatomic distance where they can form a chemical bond. From Eq. (5), it is clear that, if the concentration of substances or the temperature in the given system varies from point to point. Thus, it is impossible to introduce a common reaction rate for the entire system. In order to get closer to these ideal conditions, in classical kinetic experiments we must continuously mix the reagents and maintain a constant temperature by use of a thermostat.

In the case of heterogeneous reactions involving a condensed phase, where the reactants are not mixed on the molecular level, there is an additional parameter, which controls the rate of interaction, i.e., the contact surface area (S) between the reagents [2]. In this case, the rate of the chemical reactions can be represented as follows:

$$\frac{d\eta}{dt} = A \cdot S \cdot \Phi(\eta) \exp(-E_a/RT) \quad (7)$$

The presence of condensed phases complicates the reaction; this phase requires that transport plays a role in the reaction. Thus, in general, the kinetics of such reactions are determined both by the intrinsic rate of the chemical reaction and by mass transport (e.g., diffusion). The transport phenomena are essential for replenishing the reactants that were consumed in the reaction zone [4]. Describing the reaction rate is further complicated when the temperature of the reacting environment is changing with time. In this case, along with the processes of mass

transfer and chemical reactions, it is necessary to consider the specifics of heat transfer mechanisms [5]. Typically, the activation parameters are obtained after experiments considering the dependences of time vs. temperature (for isothermal measurements), temperature vs. heating rate (for integral and incremental methods with linear heating rates), or from reaction rate vs. temperature. Considering the above limitations and complications, only the effective or apparent activation energy can truly be considered, as it includes both the intrinsic kinetics as well as processes of heat and mass transport.

2. Techniques for studying SHS kinetics

The task of accurately determining kinetics becomes even more complicated when accounting for the extremely high temperatures of SHS processes (>1800 K) and rapid heating rates (10^3 – 10^5 K/s). Such parameters are essentially impossible to achieve using conventional approaches for measurement of kinetics parameters. While standard nonisothermal TGA/DTA-based approaches [6] are still used to evaluate the kinetics of SHS reactions, several unique methods such as electrothermal explosion (ETE) [7] and electrothermography (ET) [8] were specifically developed to fit the experimental conditions of SHS reactions. Moreover, recently a variety of advanced in situ diagnostics, including time-resolved X-ray diffraction (TRXRD) [9], high-speed X-ray phase-contrast imaging [10], and high speed transmission electron microscopy (HSTEM) [11] were modified to obtain the kinetics of phase transformations during SHS reactions.

3. Electrothermal explosion

The ETE method was developed in 1977 to study the rapid, high-temperature kinetics that occur in SHS systems [7]. It relies on rapid, uniform preheating of the sample until adiabatic thermal explosion occurs. A representation of a typical ETE setup is shown in **Figure 1**. Briefly, the sample is clamped between two metallic electrodes with sufficient clamping pressure to ensure adequate contact. The power is then initiated, leading to preheating of the sample until a set T_{off} point. After initiation, the resulting time-temperature profiles are simultaneously collected across a number of high-speed photodiodes. In the commonly used ETA-100 system (Aloft, Inc., Berkley, CA), there are 16 photodiodes present, with 1 mm in between them; this corresponds to 0.5 mm spatial resolution. The photodiodes have a temporal resolution of 10^{-5} s and are accurate within 900–3000 K. Once the sample is heated to the selected T_{off} point, the equipment heating is halted, with the consequent rate of self-heating determined solely by the chemical reaction rate. Due to the experimental conditions, i.e., the rapid initial preheating, the reaction occurs in the adiabatic mode. Once thermal ignition occurs, analysis of the time-temperature profile enables extraction of the kinetic parameters (see details in [12]). This technique can be used to study the kinetics at temperatures much higher than can be achieved in other experiments. However, it is often limited in the systems that can be studied due to the stringent heating conditions caused by Joule preheating.

ETE has been used for different gasless SHS systems. These studies have provided valuable kinetic data in extremely high-temperature ranges that are essentially inaccessible by other

Figure 1. Summary of data collected using the electrothermal explosion technique.

methods. For carbides, the Ti/C system has been studied [13–15], with additional studies in the Ta/C [14, 16] and Si/C [14, 17] mixtures. The Ti/B system was also investigated [18]. The majority of ETE work being focused on the Ni/Al system [12, 19–21]. The Ti/Fe₂O₃ system is the only thermite system investigated by ETE [22]. In addition to the experimental studies, a number of theoretical models have been developed to better understand the ETE process [23–26]. **Figure 1** shows that ranges of reported activation energies for the above mentioned gasless systems, including both intermetallics and thermites obtained by ETE. It can be seen that the results are reproducible, confirming the reliability of the ETE approach. Additionally, the technique allows for a more complete understanding of systems that have multiple steps that rapidly occur in the high-temperature regime, which gives insight into the combustion process [2].

4. Differential thermal analysis/differential scanning calorimetry

This technique has been extensively used in many fields, including: polymer science, biochemistry, and materials science. In order to utilize these methods, a sample is heated at a constant rate until the maximum set temperature is reached. Throughout the experiment, the heat release characteristics of the sample are measured against an inert reference standard.

For typical systems, the points of differing heat release characteristics can be due to phase transitions, crystallization, or reactions; however, this section will only focus on SHS-reaction kinetics. In order to determine the reaction kinetics, the experiment is conducted multiple times with different heating rates. The classical method for determining the reaction kinetics, specifically the activation energy, is by use of the Kissinger method [27], however, many alternative methods for data analysis have been suggested and are widely utilized [28–34]. The activation energy, E_a , can be computed by plotting $\ln(\beta/T_p^2)$ as a function of $1/T_p$, where T_p is the peak temperature (**Figure 2**).

The DTA/DSC based methods are the most widely used for gasless SHS systems, with multiple studies into intermetallics, specifically the Ni/Al [35–43], Ti/Al [44–46], Co/Al [47], Al/Ru [48], Nb/Al [49], and Mg/Al [50] systems, in addition to other binary solid-solid compositions, i.e., the Si/C [51], Mo/Si [52], Zr/B [53], Fe/Se [54]. More complicated ternary systems were also investigated [54–61]. In general, a wide variety of factors can influence the measured kinetics, including variations in reactant microstructure, heating rates, among other factors. Although there are a number of studies into the same systems, it would be valuable for systematic work to be conducted where these factors are studied in depth across different systems to see what

Figure 2. Summary of data collected using isothermal kinetic analysis methods.

general conclusions can be drawn. Additionally, because the experimental conditions, typically specifically heating rate and temperature ranges, are not the same as in traditional SHS, it is unclear whether the determined values can be directly compared or if there is some systemic difference that is occurring.

Figure 2 illustrates the ranges of the obtained values of activation energies for a variety of gasless exothermic reactions measured by DTA method. It can be seen that the determined values are dependent on the experimental conditions utilized, including variations in reactant microstructure, heating rates, among other factors. This issue is discussed in detail below. It would be valuable for systematic studies to be done where these factors are studied in depth across different systems. Additionally, while the activation energies reported using different DTA-based approaches does not appear to be significantly different, it is still important to understand why these differences are present and which methods of analysis are most suitable for these systems.

5. Combustion velocity/temperature analysis

There has been significant effort done to accurately correlate experimental combustion parameters, such as combustion wave velocity and temperature, with the kinetics parameters. Two major approaches have been developed to determine the activation energy by measuring the layer-by-layer combustion front combustion velocity. The first was suggested in 1977 by Merzhanov for 1D propagation [62]. The derived equation takes the form:

$$v^2 = \frac{\lambda}{(-\Delta H_r)\rho} \frac{RT_c^2}{E} \frac{k_0 \exp\left(-\frac{E}{RT_c}\right)}{f(\eta_s)} \quad (8)$$

where $f(\eta_s)$ is the selected kinetic law. This technique is most commonly used by adding diluent to the sample. This affects the combustion velocity and temperature; the change in both of these values is measured then compared, leading to the kinetic relationship being understood.

The other major approach to determining the kinetics based on the velocity was developed by Boddington et al. [63]. The relationship takes the form:

$$\frac{\partial \eta}{\partial t} = \frac{\left[\frac{T - T_0}{t_d - t_r} + \frac{\partial T}{\partial t} - \left(\frac{\alpha}{v^2} \right) \left(\frac{\partial^2 T}{\partial t^2} \right) \right]}{\tau_{ad}} \quad (9)$$

where t_d and t_r are the decay and rise times, with τ_{ad} being the temperature rise under adiabatic conditions. More complete derivations of these two models can be found in the original articles [62–64]. Additionally, a more complete understanding of these models, including their relative merits, has been examined in a number of prior works [65–68]. In order to properly use these techniques, relatively simple equipment is required. Typically, sets of thermocouples are used to measure combustion wave propagation velocities, but there are many alternatives, such as IR or high-speed cameras, to measure the propagation velocity.

Figure 3. Summary of data collected using layer velocity analysis approached for (a) binary elemental and (b) thermite systems.

Because of the relative simplicity in using these techniques, they have found widespread use within SHS reactions. These layer velocity approaches have been used to describe the kinetics in the Ni/Al system [69, 70], in boride systems, including Nb/B [71–73], Ta/B [71], Zr/B [71, 74, 75], Hf/B [71], Ti/B [76], Mo/B [77], along with other binary systems such as Ti/C [78], Ti/Si [79, 80], thermites [81–89] and more complex ternary systems [78, 90–93].

The results obtained are presented in **Figure 3**. It can be seen that there are a wide variety of systems analyzed. It worth noting that these data were obtained through direct analysis of the combustion parameters, which were obtained at extremely high temperatures and rapid heating rates, which are difficult to accomplish by other kinetics methods. However, it is important to remember that the quasi-homogeneous approximation is utilized for this layer-by-layer combustion front combustion velocity based method, which should be applied with caution [68]. Finally, because this method can be easily used for any type of system, a comparison between thermite and non-thermite type reactions can be analyzed. Comparing **Figure 3a** and **b**, it is obvious that the activation energies for thermites is significantly lower than non-thermite type reactions. This is interesting and is likely related to the specific reaction mechanism that occurs in thermites, compared to non-thermites.

6. Electrothermography

Electrothermography is a technique that utilizes metal wires in either a gaseous or clad environment [8]. The wire is resistively heated rapidly to the desired temperature, with the electric power being adjusted to compensate for the heat release due to the chemical reaction. The obtained data allows for extraction of the rate of heat generation during the reaction under

conditions similar to those in SHS wave. Additionally, because the wires are thin, the sample is quenched essentially as soon as the power is turned off. After the wire is cooled, cross-sections of the wire are collected and the width of the product films is measured, which allows for information on the kinetics of phase formation. This, when done at multiple temperatures and times, gives a more complete picture of the reaction mechanism.

The electrothermography technique has been widely used to study gas-solid reactions. This is because the wires can be exposed to any sort of gaseous environment and also because of the equipment itself; the wires can be heated with any heating rate, mirroring those found in conventional SHS reactions. Because of this, a number of experiments were conducted in nitrogen environments. In specific, the Ta/N [94], Ti/N [95–98], Nb/N [98, 99], and Zr/N [8] systems have been studied. However, the technique has also been used to study carbides, including the Ti/C [100], Zr/C [100], W/C [101], Nb/C [102], along with other systems, including Mo/Si [103–106], W/Si [107, 108], Ni/Al [109], and Ni/Ti [109].

Figure 4 shows the values of the activation energies obtained by this method in gas-solid systems. It can be seen that some reactions have limited steps relating to the gas pressure, while others are relatively independent, suggesting that there are different mechanisms for the

Figure 4. Summary of data obtained using the electrothermography approach.

two classes of reactions. This is also true for the gasless systems investigated. This method provides a window into determining the mechanism and, due to the nature of the experiment, allows for control over the experimental conditions to the degree that individual steps in the reaction can be isolated.

7. Modern in situ high-speed high-resolution methods

There currently exist a number of techniques to study in situ reactions on the time and length scales that occur during SHS reactions; these techniques are incredibly valuable to determine the reaction mechanisms. The most widespread technique is time-resolved X-ray diffraction (TRXRD), and is used to determine the phases that are present during the reaction. It allows for information on the phases present at every stage of the reaction, depending on the time resolution. The lower the time resolution, the more information that can be attained. Depending on the specific setup, whether synchrotron or laboratory-scale based, time resolutions ranging from 10^{-6} to 10^{-2} s are reasonable, with the absolute limit being continually improved with improved synchrotron and detector technology. There has been significant work done with SHS systems due to their solid nature, which is simple to use in TRXRD systems. It is possible to measure solid solution formations, intermediate phases, any melting processes, and the general reaction progress. Through these data it should be possible to extract kinetic data on all reaction stages based on the growth rates of the peaks for the new phase formation coupled with the decomposition of peaks from the previous phase, however, there are currently no established models illustrating this.

There have been a wide variety of experiments conducted on SHS systems by a number of different groups. For intermetallic systems, groups have studied the Ni–Al [9, 110–116], Fe–Al [111, 117–121], Nb–Al [122–124], and numerous other systems [110, 125–127]. Additionally, many groups have examined other SHS based systems, such as carbides, including Ti–C [110, 128, 129], Ta–C [129, 130], and other carbides and cermets [129, 131–134], nitrides [135, 136], oxides [137–139], silicides, including Fe–Si [140, 141], Mo–Si [119, 123, 142, 143] and Ti–Si [144, 145], among a variety of other systems [113, 129, 146–155].

In addition to TRXRD, there is a variety of other, less common, but still very useful techniques available. For example, high-speed X-ray phase-contrast imaging [10] utilizes a synchrotron source coupled with the fact that different phases absorb X-rays differently to determine which phase transformations occur during reaction, essentially high-speed X-ray phase contrast imaging. This technique was illustrated on the W–Si system at the Advanced Proton Source in Argonne National Laboratory. This method allowed for direct imaging of irreversible reactions in the W–Si reactive system at frame rates up to 36,000 frames per second with a 4- μ s exposure time and spatial resolution of 10 μ m. Another advanced technique is high-speed transmission electron microscopy (HSTEM) [11], which utilizes all abilities of conventional TEM, but at nanosecond time scales. This allows for direct observation of both the structural changes and crystal structure during the reaction with unprecedented resolution, as shown in **Figure 5**. Specifically, a high-time resolution dynamic transmission electron microscopy (DTEM) was developed in Lawrence Livermore National Laboratory (USA) and captures the material

Figure 5. Dynamic single-shot diffraction with 15-ns time resolution of regions before, during, and after the exothermic mixing reaction front has passed. The times indicated at right are in relation to the reaction front, set at $t = 0$ s. The crystal structure clearly changes from separate fcc Al/Ni and Ni/V layers to an intermetallic B2 structure NiAl phase within 300 ns after the arrival of the hot reaction front; a.u., arbitrary units. Adapted from Kim et al. [11].

dynamics with nanosecond time resolution. The current DTEM performance shows a spatial resolution less than 10 nm for single-shot imaging, using 15 ns electron pulses. The solid-state reactions in NiAl reactive multilayer films, the martensitic transformations in nanocrystalline Ti, and the catalytic growth of Si nanowires were studied by DTEM [156].

The above unique diagnostics, which are used to determine phase and structural transformations in situ, are incredibly valuable. Used alone, they provide information on the reaction progress and mechanism; however, there are two significant paths that would make these techniques more valuable. When coupled with current methods for determination of kinetics, the understanding of the reaction mechanisms in all systems will be improved. Furthermore, there is no current way to extract kinetic parameters from some techniques (TRXRD, DTEM, etc.); it would be valuable to develop reliable approaches for these techniques.

8. Structure-kinetics relationship of SHS systems

There have been a number of studies shown that indicated that the structure of materials plays a role in the kinetics; multiple groups using a wide variety of techniques and approaches have confirmed this conclusion. For example, it was shown that by changing the internal structure

of the reactive composite by using high-energy ball milling (HEBM) in the same binary system, one can significantly change the measured effective activation energy [20]. There are two approaches to quantifying this effect; the first is by rigorous quantification of the already existing structures, and the second is by use of more simple, so-called model microstructures, typically manifested in reactive nanofoils with periodically fabricated layers of reactants.

Shuck et al. utilized two techniques for quantitative determination of HEBM-produced materials [5, 157]. The first technique, X-ray Nanotomography, works by passing high brilliance X-rays through the sample and collecting the transmitted X-rays. In order to convert this 2D projection into three dimensions, the sample is rotated and the same quality of X-rays is passed through again and the projections at different angles are collected; this collection of images can be combined, leading to a 3D map of the internal sample. The second technique, focused ion beam (FIB) sectioning, uses a FIB to serially section the HEBM-produced particles. The series of images were first shear corrected, contrast normalized, and then aligned using a least-squares method, with the reconstructions shown in **Figure 6**. After structure analysis, Shuck and

Figure 6. Reconstructed internal volumes of the nanocomposites for different time (min) of WG: (a) 10, (b) 20, (c) 30, and (d) 40 (Ni is the gray phase, and Al is the void-space). Adapted from Shuck et al. [5].

Figure 7. Dependence of effective activation energy of the reaction as a function specific contact surface area between Ni and Al phases. Adapted from Shuck and Mukasyan [20].

Mukasyan [20] further studied these effects on the kinetics in the Ni–Al system using the ETE approach. They showed, by use of the above 3D reconstruction techniques, that it is possible to control the activation energy by modification of the contact surface area between the reactants. Effectively, they lowered the effective activation energy from 79 to 137 kJ/mol, which corresponded to a change in the contact surface area/volume ratio between 0.0120 and 0.0032 nm^{-1} , respectively; this relationship is shown in **Figure 7**. Additionally, it was suggested that, for SHS systems, the apparent activation energy is affected primarily by the contributions between the diffusion and intrinsic reaction activation energies. Additionally, they offered an explanation for the relationship, relating to the difference in contribution between the diffusive activation energies (volume, grain-boundary, and surface) in conjunction with the intrinsic activation energy. This suggests that the measured and reported activation energies presented in literature are effective, or apparent, activation energies that depend highly on the structure and experimental conditions.

9. Modification of the reaction mechanism depending on the experimental conditions

In a very early study on the reaction mechanisms, Philpot et al. examined the effect of varying factors on the reaction rate [35]. In one study, they systematically varied the aluminum concentration, the heating rate, and the nickel particle size. Briefly, they showed that, depending on the applied heating rate, two different mechanisms could be initiated. The first, when using slower heating rates, was related to the melting of the aluminum metal, followed by spreading over the nickel particles. For their studies, they saw two definite peaks relating to the reaction.

Figure 8. DTA-TG curves for the PTFE- Al_2O_3 system using heating rates of (a) 20, (b) 80, (c) 150, and (d) $160^\circ\text{C min}^{-1}$ under an argon atmosphere. The additional lines are showing the changes in heat flow and mass percentage values. Adapted from Hobosyan et al. [56].

However, when they increased the heating rate, they instead only witnessed a single peak. This peak was related to the solid state transition to the final product. For transitional values between the two extremes, they found that there were relative contributions of both different mechanisms. This is an important observation which should be accounted when investigating the reaction kinetics in highly exothermic systems. Indeed, it shows that it is possible to control the reaction mechanism depending on the applied experimental conditions. This effect was confirmed by many researchers both for gasless and gas-solid systems [36, 56, 158–162] and is illustrated in **Figure 8**. Furthermore, depending on the reaction mechanism, it is possible to control both the final product phases and their microstructures, thus producing materials with tailored properties.

10. The Ni/Al system as a model for SHS kinetics

In the SHS community, the Ni/Al system has been widely used a model system. It was chosen because of its low ignition temperature, high oxidation resistance, and ease of processing. Because of this, all of the above mentioned techniques have been utilized to study kinetics in

this system. Thus it is possible to compare the data collected across a large number of experimental conditions to give more complete understanding of this gasless reaction. Although this system has been extensively studied for over 40 years now, a consensus has not emerged on the exact activation energy, as can be seen in **Figure 9**. The data again illustrate the effect that differing experimental conditions play, whether in the material structure, heating rates, or other experimental factors.

In 1987, Philpot et al. did preliminary studies on the Ni/Al system kinetics using the Kissinger approach [35]. They showed that there is an effect of heating rate, the nickel particle size, as well as an effect of a varying Al content, on the reaction mechanism in this system [35], this work is highlighted in more detail in an above section. Hunt et al. examined the effect of particle size on the apparent activation energy using a CO₂ laser to control the heating coupled with the DTA-based Kissinger approach. Using 800 nm size Ni particles coupled with 20 μ m, 4 μ m, 80 nm, and 40 nm Al particles, it was found that that these reactions had activation energies of: 103.5 ± 10.5 , 97.3 ± 5 , 21.2 ± 2.5 , and 17.4 ± 2.85 kJ/mol, respectively [36]. They then increased the Ni size to 15 μ m and measured with the four Al sizes, resulting in 162.5 ± 1.4 , 131.2 ± 2.6 , 103.6 ± 5.2 , and 80.1 ± 6.3 kJ/mol, respectively [36]. This confirms that the initial reactant structure plays a significant impact on the kinetics. The size of either reactant significantly alters the effective kinetics. Kim et al. studied this reaction using nanolaminated composite micro-foils with different thickness ratios between Ni and Al at heating rates between 5 and 100 K/min. For 4:1 foils, they found that the formation of NiAl₃ occurred, followed by Ni₂Al₃, with activation energies of 142 and 106 kJ/mol, respectively [37].

Figure 9. Summary of kinetic data collected for the Ni/Al system.

In order to more fully understand the relationship between structure and the kinetics, White et al. investigated the effect of mechanical activation (MA) on the Ni/Al system kinetics using the Kissinger approach. Two types of Ni/Al composites were used; Ni clad Al particles, as well as Ni/Al composite particles produced by high-energy ball milling (HEBM). The Ni clad Al particles were found to have an apparent activation energy of 352 ± 8 kJ/mol, while after MA the particles had much lower activation energy of 117 ± 4 kJ/mol [38]. Reeves et al. studied the thermal and impact reaction kinetics in the Ni/Al system for both MA and nano-sized reactants using the Kissinger approach. For the nano-mixture, the reactants were both ~ 80 nm in size and, for the MA particles, they underwent 15 minutes of HEBM. The nano-mixture exhibited a 230 ± 21 kJ/mol activation energy, while the MA mixture was calculated to be 117 ± 8 kJ/mol [39]. Manukyan et al. studied the Ni/Al system after MA and the effect of a coarse vs. nanolaminated nanostructure on the kinetics using the Kissinger approach. Using heating rates between 10 and 50 K/min, they found that the reaction proceeds in three steps, NiAl_3 , Ni_2Al_3 , and then finally NiAl. For the coarse microstructure, these peaks corresponded to 99 ± 4 , 138 ± 13 , and 120 ± 37 kJ/mol, while the nanolaminated microstructure corresponded to 93 ± 2.5 , 145 ± 13 , and 146 ± 14 kJ/mol, respectively [40]. This illustrated that the activation energies depend on the microstructure, even after MA.

Kuk et al. studied compression bonded Ni/Al nanofolios with and without a BN lubricant using the Kissinger approach. With the BN lubricant, it was found that the reaction proceeded in two steps, with the activation energies being 224 and 272 kJ/mol, respectively, resulting in the formation of Al_3Ni_2 [42]. Without the lubricant, the reaction proceeded in a single step with activation energy of 470 kJ/mol, this difference was attributed to the oxide layer between the reactants [42]. Maiti and Ghoroi studied the Ni/Al system using the Friedman, Ozawa, and Kissinger approach, yielding activation energies of 437.0, 448.4, and 457.6 kJ/mol, respectively [43].

Using the ETE approach, Shteinberg et al. and Mukasyan et al. confirmed that MA affects the activation energy in the Ni/Al system, as shown in **Figure 10** [12, 19]. Initially, they studied the kinetics of the Ni clad Al system (which was also studied in [38]), which showed two distinct steps. The first step was related to the melting of Al and subsequent cracking of the Ni layer, which had an activation energy of 197 ± 29 kJ/mol. The final step was the diffusion of Ni into Al, which was measured as 523 ± 84 kJ/mol. In the MA system, they found that only a single step occurred and was measured to be 105 ± 13 kJ/mol. Shuck and Mukasyan further studied the effects of MA on the kinetics in the Ni/Al system using the ETE approach [20]. Using 3D reconstruction techniques, they showed that the surface area contact between the reactions is directly related to the effective activation energy, which ranged from 79 to 137 kJ/mol, which corresponded to a change in the contact surface area/volume ratio between 0.0120 and 0.0032 nm^{-1} , respectively. This work is further highlighted in an above section. Finally, using the ETE approach, Filimonov et al. studied the effects of MA on the nonstoichiometric, 3Ni/Al system [21]. They utilized a criterion based on the minimum curvature of the heating rate logarithm, which resulted in an anomalously low measured activation energy of 9.5 ± 2 kJ/mol.

Marin-Ayral et al. studied the Ni/Al system under different gas pressures using the Boddington-Laye method. They showed that for pressures of 100, 320, and 500 MPa, the measured activation energies were 47, 59, and 132 kJ/mol, respectively [68, 69]. Vadchenko et al. studied the Ni/Al

Figure 10. Arrhenius plots for reactions in Al clad by Ni systems before and after high energy ball milling. Adapted from Shteinberg et al. [12].

system using electrothermography. Their results showed that the reactions occur first through grain boundary diffusion, followed by diffusion of the solid metal into the liquid phase [109]. Finally, Mukasyan et al. examined the Ni/Al system using a combination of TRXRD and ETE, showing that the reaction mechanism itself changes based on the structure, this work is highlighted in an above section [116].

Thus we may conclude that although a wide variety of studies were conducted on the Ni/Al system with many different experimental and structural conditions, the reported values of activation energies vary drastically. Additionally, there would be great benefit to combining utilizing multiple methods simultaneously to bridge understanding between the different experimental techniques.

11. Future directions in SHS kinetics

More complete understanding on the kinetics of SHS reactions is vital for both fundamental science and also for practical or industrial reasons. To better understand the kinetics, combinations of techniques must be utilized, specifically coupling techniques that give information on the kinetics while simultaneously examining the phase transformations that are occurring. To further understand the reaction mechanisms, additional studies must be conducted on the relationship between the structure and the resulting kinetics. Additionally, work must be done to compare the different methods of studying kinetics and their interrelationships. In the limited cases where there is data available for the same system across different techniques,

there is a wide range of published kinetic data. It is imperative to continue to study SHS kinetics in a more systematic, fundamental fashion.

Acknowledgements

This work was supported by the Department of Energy, National Nuclear Security Administration, under the award number DE-NA0002377 as part of the Predictive Science Academic Alliance Program II. We also acknowledge the Ministry of Education and Science of the Russian Federation specifically Increase Competitiveness Program of NUST 'MISiS' (No. K2-2016-065), implemented by a governmental decree dated 16th of March 2013, N 211. Finally, this work was also supported by the U.S. Department of State through the Fulbright program.

Author details

Christopher E. Shuck¹ and Alexander S. Mukasyan^{1,2*}

*Address all correspondence to: amoukasi@nd.edu

1 Department of Chemical and Biomolecular Engineering, University of Notre Dame, Notre Dame, Indiana, United States

2 University of Notre Dame and National University of Science and Technology MISiS, Moscow, Russia

References

- [1] Merzhanov AG, Borovinskaya IP. Self-spreading high-temperature synthesis of refractory compounds. *Doklady Chemistry*. 1972;**204**(2):429-431
- [2] Rogachev AS, Mukasyan AS. *Combustion for Materials Synthesis*. CRC Press, Taylor and Francis; 2015
- [3] Gorban AN, Yablonsk GS. Three waves of chemical dynamics. *Mathematical Modelling of Natural Phenomena*. 2015;**10**(5):1-5
- [4] Shuck CE, Manukyan KV, Rouvimov S, Rogachev AS, Mukasyan AS. Solid-flame: Experimental validation. *Combustion and Flame*. 2016;**162**:487-493
- [5] Shuck CE, Pauls JM, Mukasyan AS. Ni/Al energetic nanocomposites and the solid flame phenomenon. *Journal of Physical Chemistry C*. 2016;**120**(47):27066-27078
- [6] Šimon P. Isoconversional methods. *Journal of Thermal Analysis and Calorimetry*. 2004;**76**(1):123-132

- [7] Merzhanov AG, Borovinskaya IP, Shteinberg AS, Kochetov OA, Ulybin VB, Shipilov VV. Method for production of the refractory compounds, 2130084/22-02. Russian patent: Bulletin Izobreteniy. 1977;**46**:64
- [8] Merzhanov AG, Grigorev YM, Kharatyan SL, Mashkinov LB, Vartanyan ZS. Study on heat-evolution kinetics at high-temperature nitration of zirconium wires. Fizika Goreniya i Vzryva. 1975;**11**(4):563-568
- [9] Boldyrev VV, Aleksandrov VV, Korchagin MA, Tolochko BP, Guzenko SN, Sokolov AS, Sheromov MA, Lyakhov NZ. Study of phase formation dynamics at nickel monoaluminide synthesis in combustion regime. Doklady Akademii Nauk SSSR. 1981;**259**(5):1127-1129
- [10] Reeves RV, White JDE, Dufresne EM, Fezzaa K, Son SF, Varma A, Mukasyan AS. Microstructural transformations and kinetics of high-temperature heterogeneous gasless reactions by high-speed X-ray phase-contrast imaging. Physical Review B. 2009;**80**:224103
- [11] Kim JS, LaGrange T, Reed BW, Taheri ML, Armstrong MR, King WE, Browning ND, Campbell GH. Imaging of transient structures using nanosecond in situ TEM. Science. 2008;**321**(5895):1472-1475
- [12] Shteinberg AS, Lin YC, Son SF, Mukasyan AS. Kinetics of high temperature reaction in Ni-Al system: Influence of mechanical activation. The Journal of Physical Chemistry. A. 2010;**114**(20):6111-6116
- [13] Knyazik VA, Merzhanov AG, Solomonov VB, Shteinberg AS. Macrokinetics of high-temperature titanium interaction with carbon under electrothermal explosion conditions. Combustion, Explosion and Shock Waves. 1985;**21**(3):333-337
- [14] Knyazik V, Shteinberg A, Gorovenko V. Thermal analysis of high-speed high-temperature reactions of refractory carbide synthesis. Journal of Thermal Analysis and Calorimetry. 1993;**40**(1):363-371
- [15] Kostogorova JY, Viljoen HJ, Shteinberg AS. Study of the high-temperature solid-phase titanium-carbon reaction. Industrial & Engineering Chemistry Research. 2003;**42**(26):6714-6719
- [16] Knyazik V. High-temperature interaction in the Ta-C system under electrothermal explosion conditions. Journal of Materials Synthesis and Processing. 1993;**1**(2):85-92
- [17] Gorovenko VI, Knyazik VA, Shteinberg AS. High-temperature interaction between silicon and carbon. Ceramics International. 1993;**19**(2):129-132
- [18] Popov KV, Knyazik VA, Shteinberg AS. Study of high-temperature reaction of Ti with B by the method of electrothermal explosion. Combustion, Explosion and Shock Waves. 1993;**29**(1):77-81
- [19] Mukasyan AS, Khina BB, Reeves RV, Son SF. Mechanical activation and gasless explosion: Nanostructural aspects. Chemical Engineering Journal. 2011;**174**(2):677-686
- [20] Shuck CE, Mukasyan AS. Reactive Ni/Al nanocomposites: Structural characteristics and activation energy. The Journal of Physical Chemistry. A. 2017;**121**(6):1175-1181

- [21] Filimonov VY, Korchagin MA, Smirnov EV, Lyakhov NZ. Macrokinetics of solid-phase synthesis of an activated 3Ni+ Al mixture in the thermal explosion mode. *Combustion, Explosion and Shock Waves*. 2010;**46**(4):449-456
- [22] Lin YC, Shteinberg AS, McGinn PJ, Mukasyan AS. Kinetics study in Ti-Fe₂O₃ system by electro-thermal explosion method. *International Journal of Thermal Sciences*. 2014;**84**: 369-378
- [23] Shilyaev MI, Borzykh VÉ, Dorokhov AR, Ovcharenko VE. Determination of thermokinetic parameters from the inverse problem of an electrothermal explosion. *Combustion, Explosion and Shock Waves*. 1992;**28**(3):258-262
- [24] Bostandzhiyan S, Gordopolova I, Shcherbakov V. Modeling of an electrothermal explosion in gasless systems placed into an electroconducting medium. *Combustion, Explosion and Shock Waves*. 2013;**49**(6):668-675
- [25] Bostandzhiyan SA, Gordopolova IS, Shcherbakov AV, Shcherbakov VA. Electrothermal explosion in cylindrical Ti-C charges covered with a TiC shell: A mathematical model. *International Journal of Self-Propagating High-Temperature Synthesis*. 2012;**21**(3):183-188
- [26] Bostandzhiyan SA, Shcherbakov AV, Shcherbakov VA. Mathematical modeling of electrothermal explosion in gasless systems placed in a hollow dielectric cylinder. *International Journal of Self-Propagating High-Temperature Synthesis*. 2016;**25**(2):75-79
- [27] Kissinger HE. Reaction kinetics in differential thermal analysis. *Analytical Chemistry*. 1957;**29**(11):1702-1706
- [28] Borchardt HJ, Daniels F. The application of differential thermal analysis to the study of reaction kinetics. *Journal of the American Chemical Society*. 1957;**79**(1):41-46
- [29] Friedman HL. Kinetics of thermal degradation of char-forming plastics from thermogravimetry. Application to a phenolic plastic. *Journal of Polymer Science: Polymer Symposia*. 1964;**6**(1):183-195
- [30] Ozawa T. A quick, a new method of analyzing thermogravimetric data. *Bulletin of the Chemical Society of Japan*. 1965;**38**(11):1881-1886
- [31] Flynn JH, Wall LA. Direct method for the determination of activation energy from thermogravimetric data. *Journal of Polymer Science Part C: Polymer Letters*. 1966;**4**(5): 323-328
- [32] Ozawa T. Kinetics of non-isothermal crystallization. *Polymer*. 1971;**12**(3):150-158
- [33] Starink MJ. A new method for the derivation of activation energies from experiments performed at constant heating rate. *Thermochimica Acta*. 1996;**288**(1-2):97-104
- [34] Vyazovkin S, Wight CA. Model-free and model-fitting approaches to kinetic analysis of isothermal and nonisothermal data. *Thermochimica Acta*. 1999;**340**:53-68

- [35] Philpot KA, Munir ZA, Holt JB. An investigation of the synthesis of nickel aluminides through gasless combustion. *Journal of Materials Science*. 1987;**22**(1):159-169
- [36] Hunt EM, Pantoya ML. Ignition dynamics and activation energies of metallic thermites: from nano-to micron-scale particulate composites. *Journal of Applied Physics*. 2005;**98**(3):034909
- [37] Kim HY, Chung DS, Hong SH. Reaction synthesis and microstructures of NiAl/Ni micro-laminated composites. *Materials Science and Engineering: A*. 2005;**396**(1):376-384
- [38] White JD, Reeves RV, Son SF, Mukasyan AS. Thermal explosion in Al-Ni system: Influence of mechanical activation. *Journal of Physical Chemistry C*. 2009;**113**(48):13541-13547
- [39] Reeves RV, Mukasyan AS, Son SF. *Journal of Physical Chemistry C*. 2010;**114**(35):14772-14780
- [40] Manukyan KV, Mason BA, Groven LJ, Lin YC, Cherukara M, Son SF, Strachan A, Mukasyan AS. Tailored reactivity of Ni+ Al nanocomposites: Microstructural correlations. *Journal of Physical Chemistry C*. 2012;**116**(39):21027-21038
- [41] Baghdasaryan AM, Hobosyan MA, Khachatryan HL, Niazyan OM, Kharatyan SL, Sloyan LH, Grigoryan YG. The role of chemical activation on the combustion and phase formation laws in the Ni-Al-promoter system. *Chemical Engineering Journal*. 2002;**188**:210-215
- [42] Kuk SW, Yu J, Ryu HJ. Effects of interfacial Al oxide layers: Control of reaction behavior in micrometer-scale Al/Ni multilayers. *Materials & Design*. 2015;**84**:372-377
- [43] Maiti SC, Ghoroi C. Thermo-kinetic analysis of Ni -al intermetallic phase formation in powder system. *Journal of Thermal Analysis and Calorimetry*. 2016;**124**(2):1039-1051
- [44] Illeková E, Gachon JC, Rogachev A, Grigoryan H, Schuster JC, Nosyrev A, Tsygankov P. Kinetics of intermetallic phase formation in the Ti/Al multilayers. *Thermochimica Acta*. 2008;**469**(1):77-85
- [45] Sina H, Iyengar S. Reactive synthesis and characterization of titanium aluminides produced from elemental powder mixtures. *Journal of Thermal Analysis and Calorimetry*. 2015;**122**(2):689-698
- [46] Adeli M, Seyedein SH, Aboutalebi MR, Kobashi M, Kanetake N. Implementation of DSC analysis in reaction kinetics during heating of Ti-50 at.% Al powder mixture. *Journal of Thermal Analysis and Calorimetry*. 2017;**128**(2):867-874
- [47] Reeves RV, Adams DP. Reaction instabilities in Co/Al nanolaminates due to chemical kinetics variation over micron-scales. *Journal of Applied Physics*. 2014;**115**(4):044911
- [48] Pauly C, Woll K, Bax B, Mücklich F. The role of transitional phase formation during ignition of reactive multilayers. *Applied Physics Letters*. 2015;**107**(11):113104

- [49] Mostaan H, Karimzadeh F, Abbasi MH. Synthesis and formation mechanism of nano-structured NbAl₃ intermetallic during mechanical alloying and a kinetic study on its formation. *Thermochimica Acta*. 2012;**529**:36-44
- [50] Zhou Y, Zhu Y, Zhu Y, Li L. Phase transformation, kinetics and thermodynamics during the combustion synthesis of Mg₂Al₃ alloy. *Journal of Alloys and Compounds*. 2015;**628**:257-262
- [51] Hu Q, Zhang M, Luo P, Song M, Li J. Thermal explosion synthesis of ZrC particles and their mechanism of formation from Al-Zr-C elemental powders. *International Journal of Refractory Metals and Hard Materials*. 2012;**35**:251-256
- [52] Takacs L, Soika V, Baláz P. The effect of mechanical activation on highly exothermic powder mixtures. *Solid State Ionics*. 2001;**141**:641-647
- [53] Lee D, Sim GD, Xiao K, Vlassak JJ. Low-temperature synthesis of ultra-high-temperature coatings of ZrB₂ using reactive multilayers. *Journal of Physical Chemistry C*. 2014;**118**(36):21192-21198
- [54] Liu G, Li J, Chen K. Reaction mechanism in fast combustion synthesis of superconducting FeSe and FeSe_{0.7}Te_{0.3}. *Acta Materialia*. 2017;**122**:187-198
- [55] Kim BG, Lee YW, Lee JW, Choi Y. Formation mechanism of C/SiC/C multi-layers during self-propagating high-temperature synthesis. *Surface and Coatings Technology*. 2002;**151**:26-30
- [56] Hobosyan MA, Kirakosyan KG, Kharatyan SL, Martirosyan KS. PTFE -Al₂O₃ reactive interaction at high heating rates. *Journal of Thermal Analysis and Calorimetry*. 2015;**119**(1): 245-251
- [57] Pathak LC, Bandyopadhyay D, Srikanth S, Das SK, Ramachandrarao P. Effect of heating rates on the synthesis of Al₂O₃-SiC composites by the self-propagating high-temperature synthesis (SHS) technique. *Journal of the American Ceramic Society*. 2001;**84**(5):915-920
- [58] Choi Y, Rhee SW. Reaction of TiO₂-Al-C in the combustion synthesis of TiC-Al₂O₃ composite. *Journal of the American Ceramic Society*. 1995;**78**(4):986-992
- [59] Zhu H, Jiang Y, Yao Y, Song J, Li J, Xie Z. Reaction pathways, activation energies and mechanical properties of hybrid composites synthesized in-situ from Al-TiO₂-C powder mixtures. *Materials Chemistry and Physics*. 2012;**137**(2):532-542
- [60] Rafiei M, Enayati MH, Karimzadeh F. Kinetic analysis of thermite reaction in Al-Ti-Fe₂O₃ system to produce (Fe, Ti)₃Al-Al₂O₃ nanocomposite. *Powder Technology*. 2014;**253**:553-560
- [61] Jordan JL, Thadhani NN. Effect of shock-activation on post-shock reaction synthesis of ternary ceramics. *AIP Conference Proceedings*. 2002;**620**(1):1097-1100
- [62] Merzhanov AG. New elementary combustion models of 2nd kind. *Doklady Akademii Nauk SSSR*. 1977;**233**(6):1130-1133
- [63] Boddington T, Laye PG, Tipping J, Whalley D. Kinetic analysis of temperature profiles of pyrotechnic systems. *Combustion and Flame*. 1986;**63**(3):359-368

- [64] Boddington T, Cottrell A, Laye PG. Combustion transfer in gasless pyrotechnics. *Combustion and Flame*. 1990;**79**(3–4):234-241
- [65] Laye PG, Constantinou CP, Volk F. Experimental studies of the propagation of combustion in solids [and discussion]. *Philosophical Transactions of the Royal Society A*. 1992;**339**(1654):387-394
- [66] Varma A, Lebrat JP. Combustion synthesis of advanced materials. *Chemical Engineering Science*. 1992;**47**(9–11):2179-2194
- [67] Baras F. Determination of transport and kinetic properties in self-propagating high-temperature synthesis. *Journal of Alloys and Compounds*. 2008;**455**(1):113-120
- [68] Mukasyan AS, Rogachev AS. Discrete reaction waves: Gasless combustion of solid powder mixtures. *Progress in Energy and Combustion Science*. 2008;**34**(3):377-416
- [69] Dumez MC, Marin-Ayral RM, Tédénac JC. The role of experimental parameters in combustion synthesis of NiAl under high gas pressure. *Journal of Alloys and Compounds*. 1998;**268**(1):141-151
- [70] Marin-Ayral RM, Dumez MC, Tédénac JC. Influence of high gas pressure on combustion synthesis of the solid-solid reaction of NiAl compound. *Materials Research Bulletin*. 2000;**35**(2):233-243
- [71] Zenin AA, Merzhanov AG, Nersisyan GA. Thermal wave structure in SHS processes. *Combustion, Explosion and Shock Waves*. 1981;**17**(1):63-71
- [72] Yeh CL, Chen WH. Preparation of niobium borides NbB and NbB₂ by self-propagating combustion synthesis. *Journal of Alloys and Compounds*. 2006;**420**(1):111-116
- [73] Yeh CL, Chen WH. A comparative study on combustion synthesis of Nb-B compounds. *Journal of Alloys and Compounds*. 2006;**422**(1):78-85
- [74] Munir ZA. Reaction synthesis processes: Mechanisms and characteristics. *Metallurgical Transactions A*. 1992;**23**(1):7-13
- [75] Dunmead SD, Munir ZA, Holt JB. Temperature profile analysis of combustion in the Zr-B system using the Boddington-Laye method. *International Journal of Self-Propagating High-Temperature Synthesis*. 1992;**1**:22-32
- [76] Holt JB, Kingman DD, Bianchini GM. Kinetics of the combustion synthesis of TiB₂. *Materials Science and Engineering*. 1985;**71**:321-327
- [77] Yeh CL, Hsu WS. Preparation of MoB and MoB-MoSi₂ composites by combustion synthesis in SHS mode. *Journal of Alloys and Compounds*. 2007;**440**(1):193-198
- [78] Dunmead SD, Readey DW, Semler CE, Hol JB. *Journal of the American Ceramic Society*. 1989;**72**(12):2318-2324
- [79] Wang LL, Munir ZA. *Metallurgical and Materials Transactions B*. 1995;**26**(3):595-601

- [80] Kachelmyer CR, Varma A, Rogachev AS, Sytshev AE. Kinetics of combustion synthesis in the Ti-C and Ti-C-Ni systems. *Industrial & Engineering Chemistry Research*. 1998;**37**(6): 2246-2249
- [81] Boddington T, Laye PO. Temperature dependence of the burning velocity of gasless pyrotechnics. *Thermochimica Acta*. 1987;**120**:203-206
- [82] Drennan RL, Brown ME. Binary and ternary pyrotechnic systems of Mn and/or Mo and BaO₂ and/or SrO₂: Part 3. Kinetic aspects. *Thermochimica Acta*. 1992;**208**:247-259
- [83] Anil Rugunanan R, Brown ME. Combustion of binary and ternary silicon/oxidant pyrotechnic systems, part IV: Kinetic aspects. *Combustion Science and Technology*. 1993;**95**(1-6):117-138
- [84] Brown M. Some thermal studies on pyrotechnic compositions. *Journal of Thermal Analysis and Calorimetry*. 2001;**65**(2):323-334
- [85] Tribelhorn MJ, Blenkinsop MG, Brown ME. Combustion of some iron-fuelled binary pyrotechnic systems. *Thermochimica Acta*. 1995;**256**(2):291-307
- [86] Tribelhorn MJ, Venables DS, Brown ME. Combustion of some zinc-fuelled binary pyrotechnic systems. *Thermochimica Acta*. 1995;**256**(2):309-324
- [87] Jakubko J. Combustion of the silicon-red lead system. Temperature of burning, kinetic analysis and mathematical model. *Combustion Science and Technology*. 1999;**146**(1-6): 37-55
- [88] Manukyan KV, Kirakosyan KG, Grigoryan YG, Niazyan OM, Yeghishyan AV, Kirakosyan AG, Kharatyan SL. Mechanism of molten-salt-controlled thermite reactions. *Industrial & Engineering Chemistry Research*. 2011;**50**(19):10982-10988
- [89] Won HI, Nersisyan HH, Won CW. A macrokinetic study of the WO₃/Zn reaction diluted with NaCl. *Chemical Engineering Journal*. 2009;**153**(1):193-198
- [90] LaSalvia JC, Meyers MA. Combustion synthesis in the Ti-C-Ni-Mo system: Part II, analysis. *Metallurgical and Materials Transactions A*. 1995;**26**(11):3011-3019
- [91] Tomasi R, Munir ZA. Effect of particle size on the reaction wave propagation in the combustion synthesis of Al₂O₃-ZrO₂-Nb composites. *Journal of the American Ceramic Society*. 1999;**82**(8):1985-1992
- [92] Marinšek M, Kemperl J, Likozar B, Macek J. Temperature profile analysis of the citrate-nitrate combustion system. *Industrial & Engineering Chemistry Research*. 2008;**47**(13): 4379-4386
- [93] Marinšek M. Analysis of the temperature profiles during the combustion synthesis of doped lanthanum gallate. *Materiali in tehnologije*. 2008;**42**(2):85-91
- [94] Vadchenko SG, Grigoriev YM, Merzhanov AG. The kinetics of high-temperature tantalum nitriding. *Bulletin Akademii Nauk USSR Metals*. 1980;**5**:223-229

- [95] Pelekh AE, Mukasyan AS, Varma A. Kinetics of rapid high-temperature reactions: Titanium-nitrogen system. *Industrial & Engineering Chemistry Research*. 1999;**38**(3): 793-798
- [96] Pelekh A, Mukasyan A, Varma A. Electrothermography apparatus for kinetics of rapid high-temperature reactions. *The Review of Scientific Instruments*. 2000;**71**(1):220-223
- [97] Thiers L, Leitenberger BJ, Mukasyan AS, Varma A. Influence of preheating rate on kinetics of high-temperature gas-solid reactions. *AIChE Journal*. 2000;**46**(12):2518-2524
- [98] Thiers L, Mukasyan AS, Pelekh A, Varma A. Kinetics of high-temperature reaction in titanium-nitrogen system: Nonisothermal conditions. *Chemical Engineering Journal*. 2001;**82**(1):303-310
- [99] Vadchenko SG, Grigor'ev YM. Investigation of kinetics and mechanism of high temperature nitridation of niobium. *Izvestiya Akademii Nauk USSR Metallurgy*. 1979;187-195
- [100] Vadchenko SG, Grigorev YM, Merzhanov AG. Non-isothermal kinetics and mechanism of tungsten siliconizing in gasless combustion wave. *Combustion, Explosion and Shock Waves*. 1976;**12**(5):606-612
- [101] Kharatyan SL, Chatilyan HA, Arakelyan LH. Regularities of heat release in tungsten siliconizing in a gasless combustion wave. *Materials Research Bulletin*. 2008;**43**(4):897-906
- [102] Adamyan TA, Kharatyan SL. Reaction diffusion in Mo-Si system above the melting point of silicon. *Journal of Alloys and Compounds*. 2010;**496**(1):418-422
- [103] Galstyan GS, Chatilyan HA, Kirakosyan AG, Kharatyan SL, Mukasyan AS, Varma A. Diffusion annealing of Mo/MoSi₂ couple and silicon diffusivity in Mo₅Si₃ layer. *Defect and Diffusion Forum*. 2005;**237**:873-878
- [104] Chatilyan HA, Kharatyan SL, Harutyunyan AB. Growth kinetics of Mo₃Si layer in the Mo₅Si₃/Mo diffusion couple. *Materials Science and Engineering: A*. 2007;**459**(1):227-232
- [105] Kharatyan SL, Chatilyan HA, Galstyan GS. Non-isothermal phenomena in Mo/Si diffusion couple: Reaction kinetics and structure formation. *Thin Solid Films*. 2008;**516**(15): 4876-4881
- [106] Kharatyan SL, Chatilyan HA, Aghayan MA, Rodriguez MA. Investigation of the mechanism of the ignition and combustion of the systems Ti+ C, Zr+ C by an electrothermographic method. *International Journal of Self-Propagating High-Temperature Synthesis*. 2013;**22**(1):18-26
- [107] Kharatyan SL, Chatilyan HA. On the singularity of high temperature carbidization of niobium. *International Journal of Self-Propagating High-Temperature Synthesis*. 1999; **8**:31-42
- [108] Kharatyan SL, Chatilyan AA. Kinetics of tungsten carbidization under non-isothermal conditions. *Combustion, Explosion and Shock Waves*. 2000;**36**(3):342-348

- [109] Vadchenko SG, Bulaev AM, Gal'chenko YA, Merzhanov AG. Interaction mechanism in laminar bimetal nickel-titanium and nickel-aluminum systems. *Combustion, Explosion and Shock Waves*. 1987;**23**(6):706-715
- [110] Wong J, Larson EM, Holt JB, Waide PA, Rupp B, Frahm R. Time-resolved X-ray diffraction study of solid combustion reactions. *Science*. 1990;**249**:1406-1410
- [111] Bernard F, Gaffet E, Gramond M, Gailhanou M, Gachon JC. Simultaneous Ir and time-resolved X-ray diffraction measurements for studying self-sustained reactions. *Journal of Synchrotron Radiation*. 2000;**7**(1):27-33
- [112] Curfs C, Turrillas X, Vaughan GBM, Terry AE, Kvik Å, Rodríguez MA. Al-Ni intermetallics obtained by SHS: A time-resolved X-ray diffraction study. *Intermetallics*. 2007;**15**(9):1163-1171
- [113] Tingaud D, Stuppfler L, Paris S, Vrel D, Bernard F, Penot C, Nardou F. Time-resolved X-ray diffraction study of SHS-produced NiAl and NiAl-ZrO₂ composites. *International Journal of Self-Propagating High-Temperature Synthesis*. 2007;**16**(1):12-17
- [114] Trenkle JC, Koerner LJ, Tate MW, Gruner SM, Weihs TP, Hufnagel TC. Phase transformations during rapid heating of Al/Ni multilayer foils. *Applied Physics Letters*. 2008;**93**(8):081903
- [115] Kovalev DY, Kochetov NA, Ponomarev VI, Mukasyan AS. Effect of mechanical activation on thermal explosion in Ni-Al mixtures. *International Journal of Self-Propagating High-Temperature Synthesis*. 2010;**19**(2):120-125
- [116] Mukasyan AS, White JDE, Kovalev DY, Kochetov NA, Ponomarev VI, Son SF. Dynamics of phase transformation during thermal explosion in the Al-Ni system: Influence of mechanical activation. *Physica B*. 2010;**405**(2):778-784
- [117] Gaffet E, Charlot F, Klein D, Bernard F, Niepce JC. Mechanically activated SHS reaction in the Fe-Al system: In situ time resolved diffraction using synchrotron radiation. *Materials Science Forum*. 1998;**269**:379-384
- [118] Bernard F, Charlot F, Gaffet E, Niepce JC. Optimization of MASHS parameters to obtain a nanometric FeAl intermetallic. *International Journal of Self-Propagating High-Temperature Synthesis*. 1998;**7**:233-248
- [119] Charlot F, Gras C, Gramond M, Gaffet E, Bernard F, Niepce JC. Développements Récents De L'étude En Temps Réel Par Diffraction Des Rayons X Couplée À Une Thermographie Infrarouge: Application Au Suivi De La Réaction MASHS Dans Les Systèmes FeAl, Et MoSi₂. *Le Journal de Physique IV*. 1998;**8**(PR5):497-504
- [120] Charlot F, Bernard F, Gaffet E, Klein D, Niepce JC. In situ time-resolved diffraction coupled with a thermal Ir camera to study mechanically activated SHS reaction: Case of Fe-Al binary system. *Acta Materialia*. 1998;**47**(2):619-629
- [121] Vrel D, Girodon-Boulandet N, Paris S, Mazue JF, Couqueberg E, Gailhanou M, Thiaudiere D, Gaffet E, Bernard F. A new experimental setup for the time resolved

X-ray diffraction study of self-propagating high-temperature synthesis. *The Review of Scientific Instruments*. 2002;**73**(2):422-428

- [122] Gauthier V, Bernard F, Gaffet E, Josse C, Larpin JP. In-situ time resolved X-ray diffraction study of the formation of the nanocrystalline NbAl₃ phase by mechanically activated self-propagating high-temperature synthesis reaction. *Materials Science and Engineering: A*. 1999;**272**(2):334-341
- [123] Bernard F, Charlot F, Gras C, Gauthier V, Gaffet E. In-situ time-resolved X-ray diffraction experiments applied to self-sustained reactions from mechanically activated mixtures. *Le Journal de Physique IV*. 2002;**10**:89-99
- [124] Gauthier V, Bernard F, Gaffet E, Vrel D, Gailhanou M, Larpin JP. Investigations of the formation mechanism of nanostructured NbAl₃ via MASHS reaction. *Intermetallics*. 2002;**10**:377-389
- [125] Javel JF, Dirand M, Nassik FZ, Gachon JC. Real time X-ray diffraction study of the formation by SHS of the phases γ' and H in the ternary system Al Ni Ti. *Le Journal de Physique IV*. 1996;**6**(C2):229-234
- [126] Javel JF, Dirand M, Kuntz JJ, Nassik FZ, Gachon JC. Real time X-ray diffraction study of the formation by SHS of the phases γ' and H in the ternary system Al-Ni-Ti. *Journal of Alloys and Compounds*. 1997;**247**(1-2):72-81
- [127] Vaucher S, Stir M, Ishizaki K, Catala-Civera JM, Nicula R. Reactive synthesis of Ti-Al intermetallics during microwave heating in an E-field maximum. *Thermochimica Acta*. 2011;**522**(1):151-154
- [128] Dubois S, Karnatak N, Beaufort MF, Bourdarias L, Renault PO, Vreb D. Influence of mechanical activation on TiC self propagating high temperature synthesis. *Materials and Technologies*. 2003;**18**(3):158-162
- [129] Wong J, Larson EM, Waide PA, Frahm R. Combustion front dynamics in the combustion synthesis of refractory metal carbides and Di-borides using time-resolved X-ray diffraction. *Journal of Synchrotron Radiation*. 2006;**13**(4):326-335
- [130] Larson EM, Wong J, Holt JB, Waide PA, Nutt G, Rupp B, Terminello LJ. Time resolved diffraction study of Ta-C solid combustion system. *Journal of Materials Research*. 1993;**8**(7):1533-1541
- [131] Jie-Cai H, Zhang XH, Wood JV. In-situ combustion synthesis and densification of TiC-xNi cermets. *Materials Science and Engineering: A*. 2000;**280**(2):328-333
- [132] Riley DP, Kisi EH, Hansen TC, Hewat AW. Self-propagating high-temperature synthesis of Ti₃SiC₂: I, ultra-high-speed neutron diffraction study of the reaction mechanism. *Journal of the American Ceramic Society*. 2002;**85**(10):2417-2424
- [133] Gauthier V, Cochapin B, Dubois S, Vrel D. Self-propagating high-temperature synthesis of Ti₃SiC₂: Study of the reaction mechanisms by time-resolved X-ray diffraction and infrared thermography. *Journal of the American Ceramic Society*. 2006;**89**(9):2899-2907

- [134] Boutefnouchet H, Curfs C, Triki A, Boutefnouchet A, Vrel D. Self-propagating high-temperature synthesis mechanisms within the Ti-C-Ni system: A time resolved X-ray diffraction study. *Powder Technology*. 2012;**217**:443-450
- [135] Mukasyan AS, Vadchenko SG, Khomenko IO. Combustion modes in the titanium-nitrogen system at low nitrogen pressures. *Combustion and Flame*. 1997;**111**(1-2):65-72
- [136] Carole D, Fréty N, Paris S, Vrel D, Bernard F, Marin-Ayral RM. Investigation of the SHS mechanisms of titanium nitride by in situ time-resolved diffraction and infrared thermography. *Journal of Alloys and Compounds*. 2007;**436**(1):181-186
- [137] Parkin IP, Pankhurst QA, Affleck L, Aguas MD, Kuznetsov MV. Self-propagating high temperature synthesis of $\text{BaFe}_{12}\text{O}_{19}$, $\text{Mg}_{0.5}\text{Zn}_{0.5}\text{Fe}_2\text{O}_4$ and $\text{Li}_{0.5}\text{Fe}_{2.5}\text{O}_4$; time resolved X-ray diffraction studies (TRXRD). *Journal of Materials Chemistry*. 2000;**11**(1):193-199
- [138] Spiers H, Parkin IP, Pankhurst QA, Affleck L, Green M, Caruana DJ, Kuznetsov MV, Yao J, Vaughan G, Terry A, Kvick A. Self propagating high temperature synthesis of magnesium zinc ferrites ($\text{Mg}_x\text{Zn}_{1-x}\text{Fe}_2\text{O}_3$): Thermal imaging and time resolved X-ray diffraction experiments. *Journal of Materials Chemistry*. 2004;**14**(7):1104-1111
- [139] Kovalev DY, Shkiro VM, Ponomarev VI. Dynamics of phase formation during combustion of Zr and Hf in air. *International Journal of Self-Propagating High-Temperature Synthesis*. 2007;**16**(4):169-174
- [140] Gras C, Gaffet E, Bernard F, Niepce JC. Enhancement of self-sustaining reaction by mechanical activation: Case of an Fe-Si system. *Materials Science and Engineering: A*. 1999;**264**(1):94-107
- [141] Gras C, Bernsten N, Bernard F, Gaffet E. The mechanically activated combustion reaction in the Fe-Si system: In situ time-resolved synchrotron investigations. *Intermetallics*. 2002;**10**(3):271-282
- [142] Gras C, Charlot F, Gaffet E, Bernard F, Niepce JC. In situ synchrotron characterization of mechanically activated self-propagating high-temperature synthesis applied in Mo-Si system. *Acta Materialia*. 1999;**47**(7):2113-2123
- [143] Gras C, Gaffet E, Bernard F. Combustion wave structure during the MoSi_2 synthesis by mechanically-activated self-propagating high-temperature synthesis (MASHS): In situ time-resolved investigations. *Intermetallics*. 2006;**14**(5):521-529
- [144] Kachelmyer CR, Khomenko IO, Rogachev AS, Varma A. A Time-resolved X-ray diffraction study of Ti_5Si_3 product formation during combustion synthesis. *Journal of Materials Research*. 1997;**12**(12):3230-3240
- [145] Riley DP, Oliver CP, Kisi EH. In-situ neutron diffraction of titanium silicide, Ti_5Si_3 , during self-propagating high-temperature synthesis (SHS). *Intermetallics*. 2006;**14**(1):33-38
- [146] Rupp B, Wong J, Holt JB, Waide P. The solid combustion synthesis of small $\text{REBa}_2\text{Cu}_3\text{O}_x$ samples (Re-Y, Er). The solid combustion synthesis of small $\text{REBa}_2\text{Cu}_3\text{O}_x$ samples (Re-Y, Er). *Journal of Alloys and Compounds*. 1994;**209**(1-2): 25-33

- [147] Curfs C, Cano IG, Vaughan GBM, Turrillas X, Kvik Å, Rodriguez MA. TiC-NiAl composites obtained by SHS: A time-resolved XRD study. *Journal of the European Ceramic Society*. 2002;**22**(7):1039-1044
- [148] Terry AE, Vaughan GB, Kvik Å, Walton RI, Norquist AJ, O'Hare D. In situ time-resolved X-ray diffraction: The current state of the art. *Synchrotron Radiation News*. 2002;**15**(4):4-13
- [149] Contreras L, Turrillas X, Vaughan GBM, Kvik Å, Rodriguez MA. Time-resolved XRD study of TiC-TiB₂ composites obtained by SHS. *Acta Materialia*. 2004;**52**(16):4783-4790
- [150] Mishra SK, Das SK, Ramachandrarao P, Belov DY, Mamyan SS. Self-propagating high-temperature synthesis of a zirconium diboride -alumina composite: A dynamic X-ray diffraction study. *Philosophical Magazine Letters*. 2004;**84**(1):41-46
- [151] Carole D, Frety N, Paris S, Vrel D, Bernard F, Marin-Ayral RM. Microstructural study of titanium carbonitride produced by combustion synthesis. *Ceramics International*. 2007;**33**(8):1525-1534
- [152] Mas-Guindal MJ, Turrillas X, Hansen T, Rodríguez MA. Time-resolved neutron diffraction study of Ti-TiC-Al₂O₃ composites obtained by SHS. *Journal of the European Ceramic Society*. 2008;**28**(15):2975-2982
- [153] Kovalev DY, Prokudina VK, Ratnikov VI, Ponomarev VI. Thermal decomposition of TiH₂: A TRXRD study. *International Journal of Self-Propagating High-Temperature Synthesis*. 2010;**19**(4):253-257
- [154] Bazhin PM, Stolin AM, Alymov MI. Preparation of nanostructured composite ceramic materials and products under conditions of a combination of combustion and high-temperature deformation (SHS extrusion). *Nanotechnologies in Russia*. 2014;**9**(11-12):583-600
- [155] Manukyan KV, Shuck CE, Cherukara MJ, Rouvimov S, Kovalev DY, Strachan A, Mukasyan AS. Exothermic self-sustained waves with amorphous nickel. *Journal of Physical Chemistry C*. 2016;**120**(10):5827-5838
- [156] LaGrange T, Campbell GH, Reed BW, Taheri M, Pesavento JB, Kim JS, Browning ND. Nanosecond time-resolved investigations using the in situ of dynamic transmission electron microscope (DTEM). *Ultramicroscopy*. 2008;**108**(11):1441-1449
- [157] Shuck CE, Frazee M, Gillman A, Beason MT, Gunduz IE, Matouš K, Winarski R, Mukasyan AS. X-ray nanotomography and focused-ion-beam sectioning for quantitative three-dimensional analysis of nanocomposites. *Journal of Synchrotron Radiation*. 2016;**23**(4):990-996
- [158] Lee SH, Lee JH, Lee YH, Shin DH, Kim YS. Effect of heating rate on the combustion synthesis of intermetallics. *Materials Science and Engineering: A*. 2000;**281**(1):275-285
- [159] Yi HC, Petric A, Moore JJ. Effect of heating rate on the combustion synthesis of Ti-Al intermetallic compounds. *Journal of Materials Science*. 1992;**27**(24):6797-6806

- [160] Moore JJ, Feng HJ. Combustion synthesis of advanced materials: Part I. Reaction parameters. *Progress in Materials Science*. 1995;**39**(4–5):243-273
- [161] Yi HC, Moore JJ. Self-propagating high-temperature (combustion) synthesis (SHS) of powder-compacted materials. *Journal of Materials Science*. 1990;**25**(2):1159-1168
- [162] Yum JT, Moon JT, Lee YH, Kim YS. Synthesis and microstructure control of TiAl via combustion synthesis. *Metals and Materials International*. 1995;**1**(1):19-27