We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Introductory Chapter: The Testament of Hydroxyapatite: New Prospects in Regenerative Medicinal Treatments

Jagannathan Thirumalai

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/intechopen.72767>

1. A terse testament of hydroxyapatite

The term ‘Hydroxyapatite (HAp)’ is a naturally occurring mineral and chemically identical to the mineral constituent of bones and solid tissues of mankind and mammals. As a mineral species, apatite was first known in 1786 by “the father of German geology” Abraham Gottlob Werner (1750–1817) and entitled by him on or after the antediluvian Greek ἀπατάω (apatao)—“to mislead” or “to deceive” since it had earlier been does not specify one chemical opus. Though, the word “apatite” was revealed in the 1990s and is denoted as calcium orthophosphate, which would be a very infrequent heterogeneity of tourmaline, beryl and other stones [1]. The period of HAp in reformatory science backdate to 1950s [2] furthermore for the filling of the bone defects, the bioceramics might be used as an inert scaffold. The history related to calcium orthophosphates dates back to 1770 [3] the mistaken for other minerals, such as beryl, tourmaline, chrysolite, amethyst, fluorite, etc., [1, 4, 5]. Currently, apatite is the term for a group of minerals with the same crystallographic structure and older history till 1950 could be delivered somewhere else in the published literature [6, 7]. On the basis of thorough literature survey of HAp, since 1950 in connection to its properties, production, composition and its applications were extensively studied and its usage in medicinal disciplines contributes many breakthroughs in contemporary technological developments in consideration with the interaction of materials on active species [8]. In the origin, HAp was used for grafting, which might not have reaction with neighbouring living cells. Far ahead, the development would change to the responsive nature of the material, also for the growth of bone the reactive material pretends as a conductive scaffold [7]. In recent trend, developing fabrication technology with the dawn of recognizing of regenerative medicinal growth in the field of nanotechnology and have transformed the appearance of bioceramics to a dissimilar facet [9–14].

S. No.	Methods/techniques	Outcome	Drawback	Refs.
1.	Dry	Well-crystallized	High temperature (1050°C in air)	[15, 16]
2.	Wet	High-yield, cost-effective, simple technique, and suitable for various pressure conditions	Non-crystalline and impure phase	[17]
3.	Co-precipitation	Crystalline, high-yield, cost-effective, template-assisted & various temperatures conditions	Requires high temperature annealing to yield product	[18–20]
4.	Sol-gel	Simple technique, low cost, crystalline nature	Dependent on solvent, the temperature and pH	[21, 22]
5.	Emulsion	More efficient, simple and particle agglomeration is less, Suitable for various surfactants, temperature conditions.	Dependent on ratio of aqueous and organic phases, pH and temperature	[23, 24]
6.	Hydrolysis	Simple technique, particle agglomeration is little high, sources are texture dependent	Precursors depend strongly on pH and temperature	[25]
7.	Hydrothermal	Highly crystalline micro or nano-sized structures, well-controlled morphology and porosity	Requires constant and uninterrupted temperature and pressure conditions	[26, 27]
8.	Alternate energy input (low-energy plasma spray)	Uniform thickness, good crystallinity, well-controlled morphology, porosity, micro hardness, and fracture toughness	Requires constant, uninterrupted temperature and pressure conditions. High temp. withstanding substrates and good cleaning process	[28]
9.	Microwave (MW)-assisted	Yield of perfectly, highly crystalline, homogeneous size, porosity and morphology	Requires constant, uninterrupted temperature conditions to yield product	[29]
10.	Ball-milling	Simplicity, reproducibility, and large-scale production	Requires high temperature annealing to yield product and little agglomeration	[30]
11.	Sonochemical	Nanosized products, elicits perfect control of morphology, porosity and size	Requires constant, uninterrupted temperature and pressure conditions.	[31]
12.	Others: a. Solvothermal process b. Spray pyrolysis	Yield of perfectly homogeneous size crystalline morphology	Requires organic solvents and hot zone of an electric furnace	[32, 33]

Table 1. Shows the key methods for the synthesis of hydroxyapatite (HAp).

Hydroxyapatite, HAp is an elementary calcium phosphate, and its chemical formula is $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$ present as main material of teeth, bones and mineral certainly with high bi-affinity. It is composited by below methods, and it is also applicable in various fields including biomaterials. In the meantime, amorphous HAp is no longer stable and could dissolve reliant on usage environment; a sintered body has been effectively used as a material in

general. And, the sintered body could not dissolve so much owing to its high crystallinity. Because fusion and grain growth of each particle arose on its process stage are foreseeable, it has been hard to control configuration and grain diameter on a nanoscale impartial like initial particles of amorphous HAp. The synthesis of HAp, with its numerous morphologies, structures, and textures, has enthusing a prodigious deal of interest in academic and industrial research for numerous heterogeneous catalysis applications. In the past three decades, a numerous synthetic routes for producing HAp powders have been developed. Productions of HAp powders are classified under four different methods are enumerated in **Table 1** [34].

2. Topical advancements in reformative medicinal treatments in the new prospects of application of nanotechnology

HAp is considered as bioceramics that signifies the enormous amount of regenerative scion material persisting in the flea market. HAp is analogous to the bony-like apatite structure and is considered to be an important inorganic constituent for bone. However, in the organic matrix HAp is circumscribed, so that the existences of HAp in the normal bone in the form of extra inorganic trace elements [3]. Ailments related to the ablative and bone surgical treatment known as the abscission or removing a part of the bone, which ultimately needs renovation through various available measures. Since, the HAp has found increasing demand in regenerative medicine as a possible auxiliary material second to auto graft. HAp could also be used in occurrences, wherever the defects or voids present in bone. This process leads to curing of blocks, or beads by employing powders of the mineral being positioned into or on the defected parts of bone. From the time when it is bioactive, it reassures the bone to spot on the problem for further orientation of growth and this procedure may perhaps be an alternate to bone or dental implants, means that it can integrate into bone or dental structures and support growth with the no breaking down or dissolving in the human body. Though, HAp is still used for this purpose today and it is also applicable for other purposes too. Numerous advancements in nanotechnology oriented reformative medicine for the overhaul or improvement of dented tissues function in several organ systems. However, most studies concern the goings-on of topical advancements in nanomaterials used in regenerative medicinal treatments [35], as summarized in **Table 2**, with some more literatures in HAp, on the basis of regenerative medicine in various organ systems.

Applications of nanotechnology in regenerative medicine would require the entire prospective to reform tissue repair and regeneration [35]. Till now, to trigger the regeneration process the growth of impeccable nanomaterials accomplished of transfer signals to the diseased or damaged cells and tissues it remnants a dare. By employing nano-HAp based materials in regenerative medicine is a material of significant relate to the safety in relations to human health aspects, for the reason that this area is still in its developing platform. Erstwhile to human health based applications, a systematic research work in relevance to the noxious effect of these nanomaterials would be carrying through in excessive manner. In conclusion, at the nanoscale level to make acquainted about the original mechanisms of cell-biomaterial surface interfaces, and further implement the findings from bench to bedside, a manageable teamwork flanked by the scientists and clinicians is of highly necessary for the societal benign.

S. No.	Body part	Nanomaterials	Outcome (type of study)	Refs.
1.	Bone	Poly(epsilon caprolactone)	Improved cell attachment, proliferation, differentiation, and mineralization of osteoblasts (in vitro)	[36]
			Lineage restriction of progenitor cells by topographical cues (in vitro)	[37]
		Nanoscaled calcium phosphate	Large-sized blood vessel infiltration leads to bone formation (in vivo; canines)	[38]
		HAp-coated titanium	Enhanced and accelerated osseointegration (in vivo; rats)	[39]
		Hybrid biomimetic collagen-hydroxyapatite composites	Crosslinking reactions for hard tissue engineering application with designed bioactive properties	[40]
		Nanostructured beta tri-calcium phosphate-coated over poly (lactic acid)	Enhanced osteoconductivity of scaffold (in vitro) and heterotrophic bone formation (in vivo; rabbits)	[41]
		Carbon nanotubes	Extracellular matrix calcification (in vitro); lamellar bone regeneration (in vivo; mice)	[42]
2.	Cartilage		Porous bone formation in bone defect (in vivo; rats)	[43]
		Silica nanofibers	Proliferation and maturation of MG63 cells (in vitro)	[44]
		Pentosan poly sulfate in poly (ethylene glycol) HA	Formation of cartilage like tissues by mesenchymal progenitor cells (in vitro)	[45]
		PVA/PCL [poly(vinyl alcohol) poly(caprolactone)]	Proliferation and chondrogenic differentiation of MSCs (in vitro); improved healing of cartilage defects (in vivo; rabbits)	[46]
		3D porous polycaprolactone (PCL)-hydroxyapatite (HAp) scaffold combined with MC	Improves the biological performance of 3D PCL-HAp scaffold	[47]
3.	Peripheral nervous system	POSS-PCU [polyhedral oligomeric silsesquioxane with polycarbonate polyurethane]	Enhanced survival, proliferation, and chondrogenic differentiation of adipose tissue derived stem cells (in vitro)	[48]
			Enhanced growth and proliferation of nasoseptal chondrocytes (in vitro)	[49]
		Electrospun collagen/poly (lactic-co-glycolic acid)	Axon regeneration, myelination, and action potential propagation (in vivo; rats)	[50]
		Poly(L-lactide-co-glycolide)/chitosan/hydroxyapatite(PLGA/chitosan/HAp)	In vivo application of PLGA/chitosan/HAp conduits for nerve regeneration	[51]
		POSS-PCU-MWCNT	Novel biomaterial capable of electronic interfacing with tissue holds potential to promote nerve regeneration	[52]

S. No.	Body part	Nanomaterials	Outcome (type of study)	Refs.
4.	Central nervous system	Small interfering ribonucleic acid (Si-RNA) chitosan nanoparticles	Increased delivery of drugs by crossing BBB (blood–brain barrier) (in vivo; rats)	[53]
		Nano-HAPs on the growth of human glioma U251 and SHG44 cells in vitro and in vivo	Nano-HAPs have an obvious antineoplastic function in vitro and in vivo. It reduces the poisonous, adverse reactions to 1,3-bis(2-chloroethyl)-1-nitrosourea (BCNU), strongly cooperate with certain other chemotherapy drugs, decrease the toxicity, and might become a new clinical antineoplastic drug.	[54]
5.	Myocardial tissue/myocardial infarction (MI)	Insulin-like growth factor-1 (IGF-1) with poly(lactic-co-glycolic acid)	Increased protein kinase B phosphorylation and reduced infarct size (in vivo; mice)	[55]
		Electrospun (hb/gel/fb) [poly(hemoglobin/gelatin/fibrinogen)]	Cardiomyogenic differentiation of mesenchymal stem cells (MSCs) (in vitro)	[56]
		PGS [poly(glycerol sebacate)]	Increased transplant cell retention and survival (in vitro)	[57]
		Gold nanoparticles-loaded hybrid nanofibers	Cardiomyogenic differentiation of MSCs; superior biological and functional properties (in vitro)	[58]
		Calcium hydroxyapatite–based dermal filler into the infarct	Injection of an acellular dermal filler into an MI immediately after coronary occlusion reduces early infarct expansion and limits chronic LV remodeling.	[59]
6.	Skin	Silver nanoparticles	Reduced inflammation and promotion of wound healing (in vitro)	[60]
		Plasma-treated electrospun poly(lactic-acid) co-poly(epsilon caprolactone), and gelatin	Increased fibroblast proliferation and collagen secretion (in vitro)	[61]
		Titanium abutment (control) and one HA-coated abutment (case) interface	The HAp-coated abutment can achieve integration with the surrounding skin.	[62]
		Rosette nanotubes with PHeMA [poly(2-hydroxyethyl methacrylate)]	Increased keratinocyte and fibroblast proliferation (in vitro)	[63]
7.	Eye	Polydimethylsiloxane	Topographical cue for formation of functioning corneal endothelium (in vitro)	[64]
		HAp, polytetrafluoroethylene (PTFE), polyhydroxyethyl methacrylate (HEMA), and glass (control)	Improving the initial cell adhesion environment in the skirt element of keratoprotheses may enhance tissue integration and reduce device failure rates.	[65]
		Super paramagnetic nanoparticles	Increased gene expression and neurite growth, subcellular organelle localization, and nano therapeutics delivery (in vitro)	[66]

S. No.	Body part	Nanomaterials	Outcome (type of study)	Refs.
8.	Lung	Deferoxamine	Regeneration of microvascular anastomosis in airways (in vivo; mice)	[67]
		HAPNs in both A549 and 16HBE cells	HAPNs might be a promising agent or mitochondria-targeted delivery system for effective lung cancer therapy.	[68]
		101F6 (tumor suppressor gene) nanoparticles	Increased tumor cell lysis (in vitro and in vivo; mice)	[69]

Courtesy: Reproduced from Ref. [35] with permission from Dove Medical Press, copyright 2014.

Table 2. Topical advancements in nanomaterials used in regenerative medicinal treatments [35].

3. Conclusion

In summary, hydroxyapatite is one of the well-studied biomaterials in the medical field for its established biocompatibility and for being the main content of the mineral part of bone, teeth and various organ systems. However the fact demonstrates that it has been more imperious towards ground-breaking research against novel medical applications for the cause of the society. It has all the typical topographies of biomaterials, such as, bioactive, biocompatible, non-toxic, osteoconductive, non-immunogenic, non-inflammatory, bioceramic coatings, bone void fillers for orthopedics, dental implant coating, HAp thin films, and resemblance to the inorganic component of human beings. In the midst of the major remarkable progress are in various fields of molecular biology, biochemistry, bioinformatics, microbiology, genetics, cytometry, medical diagnostics, drug & gene delivery, and the addition of nanotechnology are the most important worldwide challenges so far. The dispute of novel spectroscopic/microscopical innovation contains interdisciplinary areas that might endure to be enhanced for these innovative global developments in x-ray imaging, spectral imaging, time-correlated single-photon counting, fluorescence quenching, endo- and exo-thermic reaction rates, kinetic chemical reaction rates, *In vitro* and *In vivo* studies, visual implants, neurology and non-invasive optical biopsy. Thus, studies towards unique nano-hydroxyapatite used in regenerative medicinal treatments might give way to mechanisms of cell-biomaterial relations at the nanoscale level that may feasibly turn out to be the upcoming forerunners to human applications in the embryonic stage.

Acknowledgements

All authors contributed towards data analysis, drafting and revising the paper and agree to be accountable for all aspects of the work. The authors apologize for inadvertent omission of any pertinent references.

Conflict of interest

The authors declare that there is no conflict of interests regarding the publication of this paper.

Author details

Jagannathan Thirumalai

Address all correspondence to: thirumalaijg@gmail.com

Department of Physics, School of Electrical & Electronics Engineering, SASTRA Deemed University, Srinivasa Ramanujan Centre, Kumbakonam, Tamil Nadu, India

References

- [1] Dorozhkin SV. A detailed history of calcium orthophosphates from 1770s till 1950. *Materials Science and Engineering: C*. 2013;**33**(1):3085-3110. DOI: 10.1016/j.msec.2013.04.002
- [2] Dubok VA. Bioceramics – Yesterday, today, tomorrow. *Powder Metallurgy and Metal Ceramics*. 2000;**39**(7-8):381-394. DOI: 10.1023/A:1026617607548
- [3] Hench LL, Thompson I. Twenty-first century challenges for biomaterials. *Journal of Royal Society Interface*. 2010;**7**(Suppl 4):S379-S391. DOI: 10.1098/rsif.2010.0151.focus
- [4] Dorozhkin SV. Calcium orthophosphates in nature, Biology and Medicine. *Materials*. 2009;**2**(2):399-498. DOI: 10.3390/ma2020399
- [5] Dorozhkin SV. Calcium orthophosphates: Occurrence, properties, biomineralization, pathological calcification and biomimetic applications. *Biomatter*. 2011;**1**(2):121-164. DOI: 10.4161/biom.18790
- [6] Weiner S, Wagner HD. The Material Bone: Structure-mechanical function relations. *Annual Review of Materials Science*. 1998;**28**(1):271-298. DOI: 10.1146/annurev.matsci.28.1.271
- [7] Dorozhkin SV. *Calcium Orthophosphates Applications in Nature, Biology and Medicine*. 1st ed. Boca Raton: Pan Stanford Publishing; 2012. p. 870. DOI: 10.4032/9789814364171
- [8] LeGeros RZ. Calcium phosphate-based osteoinductive materials. *Chemical Reviews*. 2008;**108**(11):4742-4753. DOI: 10.1021/cr800427g
- [9] Ohgushi H, Dohi Y, Tamai S, Tabata S. Osteogenic differentiation of marrowstromal stem cells in porous hydroxyapatite ceramics. *Journal of Biomedical Materials Research*. 1993;**27**(11):1401-1407. DOI: 10.1002/jbm.820271107
- [10] Ripamonti U, Crooks J, Khoali L, Roden L. Te induction of bone formation by coral-derived calcium carbonate/hydroxyapatite constructs. *Biomaterials*. 2009;**30**(7):1428-1439. DOI: 10.1016/j.biomaterials.2008.10.065
- [11] Ripamonti U, Richter PW, Nilen RWN, Renton L. Te induction of bone formation by smart biphasic hydroxyapatite tricalcium phosphate biomimetic matrices in the non-human primate *Papio ursinus*. *Journal of Cellular and Molecular Medicine*. 2008;**12**(6b):1-15. DOI: 10.1111/j.1582-4934.2008.00312.x

- [12] Yuan H, Kurashina K, de Bruijn JD, Li Y, de Groot K, Zhang X A preliminary study on osteoinduction of two kinds of calcium phosphate ceramics. *Biomaterials* 1999;**20**(19): 1799-1806. DOI: 10.1016/S0142-9612(99)00075-7
- [13] Habibovic P, Gbureck U, Doillon CJ, Bassett DC, van Blitterswijk CA, Barralet JE. Osteoconduction and osteoinduction of low-temperature 3D printed bioceramic implants. *Biomaterials*. 2008;**29**(7):944-953. DOI: 10.1016/j.biomaterials.2007.10.023
- [14] Ripamonti U, Roden LC, Renton LF. Osteoinductive hydroxyapatite-coated titanium implants. *Biomaterials*. 2012;**33**(15):3813-3823. DOI: 10.1016/j.biomaterials.2012.01.050
- [15] Korber F, Trömel GZ. The formation of HAP through a solid state reaction between tri and tetra – calcium phosphates. *Journal of The Electrochemical Society*. 1932;**38**:578-580
- [16] Guo X, Yan H, Zhao S, Li Z, Li Y, Liang X. Effect of calcining temperature on particle size of hydroxyapatite synthesized by solid-state reaction at room temperature. *Advanced Powder Technology*. 2013;**24**(6):1034-1038. DOI: 10.1016/j.appt.2013.03.002
- [17] Pramanik S, Agarwal AK, Rai KN, Garg A. Development of high strength hydroxyapatite by solid-state-sintering process. *Ceramics International*. 2007;**33**(3):419-426. DOI: 10.1016/j.ceramint.2005.10.025
- [18] Ikoma T, Yamazaki A, Nakamura S, Akao M. Preparation and structure refinement of monoclinic hydroxyapatite. *Journal of Solid State Chemistry*. 1999;**144**(2):272-276. DOI: 10.1006/jssc.1998.8120
- [19] Tao J, Jiang W, Pan H, Xu X, Tang R. Preparation of large-sized hydroxyapatite single crystals using homogeneous releasing controls. *Journal of Crystal Growth*. 2007;**308**(1):151-158. DOI: 10.1016/j.jcrysgro.2007.08.009
- [20] Swain SK, Sarkar D. A comparative study: Hydroxyapatite spherical nanopowders and elongated nanorods. *Ceramics International*. 2011;**37**(2):2927-2930. DOI: 10.1016/j.ceramint.2011.03.077
- [21] Chen J, Wang Y, Chen X, Ren L, Lai C, He W, Zhang Q. A simple sol-gel technique for synthesis of nanostructured hydroxyapatite, tricalcium phosphate and biphasic powders. *Materials Letters*. 2011;**65**(12):1923-1926. DOI: 10.1016/j.matlet.2011.03.076
- [22] Rajabi-Zamani AH, Behnamghader A, Kazemzadeh A. Synthesis of nanocrystalline carbonated hydroxyapatite powder via nonalkoxide sol-gel method. *Materials Science and Engineering: C*. 2008;**28**(8):1326-1329. DOI: 10.1016/j.msec.2008.02.001
- [23] Shum HC, Bandyopadhyay A, Bose S, Weitz DA. Double emulsion droplets as microreactors for synthesis of mesoporous hydroxyapatite. *Chemistry of Materials*. 2009;**21**(22): 5548-5555. DOI: 10.1021/cm9028935
- [24] Zhou W, Wang M, Cheung W, Guo B, Jia D. Synthesis of carbonated hydroxyapatite nanospheres through nanoemulsion. *Journal of Materials Science. Materials in Medicine*. 2008;**19**(1):103-110. DOI: 10.1007/s10856-007-3156-9

- [25] Sturgeon JL, Brown PW. Effects of carbonate on hydroxyapatite formed from CaHPO_4 and $\text{Ca}_4(\text{PO}_4)_2\text{O}$. *Journal of Materials Science. Materials in Medicine*. 2009;**20**(9):1787-1794. DOI: 10.1007/s10856-009-3752-y
- [26] Lin K, Liu X, Chang J, Zhu Y. Facile synthesis of hydroxyapatite nanoparticles, nanowires and hollow nano-structured microspheres using similar structured hard-precursors. *Nanoscale*. 2011;**3**(8):3052-3055. DOI: 10.1039/c1nr10334b
- [27] Thirumalai J, Chandramohan R, Vijayan TA. Synthesis, characterization and growth mechanism of dumbbell-shaped Fluoroapatite (FHAp) superstructures. *Advanced Science Letters*. 2012;**5**(1):118-123. DOI: 10.1166/asl.2012.1925
- [28] Garcia-Alonso D, Parco M, Stokes J, Looney L. Low-Energy Plasma Spray (LEPS) deposition of hydroxyapatite/poly-ε-caprolactone biocomposite coatings. *Journal of Thermal Spray Technology*. 2012;**21**(1):132-143. DOI: 10.1007/s11666-011-9695-0
- [29] Farzadi A, Solati-Hashjin M, Bakhshi F, Aminian A. Synthesis and characterization of hydroxyapatite/ β -tricalcium phosphate nanocomposites using microwave irradiation. *Ceramics International*. 2011;**37**(1):65-71. DOI: doi.org/10.1016/j.ceramint.2010.08.021
- [30] El Briak-Benabdeslam H, Ginebra MP, Vert M, Boudeville P. Wet or dry mechanochemical synthesis of calcium phosphates? Influence of the water content on DCPD–CaO reaction kinetics. *Acta Biomaterialia*. 2008;**4**(2):378-386. DOI: 10.1016/j.actbio.2007.07.003
- [31] Giardina MA, Fanovich MA. Synthesis of nanocrystalline hydroxyapatite from $\text{Ca}(\text{OH})_2$ and H_3PO_4 assisted by ultrasonic irradiation. *Ceramics International*. 2010;**36**(6):1961-1969. DOI: 10.1016/j.ceramint.2010.05.008
- [32] Smolen D, Chudoba T, Malka I, Kedzierska A, Lojkowski W, Swieszkowski W, Kurzydowski KJ, Kolodziejczyk-Mierzynska M, Lewandowska-Szumie M. Highly biocompatible, nanocrystalline hydroxyapatite synthesized in a solvothermal process driven by high energy density microwave radiation. *International Journal of Nanomedicine*. 2013;**8**(1):653-668. DOI: 10.2147/IJN.S39299
- [33] Cho JS, Lee JC, Rhee SH. Effect of precursor concentration and spray pyrolysis temperature upon hydroxyapatite particle size and density. *Journal of Biomedical Materials Research. Part B, Applied Biomaterials*. 2016;**104**(2):422-430. DOI: 10.1002/jbm.b.33406
- [34] Fihri A, Len C, Varma RS, Solhy A. Hydroxyapatite: A review of syntheses, structure and applications in heterogeneous catalysis. *Coordination Chemistry Reviews*. 2017;**347**(9):48-76. DOI: 10.1016/j.ccr.2017.06.009
- [35] Chaudhury K, Kumar V, Kandasamy J, RoyChoudhury S. Regenerative nanomedicine: Current perspectives and future directions. *International Journal of Nanomedicine*. 2014;**9**(1):4153-4167. DOI: 10.2147/IJN.S45332
- [36] Wang J, Valmikinathan CM, Liu W, Laurencin CT, Yu X. Spiral structured, nanofibrous, 3D scaffolds for bone tissue engineering. *Journal of Biomedical Materials Research. Part A*. 2010;**93**(2):753-762. DOI: 10.1002/jbm.a.32591

- [37] Cassidy JW, Roberts JN, Smith CA, Robertson M, White K, Biggs MJ, Oreffo RO, Dalby MJ. Osteogenic lineage restriction by osteoprogenitors cultured on nanometric grooved surfaces: The role of focal adhesion maturation. *Acta Biomaterialia*. 2014;**10**(2):651-660. DOI: 10.1016/j.actbio.2013.11.008
- [38] Appleford MR, Oh S, Oh N, Ong JL. In vivo study on hydroxyapatite scaffolds with trabecular architecture for bone repair. *Journal of Biomedical Materials Research. Part A*. 2009;**89**(4):1019-1027. DOI: 10.1002/jbm.a.32049
- [39] Yamada M, Ueno T, Tsukimura N, et al. Bone integration capability of nanopolymorphic crystalline hydroxyapatite coated on titanium implants. *International Journal of Nanomedicine*. 2012;**7**(1):859-873. DOI: 10.2147/IJN.S28082
- [40] Krishnakumar GS, Gostynska N, Dapporto M, Campodoni E, Montesi M, Panseri S, Tampieri A, Kon E, Marcacci M, Sprio S, Sandric M. Evaluation of different crosslinking agents on hybrid biomimetic collagen-hydroxyapatite composites for regenerative medicine. *International Journal of Biological Macromolecules*. 2017;**106**:739-748. DOI: 10.1016/j.ijbiomac.2017.08.076
- [41] Cao L, Duan PG, Wang HR, et al. Degradation and osteogenic potential of a novel poly(lactic acid)/nano-sized β -tricalcium phosphate scaffold. *International Journal of Nanomedicine*. 2012;**7**(1):5881-5888. DOI: 10.2147/IJN.S38127
- [42] Lobo AO, Siqueira IA, Das Neves MF, Marciano FR, Corat EJ, Corat MA. In vitro and in vivo studies of a novel nanohydroxyapatite/superhydrophilic vertically aligned carbon nanotube nanocomposites. *Journal of Materials Science. Materials in Medicine*. 2013;**24**(7):1723-1732. DOI: 10.1007/s10856-013-4929-y
- [43] Hirata E, Ménard-Moyon C, Venturelli E, et al. Carbon nanotubes functionalized with fibroblast growth factor accelerate proliferation of bone marrow-derived stromal cells and bone formation. *Nanotechnology*. 2013;**24**(43):435101. DOI: 10.1088/0957-4484/24/43/435101
- [44] Ravichandran R, Gandhi S, Sundaramurthi D, Sethuraman S, Krishnan UM. Hierarchical mesoporous silica nanofibers as multifunctional scaffolds for bone tissue regeneration. *Journal of Biomaterials Science. Polymer Edition*. 2013;**24**(17):1988-2005. DOI: 10.1080/09205063.2013.816930
- [45] Frith JE, Cameron AR, Menzies DJ, et al. An injectable hydrogel incorporating mesenchymal precursor cells and pentosan polysulphate for intervertebral disc regeneration. *Biomaterials*. 2013;**34**(37):9430-9440. DOI: 10.1016/j.biomaterials.2013.08.072
- [46] Shafee A, Soleimani M, Chamheidari GA, et al. Electrospun nanofiberbased regeneration of cartilage enhanced by mesenchymal stem cells. *Journal of Biomedical Materials Research. Part A*. 2011;**99**(3):467-478. DOI: 10.1002/jbm.a.33206
- [47] Yao Q, Wei B, Liu N, Li C, Guo Y, Shamie AN, Chen J, Tang C, Jin C, Xu Y, Bian X, Zhang X, Wang L. Chondrogenic regeneration using bone marrow clots and a porous polycaprolactone-hydroxyapatite scaffold by three-dimensional printing. *Tissue Engineering. Part A*. 2015;**21**(7-8):1388-1397. DOI: 10.1089/ten.TEA.2014.0280

- [48] Guasti L, Vagaska B, Bulstrode NW, Seifalian AM, Ferretti P. Chondrogenic differentiation of adipose tissue-derived stem cells within nanocaged POSS-PCU scaffolds: A new tool for nanomedicine. *Nanomedicine*. 2014;**10**(2):279-289. DOI: 10.1016/j.nano.2013.08.006
- [49] Oseni AO, Butler PE, Seifalian AM. The application of POSS nanostructures in cartilage tissue engineering: The chondrocyte response to nanoscale geometry. *Journal of Tissue Engineering and Regenerative Medicine*. 2015;**9**(11):E27-E38. DOI: 10.1002/term.1693
- [50] Ouyang Y, Huang C, Zhu Y, Fan C, Ke Q. Fabrication of seamless electrospun collagen/PLGA conduits whose walls comprise highly longitudinal aligned nanofibers for nerve regeneration. *Journal of Biomedical Nanotechnology*. 2013;**9**(6):931-943. DOI: 10.1166/jbn.2013.1605
- [51] Shen X, Ruan J, Zhou Z, Zeng Z, Xie L. Evaluation of PLGA/chitosan/HA conduits for nerve tissue reconstruction. *Journal of Wuhan University of Technology-Materials Science Edition*. 2009;**24**(4):566-570. DOI: 10.1007/s11595-009-4566-y
- [52] Antoniadou EV, Ahmad RK, Jackman RB, Seifalian AM. Next generation brain implant coatings and nerve regeneration via novel conductive nanocomposite development. In: Nigel Lovell, editor. *Conference proceedings IEEE Engineering in Medicine and Biology Society, EMBC, 2011 annual international conference of the IEEE; 30 August 3 – September 2011; Boston, MA: IEEE; 2011*. pp. 3253-3257. DOI: 10.1109/IEMBS.2011.6090884
- [53] Malmo J, Sandvig A, Vårum KM, Strand SP. Nanoparticle mediated P-glycoprotein silencing for improved drug delivery across the blood–brain barrier: A siRNA-chitosan approach. *PLoS One*. 2013;**8**(1):e54182. DOI: 10.1371/journal.pone.0054182
- [54] Chu SH, Feng DF, Ma YB, Li Z-Q. Hydroxyapatite nanoparticles inhibit the growth of human glioma cells in vitro and in vivo. *International Journal of Nanomedicine*. 2012;**7**(7):3659-3666. DOI: 10.2147/IJN.S33584
- [55] Chang MY, Yang YJ, Chang CH, et al. Functionalized nanoparticles provide early cardioprotection after acute myocardial infarction. *Journal of Controlled Release*. 2013;**170**(2):287-294. DOI: 10.1016/j.jconrel.2013.04.022
- [56] Ravichandran R, Seitz V, Reddy Venugopal J, et al. Mimicking native extracellular matrix with phytic acid-crosslinked protein nanofibers for cardiac tissue engineering. *Macromolecular Bioscience*. 2013;**13**(3):366-375. DOI: 10.1002/mabi.201200391
- [57] Ravichandran R, Venugopal JR, Sundarrajan S, Mukherjee S, Sridhar R, Ramakrishna S. Minimally invasive injectable short nanofibers of poly(glycerol sebacate) for cardiac tissue engineering. *Nanotechnology*. 2012;**23**(38):385102. DOI: 10.1088/0957-4484/23/38/385102
- [58] Ravichandran R, Sridhar R, Venugopal JR, Sundarrajan S, Mukherjee S, Ramakrishna S. Gold nanoparticle loaded hybrid nanofibers for cardiogenic differentiation of stem cells for infarcted myocardium regeneration. *Macromolecular Bioscience*. 2014;**14**(4):515-525. DOI: 10.1002/mabi.201300407

- [59] Ryan LP, Matsuzaki K, Noma M, Jackson BM, Eperjesi TJ, Plappert TJ, St. John-Sutton MG, Gorman JH, Gorman RC. Dermal filler injection: A novel approach for limiting infarct expansion. *The Annals of Thoracic Surgery*. 2009;**87**(1):148-155. DOI: 10.1016/j.athoracsur.2008.09.028
- [60] Wu J, Zheng Y, Song W, et al. Situ synthesis of silver-nanoparticles/bacterial cellulose composites for slow-released antimicrobial wound dressing. *Carbohydrate Polymers*. 2014;**102**(2):762-771. DOI: 10.1016/j.carbpol.2013.10.093
- [61] Chandrasekaran AR, Venugopal J, Sundarrajan S, Ramakrishna S. Fabrication of a nano-fibrous scaffold with improved bioactivity for culture of human dermal fibroblasts for skin regeneration. *Biomedical Materials*. 2011;**6**(1):015001
- [62] Hoof MV, Wigren S, Duimel H, Savelkoul PHM, Flynn M, Stokroos RJ. Can the hydroxyapatite-coated skin-penetrating abutment for bone conduction hearing implants integrate with the surrounding skin? *Frontiers in Surgery*. 2015;**2**(1):1-8. DOI: 10.3389/fsurg.2015.00045
- [63] Sun L, Li D, Hemraz UD, Fenniri H, Webster TJ. Self-assembled rosette nanotubes and poly (2-hydroxyethyl methacrylate) hydrogels promote skin cell functions. *Journal of Biomedical Materials Research. Part A*. 2014;**102**(10):3446-3451. DOI: 10.1002/jbm.a.35008
- [64] Teo BK, Goh KJ, Ng ZJ, Koo S, Yim EK. Functional reconstruction of corneal endothelium using nanotopography for tissue-engineering applications. *Acta Biomaterialia*. 2012;**8**(8):2941-2952. DOI: 10.1016/j.actbio.2012.04.020
- [65] Mehta JS, Futter CE, Sandeman SR, Faragher RGAF, Hing KA, Tanner KE, Allan BDS. Hydroxyapatite promotes superior keratocyte adhesion and proliferation in comparison with current keratoprosthesis skirt materials. *Journal of Ophthalmology*. 2005;**89**(10):1356-1362. DOI: 10.1136/bjo.2004.064147
- [66] Steketee MB, Moysidis SN, Jin XL, Weinstein JE, Pita-Thomas W, Hemalatha BR, Siraj I, Jeffrey LG. Nanoparticle-mediated signalling endosome localization regulates growth cone motility and neurite growth. *Proceedings of the National Academy of Sciences of the United States of America*. 2011;**108**(47):19042-19047. DOI: 10.1073/pnas.1019624108
- [67] Jiang X, Malkovskiy AV, Tian W, Sung YK, Sun W, Hsu JL, Manickam S, Wagh D, Joubert LM, Semenza GL, Rajadas J, Nicolls MR. Promotion of airway anastomotic microvascular regeneration and alleviation of airway ischemia by deferoxamine nanoparticles. *Biomaterials*. 2014;**35**(2):803-813. DOI: 10.1016/j.biomaterials.2013.09.092
- [68] Sun Y, Chen Y, Ma X, Yuan Y, Liu CS, Kohn J, Qian JC. Mitochondria-targeted hydroxyapatite nanoparticles for selective growth inhibition of lung cancer in vitro and in vivo. *ACS Applied Materials & Interfaces*. 2016;**8**(39):25680-25690. DOI: 10.1021/acsami.6b06094
- [69] Ohtani S, Iwamaru A, Deng W, et al. Tumor suppressor 101F6 and ascorbate synergistically and selectively inhibit non-small cell lung cancer growth by caspase-independent apoptosis and autophagy. *Cancer Research*. 2007;**67**(13):6293-6303. DOI: 10.1158/0008-5472