We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Synthesis of Silver Nanoparticles

Remziye Güzel and Gülbahar Erdal

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/intechopen.75363>

Abstract

Nanoparticles of noble metals, especially the silver nanoparticles, have been widely used in different fields of science. Their unique properties, which can be incorporated into biosensor materials, composite fibers, cosmetic products, antimicrobial applications, conducting materials and electronic components, make them a very important subject to be studied by chemistry, biology, healthcare, electronic and other related branches. These unique properties depend upon size and shape of the silver nanoparticles. Different preparation methods have been reported for the synthesis of the silver nanoparticles, such as electron irradiation, laser ablation, chemical reduction, biological artificial methods, photochemical methods and microwave processing. This chapter aims to inform the synthesis methods of the silver nanoparticles.

Keywords: silver nanoparticles, physical methods, chemical methods, green synthesis, different shape

1. Introduction

Silver has too much of modern industrial uses and is considered a store of wealth. However, the story of this legendary precious metal begins with its use by ancient civilizations. Silver has many attributes that made it so valuable to early peoples. It is malleable, ductile, lustrous, resilient, conductive, antibacterial, and rare. Also, it was used as a precious commodity in currencies, ornaments, jewelry, electrical contacts and photography, among others. Although bulk silver is widely known for their brilliant surfaces and colors, there is a drastic color difference when the metal reduces in dimensions. Even though the craftsmen did not know nanoparticles in that period, the mixing of the metal chlorides with molten glass led to the formation of metallic nanoparticles of different shape and size, therefore the physical formats of the metal nanoparticles had interesting interactions with light and produced visibly beautiful colors. The metal chlorides materialized

and formed nanoparticles in the molten glass before cooling, making art, one of the first uses for nanotechnology. Nowadays, the nanoparticles are an important field of the modern research dealing with design, synthesis, and manipulation of particle structures ranging from approximately 1 to 100 nm. Nanoparticle research is currently an area of intense scientific research, due to a wide variety of potential applications in fields such as healthcare, cosmetics, food and feed, environmental health, mechanics, optics, biomedical sciences, chemical industries, electronics, space industries, drug-gene delivery, energy science, optoelectronics, catalysis, single electron transistors, light emitters, nonlinear optical devices, and photo-electrochemical area. The silver nanoparticles have been widely used in the fields of chemistry and related branches due to their high surface to volume ratio and excellent conducting capability. From electrical switches, solar panels to chemical-producing catalysts and antimicrobial activity, the silver nanoparticle is an essential component in many industries. Its unique properties make it nearly impossible to substitute and its uses contain a wide range of applications. At the same time, many of the consumer products that claim to contain nanomaterials contain nanosilver. Examples of the consumer products that include nanosilver including computers, mobile phones, automobile appliances, food packaging materials, food supplements, textiles, electronics, household appliances, cosmetics, medical devices, imaging techniques, and water and environment disinfectants. Most of these nanosilver-containing products are manufactured in North America, the Far East, especially in China, South Korea, Taiwan, Vietnam and India, the Russian Federation, and the Western Europe.

The knowledge of the silver nanomaterials synthesis methods is important due to an extensive application and area of use perspective. The main problem in synthesizing the silver nanoparticles is the control of their physical properties such as obtaining uniform particle size distribution, identical shape, morphology, nanoparticle coating or stabilizing agent, chemical composition or type and crystal structure. The methods can be classified and categorized that they follow common approaches and the differences such as reactants and the reaction conditions. Top-down versus bottom-up, green versus nongreen, and conventional versus nonconventional synthesis methods have been reported. The conventional synthesis methods contain the use of citrate, borohydride, two-phase systems (water-organic), organic reducers such as cyclodextrin, and micelles and/or polymer in the synthesis process. The unconventional methods contain laser ablation, radiocatalysis, vacuum evaporation of metal, irradiation, photolithography, electrodeposition and the electrocondensation. Top-down and bottom-up are the two synthesis approaches of metallic nanoparticles involving chemical, physical, and biological means. The common fabrication of the nanoparticles includes chemical and physical processes. The top-down approach uses macroscopic initial structures, which can be externally controlled in the processing of nanostructures. The nanoparticles synthesized by mechanical grinding of bulk metals and the addition of colloidal protecting agents are some examples of the top-down method. The bottom-up approaches contain the miniaturization of materials components (up to atomic level) with further self-assembly process. The reduction of metals, electrochemical methods, and decomposition are the examples of the bottom-up methods. In addition, the synthesis approaches can be classified as either green or non-green. Green synthetic systems use environmentally friendly agents such as sugars, plant extracts, bacteria and fungi to form and stabilize nanosilver.

It is important to measure nanosilver concentration, size, shape, surface charge, crystal structure, surface chemistry, and surface transformation in nanoparticle synthesis. The characterization

and detection techniques for the nanosilver contain transmission electron microscopy (TEM), scanning electron microscopy (SEM), electrospray scanning mobility particle sizer (ESMPS), zeta size analysis, atomic force microscopy (AFM), dynamic light scattering (DLS), Brunauer-Emmett-Teller analysis (BET), X-ray diffraction (XRD), X-ray photoelectron spectroscopy (XPS), X-ray absorption near edge structure (XANES), Fourier transform infrared spectroscopy (FTIR), Raman spectroscopy, nuclear magnetic resonance spectroscopy (NMR), inductively coupled plasma mass spectroscopy (ICP-MS), thermal gravimetric analysis (TGA), and atomic absorption spectroscopy (AAS).

2. Physical methods

The most important physical methods for the synthesis of the silver nanoparticles are evaporation-condensation, laser ablation, electrical irradiation, gamma irradiation, and lithography. Kimura and Bandow examined the measurement of the optical spectra of many metal colloid solutions and presented new preparation methods of metal colloids inorganic solvents without the chemicals such as redox reagents, polymers, electrolytes, glue or other kinds of colloid stabilizers. Three different preparation methods as the matrix isolation method, the gas flow-cold trap method, and the gas flow-solution trap method, were used to examine the synthesis of silver NPs [1]. The laser ablation method, which has several types of different applications, is another method to study the synthesis of silver nanoparticles (Ag-NPs). The laser ablation technique is a new useful and efficient method to prepare and obtain metal colloids in absence of chemical reagents. This method helps to control particle size of colloids by changing the number of laser pulses [2]. Pyatenko et al. produced silver nanoparticles by irradiating an Ag target with a 532 nm laser beam in pure water. This technique is successfully applied to produce small nanoparticles with a narrow size distribution in pure water without using any chemical additives by using a high-power laser and small laser beam spot sizes [3]. Sadrolhousseini et al. prepared a new method for the fabrication of silver nanoparticles which are dispersed in graphene oxide using the laser ablation and thermal effusivity of nanocomposite. This environmentally friendly method, which does not require any chemical agents, polymeric or surfactant stabilizers, works by releasing the nanoparticles inside liquid solution [4]. Tsuji et al. studied to perform to prepare Ag-NPs by laser ablation of a silver plate in polyvinylpyrrolidone (PVP) aqueous solutions and laser irradiation onto prepared colloidal solutions. This technique is seen as a remarkable technique due to its procedural simplicity and a very high rate of obtainability of nanoparticles of various species and materials such as metals, metal oxides semiconductors, and organic materials by the irradiation of intense laser light onto those materials settled in solvents [5]. The pulsed photoacoustic (PA) technique is another method to study the synthesis of the Ag-NPs in ethanol by laser ablation and determine the production rate laser pulse and concentration of synthesized Ag-NPs [6]. Researchers have studied mechanisms and processes such as plasma formation, dynamics of the cavitation bubble [7, 8], and also the influence of laser parameters and solvents on nanoparticles [9, 10].

Nanosphere lithography (NLS) is a simple and inexpensive nanofabrication method to produce large variety of nanoparticle (NP) structures and well-ordered 2D NP arrays. Jensen et al. studied the effect of solvent on the optical extinction spectrum of periodic arrays of surface-confined

silver nanoparticles fabricated by NSL and four separate samples of NP arrays. Jensen et al. have investigated four separate samples of nanoparticle arrays; three samples were obtained nanoparticles that are truncated tetrahedral in shape but that differ in out-of-plane height and one sample have nanoparticles that are oblate ellipsoidal in shape [11]. Jensen et al. also demonstrated that the localized surface plasmon resonance extinction maximum of a single nanoparticle material system, silver, can be continuously tuned throughout the visible, near-infrared, and mid-infrared regions of the electromagnetic spectrum [12].

3. Chemical method

3.1. Chemical reduction of silver nanoparticles

The size, shape, and surface morphology play an important role in controlling the chemical, physical, optical, and electronic properties of nanomaterials. The chemical reduction is one of the most commonly used methods for the synthesis of silver nanoparticles by inorganic and organic reducing agents. In general, different reducing agents such as sodium citrate, ascorbate, sodium borohydride (NaBH_4), elemental hydrogen, polyol process, Tollens reagent, *N,N*-dimethylformamide (DMF), and poly(ethylene glycol)-block copolymers, hydrazine, and ammonium formate are used for the reduction of the silver ions (Ag^+) in the aqueous or nonaqueous solutions.

3.2. Different shapes of silver nanoparticles synthesized with various chemical reductants

3.2.1. Synthesis of spherical silver nanoparticles

The spherical silver nanoparticles were synthesized using the reducing agents such as ascorbic acid, sodium citrate, NaBH_4 , thiosulfate, and polyethylene glycol. In addition to that, the use of the surfactants such as citrate, polyvinylpyrrolidone (PVP), cetyltrimethylammonium bromide (CTAB), and polyvinyl alcohol (PVA) for interactions with particle surfaces can stabilize particle growth and protect particles from sedimentation and agglomeration [13–17].

3.2.2. Synthesis of silver nanorods

Zhang et al. prepared silver nanorods by photoinduced synthesis (**Figure 1**). At first step, monodisperse spherical seed nanoparticles were prepared by irradiating silver nitrate, bis(*p*-sulfonatophenyl)-phenylphosphine dihydrate dipotassium salt (BSPP), trisodium citrate, and sodium hydroxide solutions with 254 nm light. Then, Silver nanorods were grown in the solution with the injection of silver seeds at the growth medium containing silver nitrate and sodium citrate and then irradiated for 24 h using a halogen lamp and a bandpass filter to selectively tune. This photomediated method provided an elegant method for controlling the architectural parameters of the resulting silver nanostructures [18]. Ojha et al. mixed the solution of AgNO_3 and citrate and added NaOH into the solution. Then solution of ice cold of NaBH_4 was added while stirring. To synthesize Ag nanorods of at three different aspect

Figure 1. (A) TEM image of the silver seed nanoparticles. (B) SEM and (C) TEM images of silver nanorods synthesized with a bandpass filter centered at 600 ± 20 nm. (D) Selective-area electron diffraction (SAED) pattern of a single silver nanorod, showing the interpenetration. [100] (red) and [112] (blue) zone patterns (scale bars: 100 nm) [18].

ratios, three stock solutions of AgNO_3 , ascorbic acid, and the surfactant cetyltrimethylammonium bromide (CTAB) were prepared separately. These stock solutions were mixed at certain quantities properly. Thereafter, 1.0, 0.5, and 0.25 ml of synthesized seed solution were added to set one, two and three, respectively, and at the end, NaOH solution was also added to each set. The color of each nanorod solutions depends on the seed concentrations added in the final solution [19]. Ajitha et al. prepared the aqueous solution containing AgNO_3 with sodium citrate dihydrate as stabilizer. Then, sodium borohydride (reducing agent) solution was injected to the above solution all at once while stirring vigorously. The solution color was changed to light yellow. The entire solution was heated under continuous stirring on magnetic stirrer. CTAB solution was prepared through heating stirring on a magnetic stirrer for dissolution of CTAB. Then, AgNO_3 and ascorbic acid solution were added. And then, the seed solution was added and at last, few drops of NaOH were added to maintain constant pH and stirred well. The synthesis temperature was varied from 30 to 70°C [20].

3.2.3. Synthesis of silver nanowires

Sun et al. studied silver nanostructures that could be varied from nanoparticles and nanorods to long nanowires by adjusting the reaction conditions, including the ratio of PVP to silver nitrate, reaction temperature, and seeding conditions. They found that the large-scale synthesis of silver nanowires with diameters ranged from 30 to 40 nm, and lengths up to $\sim 50 \mu\text{m}$

[21]. Li et al. demonstrated that the diameter of Ag nanowires produced by a polyol synthesis could be controlled by adjusting the concentration of bromide. The silver nanowires with diameters of 20 nm and aspect ratios up to 2000 have obtained by adding 2.2 mM NaBr into AgNO_3 solution [22]. Gebeyehu et al. synthesized silver nanowire using a simple polyol method (**Figure 2**). They used polyvinylpyrrolidone as stabilizing and capping agent combined with sodium chloride and potassium bromide salts, ethylene glycol was used as both solvent and a reducing agent, and silver nitrate was used as a silver precursor. They determined that the diameter and uniformity of silver nanowires can be controlled by adjusting the concentration of AgNO_3 and [PVP] to $[\text{AgNO}_3]$ molar ratio keeping the other parameters constant. AgNWs with diameters of 20 nm and aspect ratios >1000 were obtained by adding 30.5 mM AgNO_3 to a silver nanowire synthesis [23].

3.2.4. Synthesis of cubic silver nanoparticles

The synthesis of cubic silver nanoparticles was achieved by the reduction of silver nitrate using ethylene glycol in the presence of polyvinylpyrrolidone (PVP). In polyol process, ethylene glycol containing hydroxyl groups have functional structure as both solvent and reducing agent. Polyvinylpyrrolidone as capping agent was used to constitute the cubic shape. Molar ratio of the PVP and silver ions determines the shape of the product [24–26]. Siekkien et al. performed a faster method for synthesis of cubic silver nanoparticle by adding a trace amount of sodium sulfide (Na_2S) or sodium hydrosulfide (NaHS) to the conventional polyol synthesis (**Figure 3**). The reduction agent is important for the synthesis of NPs with different chemical compositions, sizes and morphologies, and controlled dispersities [27].

Figure 2. FE-SEM images of AgNWs synthesized at different [PVP] to $[\text{AgNO}_3]$ molar ratio: (A) 2:1, (B) 4:1, (C) 6:1, (D) 8:1, (E) 10:1, and (F) 12:1 [23].

Figure 3. SEM images of reactions containing increasing molar ratios between the repeating unit of PVP and silver nitrate. The ratios of PVP to silver nitrate were (a) 0.77, (b) 1.15, (c) 1.5, (d) 1.9, (e) 2.3, and (f) 0.7 [27].

3.2.5. Synthesis of triangular silver nanoparticles

Zhang et al. prepared silver triangular bipyramids using the photoinduced reduction of 0.3 mM silver nitrate in aqueous solutions containing 1.5 mM sodium citrate, 0.3 mM bis(p-sulfonatophenyl) phenylphosphine dihydrate dipotassium salt (BSPP), and 0.005 M NaOH for 8 h using a 150 W halogen lamp and a bandpass filter (**Figure 4**). The samples were irradiated in the excitation wavelength range (500 ± 20 , 550 ± 20 , 600 ± 20 , 650 ± 20 nm) [28]. Métraux and Mirkin used the chemical reduction method for the fabrication of silver nanoprisms. They synthesized silver nanoprisms at room temperature by using a mixture of $\text{AgNO}_3/\text{NaBH}_4/\text{polyvinylpyrrolidone/trisodium citrate}/\text{H}_2\text{O}_2$ in an aqueous solution as reagents [29].

3.3. Microemulsion techniques

Microemulsion includes a mixture of water, surfactant, and oil or a mixture of water, surfactant, co-surfactant, and oil. Many surfactants are available for the formation of the microemulsion in the preparation of the silver nanoparticles. Generally, many surfactants can be used

Figure 4. (A–D) SEM images of the triangular bipyramids (scale bar 300 nm) generated with the bandpass filter centered at 500 ± 20 , 550 ± 20 , 600 ± 20 , and 650 ± 20 nm, respectively. Inset of (B): a higher-magnification view, scale bar 100 nm [28].

to form microemulsion, including anionic surfactants such as bis(2-ethylhexyl)sulfosuccinate, sodium dodecyl benzene sulfonate, and lauryl sodium sulfate, cationic surfactants such as cetyltrimethylammonium bromide, polyvinylpyrrolidone, and nonionic surfactants such as Triton X-100, etc. The water droplets covered by surfactant molecules act as micro-reactors and offer a unique micro-environment for the formation of nanoparticle [30–35].

3.4. Microwave-assisted techniques

The microwave synthesis methods provide the reduction of the silver nanoparticles with changeable rate microwave radiation in comparison to the conventional heating technique. Microwave-assisted technology, by accelerating chemical reactions from hours or days to minutes, provides quick results. Also, microwave irradiation provides uniform heating for the preparation of metallic nanoparticles and aids the ripening of these materials without aggregation [36–39].

4. Green synthesis

Biosynthesis of the nanoparticles has received considerable attention due to the growing need to develop environmentally beneficial technologies in material synthesis. To illustrate, a great

deal of effort has been put into the green synthesis of inorganic materials, especially metal nanoparticles using microorganisms and plant extracts. While microorganisms such as bacteria [40], algae [41], yeast [42], and fungi [43] are continued to be examined so far for the intra and extracellular synthesis of metal nanoparticles, the use of parts of the whole plant in analogous with nanoparticles synthesis methodologies is an exciting possibility which is newly explored. In the literature, various bacterial strains such as *Bacillus amyloliquefaciens* [44], *Acinetobacter calcoaceticus* [45], *Pseudomonas aeruginosa* [46], *Escherichia coli* [47] and *Bacillus licheniformis* [48] were used effectively for the synthesis of silver nanoparticles.

The benefits of using plants for the synthesis of the nanoparticles are that the plants are easily available and possess a large variety of active functional groups that can promote the reduction of silver ions. Most of the plant parts like leaves, roots, latex, bark, stem, and seeds are being used for the nanoparticle synthesis. Major compounds that ensure the reduction of the nanoparticles are biomolecules such as polysaccharides, tannins, saponins, phenolics, terpenoids, flavones, alkaloids, proteins, enzymes, vitamins, amino acids, and alcoholic component. The procedure for the nanoparticle synthesis of plants requires the collection of the part of the plant of interest from the available sites is done and then it is washed thoroughly several times with tap and distilled water to remove impurities of plants; followed with sterile distilled water to remove related wastes if any. Then, plant is dried clean and dry place in the shade for 10–15 days and then pulverized using a blender. For the plant broth preparation, an approximate amount of the dried powder is boiled with deionized distilled water. The resulting extraction is then filtered thoroughly until no insoluble material appears in the broth. Then a few mL of the plant extract is added to the silver nitrate solution whose concentration is kept at 1 mM. The reduction of Ag^+ to Ag^0 is confirmed by the color change of the solution. Its formation is confirmed by using UV-visible spectroscopy and transmission electron microscopy or scanning electron microscopy. The most important plants like *Alternanthera dentate* [49], *Cymbopogon citratus* [50], *Argyrea nervosa* [51], phlomis [52], *Aloe vera* [53], *Carica papaya* [54], *Nelumbo nucifera* [55], *Moringa oleifera* [56], *Ziziphora tenuior* [57], *Centella asiatica* [58], *Vitex negundo* [59], *Swietenia mahagoni* [60], *Boerhavia diffusa* [61], *Cocos nucifera* [62], *Brassica rapa* [63], *Melia dubia* [64], *Pogostemon benghalensis* [65], *Garcinia mangostana* [66], *Psoralea corylifolia* [67], *Portulaca oleracea* [68], *Trachyspermum ammi* [69], *Eclipta prostrate* [70], *Vitis vinifera* [71], *Thevetia peruviana* [72], *Calotropis procera* [73], *Premna herbacea* [74], *Ficus carica* [75], *Abutilon indicum* [76], *Terminalia chebula* [77], *Acorus calamus* [78], *Tinospora cordifolia* [79], *Ocimum tenuiflorum* [80], bamboo hemicelluloses [81], *Strychnos potatorum* [82], Pine, Persimmon, Ginkgo, Magnolia, and Platanus [83] used by researchers in green synthesis.

Many different plant extracts have been used in the synthesis of silver nanoparticles with the aim of producing Ag-NPs presenting different morphologies. TEM and SEM studies have shown that the presence of reducing agent in a plant-mediated synthesis of Ag-NPs, where the plant extract acts as reducing agents, shapes the nanoparticle during its growth. The use of medicinal plants in the synthesis of Ag-NPs is not only used for size and shape control, but also for providing plant antimicrobial properties to Ag-NPs. Tippayawat et al. reported a one-step hydrothermal method to prepare silver nanoparticles which is effective against gram-positive (*Streptococcus epidermidis*) and gram-negative (*Pseudomonas aeruginosa*). Reduction of Ag^+ ions to Ag^0 nanoparticles was performed in a medium of *Aloe vera* extract

in which no extra reducing agent was used. The silver nanoparticle sizes were found to be in a range of 70.70–192.02 nm and controllable by varying temperature and time conditions of the hydrothermal process (**Figure 5**) [53]. Kagithoju et al. achieved an economic and environmentally friendly green synthesis of silver nanoparticles using an aqueous leaf extract of *Strychnos potatorum* from 3 mM silver nitrate solution. The XRD and SEM analysis have shown the average particle size of nanoparticles as 28 nm as well as revealed their (mixed, i.e., cubic and hexagonal) structure. These nanoparticles have shown bactericidal activity against multidrug-resistant human pathogenic bacteria [82].

Song and Kim compared their extracellular synthesis of metallic silver nanoparticles by using five plant leaf extracts (Pine, Persimmon, Ginkgo, Magnolia, and Platanus). Magnolia leaf

Figure 5. SEM images of Ag-NPs were obtained at (A) 100°C for 6 h, (B) 150°C for 6 h, (C) 200°C for 6 h, (D) 100°C for 12 h, (E) 150°C for 12 h, and (F) 200°C for 12 h [53].

Figure 6. Green synthesis of different shape Ag-NPs and their antibacterial activity [84].

broth was the best reductive agent for the synthesis and conversion of the silver nanoparticles. More than 90% of the conversion was completed in 11 min by using Magnolia leaf broth at 95°C of reaction temperature. The average size of the nanoparticles, which was analyzed by TEM and SEM, ranges from 15 to 500 nm. The particle size was controlled by changing the reaction temperature, leaf broth concentration, and AgNO_3 concentration [83]. Roy et al. prepared four different shapes (spherical, oval, rod and flower shape) of silver nanoparticles (Ag-NPs) using pomegranate juice as a novel reducing agent via microwave-assisted synthesis. The Ag-NPs were characterized by UV-vis spectroscopy, XRD, SEM and TEM analysis. The synthesized Ag-NPs have shown a very rapid, effective, shape-specific and dose-dependent bacteriostatic/bactericidal effect towards four different bacterial strains. Among the four different shaped AgNPs, the flower shape AgNPs exhibited the best results and led to the fastest bactericidal activity against all the tested strains at similar bacterial concentrations (Figure 6) [84].

5. Conclusions

Silver nanoparticles can be obtained by physical, chemical, and biological synthesis methods. Hundreds of research articles reporting different synthesis methods for Ag-NP are published every year. Throughout this chapter, we have reviewed only some of the most

relevant works, dealing mostly with physical, chemical, and biological methods. In literature, all known applications for metallic silver may involve the use of nanosilver in place of silver to take advantage of nanosilver's unique properties. Despite all beneficial uses for nanosilver, its impact on the environment is concerning. These synthesis methods may require the use of different raw materials and yield reaction by using toxic products or wastes. But in recent years, also known as "green chemistry", an environmental-friendly approach has become a new option in chemistry, consisting of reduction and elimination of dangerous substantives for the design of products in the environment. However, as seen, there are numerous studies for the synthesis methods (green or nongreen) of the nanosilver in literature but the most commonly used methods in the industry are not yet known. For this reason, we suggest that researchers should be directed to work on the methods of synthesizing nanosilver used in the industry.

Author details

Remziye Güzel^{1*} and Gülbahar Erdal²

*Address all correspondence to: guzel.remziye@gmail.com

1 Department of Chemistry, Dicle University, Diyarbakır, Turkey

2 Department of Medical Biology and Genetics, Dicle University, Turkey

References

- [1] Kimura K, Bandow S. The study of metal colloids produced by means of gas evaporation technique. I. Preparation method and optical properties in ethanol. *Bulletin of the Chemical Society of Japan*. 1983;**56**:3578-3584
- [2] Tsuji T, Iryo K, Watanabe N, Tsuji M. Preparation of silver nanoparticles by laser ablation in solution: Influence of laser wavelength on particle size. *Applied Surface Science*. 2002;**202**:80-85
- [3] Pyatenko A, Shimokawa K, Yamaguchi M, Nishimura O, Suzuki M. Synthesis of silver nanoparticles by laser ablation in pure water. *Applied Physics A*. 2004;**79**:803-806
- [4] Sadrolhesseini AR, Noor ASM, Mahdi MA, Kharazmi A, Zakaria A, Yunus WMM, Huang NM. Laser ablation synthesis of silver nanoparticle in graphene oxide and thermal effusivity of nanocomposite. In: *IEEE 4th International Conference on Photonics (ICP)*. 2013. pp. 62-65
- [5] Tsuji T, Thang D-H, Okazaki Y, Nakanishi M, Tsuboi Y, Tsuji M. Preparation of silver nanoparticles by laser ablation in polyvinylpyrrolidone solutions. *Applied Surface Science*. 2008;**254**:5224-5230

- [6] Valverde-Alvaa MA, García-Fernández T, Villagrán-Munizc M, Sánchez-Akéc C, Castañeda-GuzmánR, Esparza-Alegríad E, Sánchez-ValdéseCF, SánchezLlamazareseJL, Márquez Herreraf CE. Synthesis of silver nanoparticles by laser ablation in ethanol: A pulsedphotoacoustic study. *Applied Surface Science*. 2015;**355**:341-349
- [7] González MG, Liu X, Niessner R, Haisch C. Strong size-dependentphotoacoustic effect on gold nanoparticles by laser-induced nanobubbles. *Applied Physics Letters*. 2010;**96**:174104
- [8] Kudryashov SI, Lyon K, Allen SD. Photoacoustic study of relaxation dynamics in multibubble systems in laser-superheated water. *Physical Review E*. 2006;**73**:055301R (1-4)
- [9] Osegura-Galindo DO, Machorro-Mejia R, Bogdanchikova N, Mota-Morales JD. Silver nanoparticles synthesized by laser ablation confined in urea choline chloride deep-eutectic solvent. *Colloids and Interface Science Communications*. 2016;**12**:1-4
- [10] Galindo DOO, Utrera OH, Mejia RM, Aranda MAS. Silver nanoparticles by laser ablation confined in alcohol using an argon gas environment. *JLMN-Journal of Laser Micro/Nanoengineering*. 2016;**11**(2):158-163
- [11] Jensen TR, Duval ML, Kelly KL, Lazarides AA, Schatz GC, Van Duyne RP. Nanosphere lithography: Effect of the external dielectric medium on the surface plasmon resonance spectrum of a periodic array of silver nanoparticles. *The Journal of Physical Chemistry*. 1999;**103**:9846-9853
- [12] Jensen TR, Malinsky MD, Haynes CL, Van Duyne RP. Nanosphere lithography: Tunable localized surface plasmon resonance spectra of silver nanoparticles. *The Journal of Physical Chemistry B*. 2000;**104**:10549-10556
- [13] Malasis L, Deyfus R, Murphy RJ, Hough LA, Donnino B, Murray CB. One-step green synthesis of gold and silver nanoparticles with ascorbic acid and their versatile surface post-functionalization. *RSC Advances*. 2016;**6**:33092-33100
- [14] Mikac L, Ivanda M, Gotic M, Mihelj T, Horvat L. Synthesis and characterization of silver colloidal particles with different coating for SERS application. *Journal of Nanoparticle Research*. 2014;**16**(2748):1-13
- [15] Wuithschick M, Paul B, Bienert R, Sarfraz A, Vainio U, Sztucki M, Kraehnert R, Strasser P, Rademann K, Emmerling F, Polte J. Size-controlled synthesis of colloidal silver nanoparticles based on mechanistic understanding. *Chemistry of Materials*. 2013;**25**:4679-4689
- [16] Al-Thabaiti SA, Malik MA, Al-Youbi AAO, Khan Z, Hussain JI. Effects of surfactant and polymer on the morphology of advanced nanomaterials in aqueous solution. *International Journal of Electrochemical Science*. 2013;**8**:204-218
- [17] Liang H, Wang W, Huang Y, Zhang S, Wei H, Xu H. Controlled synthesis of uniform silver nanospheres. *Journal of Physical Chemistry C*. 2010;**114**:7427-7431
- [18] Zhang J, Langille MR, Mirkin CA. Synthesis of silver nanorods by low energy excitation of spherical plasmonic seeds. *Nano Letters*. 2011;**11**:2495-2498

- [19] Ojha AK, Forster S, Kumar S, Vats S, Negi S, Fischer I. Synthesis of well-dispersed silver nanorods of different aspect ratios and their antimicrobial properties against gram positive and negative bacterial strains. *Journal of Nanobiotechnology*. 2013;**11**(42):1-7
- [20] Ajitha B, Reddy YAK, Reddy PS. Influence of synthesis temperature on growth of silver nanorods. *International Journal of Engineering Science*. 2014;**3**(5):144-148
- [21] Sun Y, Yin Y, Mayers BT, Herricks T, Xia Y. Uniform silver nanowires synthesis by reducing AgNO₃ with ethylene glycol in the presence of seeds and poly(vinyl pyrrolidone). *Chemistry of Materials*. 2002;**14**(11):4736-4745
- [22] Li B, Ye S, Stewart IE, Alvarez S, Wiley BJ. Synthesis and purification of silver nanowires to make conducting films with a transmittance of 99%. *Nano Letters*. 2015;**15**(10):6722-6726
- [23] Gebeyehu MB, Chala TF, Chang S-Y, Wu C-M, Lee J-Y. Synthesis and highly effective purification of silver nanowires to enhance transmittance at low sheet resistance with simple polyol and scalable selective precipitation method. *RSC Advances*. 2017;**7**:16139-16148
- [24] Im SH, Lee YT, Wiley B, Xia Y. Large-scale synthesis of silver nanocubes: The role of HCl in promoting cube perfection and monodispersity. *Angewandte Chemie International Edition*. 2005;**44**:2154-2157
- [25] Sun Y, Xia Y. Shape-controlled synthesis of gold and silver nanoparticles. *Science*. 2002a;**298**(5601):2176-2179
- [26] Tao A, Sinsermsuksakul P, Yang PD. Polyhedral silver nanocrystals with distinct scattering signatures. *Angewandte Chemie International Edition*. 2006;**45**(28):4597-4601
- [27] Siekkinen AR, McLellan JM, Chen J, Xia Y. Rapid synthesis of small silver nanocubes by mediating polyol reduction with a trace amount of sodium sulfide or sodium hydrosulfide. *Chemical Physics Letters*. 2006;**432**:491-496
- [28] Zhang J, Li S, Wu J, Schatz GC, Mirkin CA. Plasmon-mediated synthesis of silver triangular bipyramids. *Angewandte Chemie*. 2009;**121**:7927-7931
- [29] Me'traux GS, Mirkin CA. Rapid thermal synthesis of silver nanoprisms with chemically tailorable thickness. *Advanced Materials*. 2005;**17**(4):412-415
- [30] Nourafkan A, Alamdari A. Study of effective parameters in silver nanoparticle synthesis through method of reverse microemulsion. *Journal of Industrial and Engineering Chemistry*. 2014;**20**:3639-3645
- [31] Wani IA, Khatoon S, Ganguly A, Ahmed J, Ahmad T. Structural characterization and antimicrobial properties of silver nanoparticles prepared by inverse microemulsion method. *Colloids and Surfaces B: Biointerfaces*. 2013;**101**:243-250
- [32] Chatre A, Solasa P, Sakle S, Thaokar R, Mehra A. Color and surface plasmon effects in nanoparticle systems: Case of silver nanoparticles prepared by microemulsion route. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2012;**404**:83-92

- [33] Singha D, Barman N, Sahu K. A facile synthesis of high optical quality silver nanoparticles by ascorbic acid reduction in reverse micelles at room temperature. *Journal of Colloids and Interface Science*. 2014;**413**:37-42
- [34] Sun YP, Atorngitjawat P, Meziani MJ. Preparation of silver nanoparticles via rapid expansion of water in carbon dioxide microemulsion into reductant solution. *Langmuir*. 2001;**17**(19):5707-5710
- [35] Elmas ŞNK, Güzel R, Say MG, Ersöz A, Say R. Ferritin based bionanocages as novel biomemory device concept. *Biosensors and Bioelectronics*. 2018;**103**:19-25
- [36] Pal A, Shah S, Devi S. Microwave-assisted synthesis of silver nanoparticles using ethanol as a reducing agent. *Materials Chemistry*. 2009;**114**:530-532
- [37] Guo R, Li Y, Lan J, Jiang S, Liu T, Yan W. Microwave-assisted synthesis of silver nanoparticles on cotton fabric modified with 3-aminopropyltrimethoxysilane. *Journal of Applied Polymer Science*. 2013;**130**:3862-3868
- [38] Wang B, Zhuang X, Deng W, Cheng B. Microwave-assisted synthesis of silver nanoparticles in alkalic carboxymethyl chitosan solution. *Engineering*. 2010;**2**:387-390
- [39] Pal J, Deb MK, Deshmuk DK. Microwave-assisted synthesis of silver nanoparticles using benzo-18-crown-6 as reducing and stabilizing agent. *Applied Nanoscience*. 2014;**4**(4): 507-510
- [40] Samadi N, Golkaran D, Eslamifar A, Jamalifar H, Fazeli MR, Mohseni FA. Intra/extracellular biosynthesis of silver nanoparticles by an autochthonous strain of *Proteus mirabilis* isolated from photographic waste. *Journal of Biomedical Nanotechnology*. 2009;**5**(3):247-253
- [41] El-Rafie HM, El-Rafie MH, Zahran MK. Green synthesis of silver nanoparticles using polysaccharides extracted from marine macro algae. *Carbohydrate Polymers*. 2013;**96**:403-410
- [42] Jha AK, Prasad K, Kulkarni AR. Yeast mediated synthesis of silver nanoparticles. *International Journal of Nanoscience and Nanotechnology*. 2008;**4**(1):17-21
- [43] Bhainsa KC, D'Souza SF. Extracellular synthesis using the fungus *Aspergillus fumigatus*. *Colloids Surface B Biointerfaces*. 2006;**47**:152-157
- [44] Fouad H, Hongjie L, Yanmei D, Baoting Y, El-Shakh A, Abbas G, Jianchu M. Synthesis and characterization of silver nanoparticles using *Bacillus amyloliquefaciens* and *Bacillus subtilis* to control filarial vector *Culex pipiens pallens* and its antimicrobial activity, artificial cells. *Nanomedicine and Biotechnology*. 2017;**45**(7):1369-1378
- [45] Singh R, Wagh P, Wadhwani S, Gaidhani S, Kumbhar A, Bellare J, Chopade BA. Synthesis, optimization, and characterization of silver nanoparticles from *Acinetobacter calcoaceticus* and their enhanced antibacterial activity when combined with antibiotics. *International Journal of Nanomedicine*. 2013;**8**:4277-4290

- [46] Kumar CG, Mamidyala SK. Extracellular synthesis of silver nanoparticles using culture supernatant of *Pseudomonas aeruginosa*. Colloids Surface B Biointerfaces. 2011;**84**(2):462-466
- [47] Koilparambil D, Kurian LC, Vijayan S, Shaikmoideen JM. Green synthesis of silver nanoparticles by *Escherichia coli*: Analysis of antibacterial activity. Journal of Water and Environmental Nanotechnology. 2016;**1**(1):63-74
- [48] Kalimuthu K, Suresh Babu R, Venkataraman D, Bilal M, Gurunathan S. Biosynthesis of silver nanocrystals by *Bacillus licheniformis*. Colloids Surface B Biointerfaces. 2008;**65**(1):150-153
- [49] Kumar DA, Palanichamy V, Roopan SM. Green synthesis of silver nanoparticles using Alternanthera dentata leaf extract at room temperature and their antimicrobial activity. Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy. 2014;**127**:168-171
- [50] Masurkar SA, Chaudhari PR, Shidore VB, Kamble SP. Rapid biosynthesis of silver nanoparticles using Cymbopogon Citratus (Lemongrass) and its antimicrobial activity. Nano-Micro Letters. 2011;**3**(3):189-194
- [51] Thombre R, Parekh F, Patil N. Green synthesis of silver nanoparticles using seed extract of *Argyrea nervosa*. International Journal of Pharmacy and Biological Sciences. 2014;**5**(1):114-119
- [52] Allafchian AR, Mirahmadi-Zare SZ, Jalali SAH, Hashemi SS, Vahabi MR. Green synthesis of silver nanoparticles using phlomis leaf extract and investigation of their antibacterial activity. Journal of Nanostructure Chemistry. 2016;**6**:129-135
- [53] Tippayawat P, Phromviyo N, Boueroy P, Chompoosor A. Green synthesis of silver nanoparticles in aloe vera plant extract prepared by a hydrothermal method and their synergistic antibacterial activity. PeerJ. 2016;**4**:1-15
- [54] Jain D, Daima HK, Kachhwaha S, Kothari S. Synthesis of plant-mediated silver nanoparticles using papaya fruit extract and evaluation of their antimicrobial activities. Digest Journal Nanomaterials Biostructures. 2009;**4**:557-563
- [55] Santhoshkumar T, Rahuman AA, Rajakumar G, Marimuthu S, Bagavan A, Jayaseelan C. Synthesis of silver nanoparticles using Nelumbo nucifera leaf extract and its larvicidal activity against malaria and filariasis vectors. Parasitology Research. 2011;**108**:693-702
- [56] Prasad TNVKV, Elumalai E. Biofabrication of Ag nanoparticles using Moringa oleifera leaf extract and their antimicrobial activity. Asian Pacific Journal of Tropical Biomedicine. 2011;**1**:439-442
- [57] Sadeghi B, Gholamhoseinpoor F. A study on the stability and green synthesis of silver nanoparticles using Ziziphora tenuior (Zt) extract at room temperature. Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy. 2015;**134**:310-315
- [58] Rout A, Jena PK, Parida UK, Bindhani BK. Green synthesis of silver nanoparticles using leaves extract of Centella asiatica L. For studies against human pathogens. International Journal of Pharmacy and Biological Sciences. 2013;**4**(4):661-674

- [59] Zargar M, Hamid AA, Bakar FA, Shamsudin MN, Shameli K, Jahanshiri F. Green synthesis and antibacterial effect of silver nanoparticles using *Vitexnegundo* L. *Molecules*. 2011;**16**:6667-6676
- [60] Mondal S, Roy N, Laskar RA, Sk I, Basu S, Mandal D. Biogenic synthesis of Ag, Au and bimetallic Au/Ag alloy nanoparticles using aqueous extract of mahogany (*Swietenia mahogani* JACQ) leaves. *Colloids and Surfaces B: Biointerfaces*. 2011;**82**:497-504
- [61] Nakkala JR, Mata R, Gupta AK, Sadras SR. Green synthesis and characterization of silver nanoparticles using *Boerhaavia diffusa* plant extract and their antibacterial activity. *Industrial Crops and Products*. 2014;**52**:562-566
- [62] Mariselvam R, Ranjitsingh AJA, Usha Raja Nanthini A, Kalirajan K, Padmalatha C, Selvakumar MP. Green synthesis of silver nanoparticles from the extract of the inflorescence of *Cocos nucifera* (Family: Arecaceae) for enhanced antibacterial activity. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2014;**129**:537-541
- [63] Narayanan KB, Park HH. Antifungal activity of silver nanoparticles synthesized using turnip leaf extract (*Brassica rapa* L.) against wood rotting pathogens. *European Journal of Plant Pathology*. 2014;**140**:185-192
- [64] Kathiravan V, Ravi S, Kumar SA. Synthesis of silver nanoparticles from *Meliadubia* leaf extract and their in vitro anticancer activity. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2014;**130**:116-121
- [65] Gogoi SJ. Green synthesis of silver nanoparticles from leaves extract of ethnomedicinal plants *Pogostemon benghalensis* (B) O.Ktz. *Advances in Applied Science Research*. 2013;**4**(4):274-278
- [66] Veerasamy R, Xin TZ, Gunasagaran S, Xiang TFW, Yang EFC, Jeyakumar N. Biosynthesis of silver nanoparticles using mangosteen leaf extract and evaluation of their antimicrobial activities. *Journal of Saudi Chemical Society*. 2010;**15**:113-120
- [67] Sunita D, Tambhale D, Parag V, Adhyapak A. Facile green synthesis of silver nanoparticles using *Psoralea corylifolia*. Seed extract and their in-vitro antimicrobial activities. *International Journal of Pharmacy and Biological Sciences*. 2014;**5**(1):457-467
- [68] Firdhouse MJ, Lalitha P. Green synthesis of silver nanoparticles using the aqueous extract of *Portulaca oleracea* (L). *Asian Journal of Pharmaceutical and Clinical Research*. 2012;**6**(1):92-94
- [69] Vijayaraghavan K, Nalini S, Prakash NU, Madhankumar D. One step green synthesis of silver nano/microparticles using extracts of *Trachyspermum ammi* and *Papaver somniferum*. *Colloids and Surfaces B Biointerfaces*. 2012;**94**:114-117
- [70] Rajakumar G, Abdul Rahuman A. Larvicidal activity of synthesized silver nanoparticles using *Eclipta prostrata* leaf extract against filariasis and malaria vectors. *Acta Tropica*. 2011;**118**:196-203
- [71] Gnanajobitha G, Paulkumar K, Vanaja M, Rajeshkumar S, Malarkodi C, Annadurai G, Kannan C. Fruit-mediated synthesis of silver nanoparticles using *Vitis vinifera* and evaluation of their antimicrobial efficacy. *Journal of Nanostructure in Chemistry*. 2013;**3**(67):1-6

- [72] Rupiasih NN, Aher A, Gosavi S, Vidyasagar PB. Green synthesis of silver nanoparticles using latex extract of *Thevetia peruviana*: A novel approach towards poisonous plant utilization. *Journal of Physics: Conference Series*. 2013;**423**:1-8
- [73] Gondwal M, Pant GJN. Biological evaluation and green synthesis of silver nanoparticles using aqueous extract of *Calotropis procera*. *International Journal of Pharmacy and Biological Sciences*. 2013;**4**(4):635-643
- [74] Kumar S, Daimary RM, Swargiary M, Brahma A, Kumar S, Singh M. Biosynthesis of silver nanoparticles using *Premna herbacea* leaf extract and evaluation of its antimicrobial activity against bacteria causing dysentery. *International Journal of Pharmacy and Biological Sciences*. 2013;**4**(4):378-384
- [75] Uluğ B, Türkdemir MH, Çiçek A, Mete A. Role of irradiation in the green synthesis of silver nanoparticles mediated by fig (*Ficus carica*) leaf extract. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2015;**135**:153-161
- [76] Ashok Kumar S, Ravi S, Kathiravan V, Velmurugan S. Synthesis of silver nanoparticles using *A. indicum* leaf extract and their antibacterial activity. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2015;**134**:34-39
- [77] Edison TJI, Sethuraman MG. Instant green synthesis of silver nanoparticles using terminalia chebula fruit extract and evaluation of their catalytic activity on reduction of methylene blue. *Process Biochemistry*. 2012;**47**:1351-1357
- [78] Nakkala JR, Mata R, Kumar Gupta A, Rani Sadras S. Biological activities of green silver nanoparticles synthesized with Acorous calamus rhizome extract. *European Journal of Medicinal Chemistry*. 2014;**85**:784-794
- [79] Anuj SA, Ishnava KB. Plant mediated synthesis of silver nanoparticles using dried stem powder of *Tinospora cordifolia*, its antibacterial activity and its comparison with antibiotics. *International Journal of Pharmacy and Biological Sciences*. 2013;**4**:849-863
- [80] Patil RS, Kokate MR, Kolekar SS. Bioinspired synthesis of highly stabilized silver nanoparticles using ocimum tenuiflorum leaf extract and their antibacterial activity. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2012;**91**:234-238
- [81] Peng H, Yang A, Xiong J. Green, microwave-assisted synthesis of silver nanoparticles using bamboo hemicelluloses and glucose in an aqueous medium. *Carbohydrate Polymers*. 2013;**91**:348-355
- [82] Kagithoju S, Godishala V, Nanna RS. Eco-friendly and green synthesis of silver nanoparticles using leaf extract of *Strychnos potatorum* Linn.F. and their bactericidal activities. *3 Biotech*. 2015;**5**:709-714
- [83] Song JY, Kim BS. Rapid biological synthesis of silver nanoparticles using plant leaf extracts. *Bioprocess and Biosystems Engineering*. 2009;**32**:79-84
- [84] Roy E, Patra S, Saha S, Mahduri R, Sharma PK. Shape-specific silver nanoparticles prepared by microwave assisted green synthesis using pomegranate juice for bacterial inactivation and removal. *RSC Advances*. 2015;**5**:95433-95442