We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Ionic Liquids as Environmental Benign Solvents for Cellulose Chemistry: A Review

Indra Bahadur and Ronewa Phadagi

Abstract

The application of cellulose and its derivatives is restricted because of their limited solubility in water and many organic solvents. Recently, several attempts are being made to dissolve them in inorganic and organic solvents. The solubility of these polymeric materials mainly depends upon their molecular weight, pH, and source of origin. Nowadays, there has been a new breakthrough of applying ionic liquids (ILs; designer solvents) in the field of cellulose solvent chemistry. Association of ionic liquids with several salient features such as high thermal, chemical and low vapor pressure, and so on makes them ideal environmentally green solvents to be used for cellulose. The present chapter deals with a collection of some major works in which ionic liquids have been used as solvents for cellulose dissolution. The articles also describe the works illustrating the use of ionic liquids as cosolvents (organic aprotic solvents) for the better increase of the solvent activity (solubility).

Keywords: ionic liquids, cellulose chemistry, biocompatibility, green chemistry, degree of polymerization, polysaccharides

1. Introduction

Cellulose is defined as a natural homopolymer which is obtained mainly from living organisms including fungi, bacteria, algae, and animals [1, 2]. The cellulose is constructed by repetition of D-glucose units in which two glucose units are linked together by $\beta(C1 \rightarrow C4)$ -glycosidic bond [1] as shown in **Figure 1**. Additionally, degree of polymerization of cellulose highly depends upon the raw material; for native cellulose it can be up to 15,000 [3]. Cellulose has become one of the most widely used natural polymers because of its various fascinating physical and structural properties along with its biocompatibility and wide range of availability [4]. The several magnificent properties of cellulose arise due to the presence of multiple inter- and intrahydrogen bonding interactions as illustrated in **Figure 2**. The cellulose is an unbranched homopolymer because it exists in semicrystalline form containing both crystalline and amorphous phases [5].

It is clear from **Figure 1** that cellulose consisted of two types of hydroxyl ($-OH$) substituents, one is primary hydroxyl substituent and the other is secondary hydroxyl substituent [5].

The discovery of cellulose was made in late 1830s by Anselme Paven and Hyatt. In the year 1870, manufacturing company took a positive outlook in cellulose

Figure 1.
Chemical structure of cellulose.

Figure 2.
Pictorial presentation of inter- and intramolecular H bonding in cellulose.

research and produced first cellulosic thermoplastics [4, 6, 7]. The research of cellulose modification has been developing, from one process to another, trying to find as the most eco-friendly and eco-efficient method as possible from the time when it was discovered as cellulose is the most abundant natural material on earth.

2. Cellulose dissolution history

Ever since cellulose has been discovered, many researches are being carried out on the most efficient ways to dissolve this natural polymer in various common solvents [8]. The first attempt toward cellulose dissolution was made by Hyatt Manufacturing Co. in which cellulose was converted into nitrocellulose with the aid of nitric acid. The nitric acid treatment of the cellulose gives cellulosic-based thermoplastic polymer that has several industrial and biological applications [4]. As time progresses a new and a better method, namely, “viscose,” was developed which became effective from the 1890s and is the most widely used method in processing cellulose to date. Approximately 3.2 million tons of cellulose are processed per year using this method [9–11]. This method makes the use of alkali (NaOH) and carbon disulfide (CS_2) and produces cellulose xanthate. The detail methodology about the

viscose process has been described elsewhere [12–14]. During the late 1960s, lyocell (amine oxides) technique was invented mainly to overcome the challenges of viscose method which is found to be more effective in processing of cellulose. Lyocell technique employs the use of N-methylmorpholine N-oxide (NMMO). NMMO dissolves cellulose directly due to its strong N-O dipole [15]. However lyocell technique was not as effective as “viscose” technique as it had significant engineering complications; hence viscose remained to be the most widely used technique [16]. Both of those cellulose dissolution techniques retain major environmental complications (some of which are listed below).

Viscose	Lyocell
<ul style="list-style-type: none">• For every kilogram of cellulose produced, there is two kilograms of waste [11, 17]• Makes use of carbon disulfide and dihydrogen sulfide which are both environmental rivals and also not sustainable [10]	<ul style="list-style-type: none">• Poor thermal stability of NMMO [17, 18] which leads to major investment in safety measures of the industry and difficulties in recycling the solvent [16]• NMMO requires high temperatures which leads to degradation of cellulose [19, 20]

Those challenges lead to further research in cellulose dissolution process in search of solvents which can be as environmental friendly as possible. Therefore the new solvents should be associated with low volatile, easily recyclable, high thermal stability, nontoxic, non-derivative, etc. [21]. The solvents which were found to be most effective were NaOH/thiourea and urea aqueous solvents as well as molten salts. The NaOH/thiourea was found to dissolve cellulose at low temperatures ranging from -8 to -5°C as described elsewhere in detail [22, 23]. However this method was found to produce cellulose fibers with high degree of crystallinity but lower degree of crystal orientation when compared to fibers obtained from viscose process [23, 24]. In order to advance this method, thiourea was replaced by urea forming a new solvent system NaOH/urea [12], and this solvent was found to have enhanced cellulose solubility by precooling the solution to -12°C . The advantage of the method is based on the fact that the by-products so formed were nontoxic. The methodologies related to the preparation of NaOH/Urea system can be elsewhere [11, 12, 24]. Another eco-friendly solvent that is still in the academia is ionic liquids (designated by ILs). Recently, the ILs have been identified as the most universal solvents for the future due to their several fascinating properties such as high polarity, negligible vapor pressure, nonflammability, low melting point, good thermal stability, tunable viscosity, broad liquid range, high thermal conductivity, good dissolution properties, etc. [25–27]. Because of the association of ILs with these fascinating properties, they (ILs) can be considered as most important, cost-effective, and environmental benign solvents for cellulose.

3. Ionic liquids

3.1 Brief summary of ionic liquids

Ionic liquids are commonly defined as molten salts; these salts are composed of inorganic or organic anions and organic cations. In ILs, the oppositely charged ions are held together by columbic forces [28–30]. Most widely studied ILs are room temperature ionic liquids (RTILs) having melting point of below 100°C [31–34]. The ILs are liquids at room temperature because they are composed of polyatomic, bulk, asymmetric organic cations and charge-diffuse ions [17, 35], and their ions are not packed well; hence, they remain liquid [36] at room temperature. The

S. no.	Cations	Anions	
	Name	Structure	
1	Imidazolium	[BMIM] ⁺ , [AMIM] ⁺ , [MMIM] ⁺ , [EMIM] ⁺ , [AMIM] ⁺ , [HEMIM] ⁺ , [HMIM] ⁺ , [OMIM] ⁺ , [C ₂ MIM] ⁺ , [EMMIM] ⁺	Cl ⁻ , Br ⁻ , SCN ⁻ , [PF ₆] ⁻ , [BF ₄] ⁻ , [CF ₃ SO ₃] ⁻ , [BF ₄] ⁻ , [PF ₆] ⁻ , [I] ⁻ , [CH ₃ SO ₃] ⁻ , [Ac] ⁻ , [HSCH ₂ COO] ⁻ , [HCOO] ⁻ , [(C ₆ H ₅) COO] ⁻ , [H ₂ NCH ₂ COO] ⁻ , [HOCH ₂ COO] ⁻ , [CH ₃ CHOHCOO] ⁻ , [Fmt] ⁻ , [OAc] ⁻ , [SCN] ⁻ , [Tos] ⁻ , [N(CN) ₂] ⁻ , [CH ₃ CO ₂] ⁻
2	Pyridinium	[C ₄ MPY] ⁺ , [BMPY] ⁺ , ([C _n MPy] where n = 2– 10), [AMPy] ⁺	
3	Ammonium	[BDTAC] ⁺	
4	Phosphonium

Table 1.
Structures and abbreviations of some common cations and anions of ionic liquids employed as solvents.

RTILs are considered to be designer solvents since one can alter the physicochemical properties of an IL by simply varying anions' type or alky chain length of the cations [37–40]. The RTILs are composed of nitrogen or phosphorus containing dissymmetrical organic cations such as imidazolium, pyridinium, or ammonium or phosphonium cations and wide variety of simple anions such as chloride, nitrate, bromide, tetrafluoroborate, acetate, triflate, etc. [29, 41, 42] as shown in **Table 1**. So far, the ILs have been found to have numerous applications in various areas including solvent science for manufacturing of different materials including dissolution of biomass, electrochemistry for electrolytes in batteries, polymer chemistry for plasticizers, and separation technology for extractions and separations [26, 36, 37, 43]. Since ILs have been discovered, they are widely becoming advanced; in addition, the efficient methods of synthesis ILs are being developed. The application of ILs is vastly increasing yearly; recently, ILs have been started to be researched toward biomass processing, particularly cellulose, since cellulose is the most abundant biomaterial on earth [1, 17]; therefore, the use of ILs in cellulose chemistry can bring about economic sufficient developments archiving of the United Nation (UN) mission of moving away from depending on fossils fuels as well as using of harmful convectional solvents.

3.2 Cellulose dissolution using ionic liquids

The very first cellulose dissolution research was carried out by Richard P. Swatloski in the year 2002 [44]. Swatloski along with his coworkers reported that 1-butyl-3-methylimidazolium chloride ([C₄MIM]⁺) with Cl⁻, Br⁻, and SCN⁻ could dissolve cellulose whereas with [BF₄]⁻ and [PF₆]⁻ could not. They were further

observed that as increase in the alkyl chain length of the ILs decreases the solubility of the investigated ionic liquids as [C₄MIM][Cl], [C₆MIM][Cl], and [C₈MIM][Cl] since [C₄MIM][Cl] dissolved 10 wt%, [C₆MIM][Cl] dissolved 5 wt% and [C₈MIM][Cl] were slightly soluble. In addition the dissolution could be significantly enhanced by heating the solution using oil bath, microwave, or ultrasonic technique. This research indicated that “ionic liquids” can be used as solvents for cellulose and opened a new horizon in green chemistry [45]. Ever since Swatloski et al. [44] breakthrough in cellulose chemistry, many researchers proceed with his outcomes to further understand the dynamics and factors associated with the dissolution of cellulose using ionic liquids. To determine dynamics and factors that play a role in cellulose dissolution using ILs, properties such as different structures of the ionic liquids, degree of polymerization of cellulose, dissolution time, temperature, water content, and cosolvent were investigated starting from Zhang et al. [46] to Meenatchi et al. [47] including Kosan et al. [48], Heinze et al. [49], Lee et al. [50], Kilpeläinen et al. [51], Erdmenger et al. [52], Zavrel et al. [53], Sun et al. [54], Vits et al. [55], Fukaya et al. [21, 56], Sashina et al. [43], Xu et al. [57], Sescousse et al. [58], Zhen et al. [59], and Freire et al. [60], and the detailed summary of the factors affecting cellulose solubility is given in **Table 2**. It can be concluded that most of the studied ionic liquids are imidazolium-based ionic liquids; this is due to a fact that imidazolium ILs have the finest properties among other ILs; they have the lowest melting points; many of them are liquid at room temperature; they have high conductivity and a wide electrical window stability that makes them suitable for a variety of applications including solvents for the dissolution of cellulose [61]. Among the most widely studied imidazolium-based ILs [BMIM][Cl], [BMIM][Ac], [BMIM][Fmt], and [BMIM][OAc] together with [AMIM][Cl] and [AMIM][Fmt]

Factor	Explanation	Reference
Presence of water	Water content should be very low in both IL and cellulose, typically less than 1%	Swatloski et al. [44], Muhammad et al. [62]
Anions type	ILs containing anions that have strong electronegativity such as halides, e.g., Cl ⁻ , have better dissolution properties unlike noncoordinating anions such as [BF ₄] and [PF ₆]	Holm et al. [63], Dadi et al. [64], Swatloski et al. [44]
Alkyl chain length	Methylimidazolium cations with even number of carbons were found to have high solubilizing power than the one with odd number and pyridinium-based ionic liquids showed that as alkyl chain length of the cation increases, the solubility decreases	Erdmenger et al. [52], Sashina et al. [43], Olivier-Bourdigou et al. [65]
Degree of polymerization	Solubility rate of cellulose decreases as degree of polymerization increases	Kosan et al. [48], Zhang et al. [46]
Dissolution time	Dissolution time should be short typically around 12 h at low heating temperature	Kilpeläinen et al. [51]
IL viscosity	Low viscosity promotes higher dissolution since it promotes greater ions mobility	Tywabi [24], Fort et al. [66], Kilpeläinen et al. [51]
Cosolvent	Polar aprotic cosolvents promote higher and quicker dissolution at low temperature Polar protic is non-solvent which causes precipitation of the cellulose from the IL solution	Rinaldi et al. [67], Zhao et al. [68], Xu et al. [69, 70], Xu and Zhang [71], Bengtsson [72], Andanson et al. [73], Holding et al. [74], Swatloski et al. [44]

Table 2.
Detailed summary of factors affecting cellulose solubility.

as well as [EMIM][Cl], [EMIM][OAc], and [EMIM][MP] have been documented to be one of the most effective ILs for cellulose dissolution, with [BMIM][Cl] able to dissolve up to 25% wt of cellulose having a DP = 1000 using a microwave heating method. During dissolution process, it has been shown by aid of various analytical techniques that the strong inter- and intramolecular hydrogen bonding of cellulose is broken up by formation of intense hydrogen bonding between ionic liquid anions and cellulose hydroxyls making cellulose to be soluble; hence, ILs with noncoordinating anions are nonsolvents [44].

3.3 Cellulose dissolution using ionic liquids and cosolvents (organic solvents)

The use of organic solvents in the cellulose chemistry has been vain for many decades, which lead to the use of solvents like oxide amines (NMMO), NaOH/urea, LiCl/DMI, ILs ([BMIM][Cl], [AMIM][Cl]), etc. However every solvent has its own rewards and drawbacks; so far the greenest solvents proposed are the ILs. However, the use of ILs is still not yet practical and faces a lot of industrial challenges since ILs are available in small amount, are relatively costly, and have very high viscosity compared to other common aqueous thermochemical pretreatment reagents, and it deactivates regular cellulolytic enzymes [75–77]. To overcome these challenges faced by ILs, Renaldi [67] created a solvent system, which is a bicomponent containing both ionic liquid and cosolvent (polar aprotic solvents such as DMSO, DMF DMI, etc.) that significantly lowers the IL viscosity, which increases ionic mobility, thereby promoting higher cellulose dissolving rate than net ILs [57, 67] at ambient temperature [78]. Furthermore, Renaldi [60] in his studies conducted an experiment which revealed that the use of solvent system [BMIM][Cl]/DMI dissolves more cellulose (10 wt% in few minutes) than convectional solvent LiCl/DMI (2 wt% at 150°C for 30 min). Many researches today have further carried experiments to understand the cellulose chemistry using bicomponent IL with aprotic solvent [68–71, 73–75]. The results of studied cosolvents (DMSO, DMF, DMA, and DMI) with certain ILs showed that during the dissolution of cellulose, the aprotic cosolvent does not slightly interact with the hydroxyl of the cellulose; however, it decreases the association of the IL cation with the anion making more free ions to be available for the interaction of the cellulose hydroxyls; hence, more cellulose becomes readily soluble at ambient temperatures; furthermore, as more amount of the cosolvent is added to the solution, more cellulose continues to dissolve since more IL anions become available [67–71, 73–75, 78, 79]; in addition, Xu et al. [70] further indicated that the best aprotic cosolvent are the ones which have the highest dipole moment; hence, as the dipole moment decreases, the effectiveness of the aprotic cosolvent weakens.

4. Conclusion

In this review we summarized the major solvents that are applied in the cellulose chemistry. The ILs are implemented as new solvents for the dissolution of cellulose and its derivatives having several biological and industrial applications. The cellulose can be modified such as ether, ester, sulfate, amine, hemiacetal, carbanilate, etc., and the resulting material can be used for other applications. The cellulose derivatives can be used for various purposes such as textile, medicine, agriculture, biofuels, etc. In order for ionic liquids to be applied industrially, there are major problems still to be addressed such as:

- Development of the efficient ways to synthesis ionic liquids so that ILs can be available in high quantity.

- The need to do further research in solvent recovery for both ILs and for ILs with a cosolvent.
- To do research on IL chemical and toxicological data with cellulose.
- The dissolution mechanism of cellulose with ILs in details.

IntechOpen

IntechOpen

Author details

Indra Bahadur* and Ronewa Phadagi

Department of Chemistry and Materials Science Innovation, Modelling Research Focus Area, School of Mathematical and Physical Sciences, Faculty of Agriculture, Science and Technology, North-West University, Mmabatho, South Africa

*Address all correspondence to: bahadur.indra@gmail.com

IntechOpen

© 2019 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/3.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

References

- [1] O'sullivan AC. Cellulose. The structure slowly unravels. *Cellulose*. 1997;**4**:173
- [2] Borbély É. Lyocell, the new generation of regenerated cellulose. *Acta Polytechnica Hungarica*. 2008;**5**:11-18
- [3] Sjostrom E. *Wood Chemistry: Fundamentals and Applications*. 2nd ed, Elsevier Publication; 2013
- [4] Isik M, Sardon H, Mecerreyes D. Ionic liquids and cellulose: Dissolution, chemical modification and preparation of new cellulosic materials. *International Journal of Molecular Sciences*. 2014;**15**:11922-11940
- [5] Gürdağ G, Sarmad S. *Cellulose Graft Copolymers: Synthesis, Properties, and Applications, Olysaccharide Based Graft Copolymers*. Berlin, Heidelberg: Springer; 2013. p. 15
- [6] Schönbein C. Notiz Über Eine Veränderung Der Pflanzenfaser Und Einiger Andern Organischen Substanzen, *Berichte der Naturforschenden Gesellschaft (Basel)*. 1847;**7**:27
- [7] Hyatt. US Patent. Google Patents. 1880;**232**:037
- [8] Heinze T, Koschella A. Solvents applied in the field of Cellulose Chemistry: A mini review. *Polímeros*. 2005;**15**:84-90
- [9] Ramamoorthy SK, Skrifvars M, Persson A. A review of natural fibers used in biocomposites: Plant, animal and regenerated cellulose fibers. *Polymer Reviews*. 2015;**55**:107-162
- [10] Heinze T, Liebert T. Unconventional methods in cellulose functionalization. *Progress in Polymer Science*. 2001;**26**:1689
- [11] Liebert T. Cellulose Solvents: Remarkable history, bright future, cellulose solvents. For analysis, shaping and chemical modification (chapter 1st). American Chemical Society; 2010. p. 3-54
- [12] Liebert T, Heinze T. Interaction of ionic liquids with polysaccharides. 5. Solvents and reaction media for the modification of cellulose. *BioResources*. 2008;**3**:576
- [13] Brown EK. Cellulose dissolution in ionic liquids and their mixtures with solvents: linking ion/solvent structure and efficacy of biomass pretreatment. North Carolina State University; 2012
- [14] Sixta H. *Handbook of Pulp*. Wiley Online Library; 2006
- [15] Cao Y, Wu J, Zhang J, Li H, Zhang Y, He J. Room temperature Ionic Liquids (RTILs): A new and versatile platform for cellulose processing and derivatization. *Chemical Engineering Journal*. 2009;**147**:13-21
- [16] Hermanutz F, Gähr F, Uerdingen E, Meister F, Kosan B. New developments in dissolving and processing of cellulose in ionic liquids, macromolecular symposia. Wiley Online Library; 2008. p. 23-27
- [17] Clough MT, Geyer K, Hunt PA, Son S, Vagt U, Welton T. Ionic liquids: Not always innocent solvents for cellulose. *Green Chemistry*. 2015;**17**:231-243
- [18] Dorn S, Wendler F, Meister F, Heinze T. Interactions of ionic liquids with polysaccharides–7: thermal stability of cellulose in ionic liquids and N-Methylmorpholine-N-oxide. *Macromolecular Materials and Engineering*. 2008;**293**:907-913
- [19] Wendler F, Graneß G, Heinze T. Evidence of autocatalytic reactions in cellulose/nmmo solutions with thermal

and spectroscopic methods. Lenzinger Berichte. 2005;**84**:92-102

[20] Rosenau T, Elder T, Potthast A, Herbert S, Kosma P. The lyocell process: Cellulose solutions in N-Methylmorpholine-N-oxide (NMMO)-degradation processes and stabilizers. In: 12th International Symposium on Wood and Pulping Chemistry. June 9-12. Madison, Wisconsin; 2003. pp. 305-308

[21] Fukaya Y, Hayashi K, Wada M, Ohno H. Cellulose dissolution with polar ionic liquids under mild conditions: Required factors for anions. Green Chemistry. 2008;**10**:44-46

[22] Zhang L, Ruan D, Gao S. Dissolution and regeneration of cellulose in NaOH/thiourea aqueous solution. Journal of Polymer Science Part B: Polymer Physics. 2002;**40**:1521-1529

[23] Jiang M, Zhao M, Zhou Z, Huang T, Chen X, Wang Y. Isolation of cellulose with ionic liquid from steam exploded rice straw. Industrial Crops and Products. 2011;**33**:734-738

[24] Tywabi Z. Processing of dissolving pulp in ionic liquids, Doctoral dissertation. 2015. Available from: <https://ir.dut.ac.za/handle/10321/1746>

[25] Ye C, Liu W, Chen Y, Yu L. Room-temperature ionic liquids: A novel versatile lubricant. Chemical Communications. 2001:2244-2245

[26] Han D, Row KH. Recent applications of ionic liquids in separation technology. Molecules. 2010;**15**:2405-2426

[27] Baranyai KJ, Deacon GB, MacFarlane DR, Pringle JM, Scott JL. Thermal degradation of ionic liquids at elevated temperatures. Australian Journal of Chemistry. 2004;**57**:145-147

[28] Rogers RD, Seddon KR. Ionic liquids--solvents of the future? Science. 2003;**302**:792-793

[29] Berthod A, Ruiz-Angel M, Carda-Broch S. Ionic liquids in separation techniques. Journal of Chromatography A. 2008;**1184**:6-18

[30] Heintz A. Recent Developments in thermodynamics and thermophysics of non-aqueous mixtures containing ionic liquids. A review. The Journal of Chemical Thermodynamics. 2005;**37**:525-535

[31] Yang Z, Pan W. Ionic liquids: Green solvents for nonaqueous biocatalysis. Enzyme and Microbial Technology. 2005;**37**:19-28

[32] Alvarez VH, Mattedi S, Martin-Pastor M, Aznar M, Iglesias M. Thermophysical properties of binary mixtures of {Ionic Liquid 2-Hydroxy Ethylammonium Acetate+ (Water, Methanol, or Ethanol)}. The Journal of Chemical Thermodynamics. 2011;**43**:997-1010

[33] Andreatta AE, Arce A, Rodil E, Soto A. Physical properties of binary and ternary mixtures of Ethyl Acetate, Ethanol, and 1-Octyl-3-Methyl-Imidazolium Bis (Trifluoromethylsulfonyl) Imide at 298.15 K. Journal of Chemical & Engineering Data. 2009;**54**:1022-1028

[34] Bahadur I, Kgomo M, Ebenso EE, Redhi G. Redhi, influence of temperature on molecular interactions of imidazolium-based ionic liquids with acetophenone: Thermodynamic properties and quantum chemical studies. RSC Advances. 2016;**6**:104708-104723

[35] Laus G, Bentivoglio G, Schottenberger H, Kahlenberg V, Kopacka H, Röder T, et al. Sixta, ionic liquids: Current developments, potential and drawbacks for industrial applications. Lenzinger Berichte. 2005;**84**:71-85

[36] Keskin S, Kayrak-Talay D, Akman U, Hortaçsu Ö. A review of ionic liquids

towards supercritical fluid applications. *The Journal of Supercritical Fluids*. 2007;**43**:150-180

[37] Plechkova NV, Seddon KR. Applications of ionic liquids in the chemical industry. *Chemical Society Reviews*. 2008;**37**:123-150

[38] Rogers RD, Seddon KR, Volkov S. Green industrial applications of ionic liquids. Springer Science & Business Media; 2012

[39] Wu C-T, Marsh KN, Deev AV, Boxall JA. Liquid– liquid equilibria of room-temperature ionic liquids and butan-1-ol. *Journal of Chemical & Engineering Data*. 2003;**48**:486-491

[40] Holbrey J, Seddon K. Ionic liquids. *Clean Products and Processes*. 1999;**1**:223-236

[41] Liu J-f, Jiang G-b, Jönsson JÅ. Application of ionic liquids in analytical chemistry. *TrAC Trends in Analytical Chemistry*. 2005;**24**:20-27

[42] Stepnowski P. Application of chromatographic and electrophoretic methods for the analysis of imidazolium and pyridinium cations as used in ionic liquids. *International Journal of Molecular Sciences*. 2006;**7**:497-509

[43] Sashina E, Novoselov N, Kuz'mina O, Troshenkova S. Ionic liquids as new solvents of natural polymers. *Fibre Chemistry*. 2008;**40**:270-277

[44] Swatloski RP, Spear SK, Holbrey JD, Rogers RD. Dissolution of cellose with ionic liquids. *Journal of the American Chemical Society*. 2002;**124**:4974-4975

[45] El Seoud OA, Koschella A, Fidale LC, Dorn S, Heinze T. Applications of Ionic liquids in carbohydrate chemistry: A window of opportunities. *Biomacromolecules*. 2007;**8**:2629-2647

[46] Zhang H, Wu J, Zhang J, He J. 1-Allyl-3-Methylimidazolium chloride room temperature ionic liquid: A new and powerful nonderivatizing solvent for cellulose. *Macromolecules*. 2005;**38**:8272-8277

[47] Meenatchi B, Renuga V, Manikandan A. Cellulose dissolution and regeneration using various imidazolium based protic ionic liquids. *Journal of Molecular Liquids*. 2017;**238**:582-588

[48] Kosan B, Michels C, Meister F. Dissolution and forming of cellulose with ionic liquids. *Cellulose*. 2008;**15**:59-66

[49] Heinze T, Schwikal K, Barthel S. Ionic liquids as reaction medium in cellulose functionalization. *Macromolecular Bioscience*. 2005;**5**:520-525

[50] Lee SH, Doherty TV, Linhardt RJ, Dordick JS. Ionic liquid-mediated selective extraction of lignin from wood leading to enhanced enzymatic cellulose hydrolysis. *Biotechnology and Bioengineering*. 2009;**102**:1368-1376

[51] Kilpeläinen I, Xie H, King A, Granstrom M, Heikkinen S, Argyropoulos DS. Dissolution of wood in ionic liquids. *Journal of Agricultural and Food Chemistry*. 2007;**55**:9142-9148

[52] Erdmenger T, Haensch C, HoogenboomR, SchubertUS. Homogeneous tritylation of cellulose in 1-Butyl-3-Methylimidazolium chloride. *Macromolecular Bioscience*. 2007;**7**:440-445

[53] Zavrel M, Bross D, Funke M, Büchs J, Spiess AC. High-throughput screening for ionic liquids dissolving (Ligno-) cellulose. *Bioresource Technology*. 2009;**100**:2580-2587

[54] Sun N, Rahman M, Qin Y, Maxim ML, Rodríguez H, Rogers RD. Complete

dissolution and partial delignification of wood in the ionic liquid 1-Ethyl-3-Methylimidazolium acetate. *Green Chemistry*. 2009;**11**:646-655

[55] Vitz J, Erdmenger T, Haensch C, Schubert US. Extended dissolution studies of cellulose in imidazolium based ionic liquids. *Green Chemistry*. 2009;**11**:417-424

[56] Fukaya Y, Sugimoto A, Ohno H. Superior solubility of polysaccharides in low viscosity, polar, and halogen-free 1, 3-Dialkylimidazolium formates. *Biomacromolecules*. 2006;**7**:3295-3297

[57] Xu A, Wang J, Wang H. Effects of anionic structure and lithium salts addition on the dissolution of cellulose in 1-Butyl-3-Methylimidazolium-based ionic liquid solvent systems. *Green Chemistry*. 2010;**12**:268-275

[58] Sescousse R, Gavillon R, Budtova T. Aerocellulose from cellulose-ionic liquid solutions: Preparation, properties and comparison with cellulose-naoh and cellulose-nmno routes. *Carbohydrate Polymers*. 2011;**83**:1766-1774

[59] Ding Z-D, Chi Z, Gu W-X, Gu S-M, Liu J-H, Wang H-J. Theoretical and experimental investigation on dissolution and regeneration of cellulose in ionic liquid. *Carbohydrate Polymers*. 2012;**89**:7-16

[60] Freire MG, Teles ARR, Rocha MA, Schröder B, Neves CM, Carvalho PJ, Evtuguin DV, Santos LM, Coutinho JA. Thermophysical characterization of ionic liquids able to dissolve biomass. *Journal of Chemical & Engineering Data*. 2011;**56**:4813-4822

[61] Ngo HL, LeCompte K, Hargens L, McEwen AB. McEwen, Thermal Properties of Imidazolium Ionic Liquids. *Thermochimica Acta*. 2000;**357**:97-102

[62] Muhammad N, Man Z, Khalil MAB. Ionic Liquid—A future solvent for the enhanced uses of wood biomass. *European Journal of Wood and Wood Products*. 2012;**70**:125

[63] Holm J, Lassi U. Ionic liquids in the pretreatment of lignocellulosic biomass, ionic liquids. *Applications and Perspectives*. InTech; 2011

[64] Dadi AP, Varanasi S, Schall CA. Schall, enhancement of cellulose saccharification kinetics using an ionic liquid pretreatment step. *Biotechnology and Bioengineering*. 2006;**95**:904

[65] Olivier-Bourbigou H, Magna L, Morvan D. Morvan, ionic liquids and catalysis: Recent progress from knowledge to applications. *Applied Catalysis A: General*. 2010;**373**:1

[66] Fort DA, Remsing RC, Swatloski RP, Moyna P, Moyna G, Rogers RD. Can ionic liquids dissolve wood? processing and analysis of lignocellulosic materials with 1-N-Butyl-3-Methylimidazolium chloride. *Green Chemistry*. 2007;**9**:63

[67] Rinaldi R. Instantaneous dissolution of cellulose in organic electrolyte solutions. *Chemical Communications*. 2011;**47**:511

[68] Zhao Y, Liu X, Wang J, Zhang S. Insight into the cosolvent effect of cellulose dissolution in imidazolium-based ionic liquid systems. *The Journal of Physical Chemistry B*. 2013;**117**:9042

[69] Xu A, Cao L, Wang B, Ma J. Dissolution behavior of cellulose in IL. *Advances in Materials Science and Engineering*. 2015

[70] Xu A, Cao L, Wang B. Acile Cellulose dissolution without heating in [C4mim][CH3COO]/DMF solvent. *Carbohydrate Polymers*. 2015;**125**:249

[71] Xu A, Zhang Y. Insight into dissolution mechanism of cellulose in

[C4mim][CH₃COO]/DMSO solvent by ¹³C NMR spectra. *Journal of Molecular Structure*. 2015;**1088**:101

[72] Bengtsson J, De Clerck KP, Persson AC. Evaluating recyclability and suitability of tetrabutylammonium acetate: Dimethyl sulfoxide as a solvent for cellulose. 2016

[73] Andanson J-M, Bordes E, Devémy J, Leroux F, Pádua AA, Gomes MFC. Understanding the role of co-solvents in the dissolution of cellulose in ionic liquids. *Green Chemistry*. 2014;**16**:2528

[74] Holding AJ, Parviainen A, Kilpeläinen I, Soto A, King AW, Rodríguez H. Efficiency of hydrophobic phosphonium ionic liquids and DMSO as recyclable cellulose dissolution and regeneration media. *RSC Advances*. 2017;**7**:17451

[75] Wu L, Lee S-H, Endo T. Effect of dimethyl sulfoxide on ionic liquid 1-Ethyl-3-Methylimidazolium acetate pretreatment of eucalyptus wood for enzymatic hydrolysis. *Bioresource Technology*. 2013;**140**:90

[76] Engel P, Mladenov R, Wulforth H, Jäger G, Spiess AC. Point by point analysis: How ionic liquid affects the enzymatic hydrolysis of native and modified cellulose. *Green Chemistry*. 2010;**12**:1959

[77] Turner MB, Spear SK, Huddleston JG, Holbrey JD, Rogers RD. Ionic liquid salt-induced inactivation and unfolding of cellulase from *trichoderma reesei*. *Green Chemistry*. 2003;**5**:443

[78] Xu A, Zhang Y, Zhao Y, Wang J. Cellulose dissolution at ambient temperature: Role of preferential solvation of cations of ionic liquids by a cosolvent. *Carbohydrate Polymers*. 2013;**92**:540

[79] Rein DM, Khalfin R, Szekely N, Cohen Y. True molecular solutions of natural cellulose in the binary ionic liquid-containing solvent mixtures. *Carbohydrate Polymers*. 2014;**112**:125