We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Polymer Resonant Waveguide Gratings

Muhammad Rizwan Saleem and Rizwan Ali

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/intechopen.76917>

Abstract

This chapter deals with the advances in polymeric waveguide gratings for filtering and integrated optics applications. Optical polymer materials are widely used for planar and corrugated micro-optical waveguide grating structures ranging from down a micrometer to several hundred micrometers. Light in a polymeric waveguide is transmitted in discrete modes whose propagation orders depend on incident wavelength, waveguide dimensional parameters, and material properties. Diffracted optical structures are permittivity-modulated microstructures whose micro-relief surface profiles exhibit global/local periodicity. The resonant nature and location of such globally periodic structures (diffraction gratings) excite leaky waveguide modes which couple incident light into reflected/transmitted plane wave diffraction orders. It describes design & analysis, fabrication, and characterization of sub-wavelength polymer grating structures replicated in different polymeric materials (polycarbonate, cyclic olefin copolymer,Ormocomp) by a simple, cost-effective, accurate, and large scale production method. The master stamp (mold) for polymer replication is fabricated with an etchless process with smooth surface profile.

Keywords: resonant waveguide gratings, polymeric materials, nanoimprint lithography

1. Introduction

Conventional optical waveguides work on the principle to guide waves in a material surrounded by other material media, the refractive index of the material should be slightly higher than that of surrounded media such that light can bounce along the waveguide by means of total internal reflections at the boundaries between different media. The indefinite guiding progress the waves from successive boundaries which must interfere constructively to generate a continuous and stable interference pattern along the waveguide. If the interference pattern is not fully constructive, the waves cancel, owing to the self-destruction. The conventional

optical waveguides are primarily the most common type of thin film optical filters used widely as narrowband filters in laser cavities, optical telecommunications, and light modulators [1]. However, the realization of sub-nanometer narrowband filters with thin film technique require hundreds of optical thin-films stack with stringent tolerances over thicknesses and refractive index variations [2]. Resonant Waveguide Gratings (RWGs) are a new class of narrowband filters and are widely used in applications such as polarizers [3], laser cavity reflectors [3, 4], light modulators [5], biosensors [6], and wavelength division multiplexing [7]. Such narrowband reflectance/transmittance spectral characteristics can be observed by sub-wavelength grating structures in terms of resonance anomalies [8, 9] with numerous potential applications. RWG operates with resonance effects with relatively simpler structure of few layers. Owing to the resonant nature of the sub-wavelength grating, the leaky modes are supported by the structure (waveguide layer and a grating layer) [10]. In the absence of the grating layer, waveguide layer supports a true bound mode. This bound mode becomes leaky when a grating layer is added with the waveguide layer. Eventually, optical energy is coupled out of the waveguide into radiation modes. On the other hand, the incident plane wave energy is coupled to the waveguide. The incident plane wave energy is coupled into leaky modes and then back to one or more radiation modes. This coupling mostly depends on the wavelength, angle of incidence and other structural parameters of the grating layer. At resonance a sharp peak in reflected/transmitted light might be observed at a specific combination of these parameters.

Large scale demands for cost-effective yet reliable and efficient photonic components have led many researchers to consider polymer materials. Polymeric materials become widely useful and increasingly attractive in the fabrication of various micro and nanostructures with the potential replacement of conventional inorganic materials such as SiO_2 and LiNbO_3 or semiconductors. Novel polymers have been introduced for replication of nanostructure RWG through inexpensive and mass-production process [11]. The polymeric materials offer high thermal expansion coefficient (almost an order of magnitude) in comparison to traditional inorganic materials as well as thermo-optic coefficient which enable them to use as fast rate switches. Investigations to fabricate RWG in polymeric materials have been actively pursued throughout over the past two decades [12, 13].

The capability to fabricate precise novel structures at micro to nanoscale with a wide variety of materials imposes great challenges to the advancement of nanotechnology and the nanosciences. The semiconductor industry continues pushing to lower structural size and to manufacture smaller transistors and high density integrated circuits. The demanding industrial processes through newly developed lithographic methodologies need to address some critical issues such as speed, reliability, overlay accuracy, etc. Many alternative approaches have been used to manufacture nanostructures in past two decades, despite of using expensive tools such as deep-UV projection lithography and electron beam lithography techniques. These techniques include micro-contact printing, scanning probe based techniques, dip-pen lithography, and Nanoimprint Lithography (NIL) [14]. NIL can not only fabricate nanostructures in resists but can also imprint functional devices in many polymers through ease and cost-effective processes in a number of applications such as photonics, data storage, biotechnology, and electronics [15].

In this chapter we present details of design, fabrication, and characterization of polymeric RWG employing affordable techniques and mass production processes. The fabrication of master

stamp by electron beam lithography and subsequent replication in polymer materials by NIL is presented to target a number of applications in thermoplastics and UV curable polymers.

2. Theory of resonant waveguide gratings

The grating structure to enhance the resonance anomalies of a periodic profile (periodic modulation of refractive index) by coupling illuminating plane wave to the leaky modes of the waveguide of the grating is known as resonant waveguide gratings. Diffraction grating splits incident plane wave to propagate in different directions so-called diffraction orders. The periodic structure undergo complete interference and resonates with no transmission at a particular wavelength and incident angle [16]. As a result, light couples out of the waveguide, propagates up to smaller distances, and appears in the form of narrower reflectance peaks whose power varies from 0 to 100% over a range of structural parameters [10, 16, 17].

The propagation constant of a leaky mode is complex quantity and expressed as,

$$\beta = \beta_0 + i\gamma, \quad (1)$$

where β_0 and γ are pure real numbers while the imaginary part (γ) of the propagation constant represents the propagation loss of the leaky modes [18]. Generally, the spectral width of a resonance curve is proportional to this propagation loss and the full width at half maximum is approximated by.

$$\Delta\lambda_{\text{FWHM}} = \lambda_0 \frac{d\gamma}{\pi}, \quad (2)$$

where λ_0 is the resonant wavelength, d is the periodicity.

In 1994, researchers used Effective Medium Theory (EMT) to model stratified media as a thin-film stack possessing some effective index. The attempts were made to achieve symmetric spectral response with low sidebands by varying thicknesses of thin-film stacks. This approach results in to design an effective thin-film layer to be antireflective at resonant wavelength [19, 20]. Several researchers considered thin-film model for the design of symmetric filters and suggested numerical solutions based on rigorous modeling methods [21]. To design grating layer, the effective index model was suggested for thin-film method [19]. In 1956, Rytov developed a transcendental equation based on EMT to correlate effective refractive index of a stratified medium to physical parameters and wavelength of light [22]. This equation can be applied to grating problems and written as for a TE-polarized light:

$$(n_H^2 - n_{\text{eff}}^2)^{1/2} \tan \left[\pi (n_H^2 - n_{\text{eff}}^2)^{1/2} \times \frac{fd}{\lambda} \right] = -(n_L^2 - n_{\text{eff}}^2)^{1/2} \tan \left[\pi (n_L^2 - n_{\text{eff}}^2)^{1/2} \times \frac{(1-f)d}{\lambda} \right], \quad (3)$$

where n_H , n_L , n_{eff} are the high, low, and effective indices of the grating, respectively, f is the fill factor, d is the grating periodicity, and λ is the wavelength of the light. In the long wavelength limit ($\frac{d}{\lambda} \rightarrow 0$), (Eq. (3)) can be solved in terms of an analytic relation:

$$n_{\text{eff}} = [f n_H^2 + (1-f) n_L^2]^{1/2}. \quad (4)$$

Eq. (3) is referred as the exact effective index model whereas (Eq. (4)) as zeroth order effective index model.

The fundamental structure of a RWG is shown in **Figure 1**. The waveguide grating consist of a substrate material with refractive index n_t , a coupled grating layer with refractive index distribution $n_2(x)$ along x -direction and a superstrate layer (generally air) with refractive index n_i . When light of wavelength λ illuminates the grating at an incident angle θ_i , it results in generation of various propagated diffraction orders through one-dimensional grating which can be calculated by fundamental grating equation, given as:

$$n_2 \sin \theta_m = n_i \sin \theta_{\text{in}} + m \frac{\lambda}{d}, \quad (5)$$

where λ is the wavelength, θ_{in} is the incident angle of light, d is the periodicity of the grating structure, θ_m is the diffraction order, $m = 0, \pm 1, \pm 2, \pm 3, \dots$ is the index of diffraction order, n_i and n_2 are the indices before and after the interface. For reflection gratings n_2 is replaced by n_i and for transmission gratings by n_t .

Narrow reflection or transmission peaks can be achieved by understanding the physics of the structure which depends on the excitation of leaky waveguide modes. Consider a reflection grating with periodicity smaller than the wavelength of light used to allow only zeroth-order diffraction under plane wave illumination as shown in **Figure 2**. The resulted reflecting fields from the gratings may be assumed to produce from two contributions, namely: a direct reflection and a scattered field reflection [22]. The inherent direct reflection from upper interface is primary reflection so-called *Fresnel reflection* whereas the secondary reflection from the grating structure is due to excitation and rescattering of leaky waveguide modes whose phase vary continuously to fulfill the coupling relation given below:

Figure 1. Schematic representation of resonant waveguide Grating's structure with forward and backward propagated diffraction orders.

Figure 2. Schematic view of RWG with refractive index distributions and coated high index cover layer.

$$\gamma_0 = k_x + n \frac{2\pi}{d}, \quad (6)$$

where d is periodicity of the grating, γ_0 is propagation constant of fundamental mode and k_x is wave vector associated with the illuminating plane wave. At the resonance regime the rapidly varying phase of the secondary field with respect to the incident field (wave number) becomes similar in phase which gives rise resonance in the form of narrow reflected peak with wavelength or angle of incidence [23]. In **Figure 1**, the leaky waveguide modes in lateral direction are represented by propagation constant γ . Due to the leaky nature of propagated modes, they are shown to possess both real and imaginary parts and form a plane, so-called *complex γ -plane*. A leaky mode is described by a pole on this complex γ -plane. A planar waveguide supports at least one mode, the pole of which is represented by the real value on this γ -plane. Owing to the introduction of periodicity in the planar structure, such single mode splits into an infinite number of spatially diffracted orders whose poles are represented by complex values on this complex γ -plane with a separation of $\frac{2\pi}{d}$. Thus, the leaky waveguide modes are primarily associated with the periodicity of grating structure and much more closely spaced poles can be observed for sufficiently small periodic structure compared to incident wavelength. The magnitudes of real and imaginary parts of such complex poles show the extent of leaky modes excited by the input plane wave i.e., the coupling of the real part of modes (poles) with input field and the associated coupling loss, respectively [24].

3. Selection of polymer materials for optical waveguide

Polymeric materials have become potential candidate with versatility optical device performance and functionality. In comparison to inorganic materials, polymeric materials possess many attributable characteristics. The properties of polymer materials can be changed

Figure 3. (a) Schematic representation of originally proposed NIL process by Chou. (b) Scanning Electron Microscopy (SEM) image of a mold possessing pillar array diameter of 10 nm. (c) Replicated structure of mold in PMMA polymer material with hole array of size 10 nm. Reproduced with permission from [27]. Copyright 1997, American Institute of Physics.

chemically after modifying the chemical structure of the monomers, polymer backbones, addition of functional groups or chromophores. Polymer materials can be made to manipulate easily by many conventional or unconventional fabrication methods such as reactive ion etching (dry etching), wet etching, soft lithography etc. [25]. Polymer materials offer a simple, low-cost, and reliable fabrication process irrespective to fragile silica or expensive semiconductor materials. Functional polymeric materials provide interesting properties for integrating several diversified materials with different functionalities.

Optical waveguide structures can be fabricated directly by electron beam lithography which is the most effective method to fabricate micro- and nanostructures [25]. Alternatively, soft lithography technique has been extensively developed during past 20 years and improving optical waveguide manufacturing by the use of a master stamp to generate several soft molds to reproduce its replicas [25, 26]. **Figure 3** shows schematic of the originally NIL process proposed by Chao almost two decades before [27, 28]. The master stamp or mold containing nanoscale surface relief features is pressed against a polymeric material on a substrate with tightly controlled temperature and pressure to create a thickness contrast in polymer material. Furthermore, a thin residual layer is made beneath the stamp protrusions as a cushioning layer to protect nanoscale structure on mold surface from a direct impact of mold on the substrate. However, this residual layer can be removed at the end of the process by an anisotropic O_2 plasma etching. **Figure 3b** and **c** shows Scanning Electron Microscopy (SEM) images of a mold with pillar array of diameter 10 nm and replicated hole array in poly (methyl methacrylate) (PMMA) [28].

4. RWG modeling tool

In this chapter the RWG structures are designed and modeled using most efficient method which is based on the Fourier expansion, commonly known as Fourier Modal Method (FMM) or the coupled wave method (CWM) [29]. FMM determines eigen-solution values of Maxwell's equations in a periodic or piecewise continuous medium by expanding the electromagnetic fields and permittivity functions to Fourier series and applying the boundary conditions to show fields inside the grating by an algebraic eigenvalue problem [30]. Employing FMM to periodic-modulated region, the modulated region sections in slabs

where solution of Maxwell's equations is determined at each slab. Such solutions appear in the form of forward and backward propagated fields consisting of modal fields. These fields are pseudoperiodic in nature and expressed in the $e^{\pm i\beta z}$, where β is the eigenvalue of a mode. The eigenvalue problem is shown in matrix form which expresses a set of allowed β values and transverse field distributions for each polarization of light. The emerging fields from each slab are combined at each interface by applying boundary values. This computation shows an overall field inside the modulated region which is then matched with the fields in homogeneous regions surrounding the modulated region. At the end the problem is expressed in a matrix form to calculate complex transmission and reflection field amplitudes [31].

5. Cost-effective master stamp fabrication process by electron beam lithography (EBL) and hydrogen silsesquioxane (HSQ) resist

The properties of stamping material play a significant role in replication process to achieve a well-defined replicated features. In this section, patterns are defined on a resist material

Figure 4. Schematic representation of fabrication and replication process of HSQ mold and polymeric binary grating structures with nanoscale surface-relief features. Reproduced with permission from [11]. Copyright 2012, SPIE.

which is coated on a silicon substrate and written by electron beam lithography (EBL) without reactive ion etching (RIE) of silicon. Moreover, accurate control to pattern depth is challenging and inaccuracies in depth profiles are inherent with different width structures. Furthermore, the associated EBL proximity effect increases with the pattern depths and become more pronounced when beam size becomes comparable to the pattern size. The line edge variations occurred due to incomplete suppression of resist after development process resulted in polymer molecule agglomerate formation at pattern line edges [20]. Hydrogen silsesquioxane (HSQ) is a high resolution, inorganic, negative tone EB resist material with small linewidth variations in comparison to positive EB resists such as PMMA and ZEP. To fabricate structures with high resolutions, the molecular size of resist material need to be smaller than the nanoscale features to be replicated for which HSQ resist possesses dominating properties with slight line roughness and high etch resistance in addition [32].

In this Chapter we show replication of nanoscale structures in thermoplastic thin films and UV curable polymers by using an HSQ mold. The mold is fabricated by spin coating HSQ resist layer on silicon substrate, direct e-beam writing followed by development process without reactive ion etching. The HSQ resist thickness is adjusted to obtain structure design height h . Additionally,

Figure 5. SEM images of top view of HSQ resist master stamp on silicon substrate with periodicity ($d = 325$ nm) at different magnifications: (a) 100.00 KX, (b) 150.00 KX, (c) 200.00 KX, and (d) 250.00 KX.

the formed structure is heat treated to improve mechanical properties of the resist for 180 min at 300°C temperature. Such thermal treatment improves density and hardness of HSQ resist to enable it for the use of hard stamp with high imprint pattern fidelity. The heat treated mold(s) are surface treated in nitrogen environment to deposit a silane layer to act as an antiadhesive layer for imprinting. Finally, the imprinted polymeric gratings with several periodicities are coated with high index amorphous TiO_2 thin films by atomic layer deposition. Spectral characteristics of the replicated structures are investigated by a variable angle spectroscopic ellipsometer. **Figure 4** depicts schematic representation of complete process flow of HSQ mold fabrication and imprinting into polymeric materials (thermoplastics and UV curable) with high index TiO_2 thin layer.

Figure 5 shows SEM images of top view of HSQ resist molds (grating structures) at different magnifications on silicon substrate with period d of 325 nm. **Figure 6a** and **b** shows cross-sectional view of SEM images of HSQ binary molds with period 425 nm and **Figure 6c** and **d** with period 325 nm [33].

Figure 7 shows imprinted sub-wavelength grating structures in thermoplastic and UV curable plastic materials by NIL tool. **Figure 8** shows various thin films of amorphous TiO_2 coated on polycarbonate, cyclic olefin copolymer and UV curable Ormocomp by atomic layer deposition

Figure 6. SEM images of cross-sectional view of HSQ resist master stamp on silicon with periodicities: (a and b) $d = 425$ nm and (c and d) $d = 325$ nm. Reproduced with permission from [33]. Copyright 2013, NUST.

Figure 7. SEM images of cross-sectional view of imprinted structures in: (a and b) polycarbonate with period $d = 368$ nm, (c) cyclic olefin copolymer with period $d = 325$ nm and (d) UV curable material Ormocomp with period $d = 325$ nm. Reproduced with permission from [33]. Copyright 2013, NUST.

as a waveguide layer [30]. The details of conformal growth of amorphous TiO_2 thin films by atomic layer deposition is described in Refs. [34, 35].

Figure 9 shows the ellipsometric measurement setup when a linearly polarized plane wave (electric field vector is parallel called TE or perpendicular called TM to the grating lines) incident on the sample at an incident angle Φ with respect to normal of the RWG sample. The light-matter interaction results in specular reflectance/transmittance of the resonant gratings. The polarization state (TE or TM) of the illuminated light is selected by a polarizer stage which transforms the unpolarized light beam into a linearly polarized light beam. The polarization stage composed of a polarizer mounted on a continuously rotated stepper motor with high accuracy. The rotating polarizer changes the intensity of the light. The phase and amplitude of the modulated light represents the polarization state of the beam entering the analyzer/detector. In general, ellipsometer predicts the ellipticity of the polarization state of the light, optical constants (n and k) of optical materials, and the thickness of the thin film. The ellipsometric measurement uses two parameters which are connected by Eq. (7) [36].

Figure 8. SEM images of amorphous TiO₂ coated replicated gratings: (a) polycarbonate with period $d = 368$ nm and TiO₂ thickness $t = 80$ nm, (b) polycarbonate with period $d = 368$ nm and TiO₂ thickness $t = 60$ nm, (c) cyclic olefin copolymer with period $d = 325$ nm and TiO₂ thickness $t = 50$ nm, and (d) UV curable materialOrmocomp with period $d = 325$ nm and TiO₂ thickness $t = 50$ nm. Reproduced with permission from [33]. Copyright 2013, NUST.

Figure 9. Experimental setup of an ellipsometer to measure specular reflectance or transmittance.

$$\tan\psi e^{i\Delta} = \frac{R_p}{R_s} \quad (7)$$

Where R_p and R_s are the complex-amplitude reflectance coefficients for p- and s-polarization state of light, Ψ represents elliptical state of polarization and Δ is the relative phase of the vibrations along x - and y -directions which can vary from zero to 2π .

6. Results and discussion

Figure 10 shows designed and experimentally predicted spectral response (specular reflectance) of replicated grating structures in polycarbonate (PC), cyclic olefin copolymer (COC), and UV curable polymerOrmocomp [33]. The measured specular reflectance of PC, COC, and Ormocomp show reflectance peaks at 698.6 nm, 631.4 nm, and 630.4 nm with peak reflectance efficiencies 0.71, 0.94, and 0.65, respectively as shown in **Figure 10d–f**. The resonance peaks occur at different spectral positions with lower diffraction efficiencies than those calculated theoretically as shown in **Figure 10a–c**. The spectral shifts might occur due to inaccuracies in the dimensional profile of the replicated structures including rounding of grating edges rather completely rectangular as shown in ideal profile of **Figures 1** and **2**. The reduction of measured peak efficiencies are most likely caused by scattering of light from surface roughness, slight irregularities in the straightness of the grating lines, porosity and volume variations in polymers that cause refractive index changes in microscopic scale.

The observed variations may also be explained by molecular orientations of the polymer chains. The stress induction during mold filling may result in a partial orientation and configuration of polymeric chain along principal stress directions. Such molecular orientations may relax in thermal environment over a certain length of time. If however, temperature environment is kept constant, for example, for a UV curable material, the molecular orientations can be frozen up in the glassy state of the polymers. Such frozen-in-stresses in the newly molecular chain orientations may lead to generate an anisotropic behavior in the refractive index and cause peak shift.

Figure 11a and **b** shows specular reflectance of two designed replicated gratings in polycarbonate (with periodicities $d = 425$ nm and $d = 368$ nm), illuminated with TE-polarized light (electric field is parallel to grating lines) at three different angles of incidence (18° , 19° , and 20°) with Full Width Half Maximum (FWHM) of about 11 nm. **Figure 11c** and **d** shows measured spectral reflectance of designed gratings (with periodicities $d = 425$ nm and $d = 368$ nm) with FWHM of 13.5 nm and 11 nm, respectively. The experimentally predicted spectra is in close agreement to that of calculated, however, the wavelength shifts may be attributed due to slight variations of refractive indices of materials interacted with light. **Figure 11e** shows the simulated reflectance efficiency variations of two gratings with TiO_2 thicknesses of 60 nm and 75 nm. **Figure 10f** shows experimentally measured spectral efficiencies verses calculated

Figure 10. Theoretically calculated and experimentally measured specular reflectance of replicated gratings with grating height $h = 120$ nm and TiO_2 thickness $t = 50$ nm: a) polycarbonate with periodicity ($d = 368$ nm), b) cyclic olefin copolymer with periodicity ($d = 325$ nm), c) Ormocomp with periodicity ($d = 325$ nm); measured reflectance spectra of all three designed gratings: d) polycarbonate, e) cyclic olefin copolymer, and f) ormocomp. Reproduced with permission from [37]. Copyright 2013, Elsevier.

ones with two TiO_2 thicknesses. Both experimentally measured and calculated spectra are in agreement, provided few spectral shifts occur due to reasons described above.

For replication by thermal NIL, the temperature of the polymer materials are raised above glass transition temperature (T_g) of polymers. At such a condition ($T > T_g$), both Young's modulus and viscosity of polymers reduce by several orders of magnitude in comparison to their values at room temperatures. Moreover, below T_g the value of Young's modulus of glassy polymers remains constant for many polymers, approximately 3×10^9 Pa in comparison to their respective values at room temperature. In general practice, the temperature rise for thermal NIL is $60\text{--}90^\circ\text{C}$ above T_g so that polymer transform into a viscous flow to fill micro and nanocavities, however, after imprinting process polymer is cooled down below T_g to preserve imprinted pattern. In fact, T_g is onset temperature for molecular motion in polymers. There are many factors which increase energy for molecular motion, such as, intermolecular forces, interchain steric hindrance (branching or cross-linking, bulky and stiff side groups). In some processes, it is desirable to use lower temperature values, which is then compensated by corresponding increase in the process pressure and time to obtain perfect imprinting. The requirement of high temperature and pressure for NIL process may restrict the production of NIL technology. Furthermore, the mismatch of thermal expansion coefficient between the mold material and substrate may impose limitations for pattern overlay for large substrates. Alternatively, liquid precursors having low Young's modulus and viscosity can be cured by UV light at ambient temperatures. Due to low viscosity of the fluid the imprinting process is facilitated and minimize pattern density effects.

Figure 11. Theoretically calculated specular reflectance at three illuminating angles of replicated gratings: (a) with $d = 425$ nm, (b) with $d = 368$ nm. Experimentally calculated specular reflectance at three illuminating angles of replicated gratings: (c) with $d = 425$ nm, (d) with $d = 368$ nm, (e) variation in simulated spectral reflectance as a function of TiO_2 thickness t and wavelength of illuminating TE light, and (f) theoretically calculated and experimentally predicted specular reflectance as a function of wavelength. Blue curves show layer thickness $t = 60$ nm and brown curves $t = 75$ nm. Reproduced with permission from [11]. Copyright 2012, American Optical Society.

7. Conclusions

The replication of nanophotonic components with sub-wavelength features in polymeric materials is demonstrated and described as the most promising technology to produce narrow band-pass filters which are efficient, reliable, cost-effective, environmentally stable and effective at bulk scale production. Nanoimprint lithography is an economic process which initially requires the manufacturing of a master stamp (mold) which is fabricated commonly by EBL and reactive ion etching (RIE) processes. These processes enhance cost, inaccuracies and a reduction in efficiency and device performance. This work presented the manufacturing of master stamp by EBL using a negative tone binary electron beam resist HSQ without RIE process. The sub-wavelength replicated structures' profile height was adjusted by the thickness of resist layer on silicon substrate by spin coating process. A direct pattern writing on HSQ resist was performed by EBL followed by development for sufficient time. The RIE process step was replaced by HSQ pattern resist heat treatment to improve the mechanical and physical properties such as hardness and density of HSQ resist, respectively. The simple etchless process of mold formation brings fast prototyping of nano-optical devices with rapid processing time and high pattern fidelity, superior optical performance and wide applicability to mass production.

In NIL two important steps performed are mold release and pattern transfer. The imprinting process lead strong adhesive forces between the mold and the resist at large contact area. A perfect mold release keeps both resist shape integrity and a complete mold-resist separation as well as suitable plasma-etching resistance for pattern transfer into substrate. This means, nanoimprint resists which give rise both mold-release, etch-resist properties and allow fast and precise nanoimprinting are highly desirable.

The replicated grating structures in polymer materials further coat by thin dielectric films of TiO_2 as waveguide layer to support optical modes. Theoretically simulated results agree with the experimentally measured for the RWG in a number of polymers such as polycarbonate, cyclic olefin copolymer andOrmocomp.

Acknowledgements

The author is thankful to all professors, researchers, engineers, technicians, and students who contributed to the continuous development of various different processes of the nanofabrication at the Department of Physics and Mathematics, University of Eastern Finland, Joensuu, Finland. We are greatly thankful to HoD Prof. Dr. Seppo Honkanen for providing the financial fundings to publish this Chapter from Department of Physics and Mathematics, University of Eastern Finland under Project code 931351, which is highly appreciated. We greatly appreciate the editorial support from InTech in preparing this chapter. The chapter is dedicated to my Father-in Law Mr. Ehsan Elahi (late).

Author details

Muhammad Rizwan Saleem^{1,2*} and Rizwan Ali¹

*Address all correspondence to: rizwan@casen.nust.edu.pk

1 Institute of Photonics, University of Eastern Finland, Joensuu, Finland

2 US-Pakistan Center for Advance Studies in Energy (USPCAS-E), National University of Sciences and Technology (NUST), Islamabad, Pakistan

References

- [1] Macleod HA, editor. Thin-Film Optical Filters. New York: American Elsevier; 1969
- [2] Macleod HA. Challenges in the design and production of narrow-band filters for optical fiber communications. In: Fulton ML, editor. Optical and Infrared Thin Films, Proc. SPIE 4094. SPIE; 2000. pp. 46-57
- [3] Magnusson R, Wang SS. New principle for optical filters. Applied Physics Letters. 1992;**61**:1022-1024
- [4] Cox JA, Morgan RA, Wilke R, Ford CM. Guided-mode grating resonant filters for VCSEL applications. In: Cindrich I, Lee SH, editors. Diffractive and Holographic Device Technologies and Applications V, Proc. SPIE 3291. SPIE; 1998. pp. 70-76
- [5] Sharon A, Rosenblatt D, Friesem AA, Weber HG, Engel H, Steingrueber R. Light modulation with resonant grating-waveguide structures. Optics Letters. 1996;**21**:1564-1566
- [6] Norton SM. resonant grating structures: Theory, design, and applications [dissertation]. New York: University of Rochester, Rochester; 1997
- [7] Golubenko GA, Sychugov VA, Tishchenko AV. The phenomenon of full 'external' reflection of light from the surface of a corrugated dielectric waveguide and its use in narrow-band filters. Soviet Physics/Lebedev Institute Reports. 1985;**1**(11):36-40
- [8] Wang SS, Magnusson R. Design of waveguide-grating filters with symmetrical line shapes and low sidebands. Optics Letters. 1994;**19**:919-921
- [9] Tibuleac S, Magnusson R. Reflection and transmission of guided-mode resonance filters. Journal of the Optical Society of America. 1997;**14**:1617-1626
- [10] Muhammad Rizwan Saleem. Resonant waveguide gratings by replication and atomic layer deposition [dissertation]. University of Eastern Finland, Joensuu, Finland: Publication of the University of Eastern Finland; 2012
- [11] Saleem MR, Stenberg PA, Khan MB, Khan ZM, Honkanen S, Turunen J. Hydrogen silsesquioxane resist stamp for replication of nanophotonic components in polymers. Journal of Micro/Nanolithography, MEMS, and MOEMS. 2012;**11**(1):013007

- [12] Mai X, Moshrefzadeh R, Gibstingson UJ, Stegeman GI, Seaton CT. Simple versatile method for fabricating guided-wave gratings. *Applied Optics*. 1985;**24**:3155-3156
- [13] Rochon P, Natansohmer A, Callender CL, Robitaille L. Guided mode resonance filters using polymer films. *Applied Physics Letters*. 1997;**71**:1008-1010
- [14] Byron D, Gates QX, Stewart M, Ryan D, Grant Willson C, Whitesides GM. New approaches to nanofabrication: Molding, printing, and other techniques. *Chemical Reviews*. 2005;**105**(4):1171-1196. DOI: 10.1021/cr030076o
- [15] Jay Guo L. Recent progress in nanoimprint technology and its application. *Journal of Physics D*. 2004;**37**(11):R123
- [16] Golubenko GA, Svakhin AS, Sychugov AV, Tishchenko AV. Total reflection of light from a corrugated surface of a dielectric waveguide. *Soviet Journal of Quantum Electronics*. 1985;**15**:886-887
- [17] Popov E, Mashev L, Maystre D. Theoretical study of the anomalies of coated dielectric gratings. *Optica Acta*. 1986;**33**:607-619
- [18] Thurman ST, Michael Morris G. Controlling the spectral response in guided-mode resonance filter design. *Applied Optics*. 2003;**42**(16):3225-3233
- [19] S.T. Thurman and G.M. Morris. Resonant-grating filter design: The appropriate effective-index model. In: Presented at the OSA Annual Meeting, Providence, R.I; 22-26 Oct; OSA; 2000
- [20] Hessel A, Oliner AA. A new theory of Wood's anomalies on optical gratings. *Applied Optics*. 1965;**4**:1275-1297
- [21] Hegedus Z, Netterfield R. Low sideband guided-mode resonant filters. *Applied Optics*. 2000;**39**:1469-1473
- [22] Rytov SM. Electromagnetic properties of a finally stratified medium. *Soviet Physics, JETP*. 1956;**2**:466-475
- [23] Rosenblatt D, Sharon A, Friesem AA. Resonant grating waveguide structures. *Journal of Quantum Electronics*. 1997;**33**:2038-2059
- [24] Norton SM, Erdogan T, Morris GM. Coupled-mode theory of resonant-grating filters. *Journal of the Optical Society of America. A*. 1997;**14**:629-639
- [25] Huang Y, Palocz GT, Yariv A, Cheng Z, Dalton LR. Fabrication and replication of polymer integrated optical devices using electron-beam lithography and soft lithography. *The Journal of Physical Chemistry. B*. 2004;**108**:8606-8613
- [26] Eldada L, Shacklette LW. Advances in polymer integrated optics. *IEEE Journal of Quantum Electronics*. 2000;**6**(1):54-68
- [27] Chou SY, Krauss PR, Zhang W, Guo L, Zhuang L. Sub-10 nm imprinted lithography and applications. *Journal of Vacuum Science and Technology B*. 1997;**15**:2897. DOI: 10.1116/1.589752

- [28] Jay Guo L. Nanoimprint lithography: Methods and material requirements. *Advanced Materials*. 2007;**19**:495-513. DOI: 10.1002/adma.200600882
- [29] Moharam MG, Pommet DA, Gran EB. Stable implementation of the rigorous coupled-wave analysis for surface-relief gratings: Enhanced transmittance matrix approach. *Journal of the Optical Society of America. A*. 1995;**12**:1077-1086
- [30] Li L. Use of Fourier series in the analysis of discontinuous periodic structures. *Journal of the Optical Society of America. A*. 1996;**13**:1870-1876
- [31] Kim H, Park J, Lee B. *Fourier Modal Method and its Applications in Computational Nanophotonics*. Boca Raton: CRC Press; 2012
- [32] Namatsu H et al. Three dimensional siloxane resist for the formation of nanopatterns with minimum linewidth fluctuations. *Journal of Vacuum Science and Technology B*. 1998;**16**(1):69
- [33] Saleem MR. Design, fabrication and analysis of photonic device nanostructures [dissertation]. Islamabad, Pakistan: National University of Sciences and Technology (NUST); 2013
- [34] Saleem MR, Silfsten P, Honkanen S, Turunen J. Thermal properties of TiO₂ films grown by atomic layer deposition. *Thin Solid Films*. 2012;**520**:5442-5446
- [35] Saleem MR, Ali R, Honkanen S, Turunen J. Thermal properties of thin Al₂O₃ films and their barrier layer effect on thermo-optic properties of TiO₂ films grown by atomic layer deposition. *Thin Solid Films*. 2013;**542**:257-262
- [36] Azzam RMA, Bashara NM. *Ellipsometry and Polarized Light*. Amsterdam: North Holland publishing Company; 1977
- [37] Saleem MR, Honkanen S, Turunen J. Thermo-optic coefficient of Ormocomp and comparison of polymer materials in athermal replicated subwavelength resonant waveguide gratings. *Optics Communications*. 2013;**288**:56-65