We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Different Solvents for Organosolv Pulping

Alejandro Rodríguez, Eduardo Espinosa,
Juan Domínguez-Robles, Rafael Sánchez,
Isabel Bascón and Antonio Rosal

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/intechopen.79015>

Abstract

Organosolv pulping is a two-stage process involving hydrolysis (decomposition of wood by use of a catalyst) and removal of lignin with an organic solvent (usually a mixture of alcohol and water). The main disadvantage of using an alcohol is its low boiling point, which requires operating at a high pressure and hence using special equipment that is expensive to purchase and operate. One solution to this problem is using alternative organic solvents that afford operation at pressure levels similar to those of classic pulping processes (e.g., the Kraft process). This chapter provides a comprehensive literature review on the organosolv-based production of cellulose pulp by using alternative solvents such as glycols, phenols, esters, organic acids, acetone and amines.

Keywords: organosolv, glycols, phenols, ester, organic acids, acetone, amines, pulp, paper

1. Introduction

The increasing environmental awareness of developed societies has boosted the demand for more sustainable production processes for commodities such as paper and cardboard. Traditional chemical and semi-chemical pulping processes produce large amounts of waste called “black liquor” that is highly polluting (especially when sulfur compounds are used). In response to this problem, the industrial and scientific sectors are increasingly aiming at using new raw materials to replace traditional choices such as annual plants or agricultural and forestry residues, and also at developing new pulping processes based on less polluting, more easily recovered reagents such as organic solvents. Such processes are generically called

“organosolv processes” and afford the production of high-quality pulp and paper with modest industrial investments and low production costs, as well as the efficient, integral use of raw materials to obtain pulp in high yields in addition to by-products and added value.

Since alcohols are the most widely used solvents for organosolv pulping, this chapter reviews the comparatively scant research conducted so far on the use of alternative solvents such as glycols, phenols, ester, organic acids, acetone, ammonia and amines for this purpose.

2. Background

The earliest scientific reference to delignification with organic solvents dates from 1893, when Kason used ethanol and hydrochloric acid for this purpose. This was followed by the work of Aronovsky and Grotner, and Kleinert and Tayenthal, in the 1930s; Brounstein in the 1950s and Kleinert in the 1970s [1, 2]. In those days, organosolv processes had not yet challenged the prevalence of traditional chemical pulping processes. During the 1970s, however, the scientific community began to devise solutions to the many drawbacks of the classical processes including unpleasant odors, low yields, high pollution, difficult brightening of pulp, large investments, and massive consumption of energy, water, raw materials and reagents. Initially, attempts focused on modifying the pulping process; then, new processes using no sulfur as reagent were developed. However, these attempts met new problems such as the difficulty of recovering reagents and the polluting nature of the waste [3].

In the 1980s, new processes using organic solvents started to emerge. Their greatest advantage was that they afforded full use of the raw materials. Some were used to obtain hydrolysable cellulose, phenolic polymers of lignin and sugars [4–6].

Although the Kraft process still prevailed in the 1990s, the environmental problems it caused, and the high investments involved led to the conclusion that alternative pulp production processes should be developed.

The most commonly pulping process used in industry is the Kraft or sulfate process [7]. The most common raw material for this process is wood, especially softwood for unbleached pulp, and hardwoods for bleached pulp, with a much higher consumption than alternative or non-wood vegetables, whose main disadvantage is that some of them have high ash content, which causes serious problems in the recovery circuits of black liquors.

In this process, the reagent replaced is sodium sulfate, although the real agent that acts during the delignification reaction is the sulfur that is generated. The process can be divided into two parts: the first is the production of the pulp and the second is the recovery of the chemicals used [8].

In Kraft pulping, some of the black liquor can be recirculated to be used as a pulping solution. In some cases, 40–60% of pulping solution may be black liquor without affecting the pulping yield or the characteristics of the pulps obtained. By this way, part of the reagents is reused without costly evaporation stage, the reagents' penetration into the chips is encouraged, and the heat energy of the black liquor is used.

Several authors propose modifications to the Kraft process. Wang et al. [9] propose the addition of anthraquinone to green liquor, achieving yield increases of 2% and substantial savings in reagents (23–26%) and energy. The use of polysulfides in the pre-treatment improves the pulp yield by 1.5–3.5% according to the data obtained by Luthe et al. [10]. Gustafsson et al. [11] propose a pre-treatment with polysulfide in an alkaline medium (0–2.5 molar sodium hydroxide), achieving significant improvements in the viscosity of the pulps with a low Kappa number. Brannvall et al. [12] describe hyperalkaline pulping with polysulfide, in which pre-treatment consists of two stages: the first one is an acid neutralization and the second one is a high concentration of alkali and polysulfide.

Research then focused on processes using organic solvents in order to extract not only cellulose fiber, but also other useful products from the raw materials. That is how the concept called “wood refinery” by analogy with the fractionation of crude oil was born [13].

In this way, much research into the delignification of traditional and alternative raw materials with organic solvents to obtain not only pulp, but also lignin, sugars and various other products was conducted [4, 5, 14–24].

The main advantages of organosolv process regarding Kraft process are as follows:

1. More economical than the kraft process for SME.
2. It achieves a good degree of brightness for the pulps, competitive with those obtained for conventional chemical pulps.
3. Less polluting than conventional processes, without bad smells and with less effluents and pollutants.
4. By-products are obtained in greater quantity and quality than in conventional processes.
5. Better use of the raw material due to its higher yields.
6. It requires less water than the Kraft process.

However, this process also has its drawbacks:

1. It cannot be applied to softwoods.
2. Higher production cost, due to the high cost of some solvents as ethanol.
3. Higher cost of recovery of by-products.
4. Requires more external energy than the Kraft process.

3. Organosolv solvents and catalysts

Organosolv processes use a broad range of organic solvents including methanol, ethanol, propanol, butanol, isobutyl alcohol, benzyl alcohol, glycerol, glycol, ethylene glycol, triethylene glycol, phenol, acetone, formic acid, acetic acid, propionic acid, diethyl ether, amines, ethers, esters,

formaldehyde and chloroethanol, among others, either in pure form or in aqueous solutions to which a catalyst (an acid, base or salt) may be added. Solvents with a low boiling point (e.g., methanol, ethanol, acetone and ethyl acetate) can easily be recovered by distillation; on the other hand, those with a high boiling point (e.g., triethylene glycol and ethylene glycol) afford operation at low pressures but are difficult to recover [1, 2, 4, 5, 14–17, 25–64]. In any case, all allow softwood and hardwood to be efficiently delignified without damaging cellulose in the raw material [65].

Alcohols are the most widely used solvents in organosolv processes, and ethanol is one of the most effective for this purpose as it combines a high speed of delignification under favorable operating conditions with easy recovery [5, 66]. Primary alcohols provide more selective delignification than do secondary and tertiary alcohols. Also, methanol causes less marked losses of hemicelluloses than does butanol. Only poplar and aspen wood can be efficiently delignified in the absence of a catalyst [65]. However, the catalysts used for this purpose include mineral acids (sulfuric, hydrochloric and hydrobromic), organic acids (formic, acetic, propionic, oxalic, malic, salicylic, succinic, nicotinic, benzoic, citric and phthalic), salts (chlorides, chlorosulfonates, boric fluoride, chlorides, sulfates and nitrates of calcium and magnesium, sulfites and sulfides) and other compounds such as alkalis, ammonia or anthraquinone [14, 40, 42, 43, 55, 61, 65, 67, 68].

Organic acids are more efficient than mineral acids in delignifying softwood [87–89, 123, 124]. However, sulfuric acid at a concentration below 0.01 M, but particularly 0.01 or 0.02 M, allows the processing temperature of alcohol-based pulping of cottonwood to be lowered from 200 to 170°C [4, 69–73]. Lower sulfuric concentrations cause the acid to be neutralized by ash and other alkaline components, whereas higher concentrations can result in condensation with free lignin, hydrolysis of hemicelluloses, degradation of cellulose and formation of insoluble condensation products in the pulping liquor. Lignin condensing in fibers can only be removed after a large enough amount of hemicelluloses has been dissolved; therefore, the presence of pores facilitates the process but also degrades cellulose and detracts from pulp viscosity as a result. Condensed lignin is insoluble in alcohol-water mixtures and requires another solvent such as acetone, tetrahydrofuran, dimethyl sulfoxide or a 3–5% o.d.m. soda solution [5, 40, 65].

Sulfur dioxide dissolved in the pulping liquor acts as a weak acid; by reaction with lignin, however, it forms sulfonic acids that can be as strong as mineral acids [2, 40].

Adding an alkaline earth salt as a catalyst to the alcohol-water mixture is the only way of completely releasing fibers from some vegetable species and obtaining yields as high as 60% of high-viscosity pulp [65].

Base-catalyzed organosolv processes are highly effective with conifer wood and outperform some sulfite and Kraft processes in pulp yield and properties [40, 65].

4. Delignification mechanisms

Delignification with organic solvents is believed to be resulted from hydrolysis of α -aryl-ether and lignin-hemicellulose links with a pseudo-first order kinetics [65] and from dissolution of lignin by cleavage of α -aryl and aryl-glycerol- β -aryl-ether links [40, 74–77].

The rate of delignification in acid-catalyzed organosolv pulping processes is governed by the hydrolysis of α -ether links in lignin [98–102]. The process also involves other complex reactions such as condensation, partial hydrolysis of β -aryl links, release of formaldehyde and recombination of free radicals [40, 78–81].

In acid media, the delignification of lignin is preceded by cleavage of α -aryl-ether and β -aryl-ether bonds by H^+ ions. The concentration of hydrogen ions increases with increasing ethanol concentration and liquid/solid ratio but decreases with increasing processing time [82]. Although the cleavage of α -aryl-ether linkages is a primary factor, the cleavage of β -aryl-ether links is also influential (especially with hardwood). The hydrolysis of β -aryl-ether units in addition to α -aryl-ether links was found to have a direct impact on the initial rate of delignification of aspen wood with methanol; also, the extent of delignification was additionally affected by condensation reactions with lignin [83].

The reactions involved in the soda-methanol process are possibly similar to those of the soda process except that lignin is dissolved by the alcohol and formation of condensation products which is more limited [40]. In alkaline processes, the cleavage of β -aryl-ether bonds is more important than that of α -aryl-ether bonds [84].

Phenol as solvent reacts with lignin and facilitates its dissolution; subsequently, it causes some degradation of carbohydrates and lignin through mild acid hydrolysis [85]. With butanediol, lignin-carbohydrate complexes react with benzyl ethers, especially in the presence of acetic acid [86]. The kinetics of delignification of bagasse is first order with butanol but second order with soda [87].

Removal of lignin in the pulping of eucalyptus with acetic and hydrochloric acids results from the hydrolysis of α -aryl-ether links, which occurs in two parallel first-order reactions involving the hydrolysis of hemicellulose (the faster) and cellulose (the slower) [85]. The latter reaction does not occur at low temperatures and concentrations of hydrochloric acid [88–90]. The acetosolv pulping of pinewood also involves two parallel first-order hydrolysis reactions the first of which is faster than the second [91–93].

The pulping of spruce exhibits two distinct stages of delignification, both with first-order kinetics. In the first (the faster), 70% of the lignin is rapidly removed, the remainder being eliminated more slowly. Complete release of fibers is achieved when the yield drops to 57% and the kappa number is 72 (10% lignin). Delignification at these stages occurs largely in outer cell walls and the middle lamella, and is still relatively scarce in secondary walls. Although all lignin in the middle lamella is removed with a yield of 60%, some residual lignin remains in outer and secondary walls. As confirmed by various techniques, the ease of delignification of the middle lamella decreases in the following sequence: catalyzed organic solvents > acid chlorite > neutral sulfite > acid sulfite > Kraft. On the other hand, the sequence for the secondary wall is Kraft > acid sulfite > catalyzed organic solvents > neutral sulfite > acid chlorite. Delignification of the secondary wall is governed by diffusion (specifically, by physical and chemical differences between lignin in various morphological regions of plant tissues) [94].

Overall, hardwood is easier to delignify than softwood by virtue of its lower content in lignin, higher concentration of α -aryl-ether links—which make it easier to hydrolyze, lower tendency to lignin condensation and higher reactivity of β -aryl-ether links [82].

Brogdon and Dimmel have conducted interesting research into various types of reactions involved in quinone-based pulping processes [95–99].

5. Pulping with different organic solvents

5.1. Glycols

The earliest use of ethylene glycol to obtain cellulose pulp was reported in 1941 by Nakanun and Takanti, who applied it to spruce [15]. In the late 1970s, Unger [4] confirmed that propylene glycol, butylene glycol and other higher glycols were useful for pulping, especially if the raw materials were previously impregnated with sulfuric acid. In the 1980s, Gast et al. [100–102] found the efficiency of ethylene glycol to be improved by using aluminum sulfate or chloride as a catalyst; also they studied the kinetics of pulping of birch with the glycol. In the 1990s, Thring et al. conducted research into the by-products of lignin recovery in the pulping with ethylene glycol, and also the fractionation of poplar in a two-step process yielding cellulose in one and hemicellulose and lignin in the other [4].

Several authors have explored the pulping of aspen, birch, beech and pine wood, vine shoots, olive tree prunings, forest residues and bagasse with ethylene glycol [45, 46, 49, 64, 103–108]; rice straw with diethylene glycol-ethylene glycol and diethylene glycol-ethylene glycol-soda mixtures [109]; and cellulose linters, wood sawdust, *Miscanthus sinensis* and *Eucalyptus globulus* with glycols [110]. Using glycol-acetic-water systems with aspen and pinewood proved an effective modification of the glycol delignification method with substantial savings in energy (temperature and time) [106, 111]. A study investigated the origin of the losses of ethylene glycol during pulping [112].

Glycerols have also been used in pulp production [49, 113–115]. Thus, treating *Ailanthus altissima* and *Spruce orientalis* wood with glycerol provided optimal delignification results in the presence of an alkali, which, however, led to increased cellulose losses.

Butanediol and propylene glycol have also been used for pulping [56, 64, 115], and so have mixtures of ethanol and ethylene glycol [46, 116].

5.2. Phenols

The Battelle-Genoa process uses phenol as solvent. This is the best-known pulping process using a high-boiling point solvent in combination with HCl as a catalyst. The process is especially efficient with hardwood, spruce and herbaceous plants. With softwood, however, it usually takes a long time and yields pulp with inferior properties relative to the Kraft process. The advantages of the Battelle-Genoa process include a low cost of the industrial plant and the production of small volumes of black liquor; on the other hand, its disadvantages include problems arising from washing of the pulp, recovery of the reagents and detoxification of the effluents, which usually contain small amounts of phenols and cresols [2, 39].

The phenol-ethanol process is also well known [14] and has been successfully used to delignify wood [85, 117, 118], wheat straw [119] and *Ulex europaeus* [120]. Phenols have also been used for pulp production by Schweers et al. [53, 54].

Finally, cresols have been used as reagents for spruce pulping [121]; the raw material, at 70% consistency, was delignified at 180°C for 2 h in the presence of acetic acid.

5.3. Esters

The ester pulping process, patented by Young and Baierl, uses a mixture of water, acetic acid (catalyst) and ethyl acetate (solvent) to dissolve fragmented (hydrolyzed) lignin. This process is suitable for poplar, but not for other types of hardwood (e.g., red oak, eucalyptus) and softwood species (e.g., pine, white spruce); nor is suitable when the aim is to obtain pulp for subsequent bleaching. The properties of poplar pulp obtained with this process are in between those of sulfite pulp and Kraft pulp [39]. According to some authors, however, this process efficiently delignifies both hardwood and softwood and provides pulp with good mechanical properties [14].

5.4. Organic acids

The acetocell process uses acetic acid and, usually, hydrochloric or sulfuric acid as a catalyst. The process has been used with various raw materials including bagasse [120], birch and hardwood [121, 122], *Pinus pinaster* [123, 124], *Eucalyptus globulus* [61, 125–128] and *Eucalyptus grandis* [42]. Also, it has been applied to softwood and annuals, using a high temperature but no catalyst. With Norwegian spruce, the acetocell process provides pulp with high yield and a Kappa number of 16–20 that is easily bleached with ozone and hydrogen peroxide, and largely retains its mechanical properties [129].

A study examined the kinetics of delignification of wood and correlated kinetic parameters with the catalyst concentration [126, 130]. With acetic-hydrochloric acid mixtures, the selectivity of the process was independent of the concentration of HCl and temperature, and yields were as high as 50% [131]. Another study explored the delignification of red spruce with acetic acid-water, acetic acid-carbon dioxide and acetic acid-water-carbon dioxide mixtures under supercritical conditions; also, it examined the effects of the concentration of acetic acid, pressure, temperature and time on the extent of delignification. The best results were obtained with acetic acid-water mixtures [132]. Acetic acid has also been used in the pulping of birch with provision for the influence of pre-hydrolysis, hydrogen peroxide and some other variables [133], and also in the pulping of rice straw at atmospheric pressure [134]. More recently, a study examined the pulping of beech with acetic acid in the presence of hydrochloric acid as a catalyst [135].

The use of formic acid for delignification dates from 1917, when it was applied to wood and cereal straw. This process has some advantages over others using other organic solvents such as a low cost, and the ability to use low temperatures and pressures [136, 137]. In one study, it was applied to different types of hardwood such as that from *E. globulus* and *E. grandis* [138]. The best operating conditions for the latter species were 92% formic acid, 0.22% hydrochloric acid and 90°C for 90 min, the results being even better with refluxing. The presence of water was found to benefit fibers and yields as a result of its helping remove not only lignin, but also much hemicellulose and little α -cellulose [137].

The Milox process is a variant using peroxyformic acid spontaneously formed upon mixing of formic acid (80%) and hydrogen peroxide [2, 139–141]. This process is highly suitable for

delignifying birch in three stages [142], namely: treatment with the acid at 80°C, application of formic acid at 100°C and bleaching with hydrogen peroxide to obtain pulp with 90% ISO brightness. The mechanical properties of the resulting pulp are on a par with those of Kraft pulp. The results with conifer wood are worse, however, as a consequence of solvent recovery by distillation leading to the formation of an azeotrope of inadequate concentration between formic acid and water (78%) [2]. The Milox process has also been used with spruce [139] and alternative raw materials [140, 141]. Several studies conducted in recent years were used to delignify different materials [57, 59, 143, 144] in addition to spruce [67, 145], eucalyptus [146–148], pine [149], bagasse [147], rice straw [150, 151], rods [152] and banana stems [153].

The formacell process, which uses acetic acid-water-formic acid mixtures, has enabled the production of pulp with small kappa numbers from beech, pine and aspen. With aspen and birch wood, a low temperature and a high concentration of acetic acid are recommended to prevent hemicellulose losses [154, 155]. With wheat straw, the process provides pulp with a small kappa number and a high viscosity [156].

Using acetic acid containing small amounts of sulfuric acid and phenols provided good results with birch [157], and so did the acetic acid-carbon dioxide-water system under supercritical conditions [158].

5.5. Acetone

Jiménez et al. used acetone alone [159–161] and in mixtures with ethanol [162, 163] for delignification. Other authors have used mixtures of formic acid and acetone [149, 164, 165] or acetone alone on previously steamed raw materials [166].

One process using oxygen in aqueous acetone was applied to cotton stalks, eucalyptus and poplar wood. The influence of temperature, time and oxygen partial pressure on the delignification rate was examined, and the transfer of oxygen found to be the parent stage of the delignification process [167, 168]. The process was also applied to spruce and other types of wood [111].

5.6. Ammonia and amines

The processes using ammonia or amino bases provide pulp with a high yield by effect of their preserving hemicelluloses. Thus, 1, 6-hexamethylenediamine (HMDA) gives pulp with a high yield from both hardwood and softwood, but the pulp is difficult to bleach. Ammonia in combination with acetone or methylethyl ketone provides spruce pulp with higher yields and better properties—tear index excepted—than the Kraft process. Using ammonium sulfide with ethanol allows one to operate at lower temperatures than with ammonia to obtain pulp with similarly good properties from hardwood, cereal straw and bagasse, and strong pulp with a high yield and low lignin content relative to softwood. However, the processes using ammonia and amino bases are subject to problems arising from the recovery of reagents, the high boiling point of HMDA, condensation of lignin and formation of polluting sulfur volatiles [2].

Pulping poplar chips with supercritical ammonia-water mixtures revealed that the extents of removal of cellulose, hemicellulose and lignin were a function of time, pressure and, especially, temperature and solvent concentration [169].

The earliest work on pulping with ethanolamines dates from the late 1970s, when Wallis [48] applied them to pine and eucalyptus wood, and monoethanolamine proved more effective than diethanolamine and triethanolamine; yields were 11–16% higher than with the Kraft process and the resulting pulp had similar strength-related properties. Wallis [170] also pulped *Pinus elliottii* with ethanolamine and obtained pulp similarly strong to Kraft pulp but in higher yields (5–10% higher).

Ethanolamines have also been used to pulp spruce [47] and rice straw [63]. Adding ethanolamine to the alkaline cooking liquor was found to increase the rate of lignin degradation [171]. Finally, some authors have also used amines to pulp various raw materials such as beech, spruce, olive tree prunings, jute and cotton [172–179].

5.7. Other solvents

Processing bagasse as raw material with formamide and dimethylformamide provided pulps with a high content in α -cellulose in addition to good physical and mechanical properties [180, 181]. Some authors have pulped eucalyptus with dioxane in the presence of hydrochloric acid (catalyst) [182] or its absence [55, 183–185], and hardwood with the sulfur dioxide-ethanol-water system [186].

Author details

Alejandro Rodríguez^{1*}, Eduardo Espinosa¹, Juan Domínguez-Robles¹, Rafael Sánchez¹, Isabel Bascón^{1,2} and Antonio Rosal³

*Address all correspondence to: a.rodriguez@uco.es

1 Chemical Engineering Department, Universidad de Córdoba, España

2 Department of Bromatology and Food Technology, Universidad de Córdoba, España

3 Molecular Biology and Biochemical Engineering Department, Universidad Pablo de Olavide, España

References

- [1] Johansson A, Aaltonen O, Ylinen P. Organosolv pulping: Methods and pulp properties. *Biomass*. 1987;**13**(1):45-65
- [2] Asiz S, Sarkanen K. Organosolv pulping. A review. *Tappi Journal*. 1989;**72**(3):169-175
- [3] Cox LA, Worster HL. An assessment of some sulphur-free chemical pulping process. *Tappi Journal*. 1971;**54**(11):1890-1892
- [4] Muurinen E. Organosolv pulping. A review and distillation study related to peroxy-acid pulping. [Tesis Doctoral]. Finlandia: Departamento de Ingeniería de Procesos, Universidad de Oulu; 2000

- [5] Oliet M. Estudio sobre la deslignificación de *Eucalyptus globulus* con etanol/agua como medio de cocción. [Tesis Doctoral]. Madrid, Spain: Departamento de Ingeniería Química, Universidad Complutense de Madrid; 1999
- [6] Varshney AK, Patel DP. Biomass delignification-organosolv approach. *Journal of Scientific and Industrial Research*. 1989;**47**(6):315-319
- [7] FAO 2012. Pulp and Paper Capacities 2011-2016. Available from: <http://www.fao.org/docrep/016/i3005t/i3005t.pdf>
- [8] Libby CE. Ciencia, tecnología sobre pulpa y papel. México: CECSA; 1997
- [9] Wang SF, Ban WP, Lucia LA. The effect of green liquor/anthraquinone-modified Kraft pulping on the physical and chemical properties of hardwoods. *Appita Journal*. 2004;**57**:475-480
- [10] Luthe C, Berry R, Li J. Polysulphide for Yield Enhancement in Sawdust Pulping: Does it Work?. Laboratory Simulations Suggest that PS Improves Yield. Vol. 105. Canada: Pulp and Paper; 2004. pp. 32-37
- [11] Gustafsson R, Freysoldt J, Teder A. Influence of the alkalinity in polysulphide pretreatment on results of cooking with normal liquor-to-wood ratios. *Paperi Ja Puu-Paper and Timber*. 2004;**86**:169-173
- [12] Brannvall E, Gustafsson R, Teder A. Properties of hyperalkaline polysulphide pulps. *Nordic Pulp & Paper Research Journal*. 2003;**18**:436-440
- [13] Judt M. Recent developments in pulp production and their suitability for use in industrial process in developing countries. *Cellulose Sources Exploitation*. 1990;**8**:81-88
- [14] Jiménez L, Maestre F, Pérez I. Disolventes orgánicos para la obtención de pastas con celulosa. Review. *Afinidad*. 1997;**44**(467):45-50
- [15] Hergert HL. Developments in organosolv pulping. An overview. In: Young RA, Akhtar M, editors. *Environmental Friendly Technologies for the Pulp and Paper Industry*. New York: John Wiley and Soong Inc; 1998
- [16] Rodríguez F, Gilarranz MA, Oliet M, Tijero J, Barbadillo P. Manufacture of cellulose pulps by organosolv processes. *Investigación y Técnica del Papel*. 1996;**33**(130):839-857
- [17] Neves FL, Neves JM. Organosolv pulping: A review. *Papel*. 1998;**559**(8):48-52
- [18] Rodríguez F, Gilarranz MA, Oliet M, Tijero J. Pulping of lignocellulosics by organosolv processes. *Recent Research Developments in Chemical Engineering*. 1998;**2**:9-47
- [19] Abad S, Alonso JL, Santos V, Parajó JC. Furfural from wood in catalyzed acetic-acid media. A mathematical assessment. *Bioresource Technology*. 1997;**62**(3):115-122
- [20] Montane D, Farriol X, Salvado J, Jollez P, Chornet E. Fractionation of wheat straw by steam-explosion pretreatment and alkali delignification. Cellulose pulp and byproducts from hemicellulose and lignin. *Journal of Wood Chemistry and Technology*. 1998;**18**(2):171-191

- [21] Botello JL, Gilarranz MA, Rodríguez F, Oliet M. Preliminary study on products distribution in alcohol pulping of eucalyptus globules. *Journal of Chemical Technology and Biotechnology*. 1999;**74**(2):141-148
- [22] Botello JL, Gilarranz MA, Rodríguez F, Oliet M. Recovery of solvent and by-products from organosolv black liquor. *Separation Science and Technology*. 1999;**34**(12):2431-2445
- [23] Lehnen R, Saake B, Nimz NH. Furfural and hydroxymethylfurfural as by-products of formacell pulping. *Holzforschung*. 2001;**55**(2):199-204
- [24] Guha SRD, Sirmokadan NN, Goudar TR, Rohini D. Pulping rice straw by pollution free organosolv process. *Indian Pulp and Paper Technical Association*. 1987;**24**(1):24-26
- [25] Moral A, Aguado R, Mutjé P, Tijero A. Papermaking potential of *Citrus sinensis* trimmings using organosolv pulping, chlorine-free bleaching and refining. *Journal of Cleaner Production*. 2016;**112**(Part 1):980-986
- [26] Shatalov AA, Pereira H. Polysaccharide degradation during ozone-based TCF bleaching of non-wood organosolv pulps. *Carbohydrate Polymers*. 2007;**67**(3):275-281
- [27] Kupiainen L, Ahola J, Tanskanen J. Hydrolysis of organosolv wheat pulp in formic acid at high temperature for glucose production. *Bioresource Technology*. 2012;**116**:29-35
- [28] Mutjé P, Pelach MA, García JC, Presta S, Vilaseca F, Jiménez L. Comparison of cationic demand between olive wood organosolv pulp and eucalyptus Kraft pulp. *Process Biochemistry*. 2006;**41**:1602-1607
- [29] González M, Cantón L, Rodríguez A, Labidi J. Effect of organosolv and soda pulping processes on the metals content of non-woody pulps. *Bioresource Technology*. 2008;**99**(14):6621-6625
- [30] Jiménez L, Rodríguez A, Serrano L, Moral A. Organosolv ethanolamine pulping of olive wood: Influence of the process variables on the strength properties. *Biochemical Engineering Journal*. 2008;**39**(2):230-235
- [31] Rodríguez A, Serrano L, Moral A, Jiménez L. Pulping of rice straw with high-boiling point organosolv solvents. *Biochemical Engineering Journal*. 2008;**42**(3):243-247
- [32] Snelders J, Dornez E, Benjelloun-Mlayah B, Huijgen WJJ, Courtin CM. Biorefining of wheat straw using an acetic and formic acid based organosolv fractionation process. *Bioresource Technology*. 2014;**156**:275-282
- [33] Mesa L, Albernas Y, Morales M, Corsano G, González E. Chapter 11: Integration of Organosolv process for biomass pretreatment in a biorefinery. In: Mussatto SI, editor. *Biomass Fractionation Technologies for a Lignocellulosic Feedstock Based Biorefinery*. Amsterdam: Elsevier; 2016. pp. 229-254
- [34] Ferrer A, Vega A, Rodríguez A, Jiménez L. Acetosolv pulping for the fractionation of empty fruit bunches from palm oil industry. *Bioresource Technology*. 2013;**132**:115-120
- [35] Ferrer A, Vega A, Rodríguez A, Ligeró P, Jiménez L. Milox fractionation of empty fruit bunches from *Elaeis guineensis*. *Bioresource Technology*. 2011;**102**(20):9755-9762

- [36] Jiménez L, de la Torre MJ, Maestre F, Ferrer JL, Pérez I. Delignification of wheat straw by use of low-molecular-weight organic acids. *Holzforschung*. 1998;**52**:191-196
- [37] Jiménez L, Pérez I, de la Torre MJ, López F. Use of formaldehyde for making wheat straw cellulose pulp. *Bioresource Technology*. 2000;**72**:283-288
- [38] Nada AMA, Ibrahim AA, Fahmy ME, Abou-Yousef H. Bagasse pulping with butanol-water system. *Research and Industry*. 1995;**40**(9):224-230
- [39] Asiz S, McDonough TJ. Ester pulping. A brief evaluation. *Tappi Journal*. 1987;**70**(3):137-138
- [40] Sarkanen KV. Chemistry of solvent pulping. *Tappi Journal*. 1990;**73**(10):215-219
- [41] Heitz M, Brown A, Chornet E. Solvent effects on liquefaction-solubilization profiles of a Canadian prototype wood. *Populus deltoides* in the presence of different solvents. *The Canadian Journal of Chemical Engineering*. 1994;**72**(6):1021-1027
- [42] Benar P, Schuchardt U. Eucalyptus acetosolv pulping. Optimization of the cooking conditions and characterization of the pulp and lignin. *Cellulose Chemistry and Technology*. 1994;**28**(4):435-444
- [43] Cochaux A, Crolet J, Daveni A, Robert A. Use of amines in alkaline pulping. Preparation of cellulose pulps with high tearing strength. *Cellulose Chemistry and Technology*. 1995;**29**(3):339-360
- [44] Norman E, Linggren T, Adlund U, Teder A. Reinforcement of alkaline pulping processes with organic-solvents. 2. Screening of suitable solvents. *Holzforschung*. 1997;**51**(2):142-146
- [45] Koell P, Lenhardt H. Organosolv pulping of birch wood in a flow apparatus. *Holzforschung*. 1987;**41**(2):89-96
- [46] Davis JL, Young RA. Microwave-assisted solvent pulping. *Holzforschung*. 1991;**45**:71-77
- [47] Kubes GJ, Bolker HI. Sulfur-free delignification. I. Alkaline pulping with monoethanolamine and ethylene diamine. *Cellulose Chemistry and Technology*. 1978;**12**(5):621-645
- [48] Wallis AFA. Wood pulping with mono-, di- and triethanolamine. *Appita Journal*. 1978;**31**(6):443-448
- [49] Demirbas A. Aqueous glycerol delignification of wood chips and ground wood. *Bioresource Technology*. 1998;**63**(2):179-185
- [50] Peter S. Degradation of lignin with monomethylamine. *Chemical Engineering and Technology*. 1992;**15**(3):213-217
- [51] Nimz H, Roth M, Tschimer U, Casten R. Organosolv pulping with chloroethanol. *Holzforschung*. 1986;**40**:125-132
- [52] Ghose TK, Selvam PVP, Ghosh P. Catalytic solvent delignification of agricultural residues. Organic catalysts. *Biotechnology and Bioengineering*. 1983;**25**(11):2577-2590
- [53] Schweers WHM. Phenol pulping. *Chemical Technology*. 1974;**4**(8):490-493

- [54] Schweers W, Behler H, Beinhoff O. Pulping of wood with phenols. II. Phenol balance. *Holzforschung*. 1972;**26**(3):103-105
- [55] Mostafa NYS. Base-catalyzed dioxane and dioxane-borax pulping and fine structure, chemical reactivity and viscose filterability of cotton cellulose. *Cellulose Chemistry and Technology*. 1994;**28**(2):171-175
- [56] Cheng X, Chen W, Chen Y, Li H, Fang H. Preparation and properties of HBS lignin from Masson pine. *Chemical Research in Chinese Universities*. 2004;**20**(2):225-228
- [57] Nada AMA, Abou-Yousef H, Kamel S. Peroxyformic acid pulping of palm leaves. *Journal of Scientific and Industrial Research*. 2004;**63**(2):149-155
- [58] Sun XF, Sun RC, Fowler P, Baird MS. Isolation and characterization of cellulose obtained by a two-stage treatment with organosolv and cyanamide activated hydrogen peroxide from wheat straw. *Carbohydrate Polymers*. 2004;**55**(4):379-391
- [59] Dapia S, Santos V, Parajó JC. Formic acid-peroxyformic acid pulping of *Fagus sylvaticas* wood. *Journal of Wood Chemistry and Technology*. 2000;**20**(4):395-413
- [60] Abad S, Santos V, Parajó JC. Formic acid-peroxyformic acid pulping of aspen wood: An optimization study. *Holzforschung*. 2000;**54**(5):544-552
- [61] Abad S, Santos V, Parajó JC. Multistage organosolv pulping: A method for obtaining pulps with low hemicellulose contents. *Collection of Czechoslovak Chemical Communications*. 2003;**68**(6):1163-1174
- [62] Adeeb Z. Glycerol delignification of poplar wood chips in aqueous medium. *Energy Education Science and Technology*. 2004;**13**(1/2):81-88
- [63] Jiménez L, Domínguez JC, Pérez I. Influence of cooking variables in the organosolv pulping of wheat straw using mixtures of ethanol-acetone and water. *Tappi Journal*. 2003;**2**(1):27-31
- [64] Zhang K, Pei Z, Wang D. Organic solvent pretreatment of lignocellulosic biomass for biofuels and biochemicals: A review. *Bioresource Technology*. 2016;**199**:21-33
- [65] Rodríguez A, Serrano L, Moral A, Pérez A, Jiménez L. Use of high-boiling point organic solvents for pulping oil palm empty fruit bunches. *Bioresource Technology*. 2008;**99**(6):1743-1749
- [66] Salehi K, Kordsachia O, Patt R. Comparison of MEA/AQ, soda and soda/AQ pulping of wheat and rye straw. *Industrial Crops and Products*. 2014;**52**:603-610
- [67] Hundt M, Schnitzlein K, Schnitzlein MG. Alkaline polyol pulping and enzymatic hydrolysis of hardwood: Effect of pulping severity and pulp composition on cellulase activity and overall sugar yield. *Bioresource Technology*. 2013;**136**:672-679
- [68] Hundt M, Schnitzlein K, Schnitzlein MG. Alkaline polyol pulping and enzymatic hydrolysis of softwood: Effect of pulping severity and pulp properties on cellulase activity and overall sugar yield. *Bioresource Technology*. 2013;**134**:307-315

- [69] Wang K, Yang H, Guo S, Tang Y, Jiang J, Feng X, Sun R-C. Organosolv fractionation process with various catalysts for improving bioconversion of triploid poplar. *Process Biochemistry*. 2012;**47**(10):1503-1509
- [70] Goyal GC, Lora JH, Pye EK. Autocatalyzed organosolv pulping of hardwoods. Effect of pulping conditions on pulp properties and characteristics of soluble and residual lignin. *Tappi Journal*. 1992;**75**(2):110-116
- [71] Lai YZ, Mun SP. The chemical aspects of acidic delignification processes. *Holzforschung*. 1994;**48**(3):203-206
- [72] Sano Y, Nakamura Y, Shimamoto S. Pulping of wood at atmospheric pressure. 2. Pulping of birch wood with aqueous acetic-acid containing a small amount of sulphuric-acid. *Mokuzai Gakkaishi*. 1990;**36**(3):207-211
- [73] Sano Y, Maeda H, Sakashita Y. Pulping of wood at atmospheric pressure. 1. Pulping of hardwood with aqueous acetic-acid containing a small amount of organic sulfonic acid. *Mokuzai Gakkaishi*. 1989;**35**(11):991-995
- [74] McDonough TJ. The chemistry of organosolv delignification. *Tappi Journal*. 1993;**76**(8):186-193
- [75] Kachi S, Iwata H, Araki H, Aoyogi T. Research and development of solvolysis pulping. VI. Delignification of wood chips with phenolic cooking solvent. *Mokuzai Gakkaishi*. 1990;**36**(2):108-115
- [76] Kishimoto T, Sano Y. Delignification mechanism during HBS pulping. V. Reaction of nonphenolic β -O-4 model compounds in the presence and absence of glucose. *Journal of Wood Chemistry and Technology*. 2003;**23**(3/4):279-292
- [77] Hasem KHME, Abo-Yousef HE. Kinetic approach to interpret the delignification of Egyptian bagasse organosolv pulping process. *Journal of Scientific and Industrial Research*. 1997;**56**(3):168-172
- [78] Brogdon BN, Dimmel DR. Fundamental-study of relative delignification efficiencies. 1. Conventional pulping systems. *Journal of Wood Chemistry and Technology*. 1996;**16**(3):261-283
- [79] Brogdon BN, Dimmel DR. Fundamental-study of relative delignification efficiencies. 2. Combinations of pulping additives. *Journal of Wood Chemistry and Technology*. 1996;**16**(3):285-293
- [80] Brogdon BN, Dimmel DR. Fundamental-study of relative delignification efficiencies. 3. Organosolv pulping systems. *Journal of Wood Chemistry and Technology*. 1996;**16**(3):297-310
- [81] Brogdon BN, Dimmel DR. Competing reactions affecting delignification in pulping systems. *Journal of Wood Chemistry and Technology*. 1996;**16**(4):405-419
- [82] Salapa I, Katsimpouras C, Topakas E, Sidiras D. Organosolv pretreatment of wheat straw for efficient ethanol production using various solvents. *Biomass and Bioenergy*. 2017;**100**:10-16

- [83] Aguado R, Moral A, López P, Mutjé P, Tijero A. Morphological analysis of pulps from orange tree trimmings and its relation to mechanical properties. *Measurement*. 2016;**93**:319-326
- [84] Tang C, Shan J, Chen Y, Zhong L, Shen T, Zhu C, Ying H. Organic amine catalytic organosolv pretreatment of corn Stover for enzymatic saccharification and high-quality lignin. *Bioresource Technology*. 2017;**232**:222-228
- [85] Rezayati-Charani P, Mohammadi-Rovshandeh J, Hashemi SJ, Kazemi-Najafi S. Influence of dimethyl formamide pulping of bagasse on pulp properties. *Bioresource Technology*. 2006;**97**(18):2435-2442
- [86] Constant S, Barakat A, Robitzer M, Di Renzo F, Dumas C, Quignard F. Composition, texture and methane potential of cellulosic residues from Lewis acids organosolv pulping of wheat straw. *Bioresource Technology*. 2016;**216**:737-743
- [87] Fernández-Rodríguez J, Gordobil O, Robles E, González-Alriols M, Labidi J. Lignin valorization from side-streams produced during agricultural waste pulping and total chlorine free bleaching. *Journal of Cleaner Production*. 2017;**142**(Part 4):2609-2617
- [88] Sahin HT, Young RA. Auto-catalyzed acetic acid pulping of jute. *Industrial Crops and Products*. 2008;**28**(1):24-28
- [89] Xu Y, Li K, Zhang M. Lignin precipitation on the pulp fibers in the ethanol-based organosolv pulping. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2007;**301**(1-3):255-263
- [90] Vazquez G, Antorrena G, González J. Kinetics of polysaccharide hydrolysis in the acid-catalyzed delignification of Eucalyptus globulus wood by acetic acid. *Wood Science and Technology*. 1995;**30**(1):31-38
- [91] Jiménez L, Angulo V, Rodríguez A, Sánchez R, Ferrer A. Pulp and paper from vine shoots: Neural fuzzy modeling of ethylene glycol pulping. *Bioresource Technology*. 2009;**100**(2):756-762
- [92] Ziaie-Shirkolaee Y, Mohammadi-Rovshandeh J, Rezayati-Charani P, Khajeheian MB. Influence of dimethyl formamide pulping of wheat straw on cellulose degradation and comparison with Kraft process. *Bioresource Technology*. 2008;**99**(9):3568-3578
- [93] Vazquez G, Antorrena G, González J, Freire S. Kinetic studies on acetosolv pulping of lignocellulosics. In: 8th Proceedings of the European Biomass Conference; Vol. 2. 1995. pp. 1393-1400
- [94] Uraki Y, Sano Y. Polyhydric alcohol pulping at atmospheric-pressure. An effective method for organosolv pulping of softwoods. *Holzforschung*. 1999;**53**(4):411-415
- [95] Paszner L, Cho HJ. Organosolv pulping: Acid catalysis options and their effect on fiber quality and delignification. *Tappi Journal*. 1989;**72**(2):135-142

- [96] Pereira H, Oliveira MF, Miranda I. Kinetics of ethanol-water pulping and pulp properties of *Eucalyptus globulus*. *Appita Journal*. 1986;**39**(6):455-458
- [97] Usmani TH, Thair M, Ahmed MA, Alvi SK. Catalyzed organosolv delignification of an indigenous wood-Partal (*Picea morinda*). *Journal of the Chemical Society of Pakistan*. 2001;**23**(4):210-214
- [98] Sahin HT. Base-catalyzed organosolv pulping of jute. *Journal of Chemical Technology and Biotechnology*. 2003;**78**(12):1267-1273
- [99] Lu Q, Liu W, Yang L, Zu Y, Zu B, Zhu M, Zhang Y, Zhang X, Zhang R, Sun Z, Huang J, Zhang X, Li W. Investigation of the effects of different organosolv pulping methods on antioxidant capacity and extraction efficiency of lignin. *Food Chemistry*. 2012;**131**(1):313-317
- [100] Gast D, Ayla C, Puls J. Component separation of lignocelluloses by organosolv-treatment. In: Strub A, editor. *Energy from Biomass 2nd E.C. Conference*. Barking: Applied Science Publishers Ltd; 1983
- [101] Gast D, Puls J. Ethylene glycol-water pulping. Kinetics of delignification. In: Ferrero GL, editor. *Anaerobic Digestion and Carbohydrate Hydrolysis of Waste*. Essex: Elsevier Applied Science Publishers Ltd; 1985. pp. 450-453
- [102] Gast D, Puls J. Improvement of the ethylene glycerol water system for the component separation of lignocelluloses. In: Palz W, editor. *Energy from Biomass 3rd E.C. Conference*. Essex: Elsevier Applied Science Publishers Ltd; 1985. pp. 949-951
- [103] Rutkowski J, Mroz W, Surna-Slusarsaka B, Perlinskasipa K. Glycolic delignification of hardwood. In: *Progress 93 Conference Proceeding*. Vol. 1. 1993. pp. 190-205
- [104] Chaudhuri P. Solvent pulping of bagasse. A process and system concept. In: *TAPPI Pulping Conference Proceeding*. 1996. pp. 583-594
- [105] Jiménez L, Angulo V, García E, Rodríguez A. Obtención de pastas celulósicas a partir de sarmientos de vid. *Afinidad*. 2004;**61**, **511**:194-203
- [106] Rutkowski J, Mroz W, Perlinskasipa K. Glycol-acetic wood delignification. *Cellulose Chemistry and Technology*. 1995;**28**(6):621-628
- [107] Jiménez L, Rodríguez A, Díaz MJ, López F, Ariza J. Organosolv pulping of olive tree trimmings by use of ethylene glycol/soda/water mixtures. *Holzforschung*. 2004;**58**(2):122-128
- [108] Jiménez L, Rodríguez A, Pérez I, Calero A, Ferrer JL. Ethylene glycol-soda organosolv pulping of olive tree trimmings. *Wood and Fiber Science*. 2004;**36**(3):423-431
- [109] Mohammadi-Rovshandeh J, Talebizadeh A, Rezayati-Charani P. Pulping of rice straw by high boiling solvents in atmospheric pressure. *Iranian Polymer Journal*. 2005;**14**(3):223-227

- [110] Evtuguin DV, Robert A, Zarubin MY, Deineko IP. The effect of oxygen-organosolv pulping conditions on the pulp properties. *Cellulose Chemistry and Technology*. 1996;**30**(1/2):105-115
- [111] Kunaver M, Anžlovar A, Žagar E. The fast and effective isolation of nanocellulose from selected cellulosic feedstocks. *Carbohydrate Polymers*. 2016;**148**:251-258
- [112] Surma-Slusarska B. Balance of ethylene glycol in organosolv pulping of hardwood. *Przegląd Paper*. 1998;**54**(12):712-714
- [113] Meighan BN, Lima DRS, Cardoso WJ, Baêta BEL, Adarme OFH, Santucci BS, Pimenta MTB, de Aquino SF, Gurgel LVA. Two-stage fractionation of sugarcane bagasse by autohydrolysis and glycerol organosolv delignification in a lignocellulosic biorefinery concept. *Industrial Crops and Products*. 2017;**108**:431-441
- [114] Kucuk MH, Demirbas A. Delignification of *Ailanthus altissima* and *Spruce orientalis* with glycerol or alkaline glycerol at atmospheric pressure. *Cellulose Chemistry and Technology*. 1993;**27**(6):679-686
- [115] Sano Y. Continuous organosolv pulping process using aqueous high-boiling solvents. *Japanese Kokai Tokkyo Koho*. 2001;**8**:21712-21752
- [116] Paszner L, Behera NC. Topochemistry of softwood delignification by alkali earth metal salt catalyzed organosolv pulping. *Holzforschung*. 1989;**43**(3):159-168
- [117] Vega A, Bao M, Lamas J. Application of factorial design to the modelling of organosolv delignification of *Miscanthus sinensis* (elephant grass) with phenol and dilute acid solutions. *Bioresource Technology*. 1997;**61**:1-7
- [118] Sano Y, Shimamoto S. Pulping of birchwood at atmospheric pressure with aqueous acetic acid containing small amounts of sulfuric acid and phenols. *Mokuzai Gakkaishi*. 1995;**41**(11):1006-1011
- [119] Jiménez L, de la Torre MJ, Maestre F, Ferrer JL, Pérez I. Organosolv pulping of wheat straw by use of phenol. *Bioresource Technology*. 1997;**60**:199-205
- [120] Vega A, Bao M. Organosolv fractionation of *Ulex europaeus* with dilute hydrochloric acid and phenol. Two simple kinetic models for prehydrolysis and delignification. *Wood Science and Technology*. 1993;**27**(1):61-68
- [121] Sano Y, Endo M, Sakashta Y. Solvolysis pulping of softwoods with aqueous cresols containing a small amount of acetic acid. *Mokuzai Gakkaishi*. 1989;**35**(9):807-812
- [122] Shurky N, Elmeadawy SA, Nassar MA. Pulping with organic acids. 3. Acetic acid pulping of bagasse. *Journal of Chemistry Technology and Biotechnology*. 1992;**54**(2):135-143
- [123] Parajó JC, Alonso JL, Vázquez D, Santos V. Optimization of catalyzed acetosolv fractionation of pine wood. *Holzforschung*. 1993;**47**(3):188-196

- [124] Vázquez G, Antorrena G, González J, Freire S, López S. Acetosolv pulping of pine wood. Kinetic modelling of lignin solubilization and condensation. *Bioresource Technology*. 1997;**59**(2/3):121-127
- [125] Parajó JC, Alonso JL, Vázquez D. On the behavior of lignin and hemicelluloses during the acetosolv processing of wood. *Bioresource Technology*. 1993;**46**(3):233-240
- [126] Parajó JC, Alonso JL, Santos V. Kinetics of eucalyptus wood fractionation in acetic acid-HCl-water media. *Bioresource Technology*. 1995;**51**(2/3):153-162
- [127] Vázquez G, Antorrena G, González J. Acetosolv pulping of *Eucalyptus globulus* wood. 1. The effect of operational variables on pulp yield, pulp lignin content and pulp potential glucose content. *Holzforschung*. 1995;**49**(1):69-74
- [128] Vázquez G, Antorrena G, González J, Freire S. The influence of pulping conditions on the structure of acetosolv eucalyptus lignins. *Journal of Wood Chemistry and Technology*. 1997;**17**(1/2):147-162
- [129] Neumann N, Balser K. Acetocell. An innovative process for pulping, totally free from sulfur and chlorine. *Papier*. 1993;**47**(10):V16-V23
- [130] Poppiuslevlin K, Mustonen R, Huovila T, Sundquist J. Milox pulping with acetic-acid peroxyacetic acid. *Paperi Ja Puu-Paper and Timber*. 1991;**73**:154-158
- [131] Vazquez G, Antorrena G, González J. Kinetics of acid-catalyzed delignification of *Eucalyptus globulus* wood by acetic acid. *Wood Science and Technology*. 1995;**29**(4):267-275
- [132] Kiran E, Balkan H. High-pressure extraction and delignification of red spruce with binary and ternary mixtures of acetic-acid, water and supercritical carbon-dioxide. *The Journal of Supercritical Fluids*. 1994;**7**(2):75-86
- [133] Rutkowski J, Wandelt P, Perlinskasipa K. Contribution to the technology of birch wood pulping with acetic-acid solutions. *Cellulose Chemistry and Technology*. 1998;**32**(1/2):89-96
- [134] Pan XJ, Sano Y, Ito T. Atmospheric acetic-acid pulping of rice straw. II. Behavior of ash and silica in rice straw during atmospheric acetic-acid pulping and bleaching. *Holzforschung*. 1999;**53**(1):49-55
- [135] Vila C, Santos V, Parajó JC. Optimization of beech wood pulping in catalyzed acetic-acid media. *The Canadian Journal of Chemical Engineering*. 2000;**78**(5):964-973
- [136] Li M-F, Sun S-N, Xu F, Sun R-C. Formic acid based organosolv pulping of bamboo (*Phyllostachys acuta*): Comparative characterization of the dissolved lignins with milled wood lignin. *Chemical Engineering Journal*. 2012;**179**:80-89
- [137] Erismann N d M, Freer J, Baeza J, Durán N. Organosolv pulping-VII: Delignification selectivity of formic acid pulping of *Eucalyptus grandis*. *Bioresource Technology*. 1994;**47**(3):247-256

- [138] Baeza J, Urizar S, Erismann ND, Freer J, Schmidt E. Organosolv pulping. 5. Formic-acid delignification of *Eucalyptus globulus* and *Eucalyptus grandis*. *Bioresource Technology*. 1991;**37**(1):1-6
- [139] Cimpoesu G, Obrocea P. Research on the delignification of spruce wood by organic peroxyacids. *Cellulose Chemistry and Technology*. 1995;**29**(4):487-496
- [140] Seisto A, Poppius-Levlin K, Jousimaa T. Peroxyformic acid pulping of non-wood plants by the Milox method. Part I. *Tappi Journal*. 1997;**80**(9):215-221
- [141] Seisto A, Poppiuslevlin K, Jousimaa T. Peroxyformic acid pulping of non wood plants by the Milox method. Part 2. *Tappi Journal*. 1997;**80**(10):235-240
- [142] Seisto A, Laine J. Surface chemical composition of birch Milox pulp. *Paperi Ja Puu-Paper and Timber*. 1999;**81**(1):53-58
- [143] Seisto A, Poppius-Levlin K. Formic acid/peroxyformic acid pulping of birch. Delignification selectivity and zero-span strength. *Nordic Pulp & Paper Research Journal*. 1997;**12**(3):155-161
- [144] El-Sayed ESA. Evaluation of Samaar morr (*Juncus acutus*) plant as raw material for paper making. *Journal of Scientific and Industrial Research*. 2004;**63**(2):163-171
- [145] Obracea P, Cimpoescu G. Contribution to spruce wood delignification with peroxyformic acid. *Cellulose Chemistry and Technology*. 1998;**32**(5/6):517-525
- [146] Ruggiero R, Machado AEH, Pérez DD, Grelier S, Nourmamode A, Castellan A. Bleached chemical pulp from *Eucalyptus grandis* wood produced by peroxyformic acid pulping and photochemical bleaching. *Holzforschung*. 1998;**52**(3):325-332
- [147] Silva Pérez D, Terrones MGH, Grelier S, Nourmamode A, Castellan A, Ruggiero R, Machado AEH. Peroxyformic acid pulping of *Eucalyptus grandis* wood chips and sugar cane bagasse in one stage and characterization of isolated lignins. *Journal of Wood Chemistry and Technology*. 1998;**18**(23):333-365
- [148] Dapia S, Sixta H, Borgards A, Harms H, Parajó JC. Production of acetate-grade pulps by organic acid pulping and TCF bleaching. *Tappi Journal*. 2002;**1**(3):17-22
- [149] Freer J, Rodríguez J, Baeza J, Duran N, Urizar S. Analysis of pulp and lignin extracted with formic acid-acetone mixture from *Pinus radiata* and *Eucalyptus globulus* wood. *Boletín de la Sociedad Chilena de Química*. 1999;**44**:199-207
- [150] Lam HQ, Bigot Y, Delmas M, Avignon G. Formic acid pulping of rice straw. *Industrial Crops and Products*. 2001;**14**(1):65-71
- [151] Jahan M, Lee Z, Jin Y. Organic acid pulping of rice straw II. Bleaching and beating. *Cellulose Chemistry and Technology*. 2005;**39**(1-2):85-94
- [152] Puuronen M, Muurinen E, Sohlo J. In: 8th Organosolv Pulping of Reeds International Symposium on Wood and Pulping Chemistry. Vol. 2. 1995. pp. 467-472

- [153] Mire M, Mlayah B, Delmas M, Bravo R. Formic acid-acetic acid pulping of banana stem (*Musa cavendish*). *Appita Journal*. 2005;**58**(5):393-396
- [154] Saake B, Lummitsch S, Mormanee R, Lehnen R, Nimz HH. Production of pulps using the formacell process. *Papier*. 1995;**49**(10):V1-V7
- [155] Saake B, Lahnen R, Schmekal E, Neubauer A, Nimz HH. Bleaching of Formacell pulp from aspen wood with ozone and peracetic-acid in organic-solvents. *Holzforschung*. 1998;**52**(6):643-650
- [156] Kham L, Le Bigot Y, Delmas M, Avignon G. Delignification of wheat straw using a mixture of carboxylic acids and peroxyacids. *Industrial Crops and Products*. 2005;**21**(1):9-15
- [157] Sano Y, Shimamoto S. Pulping of birch wood at atmospheric-pressure with aqueous acetic-acid containing small amounts of sulfuric-acid and phenols. *Mokuzai Gakkaishi*. 1995;**41**(11):1006-1011
- [158] Kiran E. Supercritical-fluid processing in the pulp and paper and the forest products industries. *ACS Symposium Series*. 1995;**608**:380-401
- [159] Jiménez L, de la Torre MJ, Bonilla JL, Ferrer JL. Organosolv pulping of wheat straw by use of acetone-water mixtures. *Process Biochemistry*. 1998;**33**(4):401-408
- [160] Jiménez L, García JC, Pérez I, Ferrer JL, Chica A. Influence of the operating conditions in the acetone pulping of wheat straw on the properties of the resulting paper sheets. *Bioresource Technology*. 2001;**79**(1):23-27
- [161] Jiménez L, García JC, Pérez I, Ariza J, López F. Acetone pulping of wheat straw. Influence of the cooking and beating conditions on the resulting paper sheets. *Industrial and Engineering Chemistry Research*. 2001;**40**(26):6201-6206
- [162] Jiménez L, Pérez I, López F, Ariza J, Rodríguez A. Ethanol-acetone pulping of wheat straw. Influence of the cooking and the beating of the pulps on the properties of the resulting paper sheets. *Bioresource Technology*. 2002;**83**(2):139-143
- [163] De Rosa MR, Da Silva C, Antonio A. Organosolv delignification of wheat straw. In: 5th Proceedings of Brazilian Symposium on the Chemistry of Lignins and Other Wood Components. Vol. 6. 1997. pp. 224-231
- [164] Baeza J, Urizar S, Freer J, Rodríguez J, Peralta-Zamora P, Durán N. Organosolv pulping. IX. Formic acid/acetone delignification of *Pinus radiata* and *Eucalyptus globulus*. *Cellulose Chemistry and Technology*. 1999;**33**(3/4):289-301
- [165] Ferraz A, Rodríguez J, Freer J, Baeza J. Formic acid/acetone-organosolv pulping of white-rotted *Pinus radiata* softwood. *Journal of Chemical Technology and Biotechnology*. 2000;**75**(12):1190-1196
- [166] Rosa MR, Rocha GJM, Curvelo AAS. Organosolv delignification of steam exploded wheat straw. In: 6th Proceedings of Brazilian Symposium on the Chemistry of Lignins and Other Wood Components. 2001. pp. 341-344

- [167] Delpechbarrie F, Robert A. Oxygen delignification in a water plus organic-solvent solution. 1. Delignification of poplar chips (*Populus* species) in a water-acetone solution. *Cellulose Chemistry and Technology*. 1993;27(1):87-105
- [168] Neto PG, Delpechbarrie F, Robert A. Oxygen delignification in a water plus organic-solvent solution. 2. Comparison of eucalyptus wood (*Eucalyptus globulus*) and poplar wood (*Populus* species). *Cellulose Chemistry and Technology*. 1993;27(2):185-199
- [169] Bludworth J, Knopf FC. Reactive extraction of lignin from wood using supercritical ammonia-water mixtures. *The Journal of Supercritical Fluids*. 1994;6(4):249-254
- [170] Wallis AFA. Wood pulping with monoethanolamine in pressure vessels. *Appita Journal*. 1980;33(5):351-355
- [171] Obst JR, Sanyer N. Effect of quinones and amines on the cleavage rate of β -O-4 ethers in lignin during alkaline pulping. *Tappi Journal*. 1980;63(7):111-114
- [172] Claus I, Kordsachia O, Schroeder N, Karstens T. Monoethanolamine (MEA) pulping of beech and spruce wood for production for dissolving pulp. *Holzforschung*. 2004;5886:573-580
- [173] Jahan MS, Farouqui FI, Hasan AJM. Kinetics of jute pulping by soda-amine process. *Bangladesh Journal of Scientific and Industrial Research*. 2001;36(1/4):25-31
- [174] Jiménez L, Rodríguez A, Calero A, Eugenio ME. Use of ethanolamine-soda-water mixtures for pulping olive wood trimmings. *Chemical Engineering Research and Design*. 2004;82(A8):1037-1042
- [175] Jahan MS, Farouqui FI. Kinetics of jute pulping by soda-amine processes. *Cellulose Chemistry and Technology*. 2003;36(3/4):357-366
- [176] Sarwar MJ, Farouqui FI, Abdullah IS. Pulping of jute with amines. *Cellulose Chemistry and Technology*. 2002;35(1/2):177-187
- [177] Jiménez L, Villar JC, Rodríguez A, Jiménez RM, Calero A. Influence of pulping parameters of olive prunnings with ethanolamine and soda on pulp characteristics. *Afinidad*. 2002;59(500):399-408
- [178] Jahan MS. Soda-amine pulping of cotton stalk. In: *Pulping Conference United States*. 2001. pp. 1175-1183
- [179] Jahan MS, Farouqui FI. Pulping of whole jute plant (*Corchorus capsularis*) by soda-amine process. *Holzforschung*. 2000;54(6):625-630
- [180] Elmasry AM, Mostafa NYS, Hassan HA, Aboustate MA. Formamide and dimethylformamide and their effects on bagasse dissolving pulps. *Cellulose Chemistry and Technology*. 1998;32(5/6):433-440
- [181] Rezati-Charani P, Mohammadi-Rovshandeh J. Effect of pulping variable with dimethylformamide on the characteristics of bagasse-fiber. *Bioresource Technology*. 2005;96(15):1658-1669
- [182] Balogh DT, Curvelo AAS. Successive and batch extraction of *Eucalyptus grandis* in dioxane water-HCl solution. *Paperi Ja Puu-Paper and Timber*. 1998;80(5):374-378

- [183] Selim IZ, Mansour OY, Mohamed SA. Physical characterization of pulps. II. Rice straw and bagasse pulps bleached by monoconventional two-stage hydrogen peroxide method and paper sheet making. *Polymer-Plastics Technology and Engineering*. 1996;**35**(5):649-667
- [184] Mansour OY, Selim IZ, Mohamed SA. Physical characterization of pulps. I. Rice straw bleached by nonconventional multistage method and paper sheet making. *Polymer-Plastics Technology and Engineering*. 1996;**35**(4):567-580
- [185] Machado ASR, Sardinha RMA, Gomes de Acebedo E, Nunes da Ponte M. High-pressure delignification of eucalyptus wood by 1,4-dioxane-carbon dioxide mixtures. *Journal of Supercritical Fluids*. 1994;**7**(2):87-92
- [186] Westmoreland RA, Jefcoat IA. Sulfur dioxide-ethanol-water pulping of hardwoods. *Chemical Engineering Communications*. 1991;**104**:101-115