We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Introductory Chapter: Liquid Crystals

Irina Carlescu

1. Introduction

The domain of liquid crystals represents an actual and dynamic scientific area, directly implied in top technologies as nanotechnologies, aerospace domain, microelectronics, and molecular biology [1]. For about 130 years, liquid crystals have been the subject of study for fundamental science and in many fields of research such as chemistry, physics, medicine, and engineering as well, which contributed to the progress in materials science and to innovative applications. In addition, as a result of the recent development of advanced synthetic methods and characterization techniques, the nanostructured liquid crystalline compounds that display special ordering properties and assign new functions have been highlighted, such as electro-optical effects, actuation, chromism, sensing, or templating [1–4].

Compared to other solid-state materials, liquid crystals present unique attributes, because they easily respond to external stimuli such as surfaces, light, heat, mechanical force, or electric and magnetic fields and eliminate defects by self-healing [5–9]. Thus, the understanding of the relationship between chemical structures of liquid crystalline compounds and their specific functions is becoming more important.

Liquid crystals are quintessential soft matter materials that present one to several distinct phases between the crystalline solid phase (Cr) and the isotropic liquid phase (Iso) [10–13]. These intermediary phases or mesophases not only possess some typical properties of a crystalline elastic solid like positional and orientational order as well as anisotropy of optical, electrical, and magnetic properties but also have the characteristic properties of an ordinary viscous liquid such as fluidity, formation and fusion of droplets, or mechanical properties [14–19]. Consequently, the compounds that present mesophases have intermediary symmetry properties, between an isotropic liquid and a crystalline solid; hence, a viscoelastic nature can be attributed to liquid crystals. Moreover, the unique combination of order and mobility represents the basis for self-assembly and supramolecular structure formation in technical systems. Generally, liquid crystals are elongated shape molecules, which are more or less parallel to each other in mesophases, contributing to anisotropic physical properties. These properties associated with their viscoelastic nature induce in liquid crystals the ability to easily respond under external stimuli and to change their configuration [20].

Depending on particular conditions where mesophases arise, liquid crystals have been classified into two classes: lyotropic and thermotropic. Thermotropic liquid crystals can be obtained either by heating a crystalline solid or by cooling an isotropic liquid. In the case of thermotropic liquid crystals, when the crystalline state is heated, the positional ordering of molecules vanishes but not the orientational one and so the

resultant ordered dynamic phase flows like a liquid and yet possesses the anisotropic properties of a crystal [21]. Upon further heating, this intermediary structure or mesophase loses as well the orientational ordering and transforms into a liquid. Unlike thermotropic liquid crystals, lyotropic liquid crystals are obtained by dissolving amphiphilic mesogen in a suitable solvent, to a specific concentration [22].

Most liquid crystals are organic molecules composed of π -conjugated systems and flexible alkyl chains attached to these. Although the functional conjugated units maintain the order, they have poor solubility in organic solvents, which limits the processing in optoelectronic devices [23]. Attachment of alkyl chains reduces the melting points and increases the solubility, while protecting the conjugated units from oxygen aggression. Hence, the optimum ratio between van der Waals interactions of the alkyl chains and π - π interactions of the conjugated units results in modulation of physical states and optoelectronic properties of liquid crystals [24].

Based on different geometry of the constituents, liquid crystalline molecules have been classified into calamitic or rod-like (elongated molecules), discotic (disc-shaped molecules), and bent-core or banana-shaped molecules. Another classification was based on symmetry of phases, which changes during the phase transitions. Besides, the phase symmetry targets the molecular organization in the phases and determines the physical properties of liquid crystals.

While the small calamitic liquid crystal organic molecules have been used in LCD devices [25] and π -conjugated discotic liquid crystalline molecules proved to be adequate for electron transport [26] and photoluminescence [27], the supra-molecular unconventional liquid crystals based on non-covalent interactions and polymeric systems are used for high strength fibers, encapsulation of microelectronic circuits, actuators, and organic photovoltaic or renewable energy [28–30]. Additionally, the combination between nanoparticles (e.g. CNTs) and liquid crystals that promote the self-assembly into well-defined periodic structures represents another research domain that is dealing with the improvement of electro-optic characteristics in devices or obtaining metamaterials [31–36].

Between mesophases, the nematic phase (N) is the least ordered (since it exhibits only long-range orientational order) and more fluid (less viscous) and easily responds to electric fields or formation of a mono-domain liquid crystal phase, successfully applied to flat-panel displays [37]. When chiral mesogens are introduced into a liquid crystalline structure or chiral molecules are added to a liquid crystal phase, a chiral phase is generated. In a cholesteric mesophase or chiral nematic phase (N*), the molecular orientation twists through the medium with a certain periodicity, while the positions of molecules are not correlated. Smectic phases (Sm) are distinguished from nematic ones by their stratification or ordering in the layers. Hence, in a smectic A mesophase, molecules may be on the average perpendicular to the layers; while in smectic C, the molecules adopt a uniformly tilted configuration, being inclined with a certain angle. The increase of molecular order leads to higher ordered smectic phases (Sm B, SmE, and SmG) [38]. The chiral smectic A phase (SmA*) presents about the same structure as the achiral SmA phase, except the physical properties. On the other hand, the chiral smectic C phase (SmC*) is different from any liquid crystalline phase and exhibits ferroelectric (FE) switching behavior.

Ferroelectricity appears in the case of molecules that present spontaneous and reversible electric polarization (P) that can be switched by using an external electric field [39, 40]. This physical phenomenon may be successfully accomplished by organic ferroelectric materials and used in devices like computer memories, sensors, and optics. In self-ordered liquid crystalline systems, ferroelectricity appears because of organization of chiral mesogens or the intrinsic dipole within achiral molecules,

which allows the facile switching of molecular dipoles. In mostly ordinary liquid crystalline phases (N, SmA, and SmC), the high rotational symmetry around the long molecular axis prevents the appearance of ferroelectricity. For chiral SmC* phase, electro-optical effects with speeds below microsecond order have been registered, so that SmC* liquid crystalline phase can be switched ON or OFF about 10^3 times more rapidly than nematic liquid crystals [41].

In liquid crystalline systems, chirality induces a one-dimensional helical structure, where the helical axis is perpendicular to the local director (for cholesteric mesophases) or is tilted from the normal layer so that the director precesses around the helix axis with a particular periodicity (for SmC* phases) [42]. The remarkable behavior of SmC* phases induced unique optical properties such as electro-optical effects, low-threshold laser emission, circular dichroism, or Bragg reflection [11, 43].

Similar to the SmC* phase, the discotic phase containing pendant chiral side chains forms ferroelectric columnar phases, though the switching phenomenon is not very clear. However, two possibilities have been suggested: the entire column rotates 180° around the columnar axis or the molecules reorient independently [44].

Although bent-core (BC) molecules are non-chiral mesogens, polar properties were reported for this unconventional liquid crystalline class [45]. The novelty of BC structures arises from simple bending by approximately 120° of the mesogenic core, resulting in a compact packing arrangement of molecules, which restricts rotational freedom with high impact on the structure of the liquid crystalline phases. According to the polar axis direction in adjacent layers, these phases can show ferroelectric (FE) or antiferroelectric (AF) behavior. The switching process in BC compounds under an electric field influence has been associated with π - π interaction type between the aromatic cycles that result after molecular restricted rotation around a tilted cone, while the chirality in the layers remains the same (the tilting and polar direction reverses) [46–55].

In order to be useful in devices, liquid crystals need to be forced and adequately aligned. Therefore, samples are formed between a pair of surface treated glass plates with about few microns distance. Compared to other mesophases, the alignment in the SmC* phase is more difficult to obtain. By placing a ferroelectric liquid crystal sample between crossed polarizers with the director n aligned along one of the polarizers, the helix is suppressed by surface action. Hence, the sample becomes an electro-optic switch that shows spontaneous polarization and two surfaces which interact to stably unwind the spontaneous ferroelectric helix result. This is known as a surface-stabilized-ferroelectric-liquid-crystal (SSFLC) device, very attractive for display applications because of very fast switching response [56]. Thus, the SSFLCs are of great interest for electro-optic devices based on the memory effect. Moreover, another application of optically addressed SSFLC targets optical holography [57].

IntechOpen

IntechOpen

Author details

Irina Carlescu

“Gheorghe Asachi” Technical University of Iasi, Iasi, Romania

*Address all correspondence to: icarlescu@ch.tuiasi.ro

IntechOpen

© 2018 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/3.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

References

- [1] Lagerwall JPF, Scalia G. A new era for liquid crystal research: Applications of liquid crystals in soft matter nano-, bio- and microtechnology. *Current Applied Physics*. 2012;**12**(6):1387-1412. DOI: 10.1016/j.cap.2012.03.019
- [2] Körner H, Shiota A, Bunning TJ, Ober CK. Orientation-on-demand thin films: Curing of liquid crystalline networks in ac electric fields. *Science*. 1996;**272**(5259):252-255. DOI: 10.1126/science.272.5259.252
- [3] Hulvat JF, Stupp SI. Liquid-crystal templating of conducting polymers. *Angewandte Chemie*. 2003;**42**(7): 778-781. DOI: 10.1002/anie.200390206
- [4] Hentze HP, Kaler EW. Polymerization of and within self-organized media. *Current Opinion in Colloid and Interface Science*. 2003;**8**(2):164-178. DOI: 10.1016/S1359-0294(03)00018-9
- [5] Goodby JW et al. *Handbook of Liquid Crystals*. 2nd ed. Weinheim: Wiley; 2014
- [6] Sagara Y, Kato T. Mechanically induced luminescence changes in molecular assemblies. *Nature Chemistry*. 2009;**1**:605-610. DOI: 10.1038/nchem.411
- [7] Yu Y, Nakano M, Ikeda T. Directed bending of a polymer film by light. *Nature*. 2003;**425**:145. DOI: 10.1038/425145a
- [8] Schadt M. Nematic liquid crystals and twisted nematic LCDs. *Liquid Crystals*. 2015;**42**:646-652. DOI: 10.1080/02678292.2015.1021597
- [9] Bisoyi HK, Quan L. Light-driven liquid crystalline materials: From photo-induced phase transitions and property modulations to applications. *Chemical Reviews*. 2016;**116**(24):15089-15166. DOI: 10.1021/acs.chemrev.6b00415
- [10] Li Q. *Nanoscience with Liquid Crystals: From Self-Organized Nanostructures to Applications*. Heidelberg: Springer-Verlag; 2014
- [11] de Gennes PG, Prost J. *The Physics of Liquid Crystals*. Oxford: Oxford University Press; 1993
- [12] Chandrasekhar S. *Liquid Crystals*. Cambridge, UK: Cambridge University Press; 1992
- [13] Collings PJ, Hird M. *Introduction to Liquid Crystals: Chemistry and Physics*. London: Taylor & Francis; 1997
- [14] Demus D, Goodby JW, Gray GW, Spiess HW, Vill V. *Handbook of Liquid Crystals*. Weinheim: Wiley-VCH; 1998
- [15] Collings PJ, Hird M. *Introduction to Liquid Crystals Chemistry and Physics*. London: Taylor and Francis; 1997
- [16] Kato T, Mizoshita N, Kishimoto K. Functional liquid-crystalline assemblies: Self-organized soft materials. *Angewandte Chemie, International Edition*. 2005;**45**(1):38-68. DOI: 10.1002/anie.200501384
- [17] Tschierske C. Non-conventional soft matter. *Annual Reports on the Progress of Chemistry*. 2001;**97**:191-267. DOI: 10.1039/B101114F
- [18] Goodby JW, Saez IM, Cowling SJ, Geortz V, Draper M, Hall AW, et al. Transmission and amplification of information and properties in nanostructured liquid crystals. *Angewandte Chemie, International Edition*. 2008;**47**(15):2754-2787. DOI: 10.1002/anie.200701111
- [19] Tschierske C. Liquid crystal engineering – New complex mesophase structures and their relations to polymer morphologies, nanoscale patterning and crystal engineering. *Chemical Society*

Reviews. 2007;**36**(12):1930-1970. DOI: 10.1039/B615517K

[20] Dunmur D, Sluckin T. Soap, Science and Flat-Screen TVs- A History of Liquid Crystals. Oxford: Oxford University Press; 2011

[21] Sluckin TJ, Dunmur DA, Stegemeyer H. Crystals That Flow: Classic Papers from the History of Liquid Crystals. Boca Raton, FL: CRC Press; 2004

[22] Garti N, Somasundaran P, Mezzenga R. Self-Assembled Supramolecular Architectures: Lyotropic Liquid Crystals. NJ: Wiley; 2012

[23] Moonen PF, Yakimets I, Huskens J. Fabrication of transistors on flexible substrates: From mass-printing to high-resolution alternative lithography strategies. *Advanced Materials*. 2012;**24**(41):5526-5541. DOI: 10.1002/adma.201202949

[24] Fengniu L, Takashi N. Alkyl- π engineering in state control toward versatile optoelectronic soft materials. *Science and Technology of Advanced Materials*. 2015;**16**(1):1468-6996. DOI: 10.1088/1468-6996/16/1/014805

[25] Kawamoto H. The history of liquid-crystal displays. *Proceedings of the IEEE*. 2002;**90**(4):460-500. DOI: 10.1109/JPROC.2002.1002521

[26] Kato T, Yoshio M, Ichikawa T, Soberats B, Ohno H, Funahashi M. Transport of ions and electrons in nanostructured liquid crystals. *Nature Reviews Materials*. 2017;**2**(4):1-20. DOI: 10.1038/natrevmats.2017.1

[27] Wang YF, Shi JW, Chen JH, Zhu WG, Baranoff E. Recent progress in luminescent liquid crystal materials: Design, properties and application for linearly polarised emission. *Journal of Materials Chemistry C*. 2015;**3**(31):7993-8005. DOI: 10.1039/c5tc01565k

[28] Bisoyi HK, Urbas AM, Li Q. Soft materials driven by photothermal effect and their applications. *Advanced Optical Materials*. 2018;**6**(15):1-21. DOI: 10.1002/adom.201800458

[29] Iwan A. An overview of LC polyazomethines with aliphatic-aromatic moieties: Thermal, optical, electrical and photovoltaic properties. *Renewable and Sustainable Energy Reviews*. 2015;**52**:65-79. DOI: 10.1016/j.rser.2015.07.078

[30] Dong LQ, Feng YY, Wang L, Feng W. Azobenzene-based solar thermal fuels: Design, properties, and applications. *Chemical Society Reviews*. 2018;**47**(19):7339-7368. DOI: 10.1039/c8cs00470f

[31] Agarwal A, Lilly GD, Govorov AO, Kotov NA. Optical emission and energy transfer in nanoparticle, nanorod assemblies: Potential energy pump system for negative refractive index materials. *Journal of Physical Chemistry C*. 2008;**112**(47):18314-18320. DOI: 10.1021/jp8006238

[32] Sanchez-Iglesias A, Grzelczak M, Rodriguez-Gonzalez B, Alvarez-Puebla RA, Liz-Marzan LM, Kotov NA. Gold colloids with unconventional angled shapes. *Langmuir*. 2009;**25**(19):11431-11435. DOI: 10.1021/la901590s

[33] Kretzers IKJ, Parker RJ, Olkhov RV, Shaw AM. Aggregation kinetics of gold nanoparticles at the silica-water interface. *Journal of Physical Chemistry C*. 2009;**113**(14):5514-5519. DOI: 10.1021/jp809304z

[34] Liu QK, Cui YX, Gardner D, Li X, He SL, Smalyukh II. Self-alignment of plasmonic gold nanorods in reconfigurable anisotropic fluids for tunable bulk metamaterial applications. *Nano Letters*. 2010;**10**(4):1347-1353. DOI: 10.1021/nl9042104

- [35] Lin MH, Chen HY, Gwo S. Layer-by-layer assembly of three-dimensional colloidal supercrystals with tunable plasmonic properties. *Journal of the American Chemical Society*. 2010;**132**(32):11259-11263. DOI: 10.1021/ja103722p
- [36] Garbovskiy Y, Glushchenko A. Ferroelectric nanoparticles in liquid crystals: Recent progress and current challenges. *Nanomaterials*. 2017;**7**(11):1-20. DOI: 10.3390/nano7110361
- [37] Bremer M, Kirsch P, Klasen-Memmer M, Tarumi K. The TV in your pocket: Development of liquid-crystal materials for the new millennium. *Angewandte Chemie, International Edition*. 2013;**52**:8880-8896. DOI: 10.1002/anie.201300903
- [38] Andrienko D. Introduction to liquid crystals. *Journal of Molecular Liquids*. 2018;**267**:520-541. DOI: 10.1016/j.molliq.2018.01.175
- [39] Alok ST, Kaeser A, Matsumoto M, Aida T, Stupp SI. Supramolecular ferroelectrics. *Nature Chemistry*. 2015;**7**(4):281-294. DOI: 10.1038/nchem.2206
- [40] Jakli A, Lischka C, Weissflog W, Pezl G, Rauch S, Heppke G. Structural transitions of smectic phases formed by achiral bent-core molecules. *Ferroelectrics*. 2000;**243**(1):239-247. DOI: 10.1080/00150190008008025
- [41] Lagerwall JPF, Giesselmann F. Current topics in smectic liquid crystal research. *ChemPhysChem*. 2006;**16**(1):20-45. DOI: 10.1002/cphc.200500472
- [42] Kitzerow HS, Bahr C. *Chirality in Liquid Crystals*. New York: Springer; 2001
- [43] Dunmur K. In: Demus DD, Goodby J, Gray GW, Spiess HW, Vill V, editors. *Physical Properties of Liquid Crystals*. Wiley-VCH; 1999
- [44] Guillon D. In: Prigogine I, Rice SA, Vij JK, editors. *Advances in Chemical Physics*; 2007. pp. 1-49
- [45] Niori T, Sekine T, Watanabe J, Takezoe H. Distinct ferroelectric smectic liquid crystals consisting of banana shaped achiral molecules. *Journal of Materials Chemistry*. 1996;**6**(7):1231-1233. DOI: 10.1039/JM9960601231
- [46] Görtz V, Goodby JW. Enantioselective segregation in achiral nematic liquid crystals. *Chemical Communications*. 2005;(26):3262-3264. DOI: 10.1039/B503846D
- [47] Hegmann T, Peidis F, Diele S, Tschierske C. Combination of molecular rods and half-discs: Transition from lamellar to columnar order in multichain mononuclear ortho-palladated metallomesogens. *Liquid Crystals*. 2000;**27**(10):1261-1265. DOI: 10.1080/026782900423296
- [48] Mahlstedt S, Janietz D, Schmidt C, Stracke A, Wendorff JH. Novel donor-acceptor triple mesogens incorporating disc-like and rod-like molecular sub-units. *Liquid Crystals*. 1999;**26**(9):1359-1369. DOI: 10.1080/026782999204039
- [49] Hegmann T, Kain J, Diele S, Schubert B, Bogel H, Tschierske C. Molecular design at the calamitic/discotic cross-over point. Mononuclear ortho-metallated mesogens based on the combination of rod-like phenylpyrimidines and -pyridines with bent or half-disc-shaped diketonates. *Journal of Materials Chemistry*. 2003;**13**:991-1003. DOI: 10.1039/B210250A
- [50] Chen D, Nakata M, Shao RF, Tuchband MR, Shuai M, Baumeister U,

et al. Twist-bend heliconical chiral nematic liquid crystal phase of an achiral rigid bent-core mesogen. *Physical Review E*. 2014;**89**(2). DOI: 10.1103/PhysRevE.89.022506

[51] Tschierske C. Development of structural complexity by liquid-crystal self-assembly. *Angewandte Chemie, International Edition*. 2013;**52**(34):8828-8878. DOI: 10.1002/anie.201300872

[52] Tschierske C, Photinos DJ. Biaxial nematic phases. *Journal of Materials Chemistry*. 2010;**20**(21):4263-4294. DOI: 10.1039/b924810b

[53] Popov P, Mann EK, Jakli A. Thermotropic liquid crystal films for biosensors and beyond. *Journal of Materials Chemistry C*. 2017;**5**(26): 5061-5078. DOI: 10.1039/c7tb00809k

[54] Alaasar M, Prehm M, Poppe S, Tschierske C. Development of polar order by liquid-crystal self-assembly of weakly bent molecules. *Chemistry—A European Journal*. 2017;**23**(23): 5541-5556. DOI: 10.1002/chem.201606035

[55] Tschierske C. Development of structural complexity by liquid-crystal self-assembly. *Angewandte Chemie, International Edition*. 2013;**52**(34):8828-8878. DOI: 10.1002/anie.201300872

[56] Clark NA, Lagerwall ST. Surface-stabilized ferroelectric liquid crystal electrooptics: New multistate structures and devices. *Ferroelectrics*. 1984;**59**: 25-67. DOI: 10.1080/00150198408240737

[57] Sutkowski M, Piecek W, Grudniewski T, Parka J, Nowinowski-Kruszelnicki E. Light driven optical switching of the surface stabilized antiferroelectric liquid crystals. *Optics and Lasers in Engineering*. 2011;**49**(11):1330-1334. DOI: 10.1016/j.optlaseng.2011.05.019