We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Investigation of Corrosion Inhibitors Adsorption on Metals Using Density Functional Theory and Molecular Dynamics Simulation

Ambrish Singh, Kashif R. Ansari, Mumtaz A. Quraishi and Yuanhua Lin

Abstract

The use of computational chemistry as a tool in the design and development of organic corrosion inhibitors has been greatly enhanced by the development of density functional theory (DFT) and Molecular dynamic simulation (MD). Experimentally corrosion inhibitor development requires lots of money and time. Thus, in the era of hardware and software development, corrosion scientist can select a potential inhibitor on the basis of theoretical analysis of molecular properties of inhibitor molecules, which have reduced the cost. DFT and MD are capable to accurately predict the inhibition characteristics of inhibitor molecules using molecular/electronic properties and reactivity indices. The purpose of this book chapter is to summarize some important features related to DFT and MD, giving a brief background to the selected DFT/MD-based chemical reactivity concepts, calculations and their applications to organic corrosion inhibitor design. The impact of this book chapter is to illustrate the enormous power of DFT and MD.

Keywords: corrosion, DFT, MD, inhibitor

1. Introduction

Corrosion of active metals such as iron (Fe), copper (Cu) and Aluminum (Al) can be reduced by modifying their surface using organic/polymeric corrosion inhibitors. The inhibitor molecules adsorbed onto the metal surface and form a protective barrier against corrosion [1]. The corrosion protection ability of inhibitors depends upon the extent of interaction between inhibitor molecules and metal surface [2]. The basics mechanism through which adsorbed inhibitor molecules alter the corrosion process consists of either changing the cathodic and anodic corrosion reactions or physically blocking the active sites present on metal surface or by [3].

Perusal of the literature clearly reveals that huge number of publication exists where experimental works have been carried out to understand the corrosion inhibition process, however use of theoretical studies including density functional

theory (DFT) and molecular dynamic simulation (MD) appeared in recent years. In traditional experimental work scientists has to test huge number of organic compounds for selecting them as a potential corrosion inhibitor. This kind of search takes more time and money. However, in the era of development in the field of hardware and software technology make us capable to select organic compounds as potential corrosion inhibitor without expensing huge amount of money on chemicals. The corrosion inhibition efficiency of organic compounds based on molecular and electronic properties can be predicted accurately using MD and DFT calculations. In the recent years, scientist have devoted their positive efforts in the field of corrosion using theoretical calculation [4–6]. To our knowledge, the review exists in the literature only describing separately DFT and MD and not both in relation to corrosion inhibition study [7, 8]. Here we are trying to describe both DFT and MD on the same platform simultaneously.

In this chapter we will try to explore some recent studies and concept which can provide some new concept in the field of computational chemistry related to corrosion inhibition phenomenon. Here, we summarize the adsorption of organic molecules onto the metal surface especially iron, aluminum and copper in order to study their corrosion inhibition properties using DFT and MD simulations.

2. Basic concepts related to molecular modeling

In literature, large number of publication/papers exists where corrosion inhibition property of inhibitors has been studied using theoretical study. In general organic molecules have the ability to donate electrons to empty d-orbital of metal surface and form covalent bond which is known as coordinate bond. However, they also undergo back donation, where they accept the free electrons presenting in filled metal orbitals and this is called as retrodonating bonds. Thus, these kinds of bonds make the organic compounds a potential candidate for corrosion inhibition. The theoretical parameters like highest occupied molecular orbital (HOMO), lowest unoccupied molecular orbital (LUMO), dipole moment (μ), energy gap (ΔE), Fukui indices, charge density, polarizability, softness, etc. [9–11] were discussed in DFT calculation.

DFT study separately represents the organic compound and metal surface [12–16]. In DFT, the interaction between the inhibitor molecule and metal surface was not directly modeled. However, in MD the most reactive fragment of the molecule that has greater affinity to interact with the metal surface is study using ab initio method. This method provide a real picture which is actually going in the corrosion process like interaction between inhibitor molecule and metal surface, orientation of molecule towards metal and organization of molecules.

3. Inhibitor/surface interaction study using DFT

3.1 The basics of DFT: the Hohenberg-Kohn theorem

Quantum electrochemistry is the field which includes quantum mechanics, electrochemistry and electrodynamics. In general, quantum electrochemistry is an application of density functional theory (DFT) for studying the electrochemical processes like transfer of electron towards electrode surfaces [17].

There are so many books and articles that exist in literature which describe about the basis set used in DFT [18–31]. So, here we provide only very few pints of DFT without using mathematics.

3.2 Functional

The functional is a function of a function, i.e., electron. Therefore, on the basis of fundamental quantum mechanics and from the experimental results different functional have been developed and are listed in **Table 1** [29].

There are several generations of density functional. First generation is known as X_{α} method and it is the simplest one. This functional was developed by J.C. Slater, who was working on the approximation of Hartree-Fock but unwillingly discovered the simplest for DFT. In X_{α} functional electron exchange but not the correlation was included. The results obtained from X_{α} method is as accurate as HF but in some cases it is better than HF.

The functional of second generation uses both the density and its gradients. In 1986 first gradient-corrected energy functional was proposed in which Becke, Perdew and Wang proposed exchange and Perdew correlation [32, 33]. In the present time the most popular functionalis of Becke and Perdew for exchange and correlation respectively [32], also Lee et al. [34] for correlation and Perdew and Wang for exchange and correlation both [35]. These functional are collectively known as “generalized gradient approximations (GGAs).”

The third generation is hybrid functional and it is more advanced than GGA. In this, the functional consists of both Hartree-Fock type exchange and DFT exchange calculated from the orbitals. In 1998, a hybrid functional called as B3LYP functional was introduced. In 1994, Gaussian introduced this functional in in computational package for first time and it is written by below equation:

$$E_{XC} = a_0E_{X(HF)} + a_1E_{X(LSD)}+a_2E_{X(GGA)} + a_3E_C \tag{1}$$

where $E_{X(HF)}$ represent the Hartree-Fock exchange energy, $E_{X(LSD)}$ stands for Dirac exchange energy and $E_{X(GGA)}$ and E_C are the gradient corrections to exchange energy, i.e., Be88form and Lee-Yang-Parr (LYP) functional respectively [34, 36].

3.3 Basis sets

In DFT calculation various basis sets are used [37]. The simplest one is STO-3G. In this basis set, 1s is given by three Gaussians and 2s, 2px, 2py, and 2pz each by

Acronyms	Name	Type
X_{α}	X alpha	Exchange only
HFS	Hartree-Fock Slater	HF with LDA exchange
VWN	Vosko, Wilks, and Nusair	LDA
BLYP	Becke correlation functional with Lee, Yang, Parr exchange	Gradient-corrected
B3LYP	Becke 3 term with Lee, Yang and Parr	Hybrid exchange
PW91	Perdew and Wang 1991	Gradient-corrected
G96	Gill 1996	Exchange
P86	Perdew 1986	Gradient-corrected
B96	Becke 1996	Gradient corrected
B3P86	Becke exchange, Perdew correlation	Hybrid
B3PW91	Becke exchange, Perdew and Wang	Hybrid correlation

Table 1.
List of density functional [29].

another three. Improvement in the basis set can obtain by incorporating two 1s functions for hydrogen and for 2nd row atoms like carbon two 2s and two 2p functions has incorporated. These functional are called as split-valence basis sets. Here valence and core orbitals are represented by two sets of functions and single set of functions respectively. An example for this:

Carbon 3-21G: Three Gaussians for 1s combination, same two Gaussians for 2s and 2p combination; plus 2s' and 2p' the same one Gaussian.

Carbon 6-31G: Six Gaussians for 1s combination, same three Gaussians for 2s and 2p combination; plus 2s' and 2p' the same one Gaussian.

In general it can be represented as *i-jk*, here *i* denote the number of Gaussians that are representing each core basis function, and *j* and *k* represent the numbers of Gaussians for split-valence basis functions.

Further advancement generates triple-split-valence basis sets, for example 6-311G. In this basis set core functional consists of six Gaussians and three sets of valence functions containing three, one, and one Gaussians, respectively.

Multiple zeta basis sets such as double zeta (DZ) and triple zeta (TZ) basis sets has also introduced. The difference between multiple and split-valence basis sets is that in multiple basis sets all of the orbitals are separated into either two or three sets of functions, and so forth. Also, multiple basis sets used different α -coefficients for s and p orbitals.

So, improvement in the electronic structure calculation can be achieved by adding functions corresponding to orbitals with a higher angular momentum. This concept

Basis	Options	Atoms
STO-3G	*	H-Xe
3-21G	* **	H-Cl
4-21G	* **	
4-31G	* **	H-Ne
6-21G	* **	
6-31G	+ + + * **	H-Cl
LP-31G	* **	
LP-41G	* **	
6-311G	+ + + * **	H-Ar
MC-311G	None	H-Ar
D95	+ + + * **	H-Cl
D95V	+ + + * **	H-Ne
SEC	+ + + * **	H-Cl
CEP-4G	+ + + * **	H-Cl
CEP-31G	+ + + * **	H-Cl
CEP-121G	+ + + * **	H-Cl
LANLIMB (except lanthanides)	None	H-Bi
LANLIDZ (except lanthanides)	None	H-Bi

Table 2.
Common basis set.

can explained as follows: for hydrogen atom, p functions are added; for carbon, nitrogen, oxygen, etc., d functions are added; and for transition metals, f functions are introduced. These are represented by adding an asterisk to the basis set and also specifying the p, d, f functions. This can be understood as per below example:

6-31G* or 6-31G(d): Adds d functions to 2nd row elements (C, N, O, etc.).

6.31G** or 6-31G(d,p): Adds d function to 2nd row elements (C, N, O, etc.) and p functions to H.

The lone pair of electrons on the heteroatoms can be taken into confederation by adding diffuse functions and these are represented in the basis set using + and ++ signs. For hydrogen atom polarization and diffuse functions are not very import but for other atoms like carbon, nitrogen, oxygen it is important, for example,

6-31+G: represents that diffuse functions has been added to 2nd row elements (C, N, O, etc.).

6-31++G: represents that diffuse functions has added to 2nd row elements and H.

In the case of transition elements which contain large number of electrons, requires more time for calculation. So, the LanL2DZ basis set is used for transition metal calculations. This basis set is derived by combining the valence electrons using double zeta functions and Los Alamos ECP. The software used in corrosion inhibition study with a wide range of basis sets are Spartan, Material Studio, Gaussian 03, Gaussian 09 and most recently Gaussian 14 has been introduced. **Table 2** represents commonly used basis sets [37].

4. DFT parameters and their application in corrosion inhibition study

4.1 Frontier molecular orbitals

The optical and electronic property of organic compounds is explained by analyzing their frontier molecular orbitals (FMO) like highest occupied molecular orbital (HOMO) and lowest unoccupied molecular orbital (LUMO) [38]. The interaction of organic compounds as corrosion inhibitor with the metal surface depends upon the electron donation ability of the organic compounds, i.e., ionization potential (*I.P.*). However, the electron accepting ability of organic compounds corresponds to the electron affinity (*E.A.*) [39]. So, HOMO is the electron donating orbitals and LUMO is electron accepting orbitals [40]. In general for a good corrosion inhibitor HOMO value should high, LUMO should low and energy gap between the LUMO and HOMO (ΔE) should low [40].

According to Koopmans' theorem the negative value of HOMO corresponds to the ionization potential (*I.P.*) and is given as follows [41–44]:

$$I.P. = -E_{HOMO} \quad (2)$$

Similarly negative value of LUMO corresponds to the electron affinity (*E.A.*) and is given below [41–48]:

$$E.A. = -E_{LUMO} \quad (3)$$

In literature Singh et al. [45] has correlated some important quantum chemical parameters of organic corrosion inhibitors using/B3LYP methods using 6-311G (d, p) basis set with their corrosion inhibition efficiency. They studied three triazine-based hydrazone derivatives and their molecular, orbital pictures and quantum chemical parameters are represented in **Figures 1–3**.

Figure 1.
Molecular structure of the triazine-based hydrazone derivatives. Adapted from Ref. [45].

Figure 2.
HOMO orbitals of triazine-based hydrazone derivatives.

Figure 3.
LUMO orbitals of triazine-based hydrazone derivatives.

The HOMO and LUMO are represented in **Figures 2 and 3**.

From the figure, it could be said that HOMO regions are distributed on the triazine ring, phenyl ring containing electron donating group, nitrogen and oxygen atoms. These regions correspond to the electron donating areas and inhibitor molecules interact with the metal surface through these regions and undergo adsorption over it. However, the LUMO are distributed over the triazine and phenyl ring respectively and these are corresponding to the electron accepting regions. From these LUMO regions inhibitor accept electron from metal. Order of inhibition efficiency is HT-1 > HT-2 > HT-3.

4.2. Electronegativity and the electronic chemical potential

One of the important global molecular property calculated by density functional theory (DFT) which provide an idea for chemical reactivity and selectivity of organic compound as corrosion inhibitor are electronegativity (χ) and chemical potential (μ) [46]. Mathematical form of this is as follows [47, 48]:

$$\chi = -\mu = -\left(\frac{\partial E}{\partial N}\right)_{\nu(r)} \quad (4)$$

$$\chi = -\mu = -\left(\frac{I.P. + E.A.}{2}\right) \quad (5)$$

where $I.P.$ and $E.A.$ are ionization potential and electron affinity.

4.3 Global hardness and softness

According to Parr et al. global hardness (η) measures the resistance of an atom to transfer the charge [49] and it can be calculated using below equation:

$$\eta = \frac{1}{2}(E_L + E_H) \quad (6)$$

where E_L and E_H are the HOMO and LUMO energy.

The reciprocal of global hardness is global softness (σ) and given as [50]:

$$\sigma = \frac{1}{\eta} \quad (7)$$

4.4 Electric dipole polarizability

The electric dipole polarizability (α) is a measurement of the linear response of the electron density in the presence of an infinitesimal electric field F and it describes a second-order variation in energy:

$$\alpha = -\left(\frac{\partial^2 E}{\partial^2 F_a \partial^2 F_b}\right) a, b = x, y, z \quad (8)$$

The polarizability (α) is calculated as the mean value and express through above equation:

$$\alpha = \frac{1}{3}(\alpha_{xx} + \alpha_{yy} + \alpha_{zz}) \quad (9)$$

It was discovered that polarizabilities are inversely proportional to the third power of the hardness values [51–54].

4.5 Electrophilicity index

Parr et al. has introduced the concept of global electrophilicity index (ω) and is given as follows [55, 56]:

$$\omega = \frac{\mu^2}{4\eta} \quad (10)$$

The global electrophilicity index (ω) is also related to the ionization potential ($I.P.$) and electron affinity ($E.A.$) and is given as follows [56]:

$$\omega = \frac{(I.P. + E.A.)^2}{8(I.P. + E.A.)} \quad (11)$$

The electrophilicity index accounts the ability of the molecule to accept electrons. So, higher the ω value, greater would be the molecule to accept the electrons.

4.6 The fraction of electrons transferred

When the inhibitor and metal interaction occurs, flow of electron takes place from the lower electronegativity molecule to the higher electronegativity metal. This transfer of electron continues until the chemical potential becomes equal. The fraction of electron transfer is given as follows [57]:

$$\Delta N = \frac{\chi_m - \chi_i}{2(\eta_m + \eta_i)} \quad (12)$$

where metal and inhibitor molecule are represented by m and i indices respectively. The absolute electronegativity of metal and inhibitor molecule are represented by χ_m and χ_i respectively. The absolute hardness of metals and inhibitor molecule is given by η_m and η_i , respectively. In case of iron the theoretical values of χ_m and η_m are 7 and 0 eV mol⁻¹ respectively [57]. However, the value of 7.0 eV corresponds to the free electron gas Fermi energy of iron in the free electron gas model. But the use of this value for χ_m is conceptually wrong because here electron-electron interaction has been neglected [58]. Thus, work function (ϕ_m) of the metal has been incorporated for an appropriate measurement of electronegativity. So, the new formula for the estimation of N is as follows [59]:

$$\Delta N = \frac{\phi_m - \chi_i}{2(\eta_m - \eta_i)} \quad (13)$$

The work function (ϕ) values for iron surface plan Fe (1 0 0), Fe (1 1 0) and Fe (1 1 1) surfaces are 3.91, 4.82 and 3.88 eV, respectively [59, 60]. The surface energy of iron planes for bcc structure are in order of Fe (110) < Fe (100) < Fe (111) and out of these the most stable on plan is Fe (110). Thus, most commonly Fe (110) plan is used in corrosion inhibition research [61].

4.7 Fukui function and local softness

In the field of corrosion research inhibition of corrosion is governed through donation and acceptance of electron, which basically involves the nucleophilic and electrophilic reactions. This can be achieved through the evaluation of the Fukui indices [61–63]. Thus, by invoking the HSAB principle in a local sense, one may establish the behavior of the different sites with respect to hard or soft reagents.

The Fukui function generated using the finite difference approximation is as follows:

$$f^+ = \left(\frac{\delta \rho(r)}{\delta N} \right)_\nu^+ = \rho_{(N+1)} - \rho_N \quad (14)$$

$$f^- = \left(\frac{\delta \rho(r)}{\delta N} \right)_\nu^+ = \rho_{(N)} - \rho_{(N-1)} \quad (15)$$

where f^+ is nucleophilic and f^- is electrophilic Fukui functions respectively, $\rho_{(N+1)}$, $\rho_{(N)}$ and $\rho_{(N-1)}$ are the electronic densities of anionic, neutral and cationic forms of the atoms with $N+1$, N and $N-1$ electrons.

Castro et al. [64] studied the series of isomers of the Schiff base (E)-2-(2-hydroxybenzylideneamino) phenylarsonic acid as corrosion inhibitor. The author has pictorially presented the negative Fukui, i.e., f^- function and is given as follows.

In **Figure 4**, the black region represents the area where inhibitor contains the major portion of electrons for donating to the empty d orbitals of Fe metal. The Fukui function represents the change of the electronic density in a given point with

Figure 4.
Isosurface plots for the electrophilic form of the Fukui function f^- .

respect to the change in the number of electrons N [65]. For the electrophilic attack to occur, the contributing atoms are likely to be the carbon atoms on the OH-substituted phenyl ring in all isomers, the oxygen atom in the isomer SBAs-OH-I, the nitrogen atom of the imine group of isomer SBAs-OH-III, and a region located in AsO(OH)₂-substituted phenyl ring.

Local softness is calculated using the equation [66]:

$$s(r) = \left[\frac{\partial n(r)}{\partial \mu} \right]_{\nu(r)} \quad (16)$$

The integration of equation gives global softness value:

$$S = \int s(r) dr \quad (17)$$

Local softness and Fukui function are related as per below equation:

$$s(r) = S f(r) \quad (18)$$

The local softness contains information similar to those obtained from Fukui function plus additional information about the molecular softness, which is related to the global reactivity with respect to a reaction partner.

4.8 Charge transfer: donation and back donation

The energy change in the molecule is attributed because of two processes either electron donation to the metal or acceptance from the metal, i.e., back donation. Gomez et al. [67] proposed a simple charge transfer model for donation and back donation. In this model when the molecule receives certain amount of charge (ΔN^-) the change in energy is given as follows:

$$\Delta E^+ = \delta^+ \Delta N^+ + 0.5\eta(\Delta N^+)^2 \quad (19)$$

However, when the molecule back donate certain amount of charge (ΔN^-) the change in energy is given as follows:

$$\Delta E^- = \delta^- \Delta N^- + 0.5\eta(\Delta N^-)^2 \quad (20)$$

If the total change in energy (ΔE_T) is the summation of ΔE^+ and ΔE^- , and assuming that the donation and back donation, i.e., (ΔN^-) and (ΔN^+) are equal, than:

$$\Delta E_T = \Delta E^- + \Delta E^+ = (\delta^- - \delta^+) \Delta N^+ + \eta(\Delta N^+)^2 \quad (21)$$

In a situation when the total energy change becomes a minimum with respect to ΔN^+ , then

$$\Delta N^+ = -(\delta^+ - \delta^-)/2\eta \quad (22)$$

and change in total energy becomes as follows:

$$\Delta E_T = -(\delta^+ - \delta^-)/4\eta = -\eta/4 \quad (23)$$

According to Guo et al. [68] the change in total energy are negative, i.e., $\Delta E_T < 0$. This implies that the back donation of charge from metal surface to inhibitor molecules is favorable.

5. Inhibitor/surface interaction study using molecular dynamic simulation (MD)

Molecular dynamics is a computer-based modeling technique by which the evolution as a function of time or trajectory of a molecule is described by the principles of classical Newtonian mechanics [69]. In molecular dynamics, intramolecular movements of inhibitor molecules are simulated in order to visualize the real picture of corrosion inhibition process. Molecular dynamics simulation calculation has two serve two purposes:

- a. Intramolecular movements' simulation and calculation of thermodynamic properties such as entropy, free energy, etc.
- b. Optimization of the molecular structures efficiently by avoiding multiple minima by annealing the simulation process. The range of simulation time is approximately between 10^{-14} and 10^{-10} s per simulation.

Molecular dynamics simulation involves the implementation of initial steps: In the first very step build molecular structure are introduced or immersed in a box having solvent molecules, after that simulation process starts. The total energy of the molecular system should be minimizing before the start of the simulation, in order to avoid the generation of aberrant trajectories (when the initial forces are too great). For achieving this, the steepest slope/steepest descent method and that of the conjugated gradients have been frequently used.

6. Corrosion inhibitors studied using DFT

6.1 Adsorption behavior of inhibitors on mild steel surface

In literature, several DFT calculations are observed where inhibition efficiency and molecular structure/electronic properties of organic corrosion inhibitors have

been correlated. Xu et al. [70] has studied corrosion inhibition property of Schiff's base derivatives via DFT calculation using GGA/BLYP method. The result indicates that 2-PCT molecules adsorb strongly onto iron surface and provide higher inhibition efficiency.

Zhang et al. [71] investigated the inhibition of methionine (Met) and proline (Pro) in PCMs solution using DFT and B3LYP/6-31G (d) method. The inhibition efficiency of Met and Pro follow the order of Met > Pro.

The corrosion inhibition effects of thiourea (TU), methylthiourea (MTU) and phenylthiourea (PTU) on mild steel in 0.1M H₂SO₄ was investigated by Ozcan et al. [72]. The electronic properties were calculated using ab initio RHF/6-31G(d) method. The energy of E_{HOMO} , the energy of E_{LUMO} and energy gap values supports that PTU is best inhibitor.

The corrosion inhibition performance of three naphthyridines derivatives were explored for mild steel in 1 M HCl by Singh et al. [73] using DFT methods. The inhibition efficiencies of N-3 and N-2 are higher due to the presence of electron-donating $-\text{OCH}_3$ and $-\text{CH}_3$ substituents respectively as compared to N-1, which has no substituents.

Feng et al. [74], studied inhibition activity of an imidazoline derivative, namely 1-[N,N'-bis(hydroxyethylether)- aminoethyl]-2-stearicimidazoline (HASI) for carbon steel in 5% NaCl saturated with Ca(OH)₂ solution using DMol3 module. DFT calculations reveals that N=C-N region in imidazoline ring is the most active reaction site.

6.2 Adsorption behavior of inhibitors on aluminum surface

The inhibitive action of poly ethylene glycol (PEG) against the corrosion of aluminum surface in 1 M HCl was investigated by Awad et al. [75] using B3LYP/6-31 + G(d,p) basis set. DFT was performed on repeating units of 1, 2, 3, 4 and 5. The inhibition performance increases with increase in number of repeating unit.

The author Li et al. [76] studied the corrosion inhibition effect of three oxime compounds on the corrosion of aluminum in HCl solution using BLYP in conjunction with double numerical plus d-functions (DND) basis set. In these inhibitors, HOMO and LUMO electron densities are localized principally on C=N-OH, which suggest that C=N-OH functional group could both accept and donate the electron.

Khaled et al. [77], investigated the corrosion effect of and adsorption characteristics of three imidazole derivatives on aluminum in 1.0 M HCl using local density functional (LDF) method with a double numeric polarization (DNP) basis set, and a Becke-Perdew (BP) functional. A good correlation between the rate of corrosion and E_{HOMO} , as well as with energy gap ($\Delta E = E_{\text{LUMO}} - E_{\text{HOMO}}$).

Kaya et al. [78] applied HF and DFT/B3LYP methods with SDD, 6-31++G (d, p) and 6-31 G basis sets both in gaseous and aqueous phase for studying the adsorption and corrosion inhibition properties of some benzotriazole and phosphono derivatives on aluminum. The inhibition efficiency ranking of these molecules as: PBA > PBTA > PAA > TBTA.

6.3 Adsorption behavior of inhibitors on copper surface

Corrosion inhibition of indazole (IA) and 5-aminoindazole (AIA) for copper in NaCl solution was studied by Qiang et al. [79]. The molecular structures of IA and AIA were geometrically optimized by density functional theory (DFT) using B3LYP functional with 6-311++G(d,p) basis set in aqueous phase. The higher value of HOMO and lower value of ΔE in case of AIA concludes that the interaction of AIA with copper will be stronger than that between IA and copper.

Khalid and Madkour et al. [13, 80, 81] probe the interactions between benzotriazole, methionine, phenol derivatives and copper via quantum calculations respectively. The obtained results suggests that quantum parameters are very useful in characterizing organic compounds as an adsorbate.

7. Corrosion inhibitors studied using MD

Feng et al. [74] performed the MD simulation of 1-[N,N'-bis(hydroxyethylether)-aminoethyl]-2-stearicimidazoline (HASI). The MD calculation suggests that adsorbed imidazoline molecule is parallel to the iron surface in order to maximize its contact with the surface (**Figure 5**). The interaction energy for Fe atom is -284 kJ/mol, for Fe_3O_4 is -226 kJ/mol and for Fe_2O_3 is -157 kJ/mol. So, inhibitor adsorbed on Fe surface more strongly than Fe_3O_4 and Fe_2O_3 .

MD calculation of adsorption of indazole (IA) and 5-aminoindazole (AIA) on copper surface was studied Qiang et al. [79]. The optimized equilibrium configuration of inhibitors molecules are shown in **Figure 6** and inhibitors adsorption occurs through parallel orientation. The adsorption energy between Cu (1 1 1) surface and inhibitor molecule are -250.86 kJ/mol for IA and -307.86 kJ/mol for AIA.

Molecular level MD calculation of Benzotriazole and Phospono derivatives was studied by Kaya et al. [78] on aluminum surface. The best adsorption configuration of inhibitor molecules on Al (111) surface are represented in **Figure 7**. The parallel configuration of inhibitor molecules suggests the stronger adsorption.

Figure 5. Adsorption of imidazoline molecule on (a) Fe, (b) Fe_3O_4 and (c) Fe_2O_3 surfaces. The left is top view, and the right is side view [74].

Figure 6.
Equilibrium adsorption configuration for IA and AIA on Cu (111) surface in 3% NaCl solution after optimization (inset images show the on-top views) [79].

Figure 7.
Equilibrium adsorption configuration of inhibitors PBTA (a and b), TBTA (c and d), BPA (e and f), PAA (g and h) on Al (111) surface. Top: top view and bottom: side view [78].

8. Conclusion and future work

Computational program provide an atomistic view for understanding the corrosion inhibition process and significantly contribute for the selection of adequate inhibitor molecules. DFT calculations has made possible to characterize a suitable inhibitor molecules using their intrinsic properties such as energies of HOMO and LUMO orbitals, energy gap (ΔE), electronegativity, hardness, softness, etc. It helps corrosion scientist to understand the inhibitor-metal interaction through the locations of HOMO and LUMO orbitals. The examination of local reactivity reveals the nucleophilic and electrophilic centers which react with the metal surfaces.

The literature survey suggests that with help of quantum chemistry a good understanding of corrosion system can be achieved when various metal surfaces and various inhibitor molecules are compared. DFT has ability to perform

calculations for complex or large organic molecules that can be applied as a potential corrosion inhibitor. In addition, DFT provide a platform to scientist for designing a unique inhibitor molecule and understand their molecular structure at atomistic level.

In recent years, computational modeling like DFT and MD provide real inhibitor-metal interaction picture by performing calculation in aqueous phase. Such an approach act as a benchmark for experimental study in the field of corrosion research.

Molecular dynamic simulation (MD) gives a representative image of inhibitor molecule orientation on the metal surface. This helps to analyze the inhibition activity of inhibitor molecules, i.e., inhibitor with parallel or flat orientation with respect to metal surface will cover more surface area and provide a better corrosion inhibition protection as compared to the inhibitor which have vertical orientation.

Future research includes modeling the electrochemical potential, generation of alloy surface layers, addition of thin oxide film covering onto the metal surface, calculation of more complex molecule, comprehension of solvent molecule role in adsorption, understanding the defect role in adsorption process, etc.

Acknowledgements

The authors are thankful to the Sichuan 1000 Talent Fund and financial assistance provided by the National Natural Science Foundation of China (No. 51274170).

Conflict of interest

There are no conflicts to declare.

Author details

Ambrish Singh^{1,2*}, Kashif R. Ansari³, Mumtaz A. Quraishi³ and Yuanhua Lin^{1,2}

¹ School of Materials Science and Engineering, Southwest Petroleum University, Chengdu, Sichuan, China

² State Key Laboratory of Oil and Gas Reservoir Geology and Exploitation, Southwest Petroleum University, Chengdu, Sichuan, China

³ Centre of Research Excellence in Corrosion, Research Institute, King Fahd University of Petroleum and Minerals, Dhahran, Saudi Arabia

*Address all correspondence to: vishisingh4uall@gmail.com

IntechOpen

© 2019 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/3.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

References

- [1] Mao ZJ, Jun L. Corrosion inhibition performance of carbon steel in brine solution containing H₂S and CO₂ by novel Gemini surfactants. *Acta Physico-Chimica Sinica*. 2012;**28**:623-629
- [2] Obot IB, Ebenso EE, Kabanda MM. Metronidazole as environmentally safe corrosion inhibitor for mild steel in 0.5 M HCl: Experimental and theoretical investigation. *Journal of Environmental Chemical Engineering*. 2013;**1**:431-439
- [3] Trabanelli G. *Chemical Industries Corrosion Mechanism*. Vol. 3. New York: Marcel Dekker; 1987
- [4] Gutiérrez E, Rodríguez JA, Borbolla JC, Rodríguez JGA, Thangarasu P. Development of a predictive model for corrosion inhibition of carbon steel by imidazole and benzimidazole derivatives. *Corrosion Science*. 2016;**108**:23-35
- [5] Shaban SM. N-(3-(dimethyl benzyl ammonio)propyl) alkanamide chloride derivatives as corrosion inhibitors for mild steel in 1 M HCl solution: Experimental and theoretical investigation. *RSC Advances*. 2016;**6**: 39784-39800
- [6] Ramaganthan B, Gopiraman M, Olasunkanmi LO, Kabanda MM, Yesudass S, Bahadur I, et al. Synthesized photo-cross-linking chalcones as novel corrosion inhibitors for mild steel in acidic medium: Experimental, quantum chemical and Monte Carlo simulation studies. *RSC Advances*. 2015;**5**: 76675-76688
- [7] Obot IB, Macdonald DD, Gasem ZM. Density functional theory (DFT) as a powerful tool for designing new organic corrosion inhibitors. Part 1: An overview. *Corrosion Science*. 2015;**99**:1-30
- [8] Verma C, Lgaz H, Verma DK, Ebenso EE, Bahadur I, Quraishi MA. Molecular dynamics and Monte Carlo simulations as powerful tools for study of interfacial adsorption behavior of corrosion inhibitors in aqueous phase: A review. *Journal of Molecular Liquids*. 2018;**260**: 99-120
- [9] Yang W, Parr RG, Pucci R. Electron density, Kohn–Sham frontier orbitals, and Fukui functions. *The Journal of Chemical Physics*. 1954;**81**:2862-2863
- [10] Parr RG, Yang W. Density functional approach to the frontier-electron theory of chemical reactivity. *Journal of the American Chemical Society*. 1984;**106**:4049-4050
- [11] Armaković S, Armaković SJ, Vraneš M, Tot A, Gadžurić S. DFT study of 1-butyl-3-methylimidazolium salicylate: A third-generation ionic liquid. *Journal of Molecular Modeling*. 2015;**21**:246-256
- [12] Guo L, Zhang ST, Lv TM, Feng WJ. Comparative theoretical study on the corrosion inhibition properties of benzoxazole and benzothiazole. *Research on Chemical Intermediates*. 2015;**41**:3729-3742
- [13] Madkour LH, Elshamy IH. Experimental and computational studies on the inhibition performances of benzimidazole and its derivatives for the corrosion of copper in nitric acid. *International Journal of Industrial Chemistry*. 2016;**7**:195-221
- [14] Mousavi M, Mohammadalizadeh M, Khosravan A. Theoretical investigation of corrosion inhibition effect of imidazole and its derivatives on mild steel using cluster model. *Corrosion Science*. 2011;**53**:3086-3091
- [15] Camacho RL, Montiel E, Jayanthi N, Pandiyan T, Cruz J. DFT studies of alpha-diimines adsorption over Fe-n surface (n = 1, 4, 9 and 14) as a model

for metal surface coating. *Chemical Physics Letters*. 2010;**485**(1–3):142-151

[16] Wang Y, Cheng X, Yang X, Yang X. DFT study of solvent effects for some organic molecules using a polarizable continuum model. *Journal of Solution Chemistry*. 2006;**35**:869-878

[17] Dogonadze RR. Theory of molecular electrode kinetics. In: Hush NS, editor. *Reactions of Molecules at Electrodes*. London: Interscience Pub.; 1971. pp. 135-227

[18] Sholl D, Steckel JA. *Density Functional Theory: A Practical Introduction*. New York: Wiley; 2009

[19] Enge E I, Dreizler RM. *Density Functional Theory: An Advanced Course*. Berlin, Heidelberg: Springer-Verlag; 2011

[20] Parr RG, Weitao Y. *Density-Functional Theory of Atoms and Molecules*. USA: Oxford University Press; 1989

[21] Marques MAL, Maitra NT, Nogueira FMS, Gross E, Rubio A. *Fundamentals of Time-Dependent Density Functional Theory*. Berlin, Heidelberg: Springer-Verlag; 2012

[22] Fiolhais C, Marques MAL, Nogueira F. *A Primer in Density Functional Theory*. Berlin, Heidelberg: Springer-Verlag; 2003

[23] Sahni V. *Quantal Density Functional Theory*. Berlin, Heidelberg: Springer Science & Business Media; 2004

[24] Tsuneda T. *Density Functional Theory in Quantum Chemistry*. Japan: Springer; 2014

[25] Gross E, Dreizler RM. *Density Functional Theory: An Approach to the Quantum Many-Body Problem*. Berlin, Heidelberg: Springer; 1990

[26] Gross E, Dreizler RM. *Density Functional Theory*. New York: Springer Science & Business Media; 1995

[27] Amador C. *Density Functional Theory*. Berlin, Heidelberg: Springer-Verlag; 1983

[28] Hohenberg P, Kohn W. Inhomogeneous electron gas. *Physics Review B*. 1964;**136**:864-871

[29] Koch W, Holthausen MC. *A Chemist's Guide to Density Functional Theory*. Weinheim: Wiley-VCH; 2000

[30] Bel SL, Dines TJ, Chowdhry BZ, Withnall R. Computational chemistry using modern electronic structure methods. *Journal of Chemical Education*. 2007;**84**:1364-1368

[31] Kohn W, Sham L. Self-consistent equations including exchange and correlation effects. *Physics Review*. 1965;**140**:A1133-A1138

[32] Perdew JP. Density functional approximation for the correlation energy of an inhomogeneous electron gas. *Physical Review B*. 1986;**33**:8822-8824

[33] Becke AD. Density functional calculations of molecular bond energies. *The Journal of Chemical Physics*. 1986; **84**:4524-4529

[34] Lee C, Yang W, Parr RG. Development of the Colle-Salvetti correlation energy formula into a functional of the electron density. *Physical Review B*. 1988;**37**:785-789

[35] Perdew J, Yang W. Accurate and simple density functional for the electronic exchange energy: Generalized gradient approximation. *Physical Review B*. 1986;**33**:8800-8802

[36] Becke AD. Density-functional exchange-energy approximation with

correct asymptotic behavior. *Physical Review A*. 1988;**38**:3098-3100

[37] Ramachandran KI, Deepa G, Namboori K. Computational chemistry and molecular modeling, Principles and Applications. Berlin, Heidelberg: Springer; 2008;137

[38] Arshad MN, Bibi A, Mahmood T, Asiri AM, Ayub K. Crystal structures and spectroscopic properties of triazine based hydrazone derivatives; a comparative experimental-theoretical study. *Molecules*. 2015;**20**:5851-5874. DOI: 10.3390/molecules20045851

[39] Zhan CG, Nichols JA, Dixon DA. Ionization potential, electron affinity, electronegativity, hardness, and electron excitation energy: Molecular properties from density functional theory orbital energies. *The Journal of Physical Chemistry. A*. 2003;**107**: 4184-4195

[40] Singh A, Ansari KR, Kumar A, Liu W, Songsong C, Lin Y. Electrochemical, surface and quantum chemical studies of novel imidazole derivatives as corrosion inhibitors for J55 steel in sweet corrosive environment. *Journal of Alloys and Compounds*. 2017;**712**: 121-133

[41] Tian H, Li W, Cao K, Hou B. Potent inhibition of copper corrosion in neutral chloride media by novel non-toxic thiadiazole derivatives. *Corrosion Science*. 2013;**73**:281-291

[42] Hegazy MA, Badawi AM, Abd El Rehim SS, Kamel WM. Corrosion inhibition of carbon steel using novel N-(2-(2-mercaptoacetoxy)ethyl)-N,N-dimethyl dodecan-1-aminium bromide during acid pickling. *Corrosion Science*. 2013;**69**:110-122

[43] Kovacevic N, Kokalj A. The relation between adsorption bonding and corrosion inhibition of azole molecules on copper. *Corrosion Science*. 2013;**73**: 7-17

[44] Deng S, Li X, Xie X. Hydroxymethyl urea and 1,3-bis(hydroxymethyl) urea as corrosion inhibitors for steel in HCl solution. *Corrosion Science*. 2014;**80**: 276-289

[45] Singh A, Ansari KR, Haque J, Dohare P, Lgaz H, Salghi R, et al. Effect of electron donating functional groups on corrosion inhibition of mild steel in hydrochloric acid: Experimental and quantum chemical study. *Journal of the Taiwan Institute of Chemical Engineers*. 2018;**82**:233-251

[46] Mendoza-Huizar LH, Rios-Reyes CH. Chemical reactivity of atrazine employing the Fukui function. *Journal of the Mexican Chemical Society*. 2011; **55**:142-147

[47] Chermette H. Chemical reactivity indexes in density functional theory. *Journal of Computational Chemistry*. 1999;**20**:129-154

[48] Pearson RG. Absolute electronegativity and hardness correlated with molecular orbital theory. *Proceedings of the National Academy of Sciences*. 1986;**83**: 8440-8441

[49] Parr RG, Gadre SR, Bartolotti LJ. Local density functional theory of atoms and molecules. *Proceedings of the National Academy of Sciences of the United States of America*. 1979;**76**: 2522-2526

[50] Haque J, Ansari KR, Srivastava V, Quraishi MA, Obot IB. Pyrimidine derivatives as novel acidizing corrosion inhibitors for N80 steel useful for petroleum industry: A combined experimental and theoretical approach. *Journal of Industrial and Engineering Chemistry*. 2017;**49**:176-188

[51] Zevallos J, Labbé AT. A theoretical analysis of the Kohn-Sham and Hartree-Fock orbitals and their use in the determination of electronic properties.

- Journal of the Chilean Chemical Society. 2003;**48**:39-47
- [52] Ghanty TK, Ghosh SK. Correlation between hardness, polarizability, and size of atoms, molecules, and clusters. *The Journal of Physical Chemistry*. 1993;**97**:4951-4953
- [53] Chattaraj PK, Sengupta S. Popular electronic structure principles in a dynamical context. *The Journal of Physical Chemistry*. 1996;**100**: 16126-16130
- [54] Hohm U. Is there a minimum polarizability principle in chemical reactions? *The Journal of Physical Chemistry. A*. 2000;**104**:8418-8423
- [55] Parr RG, Sventpaly L, Liu S. Electrophilicity index. *Journal of the American Chemical Society*. 1999;**121**: 1922-1924
- [56] Geerlings P, De Proft F, Langenaeker W. Conceptual density functional theory. *Chemical Reviews*. 2003;**103**:1793-1873
- [57] Pearson RG. Absolute electronegativity and hardness: Application to inorganic chemistry. *Inorganic Chemistry*. 1988;**27**:734-740
- [58] Kovačević N, Kokalj A. DFT study of interaction of azoles with Cu(111) and Al(111) surfaces: Role of azole nitrogen atoms and dipole-dipole interactions. *Journal of Physical Chemistry C*. 2011;**115**:24189-24197
- [59] Kokalj A. On the HSAB based estimate of charge transfer between adsorbates and metal surfaces. *Chemical Physics*. 2012;**393**:1-12
- [60] Cao Z, Tang Y, Cang H, Xu J, Lu G, Jing W. Novel benzimidazole derivatives as corrosion inhibitors of mild steel in the acidic media. Part II: Theoretical studies. *Corrosion Science*. 2014;**83**:292-298
- [61] Kokalj A. Is the analysis of molecular electronic structure of corrosion inhibitors sufficient to predict the trend of their inhibition performance. *Electrochimica Acta*. 2010;**56**:745-755
- [62] Lewars EG. *Computational Chemistry Introduction to the Theory and Applications of Molecular and Quantum Mechanics*. London: Springer; 2011
- [63] Oláh J, Alsenoy CV. Condensed Fukui functions derived from stockholder charges: Assessment of their performance as local reactivity descriptors. *The Journal of Physical Chemistry. A*. 2002;**106**:3885-3890
- [64] Castro ME, Percino MJ, Cerón M, Soriano G, Chapela VM. Theoretical inhibition efficiency study of Schiff Base (E)-2-(2-hydroxybenzylideneamino) phenylarsonic acid and its isomers. *International Journal of Electrochemical Science*. 2014;**9**:7890-7903
- [65] López P, Méndez F. Fukui function as a descriptor of the imidazolium protonated cation resonance hybrid structure. *Organic Letters*. 2004;**6**: 1781-1783
- [66] Yang W, Parr RG. Hardness, softness and the Fukui function in the electronic theory of metals and catalysis. *Proceedings of the National Academy of Sciences of the United States of America*. 1985;**82**:6723-6726
- [67] Gomez B, Likhanova NV, Dominguez-Aguilar MA, Martinez-Palou R, Vela A, Gazquez JL. Quantum chemical study of the inhibitive properties of 2-pyridyl-azoles. *The Journal of Physical Chemistry. B*. 2006; **110**:8928-8934
- [68] Guo L, Ren X, Zhou Y, Xu S, Gong Y, Zhang S. Theoretical evaluation of the corrosion inhibition performance of 1,3-thiazole and its amino derivatives.

Arabian Journal of Chemistry. 2017;**10**: 121-130

[69] Rives JT, Jorgensen WL. Molecular dynamics of proteins with the OPLS potential functions. Simulation of the third domain of silver pheasant ovomucoid in water. Journal of the American Chemical Society. 1990;**112**: 2773-2781

[70] Xu B, Yang W, Liu Y, Yin X, Gong W, Chen Y. Experimental and theoretical evaluation of two pyridinecarboxaldehyde thiosemicarbazone compounds as corrosion inhibitors for mild steel in hydrochloric acid solution. Corrosion Science. 2014;**78**:260-268

[71] Zhang Z, Tian N, Zhang W, Huang X, Ruan L, Wu L. Inhibition of carbon steel corrosion in phase-change-materials solution by methionine and proline. Corrosion Science. 2016;**111**: 675-689

[72] Ozcan M, Dehri I, Erbil M. Organic sulphur-containing compounds as corrosion inhibitors for mild steel in acidic media: Correlation between inhibition efficiency and chemical structure. Applied Surface Science. 2004;**236**:155-164

[73] Singh P, Ebenso EE, Olasunkanmi LO, Obot I, Quraishi M. Electrochemical, theoretical, and surface morphological studies of corrosion inhibition effect of green naphthyridine derivatives on mild steel in hydrochloric acid. Journal of Physical Chemistry C. 2016;**120**:3408-3419

[74] Feng L, Yang H, Wang F. Experimental and theoretical studies for corrosion inhibition of carbon steel by imidazoline derivative in 5% NaCl saturated Ca(OH)₂ solution. Electrochimica Acta. 2011;**58**:427-436

[75] Awad M, Metwally M, Soliman S, El-Zomrawy A. Experimental and

quantum chemical studies of the effect of poly ethylene glycol as corrosion inhibitors of aluminum surface. Journal of Industrial and Engineering Chemistry. 2014;**20**:796-808

[76] Li X, Deng S, Xie X. Experimental and theoretical study on corrosion inhibition of oxime compounds for aluminium in HCl solution. Corrosion Science. 2014;**81**:162-175

[77] Khaled K, Amin MA. Electrochemical and molecular dynamics simulation studies on the corrosion inhibition of aluminum in molar hydrochloric acid using some imidazole derivatives. Journal of Applied Electrochemistry. 2009;**39**: 2553-2568

[78] Kaya S, Banerjee P, Saha SK, Tüzün B, Kaya C. Theoretical evaluation of some benzotriazole and phosphono derivatives as aluminum corrosion inhibitors: DFT and molecular dynamics simulation approaches. RSC Advances. 2016;**6**:74550-74559

[79] Qiang Y, Zhang S, Xu S, Li W. Experimental and theoretical studies on the corrosion inhibition of copper by two indazole derivatives in 3.0% NaCl solution. Journal of Colloid and Interface Science. 2016;**472**:52-59

[80] Khaled K, Amin MA, Al-Mobarak N. On the corrosion inhibition and adsorption behaviour of some benzotriazole derivatives during copper corrosion in nitric acid solutions: A combined experimental and theoretical study. Journal of Applied Electrochemistry. 2010;**40**:601-613

[81] Khaled K. Corrosion control of copper in nitric acid solutions using some amino acids—A combined experimental and theoretical study. Corrosion Science. 2010;**52**:3225-3234