We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Progress in Ionic Liquids as Reaction Media, Monomers and Additives in High-Performance Polymers

Dan He, Zhengping Liu and Liyan Huang

Abstract

In this chapter, we will review the progress in ionic liquids (ILs) widely used as reaction media, monomers and additives in the synthesis, chemical modification and physical processing of high-performance polymers (HPPs). Using ILs as reaction media in the syntheses of HPPs, the high-molecular-weight polymers were obtained in good yields and the shortened dehydration time compared to the conventional methods, the separation efficiency of products was improved. It is particularly noteworthy that the number of novel copolymers of HPPs with polymerisable ILs has steadily increased in recent years. In addition, ILs have been used as various types of additives such as the components of polymer materials, plasticizers and porogenic agents in the physical processing of HPPs, and the materials prepared include membranes, microcapsules, nanocomposites (NCs), electrolytes and grease.

Keywords: ionic liquids (ILs), high-performance polymers (HPPs), reaction media, monomers, additives, polyimides (PIs), polysulphones (PSFs)

1. Introduction

1.1 Ionic liquids (ILs) and their properties

The melting points of ILs, also known as low-melting-point organic salts, are usually below 100°C; ILs are composed of organic cations and inorganic/organic anions, as shown in **Figure 1** [1, 2]. The number of possible cation-anion combination has been estimated to be $>10^6$ [3]. ILs are most commonly abbreviated by writing the abbreviation/formula of the cation and anion in square brackets (without charges); e.g., [bmim][PF₆], [bmim][Tf₂N] and [emim][Cl] are the abbreviations for 1-butyl-3-methyl-imidazolium hexafluorophosphate, 1-butyl-3-methylimidazolium bis(trifluoromethanesulphonyl)imide and 1-ethyl-3-methylimidazolium chloride, respectively. Owing to their high chemical and thermal stability, low volatility, and low toxicity, ILs have attracted much attention for applications in chemistry and industry. In addition, the properties of ILs include high conductivity, wide electrochemical window, low flammability, ability to dissolve organic and inorganic solutes and gases, and recyclability. As far as vapour pressures are concerned, several

Figure 1.
Typical cationic and anionic components of ILs.

ILs can be vaporised under a high vacuum at 200–300°C and then recondensed [4]; however, ILs indeed have negligible vapour pressures at near ambient conditions. Thus, for general reactivities or processes, they may be considered as low-volatile reaction media. ILs are generally chemically stable reaction media, but this cannot be taken as granted. The proton at the C(2)-position of imidazolium cation is acidic, and under basic conditions, deprotonation leading to carbene is possible [5]. ILs are considered as rational designable solvents that can be easily tuned by using various combinations of cations and anions to achieve ILs exhibiting appropriate properties and achieving practical applications for a desired task (so-called task-specific ILs), making it possible to introduce ILs into specific synthesis processes [6].

Because of these special properties, ILs have emerged as novel and exciting reaction media in their own right. Every year, an increasing number of papers are being published on the applications of ILs for enhancing reactivities or processes in both chemical research and industry. So far, free-radical polymerisation, polycondensation and ionic polymerisation have been successfully carried out using ILs as the reaction media. In the step polymerisation field, there is a huge interest for high-performance polymers (HPPs). Despite improved synthesis methods and commercial availability of various ILs for replacing typical organic reaction media, they are still more expensive than typical organic reaction media. Therefore, the application of ILs as reaction media for enhancing reactivities or processes is limited.

1.2 High-performance polymers (HPPs) and their categories

HPPs are also known as high-temperature polymers, special engineering plastics, advanced engineering materials, and heat-resistant polymers [7]. They are defined as polymers that can retain the desirable properties when exposed to very harsh conditions, including, but not limited to, a high-temperature, a high-pressure, and corrosive environment. They are well known for outstanding thermal stability and service temperatures, good mechanical properties, dimensional and environmental stability, high resistance to most chemicals, gas barrier and electrical properties, etc., under extreme conditions, even at elevated temperatures [8, 9]. To better understand the reason for their strength, one must consider the bond strength that can be quantified by bond dissociation energy. First, the higher the bond dissociation energy, the harder it is to break the polymer chain, and thus the better the resistance of the polymer to harsh environment. The bond energies of C–C and C=C bonds are 83 and 145 kcal mol^{−1}, respectively; thus, it is harder to break a C=C bond than a C–C bond. Most HPPs contain more C=C bonds than C–C bonds. Similarly, the bond energies of C–H and C–F bonds are 99 and 123 kcal mol^{−1},

respectively; some of the C–H groups are also replaced with C–F groups. The resonance stabilisation is enhanced by adding aromatic components along the backbone, and it is estimated that the incorporation of resonance-stabilised units can add 40–70 kcal mol^{−1} to the bond strength. Such a molecular structure of HPPs improves their resistance and stability; thus, they can retain the desirable properties under very harsh conditions.

HPPs include polysulphones (PSFs), polyimides (PIs), polyaryletherketones (PAEKs), poly(arylene sulphide)s (PASs), polyarylates (PARs), liquid crystalline polymers (LCPs), fluoroplastics (PVDFs), *p*-hydroxybenzoic acid polymers, poly(naphthalene), poly(oxadiazole), and high-temperature nylon (HTN). HPPs can be divided into amorphous polymers, semi-crystalline polymers, and LCPs; e.g., PSFs are described as amorphous polymers and polyetheretherketones are semi-crystalline polymers. The applications of HPPs span across aerospace, defence, weaponry, energy, electronics, automotive, construction, nuke industry, membrane technologies, etc. In recent years, new HPPs and materials containing HPPs with enhanced application potential in more fields have been reported, including materials obtained by the chemical modification and blending of HPPs containing ILs.

1.3 Overview

The aim of this article is to review the recent progress in the field of ILs as reaction media, monomers and additives in the synthesis, chemical modification and physical processing of HPPs based on recent literatures, with the main emphasis on possible advantages, limitations and importance of the work. The article is structured as follows: section 2 focuses on progress in IL application in HPPs. Section 2.1 focuses on ILs as reaction media in the synthesis of HPPs, including PIs, PSFs, and PAEKs, and synthesis of HPPs in ILs under microwave (MW) irradiation. Section 2.2 focuses on ILs as monomers for the chemical modification of HPPs. The last part of Section 2 focuses on ILs as additives for the physical processing of HPPs, including membranes, microcapsules, electrolytes, nanocomposites (NCs) and grease.

2. Progress in IL application in HPPs

2.1 ILs as reaction media for synthesis of HPPs

Most HPPs are synthesised by step polymerisation reactions. Step polymerisation is one of the main polymerisation reactions for preparing polymers, usually requiring elevated temperatures, high-boiling-point reaction solvents, high vacuum and the removal of small molecules to reach the equilibrium. Therefore, it seems to be suitable to introduce ILs into step polymerisation owing to their intrinsic properties as described above. In 2002, high-molecular-weight aromatic PIs and polyamides were synthesised for the first time, obtaining polymers with inherent viscosities from 0.52 to 1.35 dL/g in ILs 1,3-dialkylimidazolium bromides [10]. The use of ILs as novel solvents for the synthesis of other HPPs has been reported, such as PAEK [3, 11] and PSF [12, 13].

2.1.1 Synthesis of PIs in ILs

In 1908, Jones et al. first synthesised PIs, but it was difficult to process and fabricate them [14]. Until the early 1960s, Du Pont, USA, made a substantial progress in the processing of PIs; thus, PIs were developed and widely utilised in various applications [15]. These polymers are known as HPPs and possess outstanding

thermal stability, excellent electrical properties, improved mechanical properties and good resistance to organic solvents. They are widely applied in various modern industries such as gas separation membranes, insulator films for electrical/electronics, semi-conductor devices, coatings and composites, high-temperature adhesives, cell processing, and biochip design [16]. In general, PIs are produced in two steps via the formation of polyamic acids from diamines and dianhydrides. Other reported synthetic routes utilised tetracarboxylic acids, half-esters, a combination of bis(*o*-diiodoaromatics) with carbon monoxide, etc., [17]. Co-PIs with flexible linkages, such as ether and ester linkages between the aromatic rings of the main chain, have been synthesised, such as poly(amide-imide)s (PAIs), poly(ether amide-imide)s (PEAIs), poly(ester amide-imide)s, poly(ether-imidazole-imide)s, and poly(amine amide-imide)s [18].

In 2002, Vygodskii et al. first reported a novel one-step strategy for the synthesis of high-molecular-weight aromatic PIs by the polycyclisation reaction of 1,4,5,8-naphthalene tetracarboxylic acid dianhydride (DANTCA) with 3,3-bis(4'-aminophenyl)phthalide (Aph) in 1,3-dialkylimidazolium-based ILs without using catalyst at 180–200°C, as shown in **Figure 2** [10]. These ILs seem to be suitable reaction and activating media for the synthesis of aromatic PIs and polyamides. The polymerisation process and molecular weights of PIs are significantly affected by the structure and nature of ILs. The effects of IL structure include the following: (1) the best results were obtained in ILs with a symmetrical structure, obtaining polymers with a maximum inherent viscosity of 1.35 dL/g. (2) When using ILs with a symmetrical structure bearing alkyl chains of carbon atoms $n = 2-6$ and 12, polycyclisation occurred in a homogeneous solution for ILs with $n \leq 4$, but rapid precipitation of the PI occurred for ILs with $n > 4$. (3) High-molecular-weight polymers could be obtained in ILs with Br^- . (4) PIs insoluble in organic solvents do not precipitate from reaction solutions in ILs with anions SiF_6^- , HSO_4^- , NO_3^- , I^- and CH_3COO^- . (5) As far as cations were concerned, the molecular weights of PIs are lower in ILs based on quinoline and pyridine bearing the same alkyl chains longer than imidazole. In summary, it is possible to tailor ILs as active solvents for the step polymerisation reactions of PIs by varying the structures of the cations and anions of ILs. Studies on using ILs as reaction media for synthesising other step polymerisation polymers are in progress. Later, Vygodskii and co-workers reported studies on using different ILs as reaction media for synthesising other step polymerisation polymers with high molecular weights, such as poly(amide imide)s (PAIs) [19–21]. Although relatively high-molecular-weight PIs have been obtained in the absence of any added catalysts and lower reaction temperatures than the conventional synthetic method [17, 22, 23], the limited solubility of some aromatic substrates in ILs was still the main problem. In 2006, Ohno et al. reported that the solubility of starting materials was improved by adding imidazolium-type zwitterion (ZI), 1-(1-butyl-3-imidazolium)butane-4-sulphonate in ILs, leading to higher molecular weights of the resulting PIs [24]. On the other hand, in some studies of the step polymerisation of PIs, catalytic effect of ILs was observed. A type of PI was synthesised by the step polymerisation reactions of 1,4-bis(3-aminopropyl)

Figure 2.
Synthetic route for PI in IL.

piperazine with 3,3',4,4'-benzophenonetetracarboxylic dianhydride (BTDA) in the presence of ILs as the catalyst and N-methylpyrrolidone (NMP) as the solvent. The degrees of polymerisation are not only high, but the IL also exerts a detectable effect on polymer solubility. The PI with a higher degree of polydispersity was obtained in ILs based on imidazole than that obtained with pyridine and alkylamine [25]. PI nanoparticles were obtained in an IL, namely, 1-ethyl-3-methylimidazolium bis(trifluoromethyl-sulphonyl)imide ([emim][Tf₂N]), as a continuous phase without the addition of any further activating or stabilising agents by the hetero-phase step polymerisation of different aromatic tetracarboxylic acids and diamines. These PI particles with a range of 100 nm showed a high thermal stability by TGA and a decomposition temperature of ~520°C [26]. A sulphonated co-PI (SPI) was prepared in an IL, 1-ethyl-3-methyl imidazolium bromide [emim][Br], without any catalyst. These co-PIs prepared showed superior properties compared to those prepared in a common solvent, indicating promising properties for applications in proton-exchange membrane fuel cells [27, 28]. The trifluoromethylated poly(ether-imidazole-imide)s (PEII)s based on an unsymmetrical-diamine-bearing carbazole and imidazole chromophores were obtained with 80–96% yields in imidazolium-based ILs. They were amorphous with good thermal and thermo-oxidative stability, excellent solubility, and ability to form tough and flexible films [29].

Optically active PAIs were successfully synthesised in an IL, namely, 1,3-dipropylimidazolium bromide ([dpim][Br]), using triphenyl phosphite (TPP) (a condensing agent) without any additional extra components such as LiCl and pyridine. Therefore, it was concluded that ILs not only act as solvents, but also act as catalysts in this step polymerisation [30]. At the same time, various types of ILs were investigated as solvents and catalysts for the polymerisation of PAIs [31]. A PAI based on 2-[5-(3,5-dinitrophenyl)-1,3,4-oxadiazole-2-yl]pyridine was synthesised in [bmim][Br]. Heterocyclic and optically active PAIs incorporating L-amino acids were synthesised in [pmim][Br] [18, 32]. Shadpour et al. later reported several relative articles in succession. For example, organosoluble and optically active PAIs bearing an S-valine moiety were synthesised by the step polymerisation of different aliphatic and aromatic diisocyanates with a chiral diacid monomer in tetrabutylammonium bromide (TBAB) IL. These polymers exhibited good thermal properties and were soluble in amide-type solvents [33]. The poly(amide-ether-imide-urea)s (PAEIU)s were synthesised by the step polymerisation of a chiral diamine with several diisocyanates in [dpim][Br] IL [34]. Heat-stable and optically active processable PAI nanostructures bearing a hydroxyl pendant group were synthesised by step polymerisation in the presence of IL and TPP [35]. In recent years, using TBAB IL/TPP and ultrasonic irradiation, optically active PAI/TiO₂ bio-NCs containing N-trimellitylimido-L-isoleucine linkages, poly(vinyl alcohol) (PVA) with chiral PI nanoparticles containing S-valine, and optically active PAI/zinc oxide bio-NCs (PAI/ZnO BNCs) containing L-valine were obtained one after the other [36–38].

2.1.2 Synthesis of PSFs in ILs

In 1965, PSF was first successfully developed and commercialised by Union Carbide, USA, currently known as Udel PSF. Usually, the number-average molecular weights of commercial products are in the range of 16,000–35,000, and the weight-average molecular weights are in the range of 35,000–80,000 [6]. They are well known for their outstanding thermal stability, good mechanical properties, electrical properties, transparency and resistance to most chemicals. They are widely used in various modern industries such as electrical/electronics, machineries, medical equipment, transportation and aerospace, and membrane separation technologies [39–42]. In recent studies, PSFs were mainly studied in

the development of membrane technologies such as hemodialysis, micro-/ultra-filtration membrane and gas separation. PSFs are usually synthesised via nucleophilic aromatic substitution polymerisation (S_NAR) reactions [43]. For example, bisphenol-A PSF is synthesised from 2,2-bis(4-hydroxyphenyl) propane (bisphenol A) and 4,4'-dichlorodiphenylsulphone (DCDPS) or 4,4'-difluorodiphenylsulphone (DFDPS). Poly(ether sulphone)s (PESs) are usually synthesised from 4,4'-dihydroxydiphenylsulphone (bisphenol-S) and DCDPS/DFDPS [13].

Liu's research group is one of the most active research groups in this field. In 2012, high-molecular-weight PSFs were synthesised in high yields by step polymerisation of bisphenol A with DFDPS for the first time in various ILs/zwitterions (ZIs) as the reaction media in the presence of potassium carbonate (K_2CO_3) using a one-pot green protocol shown in **Figure 3**. In this work, the dehydration time was shortened to 80% (2.5–8 to 0.5 h) compared to the conventional methods, and the weight-average molecular weights ranged from 30,000 to 130,000, with great potential for commercial applications. The polarity of ILs strongly affected the molecular weight of PSF, and ILs containing PF_6^- were better [6]. Recently, PESs were also successfully synthesised by the step polymerisation of bisphenol S with DFDPS in ILs/ZIs as the reaction media in the presence of K_2CO_3 using a one-pot green protocol. The dehydration time was shortened to 0.5 h compared to the conventional methods, and a high solubility of bisphenol-s dipotassium salt in IL/ZI significantly lowered the reaction temperature (150°C) than the conventional temperature (220 – 300°C). The proposed method has clear advantages for synthesising PSF and PES compared to volatile organic solvents and, in principle, can be applied to the synthesis of other HPPs via nucleophilic aromatic substitution polymerisation reactions [13]. In 2017, the synthesis of poly(phenylene sulphide sulphone) (PPSS) in ILs was presented [44].

2.1.3 Synthesis of PAEKs in ILs

PAEK was reported by Bonner of Du Pont, USA, in 1962 and Goodman of Imperial Chemical Industries (ICI), UK, but the molecular weight of products synthesised was the lower. Until 1979, Rose et al. of ICI reported that PEK with a high molecular weight was synthesised, laying the foundation for the synthesis of PAEK. Commercially available as VICTREX® PEEK™, it was introduced into the market by ICI. Poly(ether ether ketone) (PEEK) is one of the most recently developed materials. PAEKs exhibit many outstanding characteristics including high thermal stability, excellent mechanical, thermo-oxidative, and chemical resistance

Figure 3.
Synthetic route for PSF in IL/ZI and structures of ILs and ZI.

properties under diverse conditions, and good electrical insulation [45, 46]. The PAEK applications span across automotive, aerospace or chemical industries, orthopaedics and surgery, cable insulation, and membrane technologies. In addition, high temperatures, intense mechanical stress, and/or exposure to harsh chemical environments are required; thus, PAEK can be a lightweight replacement for metals.

In 2013, PAEKs were successfully synthesised via S_NAR mechanism using ILs [*i*-pmim][PF₆] as the green reaction media. The optimised step polymerisation conditions were 50 wt% monomer concentration, dehydration at 150°C for 0.5 h and polymerisation at 180°C for further 1.5 h. The number-average molecular weights of PAEKs ranged from 10,000 to 18,000 g mol⁻¹ with high yields. In addition, the interactions of bisphenol A with ILs were investigated, exhibiting a strong influence on the PAEK synthesis [11]. In the same year, PEEKs were also synthesised in IL [bmim][Tf₂N], by polycondensation reactions of hydroquinone with 4,4'-dihalo-benzophenones in the presence of K₂CO₃ at 320°C. The materials produced in IL were similar to those produced in the industrial solvent of choice, but the molecular weights were lower, possibly due to the lower solubility of the polymer. The advantage of using IL [bmim][Tf₂N] over diphenyl sulphone as the solvent is that the separation efficiency significantly improved [3]. It is expected that more custom-designed ILs would be used for PAEK production, potentially widening the scope of the choice of solvents currently used.

2.1.4 Synthesis of HPPs in ILs under microwave irradiation

Microwave (MW) is a type of electromagnetic wave with frequency ranging from 300 MHz to 300 GHz, usually 2450 MHz for radiation chemical reaction; the temperature of the system depends on the power of MW and electrical properties of the medium. MW radiation can accelerate the reaction rate for a specific system and complete these reactions within a short period. Thus, as a non-conventional energy source, MW radiation has become an increasingly more practical and popular technology in organic chemistry, including polymerisation. Owing to their high ionic conductivity and polarisability, ILs act as excellent MW-absorbing agents and are, therefore, used in polymerisation. Mallakpour's research group is one of the most active research groups in this field. In 2007, poly(urea-urethane)s (PUU)s were prepared using IL 1,3-diallylimidazolium bromide and tetrabutyl-ammonium bromide (TBAB) under MW irradiation as well as conventional heating. The polymerisation reactions occurred rapidly, producing a series of PUUs in good yields and with moderate inherent viscosities of 0.21–0.46 dL/g. These PUUs showed a good solubility and could be readily dissolved in traditional organic solvents [47].

MW-assisted synthesis can provide higher yields and purer products than traditional heating; therefore, recently, MW radiation has been used for the synthesis of HPPs, especially PAIs. In 2010, poly(urethane-imide)s (PUIs) were prepared in the presence of IL TBAB under MW irradiation conditions. All the PUIs showed thermal stability and good solubility in various organic solvents. In *in vitro* toxicity studies, the prepared materials showed biological activity and non-toxicity to microbial growth and were classified as bioactive and biodegradable compounds [48]. In 2012, chiral-nanostructured PAIs were synthesised in TBAB IL under MW irradiation by the polymerisation reactions of several amino-acid-based chiral diacids with an aromatic diamine, 2-(3,5-diaminophenyl)-benzimidazole. The PAIs obtained were organo soluble, and the HPPs were obtained in high yields and with inherent viscosities in the range 0.40–0.52 dL/g. The materials synthesised were amorphous polymers with nanostructures containing nanosized particles in the range from 40 to 80 nm [49]. Chiral-PAI-nanostructures-bearing hydroxyphenyl pendant units in the side chain were also prepared using TBAB IL and TPP as the

condensing agent under MW irradiation. The obtained PAIs had inherent viscosities in the range 0.32–0.49 dL/g; they were amorphous polymers with nanostructures in which the nanosized particles are in the range from 66 to 78 nm [50]. Soluble, thermally stable PAIs modified with siloxane linkages with a reduced dielectric constant were synthesised via the isocyanate method in TBAB, tetrabutyl-phosphonium bromide (TBPB), and 1-butyl-3-methyl imidazolium chloride ([bmim][Cl]) under MW irradiation [51].

2.2 ILs as monomers for chemical modification of HPPs

In 2010, Li et al. reported that block co-PIs based on aromatic dianhydrides and diamines copolymerised with diamino IL monomers, specifically 1,3-di(3-aminopropyl) imidazolium bis[(trifluoromethyl)sulphonyl]imide ([DAPIM]-[Tf₂N]) and 1,12-di[3-(3-aminopropyl)imidazolium]dodecane bis[(trifluoromethyl)sulphonyl]imide ([C₁₂(DAPIM)₂][Tf₂N]₂), as shown in **Figure 4**, were synthesised by the Boc protection method and using diverse compositions. These two ILs were first reacted with 2,2-bis(3,4-carboxylphenyl)hexafluoropropane dianhydride (6FDA) to produce 6FDA-IL oligomers as the IL component for block co-PIs. Later, the oligomers were reacted with 6FDA and *m*-phenylenediamine (MDA) at an oligomer concentration from 6.5 to 25.8 mol% to form block co-PIs. As the concentration of 6FDA-IL oligomer increased in the block co-PIs, the thermal degradation temperature and glass transition temperature of the produced co-PIs decreased, but their density increased. Compared to pure 6FDA-MDA, the gas permeability of the IL-based block co-PI decreased, but the ideal permeability selectivity for CO₂/CH₄ gas pair increased [52]. The co-PIs were mainly used in the separation of gases such as O₂, N₂, CH₄ and CO₂ [53, 54].

Later, a series of poly(arylene ether sulphone)s containing bulky imidazole groups (PSf-Im-*x*) based on a monomer 2,2'-bis-(2-ethyl-4-methylimidazole-1-ylmethyl)-biphenyl-4,4'-diol (EMIPO) were successfully synthesised. After the quaternisation by *n*-bromobutane, these polymers were evaluated as alkaline anion exchange membranes (AEMs) as shown in **Figure 5**. 2-Ethyl-3-butyl-4-methylimidazolium was introduced as the functional group in these polymers; the bulky groups present around the imidazolium ring reduced the access of OH[−] to imidazolium, thus increasing the alkaline stability of the membranes. The membrane showed an IEC value of 2.07 and ionic (OH[−]) conductivity of 0.014 S cm^{−1} at 30°C, in which 80% of the ionic conductivity was maintained even for the treatment in 1 M KOH at 60°C for 144 h [12].

Figure 4.

Structures of monomers used in polyimide synthesis: (a) bis[(trifluoromethyl)sulphonyl]imide ([Tf₂N]), (b) 2,2-bis(3,4-carboxylphenyl)hexafluoropropane dianhydride (6FDA), *m*-phenylenediamine (MDA), (c) 1,3-di(3-aminopropyl)imidazolium bis[(trifluoromethyl)sulphonyl]imide ([DAPIM][Tf₂N]), and (d) 1,12-di[3-(3-aminopropyl)imidazolium]dodecane bis[(trifluoromethyl)sulphonyl]imide ([C₁₂(DAPIM)₂][Tf₂N]₂).

Figure 5.
 Synthetic routes of PSf-Im-*x* and PSf-ImmOH-*x*.

Recently, a new synthetic method was reported for the modification of PIs; the PIs were first transformed to their ionic forms via the subsequent *N*-alkylation and quaternisation of benzimidazole or quinuclidine moieties; then, an ion exchange reaction was carried out to prepare polymers bearing the bis(trifluoro-methylsulphonyl)imide anion. High-molecular-weight ($M_n = 22,000\text{--}97,000$) cationic polyelectrolytes with the degree of quaternisation as high as 96% were obtained under the optimal conditions. These new materials showed excellent mechanical and thermal properties, adjustable surface wettability, and improved gas transport properties [55]. Several recent articles reported that the incorporation of IL moieties into HPP by copolymerisation is a promising strategy to prepare novel copolymers of ILs with HPPs with improved properties. It is presumed that further related work will be reported in the future.

2.3 ILs as additives for physical processing of HPPs

The application of ILs for HPPs is not limited to their use as reaction media in polymerisations for preparing HPPs, and ILs are miscible with some HPPs and used as additives in the materials such as the components of polymer materials, plasticizers, and porogenic agents. By blending ILs with HPPs, the properties of the obtained mixtures can be considerably affected [56]. Thus, applications of ILs are being explored in the fields of membranes, microcapsules, electrolytes, NCs and grease.

2.3.1 Membrane

Supported IL materials have two main processes. First, ILs are covalently linked to polymers, inorganic surfaces or particles, thereby supporting the IL materials. In such systems, the properties of the ILs are modified to some extent, but generally,

the main features are retained. Second, ILs are dissolved and imbibed in a polymeric membrane, porous matrix, particle or bulk material as the components of the mixture, and the properties of the IL are retained [57]. In recent years, supported IL membranes (SILMs) have received considerable attention for their applications in gas separation, electrolyte, proton exchange, etc.

Early on, it was reported that ILs based on 1-*n*-alkyl-3-methylimidazolium cation (*n*-butyl, *n*-octyl, and *n*-decyl) can be used together with the anions PF_6^- or BF_4^- . Immobilisation of these ILs on a polyvinylidene fluoride (PVDF) membrane provides an extremely highly selective transport for secondary amines over tertiary amines [58]. Later, the PVDF/ILs composite membranes were prepared. A membrane using [emim][Tf₂N] and PVDF hollow fibre was prepared as a support for CO₂/N₂ separation [59].

A quasi-solid-state dye-sensitised solar cell based on poly(vinylidene fluoride-co-hexafluoro-propylene) P(VDF-HFP)/SBA-15 nanocomposite membranes was obtained using dimethyl-propylimidazolium iodide (DMPII) IL [60]. The SILM was prepared using a hydrophilic PVDF support immobilised in the IL 1-butyl-2,3-dimethylimidazolium hexafluorophosphate ([*bdmim*][PF₆]) [61]. The preparation of PVDF-blended membranes with dominating β -phase crystals was studied in ILs 1-butyl-3-methylimidazolium tetrafluoroborate ([bmim]BF₄), [bmim][PF₆] and 1-methylimidazolium trifluoromethanesulphonic ([mim]CF₃SO₃) as the co-solvents for zwitterionic copolymers [62]. A PVDF membrane with piezoelectric β -form was prepared by immersion precipitation in mixed solvents containing an IL [bmim][BF₄] [63]. Composite membranes were prepared as electroactive actuators using PVDF and [emim][Tf₂N] as the plasticiser [64]. A 1-butyl-3-methylimidazolium triflate ([bmim]OTf)/PVDF composite membrane was prepared by the impregnation method and used for the separation of C₆H₆/H₂ and C₆H₁₂/H₂, as shown in **Figure 6** [65]. Thin films containing 1-ethyl-3-methylimidazolium nitrate ([emim][NO₃]) IL and PVDF were investigated [66]. Another HFP-containing fluorine, polytetrafluoroethylene (PTFE), was often prepared using an SILM. For example, gelled SILMs were synthesised by the gelation of [bmim][PF₆] in the pores of PTFE hollow fibres and used in the separation of butanol from acetone-butanol-ethanol mixtures (ABE) by sweep gas pervaporation [67]. Amino-acid-IL-based-facilitated transport membranes containing PTFE were prepared via impregnation [68].

The SILMs prepared with PSF supports are often used for CO₂ separation such as CO₂/He, CO₂/CH₄ and CO₂/N₂ separation, even at elevated temperatures [69–71]. In addition, ion-conductive membranes were prepared by casting a solution of Udel-type PSF and IL 1-butyl-3-methylimidazolium trifluoromethane-sulphonate ([bmim][TfO]) or 1-ethylimidazolium trifluoromethanesulphonate ([eim][TfO]) [72]. The SILMs prepared with PES supports are frequently used in the separation of gases, especially SO₂ [73, 74] and CO₂ [75–78]. In addition, PES membranes with ion exchange and anti-biofouling properties were prepared by the surface immobilisation of Brønsted acidic ILs via double-click reactions [79]. A sulphonated PES (SPES) film containing ILs was obtained by solution casting and prepared using double-side, self-cleaning polymeric materials, as shown in **Figure 7** [80]. Hydrophilic porous PES membranes and microcapsules were prepared via non-solvent-induced phase separation (NIPS) using IL [bmim][PF₆] as the structure control agent [81].

The surface wettability of negatively charged PI films was tuned by the electrostatic self-assembly of ILs and formation of spherical nanoparticles, indicating the assembly of longer-substituent cations [82]. The membranes containing ILs prepared with PI supports were often used in gas separation [83–86] and fuel cells [87–89]. In addition, available PAIs [90], copolymers of poly(ethylene glycol) (PEG) and aromatic PI [91, 92], and SPI [93–95] were also used in the preparation

Figure 6.
Photographs (a and b) and SEM images (c and d) of the PVDF membrane before (a and c) and after impregnation (b and d) with [bmim] OTf.

Figure 7.
Picture and schematic of the final material.

of membranes containing ILs. For example, SPI/IL composite membranes as proton-exchange membranes have been reported in recent years [96, 97].

Composite membranes based on sulphonated poly(ether ether)ketone (SPEEK) with ILs [CH₃CH₂CH₂NH₃][CF₃COO] (TFAPA), [bmim][Cl] and [bmim][PF₆] have been prepared [98, 99]. Composite membranes have been prepared using SPEEK ILs in the presence of Y₂O₃ [100].

2.3.2 Microcapsule

In 2007, monodispersed microcapsules enclosing [bmim][PF₆] were prepared via a two-stage microfluidic approach, as shown in **Figure 8**; the hollow PSF microcapsules showed an encapsulation capacity of 30.8% [101]. PSF microcapsules containing

Figure 8.

Optical microscopic images and composition of organic phase is PSF: dichloromethane (DCM): [bmim] PF₆ = 5 g: 80 ml: 3 g; continuous phase is 0.1 wt% gelatin solution; inner size of nozzle: 0.6 mm, IL microcapsules, flow rate of continuous phases (CP): 30 ml/min; and flow rate of droplet phases (DP): 125 μl/min.

[bmim][PF₆] were also obtained by spraying a suspension dispersion with an encapsulation capacity of 29% [102]. PSF microcapsules have practical use such as the removal of caprolactam from water [103]. PEEK microcapsules containing trihexyl(tetradecyl) phosphonium chloride IL was obtained in *N,N*-dimethylformamide (DMF) as the dispersing phase and dodecane [104]. PTFE microcapsules containing [hmim][Tf₂N] IL lubricant with small sizes (below 10 μm) have been reported [105].

2.3.3 Electrolyte

ILs have also been used as solvents in extraction processes or as electrolytes. Polymer electrolytes comprising IL [emim][Tf₂N] and soluble SPI showed a high ionic conductivity and reliable mechanical strength, suitable for HPP actuators [106]. Gel polymer electrolytes (GPEs) [107–109] and solid polymer electrolytes [110–114] have been widely reported. A series of GPEs were prepared using the electrospun membranes of poly(vinylidene fluoride-co-hexafluoropropylene) [P(VdF-co-HFP)] incorporating ILs, 1-alkyl-3-methylimidazolium bis(trifluoromethylsulphonyl)imide in the presence of lithium bis(trifluoromethylsulphonyl)imide (LiTf₂N) [115]. An IL-GPE containing semi-crystal PVDF, amorphous polyvinyl acetate (PVAc) and ionic conductive [bmim][BF₄] was prepared via the solution-casting method for solid supercapacitors [116]. A PVDF-HFP/PMMA-blended microporous gel polymer electrolyte incorporating [bmim][BF₄] was fabricated for lithium-ion batteries [117]. Solid polymer electrolytes using poly(vinylidene-fluoridetrifluoroethylene) and *N,N,N*-trimethyl-*N*-(2-hydroxyethyl) ammonium bis(trifluoromethylsulphonyl)imide ([N₁₁₁₂(OH)] [Tf₂N]) IL were fabricated for energy storage applications [118]. PI/IL composite membranes for fuel cells operating at high temperatures were prepared by impregnating a porous Matrimid® membrane with protic ILs: 1-*n*-methyl-imidazolium dibutylphosphate ([C₁im][DBP]), 1-*n*-butylimidazolium dibutyl-phosphate ([C₄im][DBP]) and 1-*n*-butylimidazolium bis(2-ethylhexyl)phosphate ([C₄im][BEHP]). The electrolyte membranes were used as a proton-exchange membrane fuel cell (PEMFC) [119]. An IL-polymer electrolyte film based on a low-viscosity IL (1-ethyl-3-methylimidazolium dicyanamide) incorporated into a polymer matrix

(PVDF-HFP) was prepared, exhibiting liquid-like conductivity, and the maximum conductivity of PVDF-HFP + 25 wt% IL was as high as 10^{-3} S/cm, as shown in **Figure 9** [120]. Quasi-solid-state electrolytes (QSEs) consisting of IL-LiTf₂N-fumed silica nanoparticles were prepared for use in bulk-type all-solid-state cell configuration lithium-sulphur rechargeable batteries [121].

2.3.4 Nanocomposite

Carbon nanotubes (CNTs) consist of rolled-up graphene sheets and can be used as electronic, conductive and reinforcing fillers for polymer composites. MWCNTs possess a nanoscale diameter, a high aspect ratio, excellent mechanical properties, and good electrical conductivity. In recent years, MWCNTs have gained considerable interests of scientists and engineers, especially in polymer composites containing HPPs and ILs. A PI composite film comprising finely IL-dispersed MWCNTs in IL was obtained with a high shielding effectiveness (SE) for use in the packaging of a 2.5-Gbps plastic transceiver module with numerous applications in fibre to the home lightwave transmission systems [122]. PEI NCs consisting of bucky gels of industrial-grade MWCNTs and [bmim][PF₆] were prepared; they are suitable for the aerospace and electronics industries, as shown in **Figure 10** [123]. Some PI and PEI NCs consisting of MWCNTs and polymerised ILs (PILs) were prepared, exhibiting differential function [124, 125].

The crystal structure of PVDF was modified by utilising the long alkyl chains of [C₁₆mim][Br] and IL-modified MWCNTs, and the crystallisation kinetics of the composites was investigated [126, 127]. A series of PVDF composites with 'bucky gels' of MWNTs and ILs were obtained by simple melt compounding. According to the DSC and XRD results, the addition of ILs in the composites changed the crystallinity and crystal form of the PVDF [128]. PTFT and PVDF as the components of NCs containing HPP and ILs have received increasingly more attention. The nanomaterials with a nanoscale structure were prepared using pyridinium, imidazolium and phosphonium ILs as new synthetic building blocks in a PTFT. The cation-anion combination and functionalisation of ILs affect the ionic networks and nanostructures of materials [129, 130]. These nanomaterials show optimised thermal and mechanical properties and have numerous potential applications such as supercritical CO₂ [131]. PVDF/IL/GraNCs were fabricated via the solution casting of PVDF with graphene (Gra) modified with a long alkyl chain IL [C₁₆mim][Br], exhibiting a low loss tangent and low conductivity in the PVDF/ionic liquid-modified graphene

Figure 9. Photograph of (a) assemble DSSC and (b) I-V characteristics of DSSC comprising IL-incorporated PVDF-HFP polymer electrolyte film (maximum conductivity).

Figure 10.

Processing of PEI/bucky gel nanocomposites; the obtained composites had good toughness as the film could be curved adequately without any damage.

(GIL) composites [132, 133]. NCs, based on a homopolymer PVDF and IL, were fabricated, and the preparation process opens up a new synthesis route for nanostructured polymer composites. Dielectric NCs based on PVDF, conductive carbon black (CB) and IL 1-vinyl-3-ethylimidazolium tetrafluoroborate [VEM][BF₄] were prepared via melt blending and electron beam irradiation (EBI) methods [134].

A nanostructured PAI was prepared in TBAB as a green medium by the step polymerisation reaction of 4,4'-methylenebis(3-chloro-2,6-diethyl trimellitimidobenzene) with 3,5-diamino-*N*-(4-hydroxy-phenyl)benzamide. Then, amino acid-functionalised multiwalled carbon nanotubes (f-MWCNTs)/PAI NCs were prepared by a solution mixing method [30].

2.3.5 Grease

In 2012, two types of conductive lubricating greases consisting of ILs (abbreviated as 'ILs lubricating greases') and HPPs were synthesised using 1-octyl-3-methylimidazolium hexafluorophosphate ([omim][PF₆]) (L-P108) and 1-octyl-3-methylimidazolium tetrafluoroborate ([omim][BF₄]) (LB108) as the base oil and PTFE as the thickener, exhibiting higher conductivities than the traditional conductive lubricating greases containing conductive stuffing, as shown in **Figure 11** [135]. The conductive lubricating greases using 1-hexyl-3-methylimidazolium tetrafluoroborate ([hmim][BF₄]) and 1-hexyl-3-methylimidazolium bis(trifluoromethylsulphonyl)amide ([hmim][Tf₂N]) were prepared, and the conductivity and tribological performance of these greases were studied [136, 137]. By changing the type of ILs, different types of conductive lubricating greases were obtained [138].

In addition, the materials obtained by the blending of ILs with HPPs also include IL marbles containing PTFE and IL [139], PAI hollow fibre containing [bmim]

Figure 11.

The photo images of the IL lubricating greases and poly- α -olefin (PAO) grease: PAO10 (abbreviate as 'PAO lubricating grease') (a) L-P108 (b) and LB108 (c).

[Tf₂N] [140], IL-coated PTFE tube [141], PVDF/IL functionalised graphene oxide (GO-IL) composite (PGL) films [142] and electro-active electrospun fibre containing PVDF and [bmim][Tf₂N] [143]. For the materials obtained by the blending of ILs with HPPs, ILs based on imidazole and PF₆⁻ and Tf₂N⁻ are most often used [144, 145]. PVDF, PSF and PI are the most popular [44, 146–148].

3. Conclusions

Studies on ILs as the reaction media, monomers and additives in the synthesis, chemical modification and physical processing of HPPs are in progress. In 2017, the synthesis of poly(phenylene sulphide sulphone) (PPSS) in ILs was also presented. ILs are not only interesting as a replacement for traditional volatile and flammable organic solvents, but also have the potential to reduce energy consumption and increase chemical reactivity, thus leading to more efficient processes for the synthesis of HPPs. Using ILs in the synthesis of HPPs, promising and novel established approaches have been developed under mild conditions. Owing to their high ionic conductivity and polarisability, ILs, as excellent MW-absorbing agents, were introduced to polymerisation reactions to achieve higher yields and purer products than the traditional heating method. Notably, the number of novel copolymers of HPPs with polymerisable ILs has steadily increased in recent years, and they were mainly used in separating gases such as O₂, N₂, CH₄ and CO₂. ILs are not only used as reaction media in polymerisations for preparing HPPs and as monomers in the chemical modifications of HPPs, but also ILs are miscible with some HPPs and used as various types of additives (such as the components of polymer materials, plasticizers and porogenic agents) in the physical processing of HPPs. The materials prepared include membranes, microcapsules, electrolytes, NCs and grease. HPPs and inorganic substrates have been used to support IL materials by the covalent bonding of ILs, where the properties of ILs may be changed to some extent, and HPP membranes and NC-absorbed ILs exhibit concomitant changes in ionic conductivity and mobility. These novel green chemical approaches provide diverse possible new materials, and it is expected that more modified materials of HPPs and ILs with special properties and applications would be obtained. It is believed that more studies on ILs containing HPPs will be reported in the future.

Acknowledgements

The authors would like to acknowledge the National Science Foundation of China (grant no. 21274014), Beijing Municipal Commission of Education, the

Fundamental Research Funds for the Central Universities, and the Measuring Fund of Large Apparatus of Beijing Normal University for their financial support.

IntechOpen

IntechOpen

Author details

Dan He, Zhengping Liu* and Liyan Huang
Beijing Key Laboratory of Materials for Energy Conversion and Storage,
BNU Key Lab of Environmentally Friendly and Functional Polymer Materials,
College of Chemistry, Beijing Normal University, Beijing, PR China

*Address all correspondence to: lzp@bnu.edu.cn

IntechOpen

© 2019 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/3.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

References

- [1] Weber CC, Masters AF, Maschmeyer T. Structural features of ionic liquids: Consequences for material preparation and organic reactivity. *Green Chemistry*. 2013;**15**(10):2655-2679
- [2] Kubisa P. Ionic liquids as solvents for polymerisation processes—Progress and challenges. *Progress in Polymer Science*. 2009;**34**(12):1333-1347
- [3] Gunaratne HQN, Langrick CR, Puga AV, et al. Production of polyetheretherketone in ionic liquid media. *Green Chemistry*. 2013;**15**(5):1166-1172
- [4] Earle MJ, Esperan AJSS, Gilea MA, et al. The distillation and volatility of ionic liquids. *Nature*. 2006;**439**(7078):831-834
- [5] Chowdhury S, Mohan RS, Scott JL. Reactivity of ionic liquids. *Tetrahedron*. 2007;**63**(11):2363-2389
- [6] Wang J, Liu Z. An efficient synthetic strategy for high performance polysulfone: Ionic liquid/zwitterion as reaction medium. *Green Chemistry*. 2012;**14**(11):3204-3210
- [7] De Leon AC, Chen Q, Palaganas NB, et al. High performance polymer nanocomposites for additive manufacturing applications. *Reactive and Functional Polymers*. 2016;**103**:141-155
- [8] Mittal V. *High Performance Polymers and Engineering Plastics*. John Wiley & Sons, Inc. Front Matter [M]; 2011. p. i-xix
- [9] Nakamura M, Ishida H. Synthesis and properties of new crosslinkable telechelics with benzoxazine moiety at the chain end. *Polymer*. 2009;**50**(12):2688-2695
- [10] Vygodskii YS, Lozinskaya EI, Shaplov AS. Ionic liquids as novel reaction media for the synthesis of condensation polymers. *Macromolecular Rapid Communications*. 2002;**23**(12):676-680
- [11] Wang J, Liu Z. Ionic liquids as green reaction media for synthesis of poly(aryl ether ketone)s. *Chinese Science Bulletin*. 2013;**58**(11):1262-1266
- [12] Yang Y, Wang J, Zheng J, et al. A stable anion exchange membrane based on imidazolium salt for alkaline fuel cell. *Journal of Membrane Science*. 2014;**467**:48-55
- [13] Wang J, Wu Y, Liu Z-P. A facile and highly efficient protocol for synthesis of poly(ether sulfone)s in ionic liquid/zwitterion. *Chinese Journal of Polymer Science*. 2016;**34**(8):981-990
- [14] Wilson D, Stenzenberger H-D, Hergenrother P-M. *Polyimides*. New York: Blackie; 1990
- [15] Liou GS, Maruyama M, Kakimoto MA, et al. Preparation and properties of new soluble aromatic polyimides from 2,2'-bis(3,4-dicarboxyphenoxy) biphenyl dianhydride and aromatic diamines. *Journal of Polymer Science Part A: Polymer Chemistry*. 1998;**36**(12):2021-2027
- [16] Liaw D-J, Liaw B-Y. Synthesis and properties of polyimides derived from 3,3',5,5'-tetramethyl-bis[4-(4-aminophenoxy)phenyl] sulfone. *European Polymer Journal*. 1997;**33**(9):1423-1431
- [17] Yoneyama M, Matsui Y. Direct polycondensation of aromatic tetracarboxylic acids with aromatic diamines in ionic liquids. *High Performance Polymers*. 2006;**18**(5):817-823

- [18] Mansoori Y, Atghia SV, Sanaei SS, et al. New, organo-soluble, thermally stable aromatic polyimides and poly(amide-imide) based on 2-[5-(3,5-dinitrophenyl)-1,3,4-oxadiazole-2-yl]pyridine. *Polymer International*. 2012;**61**(7):1213-1220
- [19] Kricheldorf HR, Schwarz G, Fan S-C. Cyclic polyimides—A comparison of synthetic methods. *High Performance Polymers*. 2004;**16**(4):543-555
- [20] Vygodskii YS, Lozinskaya EI, Shaplov AS, et al. Implementation of ionic liquids as activating media for polycondensation processes. *Polymer*. 2004;**45**(15):5031-5045
- [21] Lozinskaya EI, Shaplov AS, Vygodskii YS. Direct polycondensation in ionic liquids. *European Polymer Journal*. 2004;**40**(9):2065-2075
- [22] Tsuda Y, Yoshida T, Kakoi T. Synthesis of soluble polyimides based on alicyclic dianhydride in ionic liquids. *Polymer Journal*. 2006;**38**(1):88-90
- [23] Chen M, Wang S. Non-thermal polyimidization reaction using base-ionic liquid medium as a dual catalyst-solvent. *RSC Advances*. 2016;**6**(99):96914-96917
- [24] Tamada M, Hayashi T, Ohno H. Improved solubilization of pyromellitic dianhydride and 4,4'-oxydianiline in ionic liquid by the addition of zwitterion and their polycondensation. *Tetrahedron Letters*. 2007;**48**(9):1553-1557
- [25] Alici BK, Koytepe S, Seckin T. Synthesis of piperazine based polyimide in the presence of ionic liquids. *Turkish Journal of Chemistry*. 2007;**31**(6):569-578
- [26] Frank H, Ziener U, Landfester K. Formation of polyimide nanoparticles in Heterophase with an ionic liquid as continuous phase. *Macromolecules*. 2009;**42**(20):7846-7853
- [27] Akbarian-Feizi L, Mehdipour-Ataei S, Yeganeh H. Synthesis of new sulfonated copolyimides in organic and ionic liquid media for fuel cell application. *Journal of Applied Polymer Science*. 2012;**124**(3):1981-1992
- [28] Akbarian-Feizi L, Mehdipour-Ataei S, Yeganeh H. Investigation on the preparation of new Sulfonated polyimide fuel cell membranes in organic and ionic liquid media. *International Journal of Polymeric Materials*. 2014;**63**(3):149-160
- [29] Ghaemy M, Hassanzadeh M, Taghavi M, et al. Synthesis and characterization of trifluoromethylated poly(ether-imidazole-imide)s based on unsymmetrical diamine bearing carbazole and imidazole chromophores in ionic liquids: Study of electrochemical properties by using nanocomposite electrode. *Journal of Fluorine Chemistry*. 2012;**142**:29-40
- [30] Mallakpour S, Kowsari E. Ionic liquids as novel solvents and catalysts for the direct polycondensation of N,N'-(4,4'-oxydiphthaloyl)-bis-L-phenylalanine diacid with various aromatic diamines. *Journal of Polymer Science Part A: Polymer Chemistry*. 2005;**43**(24):6545-6553
- [31] Mallakpour S, Abdolmaleki A, Rostami M. Hybrid S-valine functionalized multi-walled carbon nanotubes/poly(amid-imide) nanocomposites containing trimellitimidebenzene and 4-hydroxyphenyl benzamide moieties: Preparation, processing, and thermal properties. *Journal of Materials Science*. 2014;**49**(21):7445-7453
- [32] Zahmatkesh S. Ionic liquid catalyzed synthesis and characterization of heterocyclic and optically active poly

(amide-imide)s incorporating l-amino acids. *Amino Acids*. 2011;**40**(2):533-542

[33] Mallakpour S, Khania M. Synthesis and characterization of poly(amide-imide)s bearing a S-Valine moiety in molten ionic liquid. *Designed Monomers & Polymers*. 2011;**14**(3):221-232

[34] Mallakpour S. Synthesis of soluble poly(amide-ether-imide-urea)s bearing amino acid moieties in the main chain under green media (ionic liquid). *Amino Acids*. 2011;**40**(2):487-492

[35] Mallakpour S, Zadehnazari A. Synthesis and characterization of novel heat stable and Processable optically active poly(amide-imide) nanostructures bearing hydroxyl pendant group in an ionic green medium. *Journal of Polymers and the Environment*. 2013;**21**(1):132-140

[36] Mallakpour S, Barati A. Preparation and characterization of optically active poly(amide-imide)/TiO₂ bionanocomposites containing N-trimellitylimido-L-isoleucine linkages: Using ionic liquid and ultrasonic irradiation. *Journal of Polymer Research*. 2012;**19**(2):1-8

[37] Mallakpour S, Dinari M. Reinforcement of poly(vinyl alcohol) with chiral poly(amide-imide)s nanoparticles containing S-valine under simple ultrasonic irradiation method. *Colloid and Polymer Science*. 2013;**291**(10):2487-2494

[38] Mallakpour S, Ahmadizadegan H. Manufacture of zinc oxide/chiral poly(amide-imide)-functionalized amino acid and thiazole bionanocomposites: Using ionic liquid and ultrasonic irradiation. *Journal of Thermoplastic Composite Materials*. 2015;**28**(5):672-685

[39] Xie W, Ju H, Geise GM, et al. Effect of free volume on water and salt transport properties in

directly copolymerized disulfonated poly(arylene ether sulfone) random copolymers. *Macromolecules*. 2011;**44**(11):4428-4438

[40] Chen Y, Lee CH, Rowlett JR, et al. Synthesis and characterization of multiblock semi-crystalline hydrophobic poly(ether ether ketone)-hydrophilic disulfonated poly(arylene ether sulfone) copolymers for proton exchange membranes. *Polymer*. 2012;**53**(15):3143-3153

[41] Wang J, Xu Y, Zhu L, et al. Amphiphilic ABA copolymers used for surface modification of polysulfone membranes. Part 1: Molecular design, synthesis, and characterization. *Polymer*. 2008;**49**(15):3256-3264

[42] Temtem M, Pompeu D, Barroso T, et al. Development and characterization of a thermoresponsive polysulfone membrane using an environmental friendly technology. *Green Chemistry*. 2009;**11**(5):638-645

[43] Percec V, Clough RS, Rinaldi PL, et al. Termination by reductive elimination in the polyetherification of bis(aryl chlorides) activated by carbonyl groups, with bisphenolates. *Macromolecules*. 1991;**24**(21):5889-5892

[44] He D, Wu Y, Liu Z, et al. The synthesis of poly(phenylene sulfide sulfone) in ionic liquids at atmospheric pressure. *RSC Advances*. 2017;**7**(63):39604-39610

[45] Perng LH, Tsai CJ, Ling YC. Mechanism and kinetic modelling of PEEK pyrolysis by TG/MS. *Polymer*. 1999;**40**(26):7321-7329

[46] Roelofs KS, Hirth T, Schiestel T. Sulfonated poly(ether ether ketone)-based silica nanocomposite membranes for direct ethanol fuel cells. *Journal of Membrane Science*. 2010;**346**(1):215-226

- [47] Mallakpour S, Rafiee Z. Efficient combination of ionic liquids and microwave irradiation as a green protocol for polycondensation of 4-(3-hydroxynaphthalene)-1,2,4-triazolidine-3,5-dione with diisocyanates. *Polymer*. 2007;**48**(19):5530-5540
- [48] Mallakpour S, Tirgir F, Sabzalian MR. Novel biobased polyurethanes synthesized from nontoxic phenolic diol containing l-tyrosine moiety under green media. *Journal of Polymers and the Environment*. 2010;**18**(4):685-695
- [49] Mallakpour S, Dinari M. Straightforward and green method for the synthesis of nanostructure poly(amide-imide)s-containing benzimidazole and amino acid moieties by microwave irradiation. *Polymer Bulletin*. 2013;**70**(3):1049-1064
- [50] Mallakpour S, Zadehnazari A. Microwave-assisted synthesis and morphological characterization of chiral poly(amide-imide) nanostructures in molten ionic liquid salt. *Advances in Polymer Technology*. 2013;**32**(1):21333
- [51] Rafiemanzelat F, Khoshfetrat SM, Kolahdoozan M. Fast and eco-friendly synthesis of novel soluble thermally stable poly(amide-imide)s modified with siloxane linkage with reduced dielectric constant under microwave irradiation in TBAB, TBPB and MeBuImCl via isocyanate method. *Journal of Applied Polymer Science*. 2013;**127**(4):2371-2379
- [52] Li P, Zhao Q, Anderson JL, et al. Synthesis of copolyimides based on room temperature ionic liquid diamines. *Journal of Polymer Science Part A: Polymer Chemistry*. 2010;**48**(18):4036-4046
- [53] Li P, Coleman MR. Synthesis of room temperature ionic liquids based random copolyimides for gas separation applications. *European Polymer Journal*. 2013;**49**(2):482-491
- [54] Zhang C, Cao B, Coleman MR, et al. Gas transport properties in (6FDA-RTIL)-(6FDA-MDA) block copolyimides. *Journal of Applied Polymer Science*. 2016;**133**:43077
- [55] Shaplov AS, Morozova SM, Lozinskaya EI, et al. Turning into poly(ionic liquid)s as a tool for polyimide modification: Synthesis, characterization and CO₂ separation properties. *Polymer Chemistry*. 2016;**7**(3):580-591
- [56] Kubisa P. Ionic liquids in the synthesis and modification of polymers. *Journal of Polymer Science Part A: Polymer Chemistry*. 2005;**43**(20):4675-4683
- [57] Lu J, Yan F, Texter J. Advanced applications of ionic liquids in polymer science. *Progress in Polymer Science*. 2009;**34**(5):431-448
- [58] Branco LC, Crespo JG, Afonso CAM. Studies on the selective transport of organic compounds by using ionic liquids as novel supported liquid membranes. *Chemistry—A European Journal*. 2002;**8**(17):3865-3871
- [59] Kim D-H, Baek I-H, Hong S-U, et al. Study on immobilized liquid membrane using ionic liquid and PVDF hollow fiber as a support for CO₂/N₂ separation. *Journal of Membrane Science*. 2011;**372**(1-2):346-354
- [60] Yang C-C, Wey J-Y, Liou T-H, et al. A quasi solid state dye-sensitized solar cell based on poly(vinylidene fluoride-co-hexafluoropropylene)/SBA-15 nanocomposite membrane. *Materials Chemistry and Physics*. 2012;**132**(2-3):431-437
- [61] Pilli SR, Banerjee T, Mohanty K. 1-Butyl-2,3-dimethylimidazolium hexafluorophosphate as a green solvent

for the extraction of endosulfan from aqueous solution using supported liquid membrane. *Chemical Engineering Journal*. 2014;**257**:56-65

[62] Yi Z, Zhu L-P, Zhang H, et al. Ionic liquids as co-solvents for zwitterionic copolymers and the preparation of poly(vinylidene fluoride) blend membranes with dominated β -phase crystals. *Polymer*. 2014;**55**(11):2688-2696

[63] Li C, Zhu Y, Lv R, et al. Poly(vinylidene fluoride) membrane with piezoelectric β -form prepared by immersion precipitation from mixed solvents containing an ionic liquid. *Journal of Applied Polymer Science*. 2014;**131**:40505

[64] Dias JC, Lopes AC, Magalh ESB, et al. High performance electromechanical actuators based on ionic liquid/poly(vinylidene fluoride). *Polymer Testing*. 2015;**48**:199-205

[65] Hirota Y, Maeda Y, Nishiyama N, et al. Separation of C_6H_6 and C_6H_{12} from H_2 using ionic liquid/PVDF composite membrane. *AIChE Journal*. 2016;**62**(3):624-628

[66] Frübing P, Wang F-P, Kühle T-F, Gerhard R. AC and DC conductivity of ionic liquid containing polyvinylidene fluoride thin films. *Applied Physics A*. 2016;**122**(1):1-10

[67] Plaza A, Merlet G, Hasanoglu A, et al. Separation of butanol from ABE mixtures by sweep gas pervaporation using a supported gelled ionic liquid membrane: Analysis of transport phenomena and selectivity. *Journal of Membrane Science*. 2013;**444**:201-212

[68] Kasahara S, Kamio E, Matsuyama H. Improvements in the CO_2 permeation selectivities of amino acid ionic liquid-based facilitated transport membranes by controlling their gas absorption properties. *Journal of Membrane Science*. 2014;**454**:155-162

[69] Ilconich J, Myers C, Pennline H, et al. Experimental investigation of the permeability and selectivity of supported ionic liquid membranes for CO_2/He separation at temperatures up to $125^\circ C$. *Journal of Membrane Science*. 2007;**298**(1-2):41-47

[70] Yoo S, Won J, Kang SW, et al. CO_2 separation membranes using ionic liquids in a Nafion matrix. *Journal of Membrane Science*. 2010;**363**(1-2):72-79

[71] Dai Z, Bai L, Hval KN, et al. Pebax®/TSIL blend thin film composite membranes for CO_2 separation. *Science China Chemistry*. 2016;**59**(5):538-546

[72] Schauer J, Sikora A, Pliškov M, et al. Ion-conductive polymer membranes containing 1-butyl-3-methylimidazolium trifluoromethanesulfonate and 1-ethylimidazolium trifluoromethanesulfonate. *Journal of Membrane Science*. 2011;**367**(1-2):332-339

[73] Jiang Y-Y, Zhou Z, Jiao Z, et al. SO_2 gas separation using supported ionic liquid membranes. *The Journal of Physical Chemistry B*. 2007;**111**(19):5058-5061

[74] Jiang Y, Wu Y, Wang W, et al. Permeability and selectivity of sulfur dioxide and carbon dioxide in supported ionic liquid membranes. *Chinese Journal of Chemical Engineering*. 2009;**17**(4):594-601

[75] Zhao W, He G, Zhang L, et al. Effect of water in ionic liquid on the separation performance of supported ionic liquid membrane for CO_2/N_2 . *Journal of Membrane Science*. 2010;**350**(1-2):279-285

[76] Zhao W, He G, Nie F, et al. Membrane liquid loss mechanism of supported ionic liquid membrane for gas separation. *Journal of Membrane Science*. 2012;**411-412**:73-80

- [77] Lan W, Li S, Xu J, et al. Preparation and carbon dioxide separation performance of a hollow fiber supported ionic liquid membrane. *Industrial & Engineering Chemistry Research*. 2013;**52**(20):6770-6777
- [78] Mohshim DF, Mukhtar H, Man Z. The effect of incorporating ionic liquid into polyethersulfone-SAPO34 based mixed matrix membrane on CO₂ gas separation performance. *Separation and Purification Technology*. 2014;**135**:252-258
- [79] Yi Z, Liu C-J, Zhu L-P, et al. Ion exchange and antibiofouling properties of poly(ether sulfone) membranes prepared by the surface immobilization of brønsted acidic ionic liquids via double-click reactions. *Langmuir*. 2015;**31**(29):7970-7979
- [80] Soliveri G, Sabatini V, Farina H, et al. Double side self-cleaning polymeric materials: The hydrophobic and photoactive approach. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2015;**483**:285-291
- [81] Lakshmi DS, Cundari T, Furia E, et al. Preparation of polymeric membranes and microcapsules using an ionic liquid as morphology control additive. *Macromolecular Symposia*. 2015;**357**(1):159-167
- [82] Zhao Y, Li M, Lu Q. Tunable wettability of polyimide films based on electrostatic self-assembly of ionic liquids. *Langmuir*. 2008;**24**(8):3937-3943
- [83] Shindo R, Kishida M, Sawa H, et al. Characterization and gas permeation properties of polyimide/ZSM-5 zeolite composite membranes containing ionic liquid. *Journal of Membrane Science*. 2014;**454**:330-338
- [84] Nancarrow P, Liang L, Gan Q. Composite ionic liquid-polymer-catalyst membranes for reactive separation of hydrogen from carbon monoxide. *Journal of Membrane Science*. 2014;**472**:222-231
- [85] Nagase Y, Suleimenova B, Umeda C, et al. Syntheses of aromatic polymers containing imidazolium moiety and the surface modification of a highly gas permeable membrane using the nanosheets. *Polymer*. 2018;**135**:142-153
- [86] Abedini A, Crabtree E, Bara JE, et al. Molecular simulation of ionic polyimides and composites with ionic liquids as gas-separation membranes. *Langmuir*. 2017;**33**(42):11377-11389
- [87] Deligöz H, Yılmazoğlu M, Yilmaztürk S, Şahin Y, Ulutaş K. Synthesis and characterization of anhydrous conducting polyimide/ionic liquid complex membranes via a new route for high-temperature fuel cells. *Polymers for Advanced Technologies*. 2012;**23**(8):1156-1165
- [88] Kiatkittikul P, Nohira T, Hagiwara R. Advantages of a polyimide membrane support in nonhumidified fluorohydrogenate-polymer composite membrane fuel cells. *Fuel Cells*. 2015;**15**(4):604-609
- [89] Pang H-W, Yu H-F, Huang Y-J, et al. Electrospun membranes of imidazole-grafted PVDF-HFP polymeric ionic liquids for highly efficient quasi-solid-state dye-sensitized solar cells. *Journal of Materials Chemistry A*. 2018;**6**(29):14215-14223
- [90] Xing DY, Chan SY, Chung T-S. Fabrication of porous and interconnected PBI/P84 ultrafiltration membranes using [EMIM]OAc as the green solvent. *Chemical Engineering Science*. 2013;**87**:194-203
- [91] Coletta E, Toney MF, Frank CW. Impacts of polymer-polymer interactions and interfaces on the structure and conductivity

of PEG-containing polyimides doped with ionic liquid. *Polymer*. 2014;**55**(26):6883-6895

[92] Coletta E, Toney MF, Frank CW. Effects of aromatic regularity on the structure and conductivity of polyimide-poly(ethylene glycol) materials doped with ionic liquid. *Journal of Polymer Science Part B: Polymer Physics*. 2015;**53**(7):509-521

[93] Lee S-Y, Yasuda T, Watanabe M. Fabrication of protic ionic liquid/sulfonated polyimide composite membranes for non-humidified fuel cells. *Journal of Power Sources*. 2010;**195**(18):5909-5914

[94] Delig ZH, Yilmazoglu M. Development of a new highly conductive and thermomechanically stable complex membrane based on sulfonated polyimide/ionic liquid for high temperature anhydrous fuel cells. *Journal of Power Sources*. 2011;**196**(7):3496-3502

[95] Yasuda T, Nakamura S-I, Honda Y, et al. Effects of polymer structure on properties of sulfonated polyimide/protic ionic liquid composite membranes for nonhumidified fuel cell applications. *ACS Applied Materials & Interfaces*. 2012;**4**(3):1783-1790

[96] Chen B-K, Wu T-Y, Kuo C-W, et al. 4,4'-Oxydianiline (ODA) containing sulfonated polyimide/protic ionic liquid composite membranes for anhydrous proton conduction. *International Journal of Hydrogen Energy*. 2013;**38**(26):11321-11330

[97] Kowsari E, Zare A, Ansari V. Phosphoric acid-doped ionic liquid-functionalized graphene oxide/sulfonated polyimide composites as proton exchange membrane. *International Journal of Hydrogen Energy*. 2015;**40**(40):13964-13978

[98] Che Q, Sun B, He R. Preparation and characterization of new anhydrous,

conducting membranes based on composites of ionic liquid trifluoroacetic propylamine and polymers of sulfonated poly(ether ether) ketone or polyvinylidene fluoride. *Electrochimica Acta*. 2008;**53**(13):4428-4434

[99] Che Q, He R, Yang J, et al. Phosphoric acid doped high temperature proton exchange membranes based on sulfonated polyetheretherketone incorporated with ionic liquids. *Electrochemistry Communications*. 2010;**12**(5):647-649

[100] Li D, Guo Q, Zhai W, et al. Research on properties of SPEEK based proton exchange membranes doped with ionic liquids and Y_2O_3 in different humidity. *Procedia Engineering*. 2012;**36**:34-40

[101] Yang WW, Lu YC, Xiang ZY, et al. Monodispersed microcapsules enclosing ionic liquid of 1-butyl-3-methylimidazolium hexafluorophosphate. *Reactive and Functional Polymers*. 2007;**67**(1):81-86

[102] Gao H, Xing J, Xiong X, et al. Immobilization of ionic liquid [BMIM][PF₆] by spraying suspension dispersion method. *Industrial & Engineering Chemistry Research*. 2008;**47**(13):4414-4417

[103] Chen D-X, Ouyang X-K, Wang Y-G, et al. Adsorption of caprolactam from aqueous solution by novel polysulfone microcapsules containing [Bmim][PF₆]. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2014;**441**:72-76

[104] Shanthana Lakshmi D, Figoli A, Fiorani G, et al. Preparation and characterization of ionic liquid polymer microspheres [PEEKWC/DMF/CYPHOS IL 101] using the phase-inversion technique. *Separation and Purification Technology*. 2012;**97**:179-185

- [105] Bandeira P, Monteiro J, Baptista AM, et al. Tribological performance of PTFE-based coating modified with microencapsulated [HMIM][NTf2] ionic liquid. *Tribology Letters*. 2015;**59**(1):1-15
- [106] Imaizumi S, Ohtsuki Y, Yasuda T, et al. Printable polymer actuators from ionic liquid, soluble polyimide, and ubiquitous carbon materials. *ACS Applied Materials & Interfaces*. 2013;**5**(13):6307-6315
- [107] Tigelaar DM, Palker AE, Meador MAB, et al. Synthesis and compatibility of ionic liquid containing rod-coil polyimide gel electrolytes with lithium metal electrodes. *Journal of the Electrochemical Society*. 2008;**155**(10):A768-A774
- [108] Chaurasiask S, Singh RK, et al. Electrical, mechanical, structural, and thermal behaviors of polymeric gel electrolyte membranes of poly(vinylidene fluoride-co-hexafluoropropylene) with the ionic liquid 1-butyl-3-methylimidazolium tetrafluoroborate plus lithium tetrafluoroborate. *Journal of Applied Polymer Science*. 2015;**132**(7):41456
- [109] Dong Z, Zhang Q, Yu C, et al. Effect of ionic liquid on the properties of poly(vinylidene fluoride)-based gel polymer electrolytes. *Ionics*. 2013;**19**(11):1587-1593
- [110] Kuo P-L, Tsao C-H, Hsu C-H, et al. A new strategy for preparing oligomeric ionic liquid gel polymer electrolytes for high-performance and nonflammable lithium ion batteries. *Journal of Membrane Science*. 2016;**499**:462-469
- [111] Wen X, Dong T, Liu A, et al. A new solid-state electrolyte based on polymeric ionic liquid for high-performance supercapacitor. *Ionics*. 2018;**25**(1):241-251
- [112] Chen N, Xing Y, Wang L, et al. "Tai Chi" philosophy driven rigid-flexible hybrid ionogel electrolyte for high-performance lithium battery. *Nano Energy*. 2018;**47**:35-42
- [113] Yang HM, Kwon YK, Lee SB, et al. Physically cross-linked homopolymer ion gels for high performance electrolyte-gated transistors. *ACS Applied Materials & Interfaces*. 2017;**9**(10):8813-8818
- [114] Karuppasamy K, Reddy PA, Srinivas G, et al. An efficient way to achieve high ionic conductivity and electrochemical stability of safer nonaflate anion-based ionic liquid gel polymer electrolytes (ILGPEs) for rechargeable lithium ion batteries. *Journal of Solid State Electrochemistry*. 2016;**21**(4):1145-1155
- [115] Raghavan P, Zhao X, Choi H, et al. Electrochemical characterization of poly(vinylidene fluoride-co-hexafluoropropylene) based electrospun gel polymer electrolytes incorporating room temperature ionic liquids as green electrolytes for lithium batteries. *Solid State Ionics*. 2014;**262**:77-82
- [116] Yang L, Hu J, Lei G, et al. Ionic liquid-gelled polyvinylidene fluoride/polyvinyl acetate polymer electrolyte for solid supercapacitor. *Chemical Engineering Journal*. 2014;**258**:320-326
- [117] Zhai W, Zhu H-J, Wang L, et al. Study of PVDF-HFP/PMMA blended micro-porous gel polymer electrolyte incorporating ionic liquid [BMIM]BF₄ for Lithium ion batteries. *Electrochimica Acta*. 2014;**133**:623-630
- [118] Leones R, Costa CM, Machado AV, et al. Development of solid polymer electrolytes based on poly(vinylidene fluoride-trifluoroethylene) and the [N1 1 1 2(OH)][NTf2] ionic liquid for energy storage applications. *Solid State Ionics*. 2013;**253**:143-150
- [119] Dahi A, Fatyeyeva K, Langevin D, et al. Polyimide/ionic liquid composite

membranes for fuel cells operating at high temperatures. *Electrochimica Acta*. 2014;**130**:830-840

[120] Nawaz A, Sharif R, Rhee H-W, et al. Efficient dye sensitized solar cell and supercapacitor using 1-ethyl 3-methyl imidazolium dicyanamide incorporated PVDF-HFP polymer matrix. *Journal of Industrial and Engineering Chemistry*. 2016;**33**:381-384

[121] Unemoto A, Ogawa H, Gambe Y, et al. Development of lithium-sulfur batteries using room temperature ionic liquid-based quasi-solid-state electrolytes. *Electrochimica Acta*. 2014;**125**:386-394

[122] Chang CM, Chiu JC, Lan YF, et al. High electromagnetic shielding of a 2.5-Gbps plastic transceiver module using dispersive multiwall carbon nanotubes. *Journal of Lightwave Technology*. 2008;**26**(10):1256-1262

[123] Chen Y, Tao J, Deng L, et al. Polyetherimide/Bucky gels nanocomposites with superior conductivity and thermal stability. *ACS Applied Materials & Interfaces*. 2013;**5**(15):7478-7484

[124] Cardiano P, Fazio E, Lazzara G, et al. Highly untangled multiwalled carbon nanotube@polyhedral oligomeric silsesquioxane ionic hybrids: Synthesis, characterization and nonlinear optical properties. *Carbon*. 2015;**86**:325-337

[125] Tunckol M, Hernandez EZ, Sarasua J-R, et al. Polymerized ionic liquid functionalized multi-walled carbon nanotubes/polyetherimide composites. *European Polymer Journal*. 2013;**49**(12):3770-3777

[126] Bahader A, Gui H, Li Y, et al. Crystallization kinetics of PVDF filled with multi wall carbon nanotubes modified by amphiphilic ionic

liquid. *Macromolecular Research*. 2015;**23**(3):273-283

[127] Xing C, Zhao L, You J, et al. Impact of ionic liquid-modified multiwalled carbon nanotubes on the crystallization behavior of poly(vinylidene fluoride). *The Journal of Physical Chemistry B*. 2012;**116**(28):8312-8320

[128] Chen GX, Zhang S, Zhou Z, et al. Dielectric properties of poly(vinylidene fluoride) composites based on Bucky gels of carbon nanotubes with ionic liquids. *Polymer Composites*. 2015;**36**(1):94-101

[129] Livi S, Duchet-Rumeau J, Gerard J-F. Nanostructuration of ionic liquids in fluorinated matrix: Influence on the mechanical properties. *Polymer*. 2011;**52**(7):1523-1531

[130] Livi S, Duchet-Rumeau J, Gerard J-F. Application of supercritical CO₂ and ionic liquids for the preparation of fluorinated nanocomposites. *Journal of Colloid and Interface Science*. 2012;**369**(1):111-116

[131] Tiago G, Restolho J, Forte A, et al. Novel ionic liquids for interfacial and tribological applications. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2015;**472**:1-8

[132] Hu Y, Xu P, Gui H, et al. Effect of graphene modified by a long alkyl chain ionic liquid on crystallization kinetics behavior of poly(vinylidene fluoride). *RSC Advances*. 2015;**5**(112):92418-92427

[133] Xu P, Gui H, Wang X, et al. Improved dielectric properties of nanocomposites based on polyvinylidene fluoride and ionic liquid-functionalized graphene. *Composites Science and Technology*. 2015;**117**:282-288

[134] Xing C, Wang Y, Huang X, et al. Poly(vinylidene fluoride) nanocomposites with simultaneous

- organic nanodomains and inorganic nanoparticles. *Macromolecules*. 2016;**49**(3):1026-1035
- [135] Wang Z, Xia Y, Liu Z, et al. Conductive lubricating grease synthesized using the ionic liquid. *Tribology Letters*. 2012;**46**(1):33-42
- [136] Fan X, Wang L. Highly conductive ionic liquids toward high-performance space-lubricating greases. *ACS Applied Materials & Interfaces*. 2014;**6**(16):14660-14671
- [137] Fan X, Xia Y, Wang L. Tribological properties of conductive lubricating greases. *Friction*. 2014;**2**(4):343-353
- [138] Fan X, Xia Y, Wang L, et al. Study of the conductivity and tribological performance of ionic liquid and lithium greases. *Tribology Letters*. 2014;**53**(1):281-291
- [139] Gao L. Ionic liquid marbles. *Langmuir*. 2007;**23**(21):10445-10447
- [140] Lee JS, Hillesheim PC, Huang D, et al. Hollow fiber-supported designer ionic liquid sponges for post-combustion CO₂ scrubbing. *Polymer*. 2012;**53**(25):5806-5815
- [141] Stanis E, Werner J, Matusiewicz H. Task specific ionic liquid-coated PTFE tube for solid-phase microextraction prior to chemical and photo-induced mercury cold vapour generation. *Microchemical Journal*. 2014;**114**:229-237
- [142] Maity N, Mandal A, Nandi AK. Interface engineering of ionic liquid integrated graphene in poly(vinylidene fluoride) matrix yielding magnificent improvement in mechanical, electrical and dielectric properties. *Polymer*. 2015;**65**:154-167
- [143] Dias JC, Correia DC, Lopes AC, et al. Development of poly(vinylidene fluoride)/ionic liquid electrospun fibers for tissue engineering applications. *Journal of Materials Science*. 2016;**51**(9):4442-4450
- [144] Tu X, Zhang Y, Zhao T, et al. Rheological behavior of polyarylsulfone 1-Butyl-3-methylimidazolium chloride solutions. *Journal of Macromolecular Science: Physics*. 2006;**45**(4):665-669
- [145] Xing C, Zhao M, Zhao L, et al. Ionic liquid modified poly(vinylidene fluoride): Crystalline structures, miscibility, and physical properties. *Polymer Chemistry*. 2013;**4**(24):5726-5734
- [146] Zhu Y, Li C, Na B, et al. Polar phase formation and competition in the melt crystallization of poly(vinylidene fluoride) containing an ionic liquid. *Materials Chemistry and Physics*. 2014;**144**(1-2):194-198
- [147] Soares BG, Pontes K, Marins JA, et al. Poly(vinylidene fluoride-co-hexafluoropropylene)/polyaniline blends assisted by phosphonium-based ionic liquid: Dielectric properties and β -phase formation. *European Polymer Journal*. 2015;**73**:65-74
- [148] Qi H, Guo Y, Zhang L, et al. Covalently attached mesoporous silica-ionic liquid hybrid nanomaterial as water lubrication additives for polymer-metal tribopair. *Tribology International*. 2018;**119**:721-730