We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Biochar-Assisted Wastewater Treatment and Waste Valorization

Abhishek Pokharel, Bishnu Acharya and Aitazaz Farooque

Abstract

Biochar is the solid byproduct of pyrolysis, and its cascading use can offset the cost of the production and its use in application such as soil remediation. A wide variety of research on biochar has highlighted its ability to absorb nutrients, metal and complex compounds, filter suspended solids, enhance microorganisms' growth, retain water and nutrients as well as increasing the carbon content of the soil. Besides, sustainable biochar systems are an attractive approach for carbon sequestration and total waste management cycle. The chapter looks into such cascading use of biochar in wastewater treatment for recovering nutrients and improving the efficiency of activated sludge treatment and anaerobic digestion for producing biosolid with enhanced soil amendment properties.

Keywords: biochar, wastewater treatment, activated sludge treatment, anaerobic digestion, nutrient recovery, waste valorization

1. Introduction

Today, the global population continues to grow by 83 million annually and is predicted to be 9.8 billion in 2050 [1]. This increase in population will lead to higher demands of food, water, and energy, which have already been constrained due to the competing needs for limited resources in many parts of the world [2]. The challenges presented by climate change, pollution, and developing economy are posing significant pressure on food, water, and energy systems [3]. Efficient and integrated management of energy, food, and water resources could help address several of the biggest global challenges, such as climate change, sustainable economy, food security, environmental and social security [4, 5]. In the future, we will need increased food production, clear water sources, as well as alternative energy options with minimum resource utilization and ideally decreasing environmental impacts [6]. Work is underway to improve the food production chain as well as develop new technologies for renewable energy. So far less focus has been given to the water, especially to the management of the wastewater. There is a need for shifting the paradigm in the case of wastewater management from treatment and disposal to reuse, recycle, and resource recovery. With growing water scarcity and the fact that uncontrolled disposal of wastewater to the freshwater system is causing depletion of the system also stresses toward a change in mindset about wastewater management. This approach will prevent detrimental impacts on human health and ecosystem caused by the current handling methods. The next step toward a sustainable future will be wastewater treatment serving multiple purposes of treatment and recovery of resources like water, nutrient, and energy. The efficient wastewater management approach will see

a cascaded benefit in other sectors including production of fertilizers such as nitrogen and phosphorus. Phosphorus is obtained from ore called phosphate rocks. The quality and accessibility of currently available phosphate rock reserves are declining, and the cost to mine, refine, store, and transport them is rising [7, 8]. Similarly, the production of nitrogen and other mineral fertilizers is energy intensive as well as contributes to environmental pollution [3, 9]. The nitrogen fertilizer can leach to nearby water bodies leading to the phenomenon of eutrophication. The richness of nutrients in the water results in excessive growth of macroalgae and could lead to anoxic events and loss of aquatic system. Recovery of these nutrients from wastewater helps to close the cycle and reduce the amount of chemical fertilizer, directly contributing to the sustainability of food production.

One of the first indications of intentional nutrient recycling is documented 5000 years ago in rural Asia, where human excreta was used for fertilization of fields called “night soil” [10]. In the nineteenth and twentieth century with the industrial revolution, the population density became high, which gave rise to “Sanitation Revolution,” a transition from land-based to water-based disposal of human wastes. This disposal system changed the nutrient cycle from reuse to complete discard. Following the Industrial and Sanitation Revolutions, the Green Revolution that reformed agriculture largely abandoned organic fertilizers and put forth the mineral fertilizers [10, 11]. Furthermore, owing to the excessive population growth, producing enough food with only organic sources of plant nutrients has become impossible. Therefore, the need for mineral fertilizers is a true fact. Thus, many urban areas have dedicated wastewater treatment plant to remove the nuisance of human waste. But, it is becoming evident that future changes, particularly those associated with urbanization and population growth-related increase in volume of wastewater, add more stress to the wastewater system performance [12].

The greater dependency on fossil fuels in every sector is heavily contributing to global warming and climate change [13]. As an alternative, abundant biomass could play an essential role in reducing the dependency on fossil fuel as well as contribute toward sustainable development. Pyrolysis of biomass produces biochar and bio-oil. The bio-oil could be used as fuel to substitute the petroleum products with some upgrading that includes catalytic esterification and hydrogenation. The biochar could be used for energy and soil application [14]. Soil application helps in sequestration of carbon dioxide and subsequently supports food production. At present, the biochar application in soil remediation is not cost-effective. The financial feasibility could be improved by developing a cascaded use of biochar, as discussed in this chapter. The inherent properties of biochar make it suitable for (a) recovering nutrients from the wastewater, (b) improving the activated sludge treatment to reduce the energy use for aeration and to improve the settling ability of sludge, (c) increasing the energy recovery from sludge through anaerobic digestion, and (d) enhancing the quality of the biosolids for soil application. There are reports of biochar application having agronomic benefits in fertilizer management, yield, and soil biota [15–20]. Biochar, as a sound absorbent, also holds promise for low-cost wastewater treatment as an alternative to activated carbon [21–24]. The integrated use of biochar in wastewater treatment addresses the current issues with the management of wastewater. However, the benefit of using biochar varies with its type and characteristics, which depends on the biomass, and the pyrolysis conditions [25].

This chapter provides insights on the use of biochar in a wastewater treatment process to enhance the treatment as well as recover valuable byproducts. The chapter will discuss biochar production and properties, mechanisms involving removal of organic and inorganic compounds from the effluent phase, and role in activated sludge treatment and anaerobic digestion.

2. Biochar properties for wastewater treatment

Biochar is a carbon-rich solid material produced from biomass through a thermochemical process called pyrolysis. During pyrolysis, lignin, cellulose, hemicellulose, fat, and starch in the feedstock are thermally broken down forming three products: biochar (solid), bio-oil (partly condensed volatile matter), and non-condensable gases (CO_2 , CO , CH_4 , and H_2) [26, 27]. The bio-oil and gases can be captured to produce energy and depending on the feed valuable coproducts like wood preservatives, food flavoring, adhesive, or biochemical compounds [28]. The yield of biochar and the properties, however, depends on the pyrolysis condition. Slow pyrolysis at moderate temperature (350–500°C) and slow heating rate results in higher yield (30%) of biochar than around 10% or less yield with fast pyrolysis (600–700°C and fast heating rate) or gasification (temperature 700°C or above) [29]. The feedstock type and pyrolysis condition used during the production of biochar notably change the physiochemical properties such as surface area, polarity, atomic ratio, pH, and elemental composition [25, 30, 31]. These properties determine the effectiveness of biochar in wastewater treatment.

Biochar has wide applications in water and wastewater treatment because of its distinctive characteristics, for example, adsorption capacity, specific surface area, microporosity, and ion exchange capacity [30, 32]. The removal mechanisms of different pollutants are governed by their interactions with various attributes of biochar, which depends on pyrolysis temperature and feedstock type [33]. Pyrolysis temperature greatly affects the properties of biochar. The increase in pyrolysis temperature results in higher carbon content, hydrophobicity, aromaticity, surface area, and microporosity in biochar [34]. Similarly, the pH of the biochar increases with increasing pyrolysis temperature due to enrichment of ash content in the biochar [35, 36]. High-temperature (>500°C) biochar has low polarity and acidity due to loss of O- and H-containing functional groups [34]. Lower pyrolysis temperature (<500°C) facilitates partial carbonization, thus yielding biochar with smaller pore size, lower surface area, and high O-containing functional groups [36]. Lower temperature biochar contains a higher content of dissolved organic carbon, relatively low polarity and C/N ratio [30, 34, 37].

Biochar often compromises of both positively and negatively charged surfaces (zwitterionic) [34, 35]. The negatively charged functional groups contribute to cation exchange capacity (CEC) whereas anion exchange capacity (AEC) is also exhibited by O-containing functional groups (oxonium heterocycles) in biochar [36, 38]. Oxygen (O) containing alcohol, carbonyl, and carboxylate functional groups are generally believed to contribute to biochar cation exchange capacity because they carry a negative charge and serve as Lewis bases for the sorption of cations. Whereas, it is believed that oxonium functional groups contribute to pH-independent anion exchange and that both pyridinic functional groups and nonspecific proton adsorption by condensed aromatic rings contribute to pH-dependent anion exchange capacity in biochars [38].

Biochar derived from woody biomass and crop residues has a higher surface area compared to that of solid municipal wastes and animal manure [30]. Apart from the usual pyrolysis method, different engineering methods have been developed and used to expand biochar's applications. Engineered biochar is the derivative of biochar that is modified by physical, chemical, and biological methods to improve its physical, chemical, and biological properties (e.g., specific surface area, porosity, cation exchange capacity, surface functional group, pH etc.) and its adsorption capacity [37, 39, 40]. Some of the modification includes anaerobic digestion of feedstock before pyrolysis, steam/gas activation, pyrolysis using microwave heating, ball milling, magnetic modification, chemical modification using hydrogen

peroxide, alkali or acid, and impregnation/coating with chemicals [41]. The detail about the modified biochar for wastewater treatment will be discussed in the following sections.

2.1 Biochar modification

Researchers have discussed several methods for modifying the properties of biochar [42]. These methodologies include treatments with steam, acids, bases, metal oxides, carbonaceous materials, clay minerals, organic compounds, and biofilms [43].

2.1.1 Physical activation of biochar

Physical activation methods such as steam activation involve high-temperature steam forced through the pores of the biochar. Steam activation, which is carried out after pyrolysis, is a common modification method used to increase the structural porosity of the biochar and remove impurities such as products of incomplete combustion. According to [44], higher water flow rates and longer activation times at 800°C increased the sorption of Cd, Cu, and Zn on the surface of biochar from poultry manure feedstocks pyrolyzed at 700°C. In another study, comparison of Cu^{2+} adsorption for biochar from *Miscanthus* before (500°C pyrolysis) and after (800°C) steam activation showed no significant change [45]. It was found that steam activation of the biochar increased the surface area and aromaticity alongside a decrease in the abundance of functional groups [45]. Similarly, steam-activated biochar from pine sawdust increased the surface area but had little effect on the surface functional group as a result of which adsorption capacity of biochar for phosphate was reduced due to electrostatic repulsion by the negatively charged surface of biochar [46]. The steam-activated invasive plant (*Sicyos angulatus* L.)-derived biochar produced at 700°C showed 55% increase in sorption capacity of veterinary antibiotics (sulfamethazine) compared to that of nonactivated biochar produced at the same temperature [47]. Hence, steam activation could be a process for increasing the porosity and surface area of biochar along with aromaticity to obtain better adsorption of inorganic material in the wastewater.

2.1.2 Chemical activation using acidic and alkaline solutions

The biochar activation using acidic solutions forms carboxylic groups on the biochar surface [48] and develops micropores, thus increasing the surface area [49]. The increase of oxygenated functional groups on biochar surfaces increases the potential of biochar to bind positively charged pollutants through specific adsorption chemically. The pH dependence of Cu^{2+} sorption capacity for HNO_3 -activated cactus fiber biochar indicated chemical sorption on oxygen-containing functional groups on the biochar surface [48]. Higher O/C ratio in the post-activation of rice straw with H_2SO_4 and HNO_3 showed evidence of oxygen-containing functional group incorporated into the carbon structure [50]. Acid treatment of pine tree sawdust with diluted H_3PO_4 prior to pyrolysis increased the surface area, the total pore volume, and volume of micropores area along with P-O-P incorporation in the C structure [51]. This increased the Pb sorption capacity of the phosphoric-treated biochar by 20% in comparison to a nontreated sample, mainly due to phosphate precipitation and surface adsorption [51]. Similarly, almost double increase in cation exchange capacity was observed for pinewood biochar treated with 30% H_2O_2 because the oxygen-containing functional groups in the surface of biochar,

which were more abundant in the activated biochar, exchanged with cations in solution [52]. Treating a hydrochar, a carbon-enriched solid produced from hydrothermal carbonization of peanut hull, with a 10% H_2O_2 solution increased Pb sorption capacity compared to the unmodified hydrochar, which can be attributed to a greater abundance of carboxyl functional groups that can form complexes with Pb [53]. However, the introduction of acid or oxidizing agents dissolves mineral components (CO_3^{2-} , SiO_4^{2-} , PO_4^{3-}) in the biochar structure and removes them from the biochar matrix. These minerals in biochar are particularly important for the removal of metal cations from water due to precipitation [54], the affinity of which could be reduced by the acid treatment.

Activation of biochar using alkali (most commonly KOH and NaOH) increases adsorption by increasing porosity, surface and oxygenated functional group at the surface. Oxygenated functional groups provide proton-donating exchange sites where cation such as Pb^{2+} adsorbs chemically [55]. The activation of ipomoea plant biochar with KOH, followed by pyrolysis (350–550°C) demonstrated an increase adsorption of Cd from aqueous solution [56]. Further evidence of kinetics of sorption fitting a pseudo-second-order model and thermodynamic studies indicating spontaneous endothermic process showed that Cu sorption on KOH-activated biochar was due to chemical adsorption [57]. The adsorption capacity of As(V) on municipal solid waste biochar was increased by 1.3 times after activation with 2 M KOH [58]. It can be concluded that activation by alkali greatly enhanced the surface area and alteration of the functional group at the surface.

2.1.3 Biochar-based composites

The biochar composites are prepared by embedding different materials into the biochar structure pre- or post-pyrolysis. Generally, biochar has a higher surface area, high pH, and a negative surface charge. This facilitates specific adsorption of metal ions via oxygenated functional groups, electrostatic attraction to aromatic groups, and precipitation on the mineral ash components of the biochar. But at the same time biochar is usually a poor adsorbent for oxy-anions contaminants like NO_3^- , PO_4^{3-} , and AsO_4^{3-} [44]. This can be improved by the homogenous spread of metal oxide on biochar surfaces. It can be done by soaking biochars or the feed-stocks in a solution of metal nitrate or chloride salt solution (common examples FeCl_3 , Fe, $\text{Fe}(\text{NO}_3)_3$, and MgCl_2) and heated under atmospheric condition within a temperature range of 50–300°C. This process ensures removal of nitrite and chlorine leaving behind metals in the biochar matrix. Ca-, FeO-, and Fe^{3+} -modified biochar from soaked rice husk and municipal biomass in CaO, iron powder, and FeCl_3 respectively, increased the capability of biochar to remove As(V), but not as high for Cr(VI), from aqueous solution [59]. Taking into consideration that one of the main mechanisms for Cr(VI) removal is the electrostatic interaction to the positively charged functional groups on the surface of adsorbents, high Cr(VI) removal is observed at low pH values [60]. It is rather possible that the high pH values of the RH-Ca2p, RH-Fe0, and SW-Fe0 solutions are related to the deprotonation of their functional groups and the repelling of the negatively charged Cr(VI) [60]. Similarly, a 20-time increase in the sorption of As(V) was observed when corncob biochar was modified with $\text{Fe}(\text{NO}_3)_3$ [61]. Despite the lower surface area, modification of biochars from garden wood waste and wood chips as well as corncob showed the increased PO_4^{3-} sorption by a factor of 12–50% [58]. Further research has been carried out for preparing biochar-based composites by impregnation or coating the surface of the biochar with metal oxides of Al, Mn, and Mg [58]; clay minerals [62]; complex organic compounds, such as chitosan [63] or amino acids [64]; or inoculation with microorganisms [65].

Thus, the selection of biochar and modification methods for the application in wastewater treatment requires a considerable understanding of the biochar properties and mechanism by which it supports the treatment process at different stages of wastewater treatment.

3. Role of biochar use in wastewater treatment process

Biochar could be used at different stages of wastewater treatment (**Figure 1**) to improve the treatment efficiency and recovery of value-added byproducts. Biochar application in wastewater treatment could be governed by the mechanism of adsorption, buffering, and immobilization of microbial cells. If used on the treated effluents, suitably modified biochar could efficiently adsorb nutrients like nitrogen and phosphorus, which can later be used as a nutrient-enriched material for soil remediation. When used in the activated sludge treatment process, biochar could play a role for improving the treatment and settling ability of the sludge by adsorption of inhibitors and toxic compounds or provide a surface for immobilization of microbes. Addition of biochar in the biological system could eventually help to improve the soil amendment properties of the biosolid as well. As interest grows in the use of biochar in soil applications, its use in wastewater treatment could expand the value chain and create additional economic benefits [66]. The following section will discuss the role of biochar for various applications in the wastewater treatment plant.

3.1 Organic pollutant removal

In recent years, significant amount of research has been done to examine the application of biochar for removal of various organic compounds from water, which includes agrochemicals, antibiotics/drugs, polycyclic aromatic

Figure 1.
Use of biochar at different stages of wastewater treatment.

hydrocarbons (PAHs), volatile organic compounds or (VOCs), cationic aromatic dyes [67–70]. Similarly, removal of organic compounds present in specific waste streams such as estrogen compounds in animal manure and sewage, inhibitory compounds of biomass degradation (furfural, hydroxymethylfurfural, phenolic compounds), and toxic organic compounds in landfill leachate has been studied using biochar [71, 72]. **Figure 2** schematically shows different interactions of the organic pollutant with biochar.

Biochar produced at higher pyrolysis temperature is found better for removal of nonpolar organic compounds due to higher surface area and microporosity [30, 73]. In contrast, biochar produced at a temperature below 500°C contains more O- and H-containing functional groups; thus, they are likely to have a high affinity to polar organic compounds [26]. For example, rice husk and soybean-derived biochar (600–700°C) facilitates removal of nonpolar carbofuran (pesticide) and trichloromethylene (VOC) from contaminated water [26]. Efficient removal of pyrimethanil and diesopropylatrazine (fungicide/pesticide) was observed with red-gum wood chips and broiler litter-derived biochar at temperature >700°C, whereas the same biochar at temperature <500°C was inefficient [74, 75]. On the other hand, removal of polar insecticide and herbicide like 1-naphthol, norflurazon, and fluridone was observed with biochar produced at <300°C, due to interaction of pollutant and the functional groups of biochar [76, 77]. Likewise, higher sorption of aromatic cationic dyes like methyl-violet and methyl-blue was observed with biochar containing more O- and H-functional groups (<400°C) but the mechanism was highly dependent on pH [70, 78]. The sorption of polar antibiotic sulfamethazine (SMZ) by hardwood/softwood-derived biochars (produced at 300–700°C) has pH-dependent

Figure 2. Biochar interaction with organic and inorganic compounds in wastewater (adapted from Ahmad et al. [33]).

interactions [79]. It can be said that pH is the most important factor for biochar interactions and removal of polar organic pollutants.

3.2 Inorganic pollutant removal

Inorganic pollutant in wastewater includes heavy metals (Cr, Cu, Pb, Cd, Hg, Fe, Zn, and As ions) and compounds like nitrate (NO_3), nitrite (NO_2), ammonium (NH_4), phosphorus (P), and hydrogen sulfide (H_2S) that cause significant risk to public health and environment [80]. Biochar produced at lower pyrolysis temperature ($<500^\circ\text{C}$) has properties that are better suited for removal of inorganic compounds. The chemical composition and the morphological structure play an important role in the sorption nature of biochar [81]. **Figure 2** summarizes the interaction methods for inorganic pollutant and biochar.

3.2.1 Heavy metals

Biochar with high organic carbon content (at non-carbonized fraction), specific porous structure, and numerous functional groups interacts with heavy metals in many ways [82]. The sorption of heavy metals by biochar is mainly by surface interaction through ion exchange and complexation between biochar functional groups (e.g., OH, COOH, R-OH) and heavy metal ions [83, 84], moreover formation of metal precipitates with inorganic constituents [83–85] and coordination of metal ions with π electrons ($\text{C}=\text{C}$) of biochar [74]. The physiochemical properties of biochar affect the adsorption throughout its matrix and are dependent on pyrolysis temperature, feedstock type, pH, and application rate. Cu^{2+} showed high affinity toward COOH– and OH– groups of hardwood and crop-derived biochars with dependency on pH and feedstock types [86]. Similarly, sida hermaphrodita-, guayule shrub-, soybean straw-, and wheat straw-derived biochars were effective for removal of Cd^{2+} , Ni^{2+} , and Zn^{2+} along with Cu^{2+} [87]. The higher efficiency of the above-mentioned biochar was due to high C and O contents, high O/C molar ratio, and polarity index, which were mainly regulated by pH [88, 89]. Alkaline biochars derived from various agricultural residues (e.g., soybean straw, corncob, cocoa husk, corn stover, switchgrass) and manure were efficient for Hg^{2+} removal. Animal manure-derived and cocoa husk biochar was highly effective for Hg^{2+} removal due to high sulfur (SH groups and sulfate) to precipitate 90% of Hg^{2+} as $\text{Hg}(\text{OH})_2$ or HgCl_2 mainly through coprecipitation with anions (Cl, O, S) of biochar [73, 90].

For Cd^{2+} , Zn^{2+} , Pb^{2+} , and Cu^{2+} dosage of biochar also affects the removal of heavy metals. The higher removal efficiency is observed with increasing biochar loading in the aqueous system, due to increased pH and surface area with biochar addition [54, 91].

3.2.2 Nitrogen and phosphorus

The high surface charge density allows biochars to retain cations by cation exchange and the high surface area, internal porosity, and presence of both polar and nonpolar surface sites on biochar enable it to adsorb nutrients [92]. In the limited studies carried out without soil, biochar has shown the absorption NH_4^+ , NO_3^- , and PO_4^{3-} despite the different charges and properties of these nutrients [93]. Some examples include digested sugar beet tailing biochar pyrolyzed at 600°C that adsorbed PO_4 ions most likely in binding sites contained in colloidal and nano sized MgO particles on the biochar surface [94]. Also, orange peel biochars pyrolyzed between 250 and 700°C removed between 8 and 83% of phosphate from solution

[95]. NH_4 was adsorbed to biochars produced from rice husk [96] and a mixture of tree trunks and branches [97], albeit weakly, as the partitioning coefficients between water and biochar were low (Freundlich coefficients of 0.251 mg g^{-1}). Similarly, NO_3^- has been adsorbed to bamboo charcoal biochar in the concentration range of $0\text{--}10 \text{ mg L}^{-1}$ [98].

3.3 Activated sludge treatment

One of the most utilized systems for treatment of municipal wastewater is biological treatment process like activated sludge system (ASS) because of its cost-effectiveness and comparatively more straightforward operation to advance systems. Activated sludge process is a suspended growth treatment where aerobic microorganism decomposes the organic matter in wastewater, which eventually settles as solids by gravity. Currently, increasing concerns are being raised about the presence of various micro-pollutants from pharmaceuticals, personal care products (PCPs), pesticides, disinfectants, and antiseptic in domestic and municipal wastewaters. These pollutants are alien to the biota in the system, and the conventional treatment process often leads to inadequate removal of these compounds. Correspondingly, discharge requirements are currently being stringent for protection of receiving waters from possible contamination and public health hazard. There have been several modifications and changes in the activated sludge system to address the problem. One such method is AS-PACT (Activated Sludge with Powdered Activated Carbon Treatment) where powdered activated carbon is added to the aeration basin of activated sludge system. The larger surface area of carbon provides various benefits including adsorption of toxic substances such as pharmaceuticals and industrial chemicals, immobilization of bacteria, and increased sedimentation of activated sludge [99, 100]. Such system, however, requires a continuous makeup of fresh carbon [101].

Despite the benefits, the higher cost of activated carbon limits its use in municipal wastewater treatment [101]. The biochar could be a low-cost substitute to activated carbon [102], but its merits are less known. The addition of biochar to a biological treatment system, such as within the aeration tank, could result in increased process stability by (a) adsorption of inhibitors (heavy metals, polycyclic aromatic hydrocarbon), (b) increasing the buffering capacity of the system, and (c) immobilization of microbial cells [103]. Limited studies done on the use of biochar in the aeration tank showed increased settling ability of activated sludge [104]. Dissolved organic matter in the biochar could also provide additional carbon to promote denitrification [105]. The availability of organic matter, however, depends on the type of biomass and pyrolysis conditions used for producing biochar. Furthermore, the cascading benefits of using biochar in activated sludge treatment could also be seen on anaerobic digestion of the sludge and in the final quality of the biosolids.

3.4 Anaerobic digestion

In the case of anaerobic digestion, the addition of biochar has shown increases in the rate and amount of biogas production [106–108]. This is attributed to the buffering properties of biochar, promoting methanogenesis for higher biogas yield [109, 110]. Several studies have suggested increases in microbial metabolism and growth because of the support provided by the biochar [107, 111]. The biochar could also play a significant role in reducing the mobility or availability of the inhibitors like heavy metals, pesticides, antibiotics, and other organic compounds by binding them in its porous structure and maintain proper microbial activity for the

digestion process [103]. Further, the adsorption of nutrients in biochar and its slow release increase the availability of nutrients to the soil while preventing leaching to surrounding water bodies, as it is prevalent in the case of biosolids [103]. Therefore, the addition of biochar in the biological system could eventually help to improve the soil amendment properties of the biosolid as well.

4. Conclusion

Biochar is a unique renewable resource, which can be used in a wide variety of applications from addressing various environmental problems like climate change, remediation of pollutants in water and soil to an alternative fuel source. The cascading use of biochar as a byproduct of pyrolysis for wastewater treatment and nutrient recycling can synergistically improve soil and water quality, carbon sequestration, greenhouse gas emissions, nutrient cycling, and fuel crisis. The approach perfectly fits the ideas of the circular economy: reuse and recycle of waste, keeping material and product in use. This approach is connected with three natural cycles: water, carbon, and nutrient and has a direct impact on energy, water, and food systems. While much work has been done in modifying the biochar for adsorption of desired organic or inorganic compounds, very less is known on its application in activated sludge treatment, anaerobic digestion, and the overall quality of the biosolids. As the benefits of the integrated use of biochar in wastewater treatment to soil application is established in this chapter, future experimental research work could verify its effectiveness.

Conflict of interest

The authors declare no conflict of interest.

Nomenclature

CO ₂	carbon dioxide
CO	carbon monoxide
CH ₄	methane
H ₂	hydrogen
C	carbon
N	nitrogen
O	oxygen
Cu	copper
HNO ₃	nitric acid
H ₂ SO ₄	sulfuric acid
H ₃ PO ₄	phosphoric acid
Pb	lead
H ₂ O ₂	hydrogen peroxide
P	phosphorus
Ca	calcium
Mg	magnesium
K	potassium
Na	sodium
KOH	potassium hydroxide
NaOH	sodium hydroxide
Cd	cadmium

2M	2-molar concentration
As(V)	pentavalent arsenic
NO ₃ ⁻	nitrate
PO ₄ ³⁻	phosphate
AsO ₄ ³⁻	arsenate ion
FeCl ₃	ferric chloride
Fe	iron
Fe(NO ₃) ₃	ferric nitrate
MgCl ₂	magnesium chloride
Ca	calcium
FeO	ferrous oxide
Fe ³⁺	ferric ion
Cr(VI)	hexavalent chromium
Al	aluminum
Mn	manganese
Cr	chromium
Hg	mercury
Zn	zinc
As	arsenic
COOH-	carboxylic acid functional group
OH-	hydroxy functional group
R-OH	carbon chain with hydroxy functional group
Hg(OH) ₂	mercury hydroxide (bivalent)
S	sulfur
H ₂ S	hydrogen sulfide
Cl	chlorine
SH	sulfanyl or thiol
E ^{+/-}	ions of compound/element E
Abbreviations	
CEC	cation exchange capacity
AEC	anion exchange capacity
PAHs	polycyclic aromatic hydrocarbons
VOCs	volatile organic compounds
SMZ	sulfamethazine
AS-PACT	Activated Sludge-Powdered Activated Carbon Treatment

Author details

Abhishek Pokharel, Bishnu Acharya* and Aitazaz Farooque
Faculty of Sustainable Design Engineering, University of Prince Edward Island,
Charlottetown, Canada

*Address all correspondence to: bacharya@upei.ca

IntechOpen

© 2020 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/3.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

References

- [1] United Nations, Department of Economic and Social Affairs, Population Division. World Population Prospects: The 2017 Revision, Key Findings and Advance Tables. Working Paper No. ESA/P/WP/248. 2017
- [2] Godfray HCJ, Beddington JR, Crute IR, Haddad L, Lawrence D, Muir JF, et al. Food security: The challenge of feeding 9 billion people. *Science*. 2010;**327**(5967):812-818
- [3] de Amorim WS, Valduga IB, Ribeiro JMP, Williamson VG, Krauser GE, Magtoto MK, et al. The nexus between water, energy, and food in the context of the global risks: An analysis of the interactions between food, water, and energy security. *Environmental Impact Assessment Review*. 2018;**72**:1-11
- [4] Brandoni C, Bosnjakovic B. Energy, food and water nexus in the European Union: Towards a circular economy. *Proceedings of the Institution of Civil Engineers-Energy*. 2018;**171**(3):140-144
- [5] United Nation – General Assembly, Seventieth session. Resolution adopted by the General Assembly on 25 September 2015. Transforming Our World: The 2030 Agenda for Sustainable Development. United Nation-A/RES/70/1
- [6] Foereid B. Biochar in nutrient recycling—The effect and its use in wastewater treatment. *Open Journal of Soil Science*. 2015;**5**(02):39
- [7] Cho R. Phosphorus: Essential to life-are we running out. In: *Agriculture, Earth Sciences*. Columbia: Earth Institute; 2013
- [8] Withers PJ, Sylvester-Bradley R, Jones DL, Healey JR, Talboys PJ. Feed the crop not the soil: Rethinking phosphorus management in the food chain. *Environmental Science & Technology*. 2014;**48**(12):6523-6530. DOI: 10.1021/es501670j
- [9] Gellings CW, Parmenter KE. Efficient use and conservation of energy - energy efficiency in fertilizer production and use. *UNESCO-Encyclopedia of Life Support Systems*. 2016:123-136
- [10] Ashley K, Cordell D, Mavinic D. A brief history of phosphorus: From the philosopher's stone to nutrient recovery and reuse. *Chemosphere*. 2011;**84**(6):737-746
- [11] Angelakis A, Snyder S. Wastewater treatment and reuse: Past, present, and future. *Water*. 2015;**7**:4887-4895. DOI: 10.3390/w7094887
- [12] Butler D, McEntee B, Onof C, Hagger A. Sewer storage tank performance under climate change. *Water Science and Technology*. 2007;**56**(12):29-35
- [13] Bilgen S. Structure and environmental impact of global energy consumption. *Renewable and Sustainable Energy Reviews*. 2014;**38**:890-902
- [14] Lehmann J. Bio-energy in the black. *Frontiers in Ecology and the Environment*. 2007;**5**(7):381-387
- [15] Lehmann J, da Silva JP, Steiner C, Nehls T, Zech W, Glaser B. Nutrient availability and leaching in an archaeological Anthrosol and a Ferralsol of the Central Amazon basin: Fertilizer, manure and charcoal amendments. *Plant and Soil*. 2003;**249**(2):343-357
- [16] Major J, Rondon M, Molina D, Riha SJ, Lehmann J. Maize yield and nutrition during 4 years after biochar application to a Colombian

savanna oxisol. *Plant and Soil*. 2010;**333**(1-2):117-128

[17] Knowles OA, Robinson BH, Contangelo A, Clucas L. Biochar for the mitigation of nitrate leaching from soil amended with biosolids. *Science of the Total Environment*. 2011;**409**(17):3206-3210

[18] Clough T, Condon L, Kammann C, Müller C. A review of biochar and soil nitrogen dynamics. *Agronomy*. 2013;**3**(2):275-293

[19] Zheng H, Wang Z, Deng X, Herbert S, Xing B. Impacts of adding biochar on nitrogen retention and bioavailability in agricultural soil. *Geoderma*. 2013;**206**:32-39

[20] Liu X, Zhang A, Ji C, Joseph S, Bian R, Li L, et al. Biochar's effect on crop productivity and the dependence on experimental conditions—A meta-analysis of literature data. *Plant and soil*. 2013;**373**(1-2):583-594

[21] Reddy KR, Xie T, Dastgheibi S. Evaluation of biochar as a potential filter media for the removal of mixed contaminants from urban storm water runoff. *Journal of Environmental Engineering*. 2014;**140**(12):04014043

[22] Perez-Mercado L, Lalander C, Berger C, Dalahmeh S. Potential of biochar filters for onsite wastewater treatment: Effects of biochar type, physical properties and operating conditions. *Water*. 2018;**10**(12):1835

[23] Jung C, Phal N, Oh J, Chu KH, Jang M, Yoon Y. Removal of humic and tannic acids by adsorption–coagulation combined systems with activated biochar. *Journal of Hazardous Materials*. 2015;**300**:808-814

[24] Ding Z, Hu X, Wan Y, Wang S, Gao B. Removal of lead, copper, cadmium, zinc, and nickel from aqueous solutions by alkali-modified

biochar: Batch and column tests. *Journal of Industrial and Engineering Chemistry*. 2016;**33**:239-245

[25] Sun Y, Gao B, Yao Y, Fang J, Zhang M, Zhou Y, et al. Effects of feedstock type, production method, and pyrolysis temperature on biochar and hydrochar properties. *Chemical Engineering Journal*. 2014;**240**:574-578

[26] Suliman W, Harsh JB, Abu-Lail NI, Fortuna AM, Dallmeyer I, Garcia-Perez M. Influence of feedstock source and pyrolysis temperature on biochar bulk and surface properties. *Biomass and Bioenergy*. 2016;**84**:37-48

[27] Brewer CE, Hu YY, Schmidt-Rohr K, Loynachan TE, Laird DA, Brown RC. Extent of pyrolysis impacts on fast pyrolysis biochar properties. *Journal of Environmental Quality*. 2012;**41**(4):1115-1122

[28] Czernik S, Bridgwater AV. Overview of applications of biomass fast pyrolysis oil. *Energy & Fuels*. 2004;**18**(2):590-598

[29] Ahmad M, Lee SS, Dou X, Mohan D, Sung JK, Yang JE, et al. Effects of pyrolysis temperature on soybean stover- and peanut shell-derived biochar properties and TCE adsorption in water. *Bioresource Technology*. 2012;**118**:536-544

[30] Mohanty P, Nanda S, Pant KK, Naik S, Kozinski JA, Dalai AK. Evaluation of the physiochemical development of biochars obtained from pyrolysis of wheat straw, timothy grass and pinewood: Effects of heating rate. *Journal of Analytical and Applied Pyrolysis*. 2013;**104**:485-493

[31] Uchimiya M, Ohno T, He Z. Pyrolysis temperature-dependent release of dissolved organic carbon from plant, manure, and biorefinery wastes. *Journal of Analytical and Applied Pyrolysis*. 2013;**104**:84-94

- [32] Ronsse F, Van Hecke S, Dickinson D, Prins W. Production and characterization of slow pyrolysis biochar: Influence of feedstock type and pyrolysis conditions. *Gcb Bioenergy*. 2013;**5**(2):104-115
- [33] Ahmad M, Rajapaksha AU, Lim JE, Zhang M, Bolan N, Mohan D, et al. Biochar as a sorbent for contaminant management in soil and water: A review. *Chemosphere*. 2014;**99**:19-33
- [34] Windeatt JH, Ross AB, Williams PT, Forster PM, Nahil MA, Singh S. Characteristics of biochars from crop residues: Potential for carbon sequestration and soil amendment. *Journal of Environmental Management*. 2014;**146**:189-197
- [35] Keiluweit M, Nico PS, Johnson MG, Kleber M. Dynamic molecular structure of plant biomass-derived black carbon (biochar). *Environmental Science & Technology*. 2010;**44**(4):1247-1253
- [36] Lawrinenko M, Laird DA. Anion exchange capacity of biochar. *Green Chemistry*. 2015;**17**(9):4628-4636
- [37] Yao Y, Gao B, Chen J, Zhang M, Inyang M, Li Y, et al. Engineered carbon (biochar) prepared by direct pyrolysis of Mg-accumulated tomato tissues: Characterization and phosphate removal potential. *Bioresource Technology*. 2013;**138**:8-13
- [38] Kong H, He J, Gao Y, Wu H, Zhu X. Cosorption of phenanthrene and mercury (II) from aqueous solution by soybean stalk-based biochar. *Journal of Agricultural and Food Chemistry*. 2011;**59**(22):12116-12123
- [39] Rajapaksha AU, Chen SS, Tsang DC, Zhang M, Vithanage M, Mandal S, et al. Engineered/designer biochar for contaminant removal/immobilization from soil and water: Potential and implication of biochar modification. *Chemosphere*. 2016;**148**:276-291
- [40] Wang B, Gao B, Fang J. Recent advances in engineered biochar productions and applications. *Critical Reviews in Environmental Science and Technology*. 2017;**47**(22):2158-2207
- [41] Inyang M, Dickenson E. The potential role of biochar in the removal of organic and microbial contaminants from potable and reuse water: A review. *Chemosphere*. 2015;**134**:232-240
- [42] Rajapaksha AU, Chen SS, Tsang DC, Zhang M, Vithanage M, Mandal S, et al. Engineered/designer biochar for contaminant 848 removal/immobilization from soil and water: Potential and implication of biochar 849 modification. *Chemosphere*. 2016;**148**(27):6e291
- [43] Sizmur T, Fresno T, Akgül G, Frost H, Moreno-Jiménez E. Biochar modification to enhance sorption of inorganics from water. *Bioresource Technology*. 2017;**246**:34-47
- [44] Lima IM, Marshall WE. Adsorption of selected environmentally important metals by poultry manure-based granular activated carbons. *Journal of Chemical Technology & Biotechnology: International Research in Process, Environmental & Clean Technology*. 2005;**80**(9):1054-1061
- [45] Shim T, Yoo J, Ryu C, Park YK, Jung J. Effect of steam activation of biochar produced from a giant Miscanthus on copper sorption and toxicity. *Bioresource Technology*. 2015;**197**:85-90
- [46] Lou K, Rajapaksha AU, Ok YS, Chang SX. Pyrolysis temperature and steam activation effects on sorption of phosphate on pine sawdust biochars in aqueous solutions. *Chemical Speciation & Bioavailability*. 2016;**28**(1-4):42-50
- [47] Rajapaksha AU, Vithanage M, Ahmad M, Seo DC, Cho JS, Lee SE, et al. Enhanced sulfamethazine removal by

- steam-activated invasive plant-derived biochar. *Journal of Hazardous Materials*. 2015;**290**:43-50
- [48] Hadjittofi L, Prodromou M, Pashalidis I. Activated biochar derived from cactus fibres–preparation, characterization and application on Cu (II) removal from aqueous solutions. *Bioresource Technology*. 2014;**159**:460-464
- [49] Iriarte-Velasco U, Sierra I, Zudaire L, Ayastuy JL. Preparation of a porous biochar from the acid activation of pork bones. *Food and Bioproducts Processing*. 2016;**98**:341-353
- [50] Qian K, Kumar A, Patil K, Bellmer D, Wang D, Yuan W, et al. Effects of biomass feedstocks and gasification conditions on the physiochemical properties of char. *Energies*. 2013;**6**(8):3972-3986
- [51] Zhao L, Zheng W, Mašek O, Chen X, Gu B, Sharma BK, et al. Roles of phosphoric acid in biochar formation: Synchronously improving carbon retention and sorption capacity. *Journal of Environmental Quality*. 2017;**46**(2):393-401
- [52] Huff MD, Lee JW. Biochar-surface oxygenation with hydrogen peroxide. *Journal of Environmental Management*. 2016;**165**:17-21
- [53] Xue Y, Gao B, Yao Y, Inyang M, Zhang M, Zimmerman AR, et al. Hydrogen peroxide modification enhances the ability of biochar (hydrochar) produced from hydrothermal carbonization of peanut hull to remove aqueous heavy metals: Batch and column tests. *Chemical Engineering Journal*. 2012;**200**:673-680
- [54] Xu X, Cao X, Zhao L. Comparison of rice husk-and dairy manure-derived biochars for simultaneously removing heavy metals from aqueous solutions: Role of mineral components in biochars. *Chemosphere*. 2013;**92**(8):955-961
- [55] Petrović JT, Stojanović MD, Milojković JV, Petrović MS, Šošćarić TD, Laušević MD, et al. Alkali modified hydrochar of grape pomace as a perspective adsorbent of Pb²⁺ from aqueous solution. *Journal of Environmental Management*. 2016;**182**:292-300
- [56] Goswami R, Shim J, Deka S, Kumari D, Kataki R, Kumar M. Characterization of cadmium removal from aqueous solution by biochar produced from *Ipomoea fistulosa* at different pyrolytic temperatures. *Ecological Engineering*. 2016;**97**: 444-451
- [57] Hamid SBA, Chowdhury ZZ, Zain SM. Base catalytic approach: A promising technique for the activation of biochar for equilibrium sorption studies of copper, Cu (II) ions in single solute system. *Materials*. 2014;**7**(4):2815-2832
- [58] Micháleková-RichveisováB, FrištákV, Pipiška M, Ďuriška L, Moreno-Jimenez E, Soja G. Iron-impregnated biochars as effective phosphate sorption materials. *Environmental Science and Pollution Research*. 2017;**24**(1):463-475
- [59] Agrafioti E, Kalderis D, Diamadopoulos E. Ca and Fe modified biochars as adsorbents of arsenic and chromium in aqueous solutions. *Journal of Environmental Management*. 2014;**146**:444-450
- [60] Saha B, Orvig C. Biosorbents for hexavalent chromium elimination from industrial and municipal effluents. *Coordination Chemistry Reviews*. 2010;**254**(23-24):2959-2972
- [61] FrištákV, Micháleková-RichveisováB, Víglásová E, Ďuriška L, Galamboš M, Moreno-Jiménez E, et al. Sorption separation of Eu and As from

- single-component systems by Fe-modified biochar: Kinetic and equilibrium study. *Journal of the Iranian Chemical Society*. 2017;**14**(3):521-530
- [62] Chen L, Chen XL, Zhou CH, Yang HM, Ji SF, Tong DS, et al. Environmental-friendly montmorillonite-biochar composites: Facile production and tunable adsorption-release of ammonium and phosphate. *Journal of Cleaner Production*. 2017;**156**:648-659
- [63] Zhou Y, Gao B, Zimmerman AR, Fang J, Sun Y, Cao X. Sorption of heavy metals on chitosan-modified biochars and its biological effects. *Chemical Engineering Journal*. 2013;**231**:512-518
- [64] Yang GX, Jiang H. Amino modification of biochar for enhanced adsorption of copper ions from synthetic wastewater. *Water Research*. 2014;**48**:396-405
- [65] Frankel ML, Bhuiyan TI, Veksha A, Demeter MA, Layzell DB, Helleur RJ, et al. Removal and biodegradation of naphthenic acids by biochar and attached environmental biofilms in the presence of co-contaminating metals. *Bioresource Technology*. 2016;**216**:352-361
- [66] Mumme J, Srocke F, Heeg K, Werner M. Use of biochars in anaerobic digestion. *Bioresource Technology*. 2014;**164**:189-197
- [67] Mondal S, Bobde K, Aikat K, Halder G. Biosorptive uptake of ibuprofen by steam activated biochar derived from mung bean husk: Equilibrium, kinetics, thermodynamics, modeling and eco-toxicological studies. *Journal of Environmental Management*. 2016;**182**:581-594
- [68] Jung C, Oh J, Yoon Y. Removal of acetaminophen and naproxen by combined coagulation and adsorption using biochar: Influence of combined sewer overflow components. *Environmental Science and Pollution Research*. 2015;**22**(13):10058-10069
- [69] Xu RK, Xiao SC, Yuan JH, Zhao AZ. Adsorption of methyl violet from aqueous solutions by the biochars derived from crop residues. *Bioresource Technology*. 2011;**102**(22):10293-10298
- [70] Adeel M, Song X, Wang Y, Francis D, Yang Y. Environmental impact of estrogens on human, animal and plant life: A critical review. *Environment International*. 2017;**99**:107-119
- [71] Li Y, Shao J, Wang X, Deng Y, Yang H, Chen H. Characterization of modified biochars derived from bamboo pyrolysis and their utilization for target component (furfural) adsorption. *Energy & Fuels*. 2014;**28**(8):5119-5127
- [72] Uchimiya M, Wartelle LH, Lima IM, Klasson KT. Sorption of deisopropylatrazine on broiler litter biochars. *Journal of Agricultural and Food Chemistry*. 2010;**58**(23):12350-12356
- [73] Mohamed BA, Ellis N, Kim CS, Bi X, Emam AER. Engineered biochar from microwave-assisted catalytic pyrolysis of switchgrass for increasing water-holding capacity and fertility of sandy soil. *Science of the Total Environment*. 2016;**566**:387-397
- [74] Yu X, Pan L, Ying G, Kookana RS. Enhanced and irreversible sorption of pesticide pyrimethanil by soil amended with biochars. *Journal of Environmental Sciences*. 2010;**22**(4):615-620
- [75] Chen B, Chen Z. Sorption of naphthalene and 1-naphthol by biochars of orange peels with different pyrolytic temperatures. *Chemosphere*. 2009;**76**(1):127-133
- [76] Sun K, Ro K, Guo M, Novak J, Mashayekhi H, Xing B. Sorption of bisphenol A, 17 α -ethinyl estradiol and phenanthrene on thermally

and hydrothermally produced biochars. *Bioresource Technology*. 2011;**102**(10):5757-5763

[77] Li G, Zhu W, Zhang C, Zhang S, Liu L, Zhu L, et al. Effect of a magnetic field on the adsorptive removal of methylene blue onto wheat straw biochar. *Bioresource Technology*. 2016;**206**:16-22

[78] Teixidó M, Pignatello JJ, Beltrán JL, Granados M, Peccia J. Speciation of the ionizable antibiotic sulfamethazine on black carbon (biochar). *Environmental Science & Technology*. 2011;**45**(23):10020-10027

[79] Mohan D, Sarswat A, Ok YS, Pittman CU Jr. Organic and inorganic contaminants removal from water with biochar, a renewable, low cost and sustainable adsorbent—A critical review. *Bioresource Technology*. 2014;**160**:191-202

[80] Cao X, Ma L, Gao B, Harris W. Dairy-manure derived biochar effectively sorbs lead and atrazine. *Environmental Science & Technology*. 2009;**43**(9):3285-3291

[81] Abdelhafez AA, Li J. Removal of Pb (II) from aqueous solution by using biochars derived from sugar cane bagasse and orange peel. *Journal of the Taiwan Institute of Chemical Engineers*. 2016;**61**:367-375

[82] Oliveira FR, Patel AK, Jaisi DP, Adhikari S, Lu H, Khanal SK. Environmental application of biochar: Current status and perspectives. *Bioresource Technology*. 2017;**246**:110-122

[83] Lu H, Zhang W, Yang Y, Huang X, Wang S, Qiu R. Relative distribution of Pb²⁺ sorption mechanisms by sludge-derived biochar. *Water Research*. 2012;**46**(3):854-862

[84] Hsu NH, Wang SL, Liao YH, Huang ST, Tzou YM, Huang YM.

Removal of hexavalent chromium from acidic aqueous solutions using rice straw-derived carbon. *Journal of Hazardous Materials*. 2009;**171**(1-3):1066-1070

[85] Ippolito JA, Strawn DG, Scheckel KG, Novak JM, Ahmedna M, Niandou MAS. Macroscopic and molecular investigations of copper sorption by a steam-activated biochar. *Journal of Environmental Quality*. 2012;**41**(4):1150-1156

[86] Lima IM, Boateng AA, Klasson KT. Physicochemical and adsorptive properties of fast-pyrolysis bio-chars and their steam activated counterparts. *Journal of Chemical Technology & Biotechnology*. 2010;**85**(11):1515-1521

[87] Lu K, Yang X, Gielen G, Bolan N, Ok YS, Niazi NK, et al. Effect of bamboo and rice straw biochars on the mobility and redistribution of heavy metals (Cd, Cu, Pb and Zn) in contaminated soil. *Journal of Environmental Management*. 2017;**186**:285-292

[88] Bogusz A, Oleszczuk P, Dobrowolski R. Application of laboratory prepared and commercially available biochars to adsorption of cadmium, copper and zinc ions from water. *Bioresource Technology*. 2015;**196**:540-549

[89] Liu P, Ptacek CJ, Blowes DW, Landis RC. Mechanisms of mercury removal by biochars produced from different feedstocks determined using X-ray absorption spectroscopy. *Journal of Hazardous Materials*. 2016;**308**:233-242

[90] Komkiene J, Baltreinaite E. Biochar as adsorbent for removal of heavy metal ions [Cadmium (II), Copper (II), Lead (II), Zinc (II)] from aqueous phase. *International Journal of Environmental Science and Technology*. 2016;**13**(2):471-482

- [91] Laird D, Fleming P, Wang B, Horton R, Karlen D. Biochar impact on nutrient leaching from a Midwestern agricultural soil. *Geoderma*. 2010;**158**(3-4):436-442
- [92] Hale SE, Alling V, Martinsen V, Mulder J, Breedveld GD, Cornelissen G. The sorption and desorption of phosphate-P, ammonium-N and nitrate-N in cacao shell and corn cob biochars. *Chemosphere*. 2013;**91**(11):1612-1619
- [93] Yao Y, Gao B, Inyang M, Zimmerman AR, Cao X, Pullammanappallil P, et al. Removal of phosphate from aqueous solution by biochar derived from anaerobically digested sugar beet tailings. *Journal of Hazardous Materials*. 2011;**190**(1-3):501-507
- [94] Chen B, Chen Z, Lv S. A novel magnetic biochar efficiently sorbs organic pollutants and phosphate. *Bioresource Technology*. 2011;**102**(2):716-723
- [95] Zhu K, Fu H, Zhang J, Lv X, Tang J, Xu X. Studies on removal of NH_4^+ -N from aqueous solution by using the activated carbons derived from rice husk. *Biomass and Bioenergy*. 2012;**43**:18-25
- [96] Jones DL, Rousk J, Edwards-Jones G, DeLuca TH, Murphy DV. Biochar-mediated changes in soil quality and plant growth in a three year field trial. *Soil Biology and Biochemistry*. 2012;**45**:113-124
- [97] Mizuta K, Matsumoto T, Hatate Y, Nishihara K, Nakanishi T. Removal of nitrate-nitrogen from drinking water using bamboo powder charcoal. *Bioresource Technology*. 2004;**95**(3):255-257
- [98] Kalantar-Zadeh K, Gutekunst L, Mehrotra R, Kovesdy CP, Bross R, Shinaberger CS, et al. Understanding sources of dietary phosphorus in the treatment of patients with chronic kidney disease. *Clinical Journal of the American Society of Nephrology*. 2010;**5**(3):519-530
- [99] Olmstead KP, Weber WJ. Interactions between microorganisms and activated carbon in water and waste treatment operations. *Chemical Engineering Communications*. 1991;**108**:113-125
- [100] Bornhardt C, Drewes JE, Jekel M. Removal of organic halogens (AOX) from municipal wastewater by powdered activated carbon (PAC) activated sludge (AS) treatment. *Water Science and Technology*. 1997;**35**(10):147-153
- [101] Jafarinejad S. Activated sludge combined with powder activated carbon (PACT process) for petroleum industry wastewater treatment: A review. *Chemistry International*. 2017;**3**:268-277
- [102] Lehmann J, Joseph S. Chapter 1: Biochar for environmental management: An introduction. In: *Biochar for Environmental Management: Science, Technology and Implementation*. 2nd edn. Routledge. 2015. ISBN: 9780415704151
- [103] Fagbohunbe MO, Herbert BMJ, Hurst L, Ibeto CN, Li H, Usmani SQ, et al. The challenges of anaerobic digestion and the role of biochar in optimizing anaerobic digestion. *Waste Management*. 2017;**61**:236-249
- [104] Sima X, Li B, Jiang H. Influence of pyrolysis biochar on settleability and denitrification of activated sludge process. *Chinese Journal of Chemical Physics*. 2017;**30**:357-364
- [105] Jamieson T, Sager E, Gueguen C. Characterization of biochar-derived dissolved organic matter using UV-visible absorption and

excitation-emission fluorescence
spectroscopies. *Chemosphere*.
2014;**103**:197-204

[106] Luo C, Lü F, Shao L, He P.
Application of eco-compatible biochar
in anaerobic digestion to relieve acid
stress and promote the selective
colonization of functional microbes.
Water Research. 2015;**68**:710-718

[107] Sunyoto NM, Zhu M, Zhang Z,
Zhang D. Effect of biochar addition
on hydrogen and methane production
in two-phase anaerobic digestion of
aqueous carbohydrates food waste.
Bioresource Technology. 2016;**219**:29-36

[108] Viggi CC, Simonetti S, Palma E,
et al. Enhancing methane production
from food waste fermentate
using biochar: The added value of
electrochemical testing in pre-selecting
the most effective type of biochar.
Biotechnology for Biofuels. 2017;**10**:303.
DOI: 10.1186/s13068-017-0994-7

[109] Cao G-L, Guo W-Q, Wang
A-J, Zhao L, Xu C-J, Zhao Q-L,
et al. Enhanced cellulosic hydrogen
production from lime-treated cornstalk
wastes using thermophilic anaerobic
microflora. *International Journal of
Hydrogen Energy*. 2012;**37**:13161-13166

[110] Zhang J, Wang Q, Zheng P,
Wang Y. Anaerobic digestion of food
waste stabilized by lime mud from
papermaking process. *Bioresource
Technology*. 2014;**170**:270-277

[111] Cai J, He P, Wang Y, Shao L,
Lü F. Effects and optimization of the
use of biochar in anaerobic digestion of
food wastes. *Waste Management and
Research*. 2016;**34**:409-416