We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Wearable Supercapacitors, Performance, and Future Trends

Litty V. Thekkekara and Imtiaz Ahmed Khan

Abstract

The progress in portable technologies demands compactable energy harvesting and storage. In recent years, carbon-based lightweight and wearable supercapacitors are the new energy storage trends in the market. Moreover, the non-volatile nature, long durability, eco-friendliness, and electrostatic interaction mechanism of supercapacitors make it a better choice than traditional batteries. This chapter will focus on the progress of the wearable supercapacitor developments, the preferred material, design choices for energy storage, and their performance. We will be discussing the integrability of these supercapacitors with the next generation wearable technologies like sensors for health monitoring, biosensing and e-textiles. Besides, we will investigate the limitations and challenges involved in realizing those supercapacitor integrated technologies.

Keywords: carbon, energy storages, E-textiles, health monitoring, biosensing

1. Introduction

Wearable technologies can be defined as intelligent devices that can be worn or attached to the skin's surface where they can detect, analyze and transfer the data to relevant systems [1]. The best example of E-textiles in the current market is sensors integrated apparels incorporating technologies like antennas, energy harvesters, and sensors [2]. These can enable the development of next-generation self-reliant wearable applications for wireless communications [3, 4], health sensing and monitoring [5–7], and light-emitting devices [8–10], which can find applications in smart cities, remote areas, telecommunications, and biomedical industries [11].

In the current commercial market, we can find more than 1000 types of wearables. Some of them include products from famous brands like Apple smartwatches which includes healthcare monitoring, fitness trackers from Garmin, integrated sensors in apparels from Nike and Adidas [12]. In the modern days, the research is focused on developing textiles itself as a sensor to monitor the body functions [13]. The expected market size of wearables is around \$57,653 million by 2022 [14].

In general, energy harvesters like piezo generators, which utilizes the energy delivered from the mechanical motions within the body functions, or solar cells which harvest energy from the Sun are utilized as a medium of energy harvesters, and traditional batteries are used as energy storage in wearable devices [15–18]. Further, wireless charging is a promising concept for the powering of wearables [19]. However, current wearable technologies are limited for continuous monitoring due to the power failures from the integrated coin-cells or pouch cell lithium-ion batteries [20]. Besides, batteries are volatile and suffer from heating issues [21].

Flexible supercapacitors are an alternative energy storage to be considered for wearable technologies due to the features like fast charging nature, long durability, integrability with the technologies, and eco-friendliness [22–24]. In the chapter, we will discuss how supercapacitors can be used as energy storage for supporting wearable technologies and the challenges involved in it.

2. Performance

Supercapacitors are generally divided into two types: *symmetric and asymmetric* based on their working mechanism. Symmetric supercapacitors can store electrical energy through ion adsorption–desorption (electrical double layer capacitive, EDLC) mechanism. In contrast, asymmetric supercapacitors work through the Faradaic reaction (pseudocapacitive) between the electrode and electrolyte [25]. Besides, there are two types of configuration for the supercapacitors: (1) those have a vertical structure comprising a separator sandwiched between two electrodes are known as sandwich supercapacitors and (2) a micro supercapacitor (MSC) is based on an interdigitated structures in the same plane as the current collectors, separated from each other by an insulating gap (typically in the range of 10–100 s of micrometers) [26]. Finally, an electrolyte is coated on top and between the electrodes and ensures ion transport along the basal plane of the electrodes [27].

In MSC, the insulating gap between the electrodes and electrode width decides the migrating distance of electrolyte ions, which generates the equivalent series resistance (ESR) [28]. With the reduction of the ESR, the performance of the MSCs can be improved, and the calculation can be. The electrode thickness is another factor deciding the storage capacity of the MSCs [29]. The ESR energy storage capacity of the supercapacitors is defined through the energy density (E_{den}), and the rate of the charge transfer process, power density (P_{den}) is analyzed using measurements like cyclic voltammetry (CV), galvanic charge–discharge (CC), and impedance measurements [27].

The formulas for calculating the ESR, E_{den} (Wh cm^{-2}) and P_{den} (W cm^{-2}), can be defined as follows;

$$R_{\text{ESR}} = V_{\text{drop}} / 2i \quad (1)$$

$$E_{\text{den}} = C_v \times (\Delta E)^2 \times (2 \times 3600) \quad (2)$$

$$P_{\text{den}} = (\Delta E)^2 / (4\text{ESR} \times V) \quad (3)$$

where R_{ESR} is the internal voltage drop at the beginning of the discharge, V_{drop} , at a constant current density, i calculated from the CC measurements, C_v is the volumetric capacitance, ΔE is the operating voltage window in Volts, V is the volume of the electrodes.

3. Materials and designs

Materials and designs are an essential factor that decides the energy storage performance like flexibility, lightweight, storage capacity, how fast electrolyte ions can move within the device, and electrochemical window of the device [27, 30].

For wearables, a particular type of supercapacitors needs to be designed to match the above specific requirements. In this session, we will discuss these aspects in detail.

3.1 Materials

3.1.1 Electrodes

The electrodes of supercapacitors require high surface area, long term stability, resistance to electrochemical oxidation or reduction, the capability of multiple cycling materials, optimum pore size distribution, minimized ohmic resistance with the contacts, sufficient electrode-electrolyte solution contact interface, mechanical integrity, and less self-discharge [25, 27, 31].

EDLCs mainly utilize carbon-based materials for the electrodes due to their high performance [32]. One of the first EDLC developed employs activated carbon as the electrode material, which exhibited capacity values of 2 F cm^{-2} in H_2SO_4 solutions [33]. However, carbon exhibits slow oxidation, besides having high ESR. The low performance of carbon is due to poor particle to particle contact of the agglomerates as well as the high ionic resistance from the electrolyte distributed in the microporous structure, resulting in the poor high-frequency characteristics of carbon-based capacitors. On the other hand, the carbon nanotubes do not produce satisfactory capacitance unless a conducting polymer [34] is used to form a pseudocapacitance.

Graphene is a form of carbon with a high surface area up to $2675 \text{ m}^2 \text{ g}^{-1}$ and intrinsic capacitance of $21 \mu\text{F cm}^{-2}$, which set the upper limit of EDLC capacitance of all carbon-based materials [35]. Besides, both faces of graphene sheets are readily accessible by the electrolyte. However, in practical applications, the surface area of graphene will be much reduced due to agglomeration. Graphene-related materials like reduced graphene oxide are cost-effective and widely used electrode materials for EDLCs [36].

Pseudocapacitors which are asymmetric supercapacitors using different materials like RuO_2 , Manganese oxide (MnO_2), and conductive polymers like polyaniline (PANI) with or without the symmetric electrode materials, becomes a direction of interest to achieve the high-performance supercapacitors [37]. For example, the hybrid of ultrathin supercapacitors made of MnO_2 sheets and graphene sheets using the direct laser writing method offers an electrochemically active surface for fast absorption/desorption electrolyte ions (22). The contributions of additional interfaces at the hybridized interlayer areas to accelerate charge transport during the charge/discharge process resulting in an energy density and power density of 2.4 mWh cm^{-3} and 298 mW cm^{-3} , respectively. Flexible supercapacitors based on manganese hexacyanoferrate-manganese oxide and electrochemically reduced graphene oxide electrode materials ($\text{MnHCF-MnO}_x/\text{ErGO}$) exhibiting a remarkable areal capacitance of 16.8 mF cm^{-2} and considerable energy and power density of 0.5 mWh cm^{-2} and $0.0023 \text{ mW cm}^{-2}$ [38].

Another approach is to use metals like the well-connected nanoporous gold film to fabricate interdigital electrode materials for supercapacitors with high mechanical flexibility [39]. These supercapacitors exhibit a capacitance of 127 F cm^{-3} and an energy density of 0.045 Wh cm^{-3} . The gold metal is known for its high electrical conductivity, and the concept adopted can be effectively used to integrate with devices in a lesser aerial footprint.

3.1.2 Electrolytes

The electrolyte of supercapacitors has a crucial role in deciding properties such as the energy density, power density, internal resistance, rate performance,

operating temperature range, cycling lifetime, self-discharge, non-volatile nature, and toxicity of the energy storage. The electrochemical range of an electrolyte decides the cell voltage window of the energy storage like the batteries and supercapacitors [25] and is governed by the equation,

$$E = \frac{1}{2} CV^2 \quad (4)$$

where E = energy density, C = specific capacitance and V = cell voltage.

The electrolytes used in energy storage can be classified as liquid electrolytes and solid/quasi-solid state electrolytes [40]. Liquid electrolytes can be further classified as aqueous electrolytes with a voltage range of 1.0 to 1.3 V, organic electrolytes within the voltage range of 1 to 2 V, and ionic liquids (IL) with a voltage range of 3.5 to 4.0 V [41]. The solid or quasi-solid state electrolytes can be classified as organic and inorganic electrolytes with a voltage range of 2.5 to 2.7 V.

Among different electrolytes, aqueous-based electrolytes possess high conductivity and capacitance. However, they are limited by low cell voltage windows whereas organic, and IL electrolytes can operate at higher cell voltage windows. ILs are used in wearable energy storage owing to their interesting properties like non-flammability, low vapor pressure, and significant operating potential window. Solid-state electrolytes are devoid of leakage issues but are limited by the low conductivity [42].

3.1.3 Designs

It is highly recommended to have an optimized design for supercapacitor electrodes for high output performance. In the commercial supercapacitors, sandwich structures in which electrode-electrolyte-electrode configuration is utilized [26]. Nevertheless, these designs can result in bulky storages, which is less favorable for lightweight wearable technologies.

On the other hand, the printed supercapacitor, based on 2D planar interelectrode configuration, is utilized as the basic designs for the printed electrodes. However, the performance is limited in comparison to the sandwich counterpart [43]. This has led to the consideration of other designs like a spiral, split rings, and onion petals which demonstrated an increase in the electrode-electrolyte interactions in the supercapacitor [44]. A considerable enhancement in the storage capacitance and power density was offered with the utilization of the fractals designs [18], which can offer an unlock towards the development of high capacity miniaturized [23, 45, 46] as well as large scale supercapacitors that can be integrated with the textiles and other wearables [47].

The other area of recent interest in the designs is the origami concepts to improve the performance of the printed supercapacitors [48]. The research used the active materials in suitable geometry to create self-folding structures to perform folding or unfolding functions without having kinetic movements due to external forces.

3.1.4 Encapsulation

The wearable energy storage will be exposed to conditions like water moisture conditions from sweating, washing, weather conditions, and atmospheric pollution. All these conditions can adversely affect the performance of these energy storage. Besides, the presence of corrosive and volatile electrolytes can be dangerous to the user's health. Effective encapsulation is an essential condition to sustain a safer

storage performance while maintaining a flexible nature [49–51]. Ecoflex and polyvinyl alcohol (PVA) are the standard encapsulations used for the current wearable energy storage [47, 52].

4. Types of wearable supercapacitors

4.1 Coin/pouch supercapacitors

The most commonly used energy storages for portable devices like smartwatches are the coin and pouch cells. Due to the well-developed production line for the long-used methodology, there is high interest in the adaptability of the technique with the extension towards the supercapacitors for the emerging wearable technologies [53–55]. Poochi et al. recently developed prototypes of coin cells and pouch cells from nitrogen-doped reduced graphene oxide electrodes with phenylenediamine-mediated organic electrolyte with a high specific capacitance of 563 and 340 F g⁻¹ with high energy density 149.4 and 77.2 Wh·kg⁻¹ at 1 A g⁻¹ [56].

4.2 Printed supercapacitors

A less complex solution to the energy storage demands of wearables, printed technologies offer highly adaptive methodologies for producing adhesion between the electrodes and current collectors/substrates and eliminates the requirement of inert additives for active materials. In general, supercapacitor printing techniques can be classified into two categories, techniques which do not require a template (example-inkjet printing and 3D printing) and techniques utilizing a template (example-screen printing). All these techniques must be coordinated with the printable materials for improving electrochemical and mechanical performance in a less footprint [57].

Among them, laser-induced graphene based supercapacitors attained exceptional attention due to the cost-effectiveness and ability to integrate with wearable applications in specific scales [58, 59]. Recently, demonstrated textile integrated solar graphene energy storages of 100 cm² with a performance of an areal capacitance, 49 mF cm⁻², energy density, 6.73 mWh cm⁻², power density, 2.5 mW cm⁻², and stretchability up to 200%, which can effectively be utilized for the realization of functional textiles to support applications like sensors, and displays [47, 60].

Printing high-performance supercapacitors in lesser footprints can develop three-dimensional (3D) supercapacitors [61]. The concept of the layer by layer stacking of individual supercapacitors obtained from the laser-induced graphenes from PET sheets which result in an areal capacitance >9 mF cm⁻² [62, 63]. This methodology is a promising direction towards the future of energy storages to be considered for the ultra-portable and flexible applications. Besides, there are reports of using multilayered structures made of rGO/Au particles [64]. The development of additional features like stretchability up to 50% in 1000 stretch cycles with the 3D supercapacitors will contribute towards the withstanding of the deformations and prevention against the performance degradation [65].

Nonimpact printing technology like inkjet printing is an additive-based approach that can create patterns either continuously or in steps by propelling droplets of liquid precursor materials onto various substrates without the aid of pre-designed masks through the control of printer head and ink toner [66]. The formation of printed features depends on the capability of the inkjet printing apparatus, the viscosity, surface tension, dispersibility of the inks, and the wettability of the substrates to be printed on [67]. Yu and co-workers reported paper-based, all-solid, flexible, planar supercapacitors by inkjet printing PEDOT: PSS-CNT/silver

nanoparticle as the electrode material [68]. The obtained microdevices were able to demonstrate rate capability up to $10\,000\text{ mV s}^{-1}$, fast frequency response (relaxation time constant of 8.5 ms), high volumetric specific capacitance (23.6 F cm^{-3}), and long cycle stability (92% capacitance retention after 10,000 cycles).

Screen printing is another approach for printing and is conducted through squeegee by pressing the ink down with enough force to penetrate through pre-patterned masks (screen or stencil) onto the desired substrate [69]. The process can be conducted on both rigid (silicon or glass) and flexible substrates (textiles or papers) and can reach a minimum resolution of $30\text{--}50\text{ }\mu\text{m}$ [70]. The quality of the resulting features depends on the stenciling techniques, the printability of the inks, and the affinity between the ink and substrate. Even though this method is capable of mass production, some issues like printable ink must have a high viscosity, and suitable shear-thinning property limits the potential. Using this methodology, Lu et al. prepared an all-solid MSC by screen-printing $\text{FeOOH}/\text{MnO}_2$ composites on different substrates like PET, paper, and textile. The fully printed supercapacitor exhibits a high area-specific capacitance of 5.7 mF cm^{-2} and an energy density of $0.0005\text{ mWh cm}^{-2}$ at a power density of 0.04 mW cm^{-2} [71].

Roll to roll printing of supercapacitors through the low-temperature laser annealing process of roll-to-roll (R2R) printed metal nanoparticle (NP) ink on a polymer substrate is an area of interest that can have the largescale commercial applications [72]. Another approach is to laser-print the toner on metal foils, followed by thermal annealing in a hydrogen environment, finally resulting in the patterned thin graphitic carbon or graphene electrodes for supercapacitors. The electrochemical cells are made of graphene-graphitic carbon electrodes, which can be roll-to-roll printed [73].

4.3 Yarn based supercapacitors

E-textiles are the new frontiers in the history of fabrics that incorporate the technologies like displays and sensing [60, 74, 75]. Textiles or fabrics are flexible materials, which use fibers originating from natural or synthetic as fundamental building blocks, with a considerable length to diameter ratio (~ 1000 to 1) [76]. The fabrics can be in the form of staples or filament.

Natural fibers such as cotton staple fiber have a limited length. Filament fiber tends to be continuous in length, whereas silk is an example of a natural filament. An example of synthetic fibers are filament fibers. Both staple fibers and threads can be made into yarns and fabrics. A more recent form of textile is electrospun, where the fabrication is achieved by applying a high voltage to an aqueous polymeric solution. The polymer can be organic or inorganic, depending on the intended application. *Yarn* is a long strand constituting textile fibers, filaments, or similar material converted to a textile fabric through weaving, knitting, or other intertwining techniques [77]. The yarn can be formed from various manufacturing processes. The spinning process is used to convert fibers into yarns, usually by twisting together several fibers. Usually, in spinning, fibers are aligned in one axis and are axially twisted. The direction of twist is denoted by 'S' or 'Z' twist.

When looking for 2D fabric devices such as supercapacitor devices, the usual architecture found in the sandwich [78] and in-plane (planar) configurations [79]. The in-plane architecture is more flexible than its sandwich structure counterpart due to its lightweight and flexibility (structural design), making it a more suitable option when working with 2D active electrode materials [80]. In the case of 1D yarn supercapacitors, common existing device shapes include coaxial [81], core-spun [82], parallel [83], two-ply twisted [84], and helical structures [85].

5. Future trends—scalability and integration of wearable supercapacitors

The major hindrance of the current wearable energy storage to be commercialized is its limitation for large-scale fabrications to meet the power requirements of integrated technologies [86]. Besides, for textile-based wearable technologies, another challenge is developing a single textile unit incorporating energy storage and devices together. The achievement of cost-effective all-in-one wearable technologies without compensating the performance of the technologies is a great challenge in this area [87–96]. Some of the research groups demonstrated the laboratory prototypes in this area and in **Figure 1**, we summarized these studies.

Only a few groups so far that reported about the possibilities of developing their energy storages can be developed into self-powered wearable technologies using the industrial machinery because of the low performance [97]. Besides, the cost-effectiveness of the process needs to be attractive in comparison to the existing battery technology. Nevertheless, the development of printing methodologies like screen printing [56], inkjet printing [61], and laser printing seems to be a solution to the stitching issues currently faced by the yarn-based energy storages. The successful generation of high-performance flexible, lightweight, miniaturized supercapacitors will enable a step closer to realizing eco-friendly, non-volatile portable and wearable devices.

Figure 1.
Applications benefited from the wearable supercapacitors.

6. Conclusions

Supercapacitors which leaves the further possibilities of miniaturization without compromising the high energy storage capacity and transfer rate provides the scope of improvement to be adopted as an eco-friendly, non-volatile energy storage source for the future wearable technologies.

Acknowledgements

LVT acknowledge the RMIT seed fund, 2018 to support this work. IAK thanks Australian Research Council (ARC) linkage grant- LP 110100455 for the PhD scholarship.

Conflict of interest

The authors declare no conflict-of-interest declaration.

Appendices and nomenclature

MSC	Microsupercapacitor
EDLC	Electrochemical double layer capacitance

Author details

Litty V. Thekkekara^{1,2*} and Imtiaz Ahmed Khan¹

¹ Department of Manufacturing, Materials and Mechatronics, School of Engineering, RMIT University, Melbourne, Australia

² Functional Materials and Microsystems, Department of Electronic and Telecommunications, School of Engineering, RMIT University, Melbourne, Australia

*Address all correspondence to: littyvarghese.thekkekara@rmit.edu.au

IntechOpen

© 2021 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/3.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

References

- [1] Schwab, K., *The Fourth Industrial Revolution*. 2017: Penguin Books Limited.
- [2] Schneegass, S. and O. Amft, *Smart textiles*. 2017: Springer.
- [3] Huang, X., et al., Highly flexible and conductive printed graphene for wireless wearable communications applications. *Scientific reports*, 2015. 5(1): p. 1-8.
- [4] Rein, M., et al., Diode fibres for fabric-based optical communications. *Nature*, 2018. 560(7717): p. 214-218.
- [5] Rodgers, M.M., V.M. Pai, and R.S. Conroy, Recent advances in wearable sensors for health monitoring. *IEEE Sensors Journal*, 2014. 15(6): p. 3119-3126.
- [6] He, W., et al., Integrated textile sensor patch for real-time and multiplex sweat analysis. *Science Advances*, 2019. 5(11): p. eaax0649.
- [7] Van Langenhove, L., *Smart Textiles for Medicine and Healthcare: Materials, Systems and Applications*. 2007: Elsevier.
- [8] Choi, S., et al., Highly flexible and efficient fabric-based organic light-emitting devices for clothing-shaped wearable displays. *Scientific reports*, 2017. 7(1): p. 1-8.
- [9] Graham-Rowe, D., Photonic fabrics take shape. *Nature Photonics*, 2007. 1(1): p. 6-7.
- [10] Zhang, Z., et al., Textile display for electronic and brain-interfaced communications. *Advanced Materials*, 2018. 30(18): p. 1800323.
- [11] Shi, J., et al., Smart textile-integrated microelectronic Systems for Wearable Applications. *Advanced Materials*, 2020. 32(5): p. 1901958.
- [12] Seneviratne, S., et al., A survey of wearable devices and challenges. *IEEE Communications Surveys & Tutorials*, 2017. 19(4): p. 2573-2620.
- [13] Koncar, V., *Smart Textiles and their Applications*. 2016: Woodhead Publishing.
- [14] Research and Markets Offers Report: Global Wearable Technology Market Analysis & Trends - Industry Forecast to 2025. *Telecommunications Reports, Wireless News*, 2018.
- [15] Wang, X., et al., Flexible energy-storage devices: Design consideration and recent Progress. *Advanced Materials*, 2014. 26(28): p. 4763-4782.
- [16] Ostfeld, A.E., et al., High-performance flexible energy storage and harvesting system for wearable electronics. *Scientific reports*, 2016. 6(1): p. 1-10.
- [17] Wen, Z., et al., Self-powered textile for wearable electronics by hybridizing fiber-shaped nanogenerators, solar cells, and supercapacitors. *Science Advances*, 2016. 2(10): p. e1600097.
- [18] Thekkekara, L.V. and M. Gu, Bioinspired fractal electrodes for solar energy storages. *Scientific reports*, 2017. 7(1): p. 1-9.
- [19] Burket, C., Wireless charging opportunities and challenges for wearables: One size does not fit all. *IEEE Power Electronics Magazine*, 2017. 4(4): p. 53-57.
- [20] Çiçek, M., Wearable technologies and its future applications. *International Journal of Electrical, Electronics and Data Communication*, 2015. 3(4): p. 45-50.
- [21] Habibipour, A., A.M. Padyab, and A. Ståhlbröst. Social, ethical and

ecological issues in wearable technologies. in AMCIS 2019, Twenty-Fifth Americas Conference on Information Systems, Cancun, México, Augusti 15-17 2019. 2019.

[22] Hashmi, S., Supercapacitor: An emerging power source. *National Academy Science Letters*, 2004. 27(1-2): p. 27-46.

[23] Thekkekara, L.V., X. Chen, and M. Gu, Two-photon-induced stretchable graphene supercapacitors. *Scientific Reports*, 2018. 8(1): p. 11722.

[24] Miller, J.R. and P. Simon, Electrochemical capacitors for energy management. *Science*, 2008. 321(5889): p. 651-652.

[25] Conway, B., Springer Science & Business Media. 1999.

[26] Yu, A., V. Chabot, and J. Zhang, *Electrochemical Supercapacitors for Energy Storage and Delivery: Fundamentals and Applications*. 2013: Taylor & Francis.

[27] Conway, B.E., *Electrochemical Supercapacitors: Scientific Fundamentals and Technological Applications*. 2013: Springer Science & Business Media.

[28] Liu, N. and Y. Gao, Recent progress in micro-supercapacitors with in-plane interdigital electrode architecture. *Small*, 2017. 13(45): p. 1701989.

[29] Xiong, G., et al., A review of graphene-based electrochemical microsupercapacitors. *Electroanalysis*, 2014. 26(1): p. 30-51.

[30] Simon, P. and Y. Gogotsi, *Materials for electrochemical capacitors. Nanoscience and technology: a collection of reviews from Nature journals*, 2010: p. 320-329.

[31] Stoller, M.D. and R.S. Ruoff, Best practice methods for determining an

electrode material's performance for ultracapacitors. *Energy & Environmental Science*, 2010. 3(9): p. 1294-1301.

[32] Inagaki, M., H. Konno, and O. Tanaike, Carbon materials for electrochemical capacitors. *Journal of power sources*, 2010. 195(24): p. 7880-7903.

[33] Boos, D.L., *Electrolytic capacitor having carbon paste electrodes*. 1970, Google Patents.

[34] Obreja, V.V., On the performance of supercapacitors with electrodes based on carbon nanotubes and carbon activated material—A review. *Physica E: Low-dimensional Systems and Nanostructures*, 2008. 40(7): p. 2596-2605.

[35] Simon, P. and Y. Gogotsi, *Materials for electrochemical capacitors. Nature materials*, 2008. 7(11): p. 845-854.

[36] Purkait, T., et al., High-performance flexible supercapacitors based on electrochemically tailored three-dimensional reduced graphene oxide networks. *Scientific reports*, 2018. 8(1): p. 1-13.

[37] Wang, J., et al., Pseudocapacitive materials for electrochemical capacitors: From rational synthesis to capacitance optimization. *National Science Review*, 2017. 4(1): p. 71-90.

[38] Liang, J., et al., All-printed MnHCF-MnOx-based high-performance flexible supercapacitors. *Advanced Energy Materials*, 2020. 10(12): p. 2000022.

[39] Zhang, C., et al., Planar integration of flexible micro-supercapacitors with ultrafast charge and discharge based on interdigital nanoporous gold electrodes on a chip. *Journal of Materials Chemistry A*, 2016. 4(24): p. 9502-9510.

[40] Zhong, C., et al., A review of electrolyte materials and compositions

for electrochemical supercapacitors. *Chemical Society Reviews*, 2015. 44(21): p. 7484-7539.

[41] Armand, M., et al., Ionic-liquid materials for the electrochemical challenges of the future. *Nature materials*, 2009. 8(8): p. 621-629.

[42] Samui, A.B. and P. Sivaraman, 11 - Solid Polymer Electrolytes for Supercapacitors, in *Polymer Electrolytes*. 2010, Woodhead Publishing. p. 431-470.

[43] Wang, F., et al., Latest advances in supercapacitors: From new electrode materials to novel device designs. *Chemical Society Reviews*, 2017. 46(22): p. 6816-6854.

[44] Gao, W., et al., Direct laser writing of micro-supercapacitors on hydrated graphite oxide films. *Nature nanotechnology*, 2011. 6(8): p. 496-500.

[45] Soavi, F., et al., Miniaturized supercapacitors: Key materials and structures towards autonomous and sustainable devices and systems. *Journal of power sources*, 2016. 326: p. 717-725.

[46] Kyeremateng, N.A., T. Brousse, and D. Pech, Microsupercapacitors as miniaturized energy-storage components for on-chip electronics. *Nature nanotechnology*, 2017. 12(1): p. 7-15.

[47] Thekkekara, L.V. and M. Gu, Large-scale waterproof and stretchable textile-integrated laser-printed graphene energy storages. *Scientific reports*, 2019. 9(1): p. 1-7.

[48] Nam, I., et al., All-solid-state, origami-type foldable supercapacitor chips with integrated series circuit analogues. *Energy & Environmental Science*, 2014. 7(3): p. 1095-1102.

[49] Ji, W., et al., Polypyrrole encapsulation on flower-like porous NiO for advanced high-performance

supercapacitors. *Chemical Communications*, 2015. 51(36): p. 7669-7672.

[50] Kim, H., et al., Encapsulated, high-performance, stretchable array of stacked planar micro-supercapacitors as waterproof wearable energy storage devices. *ACS applied materials & interfaces*, 2016. 8(25): p. 16016-16025.

[51] Kavinkumar, T., et al., Interface-modulated uniform outer nanolayer: A category of electrodes of nanolayer-encapsulated core-shell configuration for supercapacitors. *Nano Energy*, 2021. 81: p. 105667.

[52] Li, H. and J. Liang, Recent development of printed micro-supercapacitors: Printable materials, printing technologies, and perspectives. *Advanced Materials*, 2020. 32(3): p. 1805864.

[53] Hung, T.-F., et al., High-mass loading hierarchically porous activated carbon electrode for pouch-type supercapacitors with propylene carbonate-based electrolyte. *Nanomaterials*, 2021. 11(3): p. 785.

[54] Ojha, M., et al., Holey graphitic carbon nano-flakes with enhanced storage characteristics scaled to a pouch cell supercapacitor. *Fuel*, 2021. 285: p. 119246.

[55] Roberts, A.J., et al. Supercapacitors: From coin cell to 800 F pouch cell. in *ECS Meeting Abstracts*. 2016. IOP Publishing.

[56] Poochai, C., et al., High performance coin-cell and pouch-cell supercapacitors based on nitrogen-doped reduced graphene oxide electrodes with phenylenediamine-mediated organic electrolyte. *Applied Surface Science*, 2019. 489: p. 989-1001.

[57] Gopi, C.V.M., et al., Recent progress of advanced energy storage materials for

flexible and wearable supercapacitor: From design and development to applications. *Journal of Energy Storage*, 2020. 27: p. 101035.

[58] Fu, X.-Y., et al., Laser fabrication of graphene-based supercapacitors. *Photonics Research*, 2020. 8(4): p. 577-588.

[59] Maher, F.E., et al., Laser scribing of high-performance and flexible graphene-based electrochemical capacitors, *Science*. 2012. p. 1326-1330.

[60] Ergoktas, M.S., et al., Graphene-enabled adaptive infrared textiles. *Nano Letters*, 2020. 20(7): p. 5346-5352.

[61] Zhao, C., et al., Three dimensional (3D) printed electrodes for interdigitated supercapacitors. *Electrochemistry Communications*, 2014. 41: p. 20-23.

[62] Lin, J., et al., Laser-induced porous graphene films from commercial polymers. *Nature communications*, 2014. 5(1): p. 1-8.

[63] Peng, Z., et al., Flexible and stackable laser-induced graphene supercapacitors. *ACS applied materials & interfaces*, 2015. 7(5): p. 3414-3419.

[64] Li, R.-Z., et al., High-rate in-plane micro-supercapacitors scribed onto photo paper using in situ femtolaser-reduced graphene oxide/Au nanoparticle microelectrodes. *Energy & Environmental Science*, 2016. 9(4): p. 1458-1467.

[65] Li, X., et al., 3D-printed stretchable micro-supercapacitor with remarkable areal performance. *Advanced Energy Materials*, 2020. 10(14): p. 1903794.

[66] De Gans, B.J., P.C. Duineveld, and U.S. Schubert, Inkjet printing of polymers: State of the art and future developments. *Advanced materials*, 2004. 16(3): p. 203-213.

[67] Wu L., et al., Emerging progress of inkjet technology in printing optical materials. *Advanced Optical Materials*, 2016. 4(12): p. 1915-1932.

[68] Liu, W., et al., Based all-solid-state flexible micro-supercapacitors with ultra-high rate and rapid frequency response capabilities. *Journal of Materials Chemistry A*, 2016. 4(10): p. 3754-3764.

[69] Xu, Y., et al., Screen-printable thin film supercapacitor device utilizing graphene/polyaniline inks. *Advanced Energy Materials*, 2013. 3(8): p. 1035-1040.

[70] Cao, X., et al., Screen printing as a scalable and low-cost approach for rigid and flexible thin-film transistors using separated carbon nanotubes. *ACS nano*, 2014. 8(12): p. 12769-12776.

[71] Lu, Q., et al., Facile synthesis of amorphous FeOOH/MnO₂ composites as screen-printed electrode materials for all-printed solid-state flexible supercapacitors. *Journal of Power Sources*, 2017. 361: p. 31-38.

[72] Yeo, J., et al., Flexible supercapacitor fabrication by room temperature rapid laser processing of roll-to-roll printed metal nanoparticle ink for wearable electronics application. *Journal of Power Sources*, 2014. 246: p. 562-568.

[73] Kang, S., et al., Roll-to-roll laser-printed graphene-graphitic carbon electrodes for high-performance supercapacitors. *ACS applied materials & interfaces*, 2018. 10(1): p. 1033-1038.

[74] Service, R.F., Electronic textiles charge ahead. *Science*, 2003. 301(5635): p. 909-911.

[75] Dias, T., *Electronic Textiles: Smart Fabrics and Wearable Technology*. 2015: Woodhead Publishing.

[76] Murthy, H.S., *Introduction to Textile Fibres*. 2016: CRC Press.

- [77] ASTM, D123-17 Standard Terminology Related to Textiles. 2017: West Conshohocken, PA.
- [78] Hu, L., et al., Stretchable, porous, and conductive energy textiles. *Nano Letters*, 2010. 10(2): p. 708-714.
- [79] Raj, C.J., et al., Highly flexible and planar supercapacitors using graphite flakes/polypyrrole in polymer lapping film. *ACS applied materials & interfaces*, 2015. 7(24): p. 13405-13414.
- [80] Peng, X., et al., Two dimensional nanomaterials for flexible supercapacitors. *Chemical Society Reviews*, 2014. 43(10): p. 3303-3323.
- [81] Harrison, D., et al., A coaxial single fibre supercapacitor for energy storage. *Physical Chemistry Chemical Physics*, 2013. 15(29): p. 12215-12219.
- [82] Zhang, D., et al., Core-spun carbon nanotube yarn supercapacitors for wearable electronic textiles. *Acs Nano*, 2014. 8(5): p. 4571-4579.
- [83] Cao, Y., et al., Boosting supercapacitor performance of carbon fibres using electrochemically reduced graphene oxide additives. *Physical Chemistry Chemical Physics*, 2013. 15(45): p. 19550-19556.
- [84] Chen, Q., et al., MnO₂-modified hierarchical graphene fiber electrochemical supercapacitor. *Journal of Power Sources*, 2014. 247: p. 32-39.
- [85] Bae, J., et al., Fiber supercapacitors made of nanowire-fiber hybrid structures for wearable/flexible energy storage. *Angewandte Chemie International Edition*, 2011. 50(7): p. 1683-1687.
- [86] Tsai, I.-L., et al., Graphene-enhanced electrodes for scalable supercapacitors. *Electrochimica Acta*, 2017. 257: p. 372-379.
- [87] Li, L., et al., Flexible planar concentric circular micro-supercapacitor arrays for wearable gas sensing application. *Nano Energy*, 2017. 41: p. 261-268.
- [88] Park, H., et al., Dynamically stretchable supercapacitor for powering an integrated biosensor in an all-in-one textile system. *ACS nano*, 2019. 13(9): p. 10469-10480.
- [89] Lu, Y., et al., Wearable sweat monitoring system with integrated micro-supercapacitors. *Nano Energy*, 2019. 58: p. 624-632.
- [90] Sun, Tongrui, et al., Wearable textile supercapacitors for self-powered enzyme-free Smartsensors. *ACS applied materials & interfaces*, 2020. 12(19): 21779-21787.
- [91] He, Z, et al. Piezoelectric-driven self-powered patterned electrochromic supercapacitor for human motion energy harvesting. *ACS Sustainable Chemistry & Engineering*, 2018. 7 (1): 1745-1752.
- [92] Vaghasiya, Jayraj V., et al. Integrated biomonitoring sensing with wearable asymmetric supercapacitors based on Ti₃C₂ MXene and 1T-phase WS₂ Nanosheets. *Advanced Functional Materials*, 2020. 30(39): 2003673.
- [93] Wang, X, et al. Fiber-based flexible all-solid-state asymmetric supercapacitors for integrated photodetecting system. *Angewandte Chemie*, 2014. 126(7): 1880-1884.
- [94] Huang, Yang, et al. A shape memory supercapacitor and its application in smart energy storage textiles. *Journal of Materials Chemistry A*, 2016 4(4): 1290-1297.
- [95] Huang, J, et al. Self-powered integrated system of a strain sensor and flexible all-solid-state supercapacitor by using a high performance ionic

organohydrogel. *Materials Horizons*, 2020 7(8): 2085-2096.

[96] Liao, M, et al. Multicolor, fluorescent supercapacitor fiber. *Small*, 2018 14(43): 1702052.

[97] Wang, K., et al., Integrated energy storage and electrochromic function in one flexible device: An energy storage smart window. *Energy & Environmental Science*, 2012. 5(8): p. 8384-8389.