We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

6,300

Open access books available

172,000

International authors and editors

190M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities

WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com

Synthesis of Ag Nanoparticles by Through Thin Film Ablation

P. Terrence Murray and Eunsung Shin
University of Dayton
 USA

1. Introduction

There are several applications that require a thin layer of nanoparticles that are spread uniformly and without agglomeration over a surface. Among these applications are carbon nanotube synthesis and the development of fuel cells, advanced sensors, and optoelectronic devices. There is a need for improved processes of forming these nanoparticles. Among the numerous methods that have been developed, pulsed laser ablation has proved (ElShall et al., 1995; Burr et al., 1997; Seraphin et al., 1997; Geohegan et al., 1998; Lowndes et al., 1998; Makimura et al., 1998; Becker et al., 1998; Lowndes et al., 1999; Makino et al., 1999; Link and El-Sayed, 2000; Mafune et al., 2000; Mafune et al., 2001; Ogawa et al., 2000; Tang et al., 2001; Ozawa et al., 2001; Hata et al., 2001; Barnes et al., 2002) to be especially effective because of the potential for congruent ablation, the ability to produce nanoparticles of high purity, the ability to deposit nanoparticles on room temperature substrates, and the relative simplicity of the process. One problem with conventional pulsed laser ablation is the observation that the deposited material, in addition to containing nanoparticles, also contains large, μm -sized particles. These are formed through a process denoted splashing (Ready, 1963), which occurs when a transient liquid layer is formed in the irradiated volume of the target; liquid droplets can be ejected from the target by the recoil pressure of the expanding gas on the transient liquid layer. Traditionally, splashing has been minimized (but not eliminated) by ablating very smooth targets or by using low laser energy densities. Target splashing is an issue in nanoparticle synthesis since the deposition of large particles within a field of nanoparticles makes it considerably more difficult to exploit the unique properties of isolated, non-agglomerated nanoparticles. Target splashing is also an issue because it represents material waste. There is, therefore, a need for a laser ablation process that further reduces or, ideally, eliminates splashing in nanoparticle synthesis. In addition, there is the further need for a process that minimizes nanoparticle agglomeration.

Presented here is a process, denoted Through Thin Film Ablation (TTFA), which enables the efficient synthesis of nanoparticles. TTFA, in addition to substantially reducing the probability of large particle splashing, also reduces significantly the problem of nanoparticle agglomeration. The TTFA process is based on irradiating a very thin layer of target material from the backside. The use of such a thin target allows one to reduce the thickness of the

liquid layer to such an extent that splashing of large particles is eliminated. Use of a very thin target has the added benefit of minimizing nanoparticle agglomeration. TTFA was originally developed as a method to synthesize transition metal nanoparticles for catalytic growth of single walled carbon nanotubes. The TTFA process has since been used to synthesize nanoparticles of several other materials including Fe (Murray and Shin, 2009), Pt (Petry, 2009; Tschopp et al., 2009), Ni, Ti, and Si. TTFA is illustrated here by presenting the results for Ag (Murray and Shin, 2008) nanoparticle formation.

2. Experimental

Nanoparticle synthesis by TTFA is carried out by ablating, from the backside, a very thin (10's of nm) film of the selected nanoparticle material. Ablation is carried out in the presence of a background gas (typically Ar), which serves to slow the species that are ejected from the target with initial kinetic energy of a few 10's of eV. The slowed atoms recombine in the gas phase to form nanoparticles, which are easily collected on an appropriately placed substrate. The experimental setup is presented in Figure 1(a), and a false color photograph of a TTFA plume is presented in Figure 1(b).

Fig. 1. (a) Schematic of the TTFA experiment. (b) photograph (false color) showing light emission from the ablated material.

For the work described here, the target consisted of a thin film (20 nm) of Ag that was sputter deposited onto a 5 cm diameter disk of UV-transparent fused silica. This structure was irradiated from the back side through the silica support with the output of a KrF excimer laser ($\lambda = 248$ nm). The laser beam struck the target at an angle of 45° , and the laser energy density at the target was 0.6 J/cm^2 . The target was rotated after each laser pulse in order to expose a fresh area for subsequent ablation.

Ablation was carried out in vacuum ($p = 2 \times 10^{-4} \text{ Pa}$) and with the ablation chamber filled with Ar at pressures of 133, 266, and 665 Pa. Ag nanoparticles were deposited onto TEM grids placed 5 cm from the target on a substrate of single crystal Si. Each deposition was carried out by using a single laser pulse, and the substrates were nominally at room temperature.

during deposition. All nanoparticle samples described here were prepared by ablating different area of the same target.

3. Results and Discussion

Shown in Figures 2(a)-2(d) are TEM micrographs of Ag nanoparticles deposited by TTFA; each sample was prepared by using a single laser pulse.

Fig. 2. TEM micrographs of Ag nanoparticles synthesized by TTFA in: (a) Vacuum, (b) 133 Pa, (c) 266 Pa, and (d) 665 Pa of Ar.

All micrographs were acquired with the same magnification, and the scale bar seen in Figure 2(a) represents a distance of 20 nm. The micrograph presented in Figure 2(a) was obtained from a sample formed by TTFA in vacuum. There is no discernible agglomeration of the nanoparticles, and the largest particles have diameters less than 20 nm. Presented in

Figure 2(b) is a micrograph of the Ag nanoparticles formed by TTFA in 133 Pa of Ar. There appear to be additional, even smaller particles formed in 133 Pa of Ar. Presented in figure 2(c) is a micrograph acquired from a sample prepared in 266 Pa of Ar. It is interesting to note that there are numerous smaller nanoparticles as well as fewer of the larger particles. Presented in Figure 2(d) is a micrograph of the sample synthesized in 665 Pa of Ar. There is no evidence of agglomeration in any of the TEM micrographs shown in Figure 2. This is in contrast to previous work (Murray et al., 2006; Koehler et al., 2006) that reported extensive agglomeration of nanoparticles made by conventional pulsed laser ablation. The absence of agglomeration in the TTFA process is attributed to the smaller amount of material ablated per laser shot compared to the conventional process. There are no particles larger than 20 nm seen in Figure 2 or in other, lower magnification images.

Fig. 3. Size distributions of Ag nanoparticles synthesized by TTFA in: (a) vacuum, (b) 133 Pa, (c) 266 Pa, and (d) 665 Pa of Ar.

Presented in Figures 3(a) through 3(d) are the Ag nanoparticle size distributions that were extracted from the TEM images. The distribution presented in Figure 3(a) was obtained from the sample made by TTFA in vacuum, and the inset shows an expanded region of the same distribution. The distribution of particles formed in vacuum is bimodal, with one component centered near 2 nm and another near 8 nm. We hypothesize that the 8 nm component was formed by splashing of a very thin, transient liquid layer on the irradiated target. Gated, high speed images recorded during ablation indicated the presence of a slow ($\sim 100\text{m/s}$) component that is attributed to hot, Ag nanoparticles ejected directly from the target. The 2 nm component is most likely due to gas phase recombination of ablated atomic and molecular species. Indeed, analysis by optical emission spectroscopy showed a large (excited) atomic Ag component in the ablated flux. Furthermore, gated, high speed images recorded during ablation (in vacuum) indicated the presence of a fast ($\sim 3\text{ km/s}$) component due to fast atomic Ag (which was confirmed by optical emission spectroscopy). The observation of a fast atomic component suggests that TTFA deposition in vacuum is a process in which a thin film of Ag is formed on the substrate by the atomic component, and the slower nanoparticles land on this nascent thin film some time later.

Shown in Figure 3(b) is the size distribution of Ag nanoparticles formed by TTFA in 133 Pa of Ar. Comparison of Figures 3(a) and 3(b) indicates that the number of small ($\sim 2\text{ nm}$) Ag nanoparticles formed by TTFA in Ar is nearly an order of magnitude greater than that formed in vacuum. This is reasonable given the fact that these species were formed by recombination of ablated Ag atoms following collision with background Ar. The inset in Figure 3(b) presents an expanded portion of the size distribution. It can be seen that the most probable nanoparticle size is approximately 2 nm. It can also be seen that the larger (8 nm) component is still present, albeit with a smaller intensity.

Presented in Figure 3(c) is the size distribution of nanoparticles formed in 266 Pa of Ar. The smaller component is nearly a factor of 3 more intense than seen at 166 Pa, and the most probable size is near 1 nm. It is interesting to note that the most probable size of the larger component is near 4 nm, suggesting that the hot, molten nanoparticles splashed from the target undergo enough collisions with background Ar (and with slowed atomic Ag and with nanoparticles newly formed by gas phase recombination) to undergo fragmentation by the time they land on the substrate.

The size distribution of particles formed in 665 Pa of Ar is shown in Figure 3(d). The overall number of particles (large and small component) is smaller than that seen at lower pressure; this suggests that, at this pressure, there are a sufficient number of collisions with background gas (and other species) that prevent the nanoparticles from reaching the substrate. These data illustrate the importance of finding the proper combination of background pressure and substrate distance to collect the optimal number of nanoparticles.

TTFA of Ag in Ar under the current conditions results in the formation of non-agglomerated nanoparticles with a most probable size of between 1 and 2 nm. The most probable size can, most likely, be altered by varying the nature of the background gas (i.e. by using He instead of Ar), the background gas pressure, and the target-substrate distance. The results presented here were obtained with a laser energy density at the target of 0.6 J/cm^2 .

Ablation at energy densities greater than $\sim 1 \text{ J/cm}^2$ resulted in damage to the fused silica support structure (as indicated by the presence of excited Si lines in the optical emission spectra). Ablation at energy densities less than 1 J/cm^2 caused no detectable damage to the silica support and no detectable contamination of the nanoparticle deposit.

The TTFA process allows one to synthesize nanoparticles with minimal contribution from larger particles. This is in contrast to the conventional laser ablation process in which larger, splashed particles are formed in addition to nanoparticles. We hypothesize that this difference lies in the two distinct target geometries. Conventional laser ablation entails irradiating a bulk target from the front. With this configuration, the region of highest transient temperature rise lies at the surface of the target; the temperature rise will decrease as a function of depth into the target. At some critical distance from the surface, the temperature rise will be insufficient to cause explosive ejection of atomic species but will be sufficient to cause target melting. At this point and deeper, the transient liquid layer of molten target will be formed, and this will be the source of large particles that are splashed from the target. In contrast, TTFA entails irradiating the target film from the back side. In this geometry, the region of highest transient temperature rise will lie at the interface between the target support and target film. Target material at this interface will be predominantly atomized, and regions away from the interface (toward the target surface) will experience smaller temperature rises. At some critical distance from the interface, the temperature rise will be insufficient to cause explosive ejection but will be sufficient to melt the target. By choosing a target thickness that is less than this critical distance, one can ablate a target with minimal melting and therefore with a minimal amount of splashed particles.

4. Conclusion

Well dispersed Ag nanoparticles have been formed by TTFA. The nanoparticles were deposited on room temperature substrates, had a most probable size between 1 and 2 nm, and were not agglomerated. The nanoparticle deposit produced by TTFA showed no evidence of the larger particles μm -sized commonly observed from conventional pulsed laser ablation from a bulk target. Synthesis of nanoparticles by TTFA should be possible for any material that can be made as a thin film target and may enable the unique properties of isolated, non-agglomerated nanoparticles to be exploited more fully.

5. Acknowledgment

The excellent technical work of Scott Streiker in the Nanoscale Engineering Science and Technology Laboratory at the University of Dayton is greatly appreciated.

6. References

- Barnes, P.N.; Murray, P.T.; Haugan, T.; Rogow, R.; and Perram, G. (2002). In situ creation of nanoparticles from YBCO by pulsed laser deposition. *Physica C- Superconductivity and Its Applications*. Vol. 377, Issue 4. (Sep 15, 2002) 578-584, ISSN: 0921-4534.

- Becker, M.F.; Brock, J.R.; Cai, H.; Henneke, D.E.; Keto, J.W.; Lee, J.Y.; Nichols, W.T.; Glicksman, H.D. (1998). Metal Nanoparticles Generated by Laser Ablation. *Nanostructured Materials*. Vol. 10, Issue 5. (Jul 1998). 853-863. ISSN: 0965-9773.
- Burr, T.A.; Seraphin, A.A.; Werwa, E.; and K. D. Kolenbrander, K.D. (1997). Carrier transport in thin films of silicon nanoparticles. *Physical Review B*. Vol. 56, Issue 8 (Aug 15, 1997). 4818-4824, ISSN: 0163-1829.
- ElShall, M.S.; Li, S.; Turkki, T.; Graiver, D., Pernis, U.C.; and Baraton, M.I. (1995). Synthesis and Photoluminescence of Weblike Agglomeration of Silica Nanoparticles. *Journal of Physical Chemistry*, Vol.99, Issue 51 (Dec. 21, 1995) 17805-17809, ISSN: 0022-3654.
- Geohegan, D.B.; Puretzky, A.A.; Duscher, G.; and Pennycook, S.J. (1998). Time-Resolved Imaging of Gas Phase Nanoparticle Synthesis by Laser Ablation. *Applied Physics Letters*. Vol. 72, Issue 23 (Jun 8, 1998). 2987-2989 ISSN: 0003-6951.
- Hata, K.; Fujita, M.; Yoshida, S.; Yasuda, Makimura, T.; Murakami, K.; Shigekawa, H.; Mizutani, W.; and Tokumoto, H. (2001). Selective adsorption and patterning of Si nanoparticles fabricated by laser ablation on functionalized self-assembled monolayer. *Applied Physics Letters*. Vol. 79, Issue 5 (Jul 30, 2001). 692-694, ISSN: 0003-6951.
- Koehler, B.; Murray, P.T.; Shin, E.; Lipfert, S.; and Schreiber, J. (2006). Nanomaterials produced by laser ablation techniques, Part II - High-spatially resolved nondestructive characterization of nanostructures, *Proceedings of SPIE*, pp. U144-U152, ISBN 0-8194-6228-4, San Diego, CA, Feb 28-Mar 02, 2006, SPIE-Int. Society for Optical Engineering, Bellingham, WA.
- Link, S. and El-Sayed, M.A. (2000). Shape and size dependence of radiative, non-radiative and photothermal properties of gold nanocrystals. *International Reviews in Physical Chemistry*. Vol. 19, Issue 3. (Jul-Sep 2000). 409-453 Published: JUL-SEP 2000. ISSN: 0144235X.
- Lowndes, D.H.; Rouleau, C.M.; Thundat, T.G., Duscher, G.; Kenik, E.A.; and Pennycook, S.J. (1999). Silicon and Zinc Telluride Nanoparticles Synthesized by Low Energy Density Pulsed Laser Ablation into Ambient Gases. *Journal of Materials Research*. Vol. 14, Issue 2. (Feb 1999). 359-370.
- Lowndes, D.H.; Rouleau, C.M.; Thundat, T.; Duscher, G.; Kenik, E.A.; and Pennycook, S.J. (1997). Silicon and Zinc Telluride Nanoparticles Synthesized by Pulsed Laser Ablation: Size Distributions and Nanoscale Structure. 4th International Conference on Laser Ablation (COLA 97), *Applied Surface Science*. Vol. 127 (Jul, 1997). 355-361 ISSN: 0169-4332.
- Mafune, F.; Kohno, J.; Takeda, Y.; Kondow, T.; and Sawabe, H. (2000). Structure and stability of silver nanoparticles in aqueous solution produced by laser ablation. *Journal of Physical Chemistry B*. Vol. 104, (Sep 2000). 8333-8337, ISSN: 1089-5647.
- Mafune, F.; Kohno, J.Y.; Takeda, Y.; Kondow, T.; and Sawabe, H. (2001). Formation of gold nanoparticles by laser ablation in aqueous solution of surfactant, *Journal of Physical Chemistry B*. Vol. 105, Issue 22. (Jun 7, 2001). 5114-5120. ISSN: 1089-5647.
- Makimura, T.; Kunii, Y.; Ono, N., and Murakami, K. Silicon Nanoparticles Embedded in SiO₂ Films with Visible Photoluminescence. (1997). 4th International Conference on Laser Ablation (COLA 97), *Applied Surface Science*, Vol. 127 (Jul 1997) 388-392, ISSN: 0169-4332.

- Makino, T.; Suzuki, N.; Yamada, Y., Oshida, T.; Seto, T.; and Aya, N. (1999). Size Classification of Si Nanoparticles Formed by Pulsed Laser Ablation in Helium Background Gas. 5th International Conference on Laser Ablation (COLA'99). *Applied Physics-A. Materials Science and Processing*. Vol. 69 (1999). S243-S247, ISSN: 0947-8396.
- Murray, P.T and Shin, E. (2008). Formation of silver nanoparticles by through thin film ablation. *Materials Letters*. Vol. 62, Issue 28 (Nov. 15, 2008) 4336-4338, ISSN: 0167-577X.
- Murray, P.T.; Koehler, B; Lipfert, S.; and Schreiber, J. (2006). Nanomaterials produced by laser ablation techniques Part I-Synthesis and passivation of nanoparticles, *Proceedings of SPIE*, pp. U153-U160, ISBN 0-8194-6228-4, San Diego, CA, Feb 28-Mar 02, 2006, SPIE-Int. Society for Optical Engineering, Bellingham, WA.
- Murray, P.T. and Shin, E. (2009). Thin film, nanoparticle, and nanocomposite fabrication by through thin film ablation. *Proceedings of SPIE*, ISSN 0277-786X, San Diego, CA, Aug 5, 2009, SPIE-Int. Society for Optical Engineering, Bellingham, WA.
- Petry, L.. Ph.D. Dissertation, University of Dayton (2009).
- Ogawa, K.; Vogt, T.; Ullmann, M., Johnson, S.; and Friedlander, S.K. (2000). Elastic properties of nanoparticle chain aggregates of TiO_2 , Al_2O_3 , and Fe_2O_3 generated by laser ablation. *Journal of Applied Physics*. Vol. 87, Issue 1 (Jan 2000). 63-73. ISSN: 0021-8979.
- Ozawa, E; Kawakami, Y; Seto, T. (2001). Formation and size control of tungsten nano particles produced by Nd : YAG laser irradiation. 5th International Conference on Nanostructured Materials (NANO 2000), *Scripta Materialia*. Vol. 44, Issue: 8-9 (2001) 2279-2283, ISSN: 1359-6462.
- Ready, J.F. (1963). Development of Plume of Material Vaporized by Giant-Pulse Laser, *Applied Physics Letters*. Vol. 3, 11 (1963).
- Seraphin, A.A.; Werwa, E.; Kolenbrander, K.D. (1997). Influence of nanostructure size on the luminescence behavior of silicon nanoparticle thin films, *Journal of Materials Research*. Vol. 12, Issue 12 (Dec. 1997). 3386-3392 .
- Tang, Y.H.; Sun, X.H.; Au, F.C.K.; Liao, L.S.; Peng, H.Y.; Lee, C.S.; Lee, S.T.; and Sham, T. (2001). Microstructure and field-emission characteristics of boron-doped Si nanoparticle chains. *Applied Physics Letters*. Vol. 79, Issue 11 (Sep 10, 2001). 1673-1675, ISSN: 0003-6951.
- Tschopp, M. A.; Bartha, B. B.; Porter, W. J.; Murray, P. T.; Fairchild, S. B. (2009). Microstructure-Dependent Local Strain Behavior in Polycrystals through In-Situ Scanning Electron Microscope Tensile Experiments. *Metallurgical and Materials Transactions A- Physical Metallurgy and Materials Science*. Vol. 40A, Issue 10 (Oct 2009). 2363-2368.

Silver Nanoparticles

Edited by David Pozo Perez

ISBN 978-953-307-028-5

Hard cover, 334 pages

Publisher InTech

Published online 01, March, 2010

Published in print edition March, 2010

Nanotechnology will be soon required in most engineering and science curricula. It cannot be questioned that cutting-edge applications based on nanoscience are having a considerable impact in nearly all fields of research, from basic to more problem-solving scientific enterprises. In this sense, books like “Silver Nanoparticles” aim at filling the gaps for comprehensive information to help both newcomers and experts, in a particular fast-growing area of research. Besides, one of the key features of this book is that it could serve both academia and industry. “Silver nanoparticles” is a collection of eighteen chapters written by experts in their respective fields. These reviews are representative of the current research areas within silver nanoparticle nanoscience and nanotechnology.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

P. Terrence Murray and Eunsung Shin (2010). Synthesis of Ag Nanoparticles by Through Thin Film Ablation, Silver Nanoparticles, David Pozo Perez (Ed.), ISBN: 978-953-307-028-5, InTech, Available from: <http://www.intechopen.com/books/silver-nanoparticles/synthesis-of-ag-nanoparticles-by-through-thin-film-ablation>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2010 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the [Creative Commons Attribution-NonCommercial-ShareAlike-3.0 License](https://creativecommons.org/licenses/by-nc-sa/3.0/), which permits use, distribution and reproduction for non-commercial purposes, provided the original is properly cited and derivative works building on this content are distributed under the same license.

IntechOpen

IntechOpen